


Deutsches Institut für Bautechnik

Anstalt des öffentlichen Rechts

Kolonnenstr. 30 L
10829 Berlin
Germany

Tel.: +49(0)30 787 30 0
Fax: +49(0)30 787 30 320
E-mail: dibt@dibt.de
Internet: www.dibt.de



DIBt

Mitglied der EOTA
Member of EOTA

European Technical Approval ETA-05/0135

English translation prepared by DIBt - Original version in German language

Handelsbezeichnung
Trade name

Pattex CF 900 mit Ankerstange HC
Pattex CF 900 with anchor rod HC

Zulassungsinhaber
Holder of approval

Henkel KGaA
Henkelstraße 67
40191 Düsseldorf

**Zulassungsgegenstand
und Verwendungszweck**

**Verbunddübel (Injektionssystem) mit Ankerstange aus
nichtrostendem Stahl 1.4529/1.4565 in den Größen M10,
M12 und M16 zur Verankerung im ungerissenen Beton**

*Generic type and use
of construction product*

*Bonded anchor (injection type) with anchor rod made of stainless steel
1.4529/1.4565 of sizes M10, M12 and M16 for use in non-cracked
concrete*

Geltungsdauer: vom
Validity: from
bis
to

19 May 2005
25 February 2010

Herstellwerk
Manufacturing plant

Henkel KGaA, Werk 2, Deutschland

Diese Zulassung umfasst
This Approval contains

16 Seiten einschließlich 7 Anhänge
16 pages including 7 annexes



Europäische Organisation für Technische Zulassungen
European Organisation for Technical Approvals

I LEGAL BASES AND GENERAL CONDITIONS

- 1 This European Technical Approval is issued by the Deutsches Institut für Bautechnik in accordance with:
 - Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of Member States relating to construction products¹, modified by Council Directive 93/68/EEC² and Regulation (EC) N° 1882/2003 of the European Parliament and of the Council³;
 - Gesetz über das In-Verkehr-Bringen von und den freien Warenverkehr mit Bauprodukten zur Umsetzung der Richtlinie 89/106/EWG des Rates vom 21. Dezember 1988 zur Angleichung der Rechts- und Verwaltungsvorschriften der Mitgliedstaaten über Bauprodukte und anderer Rechtsakte der Europäischen Gemeinschaften (Bauproduktengesetz - BauPG) vom 28. April 1998⁴, zuletzt geändert durch Gesetz vom 06.01.2004⁵.
 - Common Procedural Rules for Requesting, Preparing and the Granting of European Technical Approvals set out in the Annex to Commission Decision 94/23/EC⁶;
 - Guideline for European Technical Approval of "Metal Anchors for Use in Concrete" ETAG 001, edition 1997, Part 1 "Anchors in general" and Part 5 "Bonded anchors".
- 2 The Deutsches Institut für Bautechnik is authorized to check whether the provisions of this European Technical Approval are met. Checking may take place in the manufacturing plant. Nevertheless, the responsibility for the conformity of the products to the European Technical Approval and for their fitness for the intended use remains with the holder of the European Technical Approval.
- 3 This European Technical Approval is not to be transferred to manufacturers or agents of manufacturers other than those indicated on page 1, or manufacturing plants other than those indicated on page 1 of this European Technical Approval.
- 4 This European Technical Approval may be withdrawn by the Deutsches Institut für Bautechnik, in particular pursuant to information by the Commission according to Article 5(1) of Council Directive 89/106/EEC.
- 5 Reproduction of this European Technical Approval including transmission by electronic means shall be in full. However, partial reproduction can be made with the written consent of the Deutsches Institut für Bautechnik. In this case partial reproduction has to be designated as such. Texts and drawings of advertising brochures shall not contradict or misuse the European Technical Approval.
- 6 The European Technical Approval is issued by the approval body in its official language. This version corresponds fully to the version circulated in EOTA. Translations into other languages have to be designated as such.

1 Official Journal of the European Communities N° L 40, 11.02.1989, p. 12
2 Official Journal of the European Communities N° L 220, 30.08.1993, p. 1
3 Official Journal of the European Union N° L 284, 31.10.2003, p. 1
4 Bundesgesetzblatt I, p. 812
5 Bundesgesetzblatt I, p.2, 15
6 Official Journal of the European Communities N° L 17, 20.01.1994, p. 34

II SPECIFIC CONDITIONS OF THE EUROPEAN TECHNICAL APPROVAL

1 Definition of product and intended use

1.1 Definition of product

The Pattex CF 900 with anchor rod HC is a bonded anchor (injection type) consisting of a mortar cartridge with Injection Mortar Pattex CF 900 and an anchor rod with hexagon nut and washer in the range of M10, M12 and M16. The anchor rod (including nut and washer) are made of stainless steel 1.4529 or 1.4565. The anchor rod is placed into a drilled hole filled with injection mortar and is anchored via the bond between anchor rod, injection mortar and concrete.

An illustration of the product and intended use is given in Annex 1.

1.2 Intended use

The anchor is intended to be used for anchorages for which requirements for mechanical resistance and stability and safety in use in the sense of the Essential Requirements 1 and 4 of Council Directive 89/106 EEC shall be fulfilled and failure of anchorages made with these products would cause risk to human life and/or lead to considerable economic consequences. Safety in case of fire (Essential Requirement 2) is not covered in this ETA. The anchor is to be used only for anchorages subject to static or quasi-static loading in reinforced or unreinforced normal weight concrete of strength classes C20/25 at minimum and C50/60 at most according to EN 206:2000-12. It may be anchored in non-cracked concrete only.

The anchor may be used in structures subject to dry internal conditions and also in structures subject to external atmospheric exposure, in permanently damp internal conditions or in other particular aggressive conditions. Such particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

The anchor may be installed in dry or wet concrete, it must not be installed in flooded holes. Overhead installation is not admissible.

The anchor may be used in the following temperature ranges:

Temperature range: -40 °C to +80 °C (max short term temperature +80 °C and max long term temperature +50 °C)

Temperature range: -40 °C to +120 °C (max short term temperature +120 °C and max long term temperature +72 °C).

The provisions made in this European Technical Approval are based on an assumed intended working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

2 Characteristics of product and methods of verification

2.1 Characteristics of product

The anchor corresponds to the drawings and provisions given in Annexes 2 to 4. The characteristic material values, dimensions and tolerances of the anchor not given in Annexes 2 to

4 shall correspond to the respective values laid down in the technical documentation⁷ of this European Technical Approval.

The characteristic anchor values for the design of anchorages are given in Annexes 6 and 7. Each anchor rod shall be marked with the works symbol, the anchor identity, with the anchor size and the letters "HC" for the steel grades 1.4529 or 1.4565 in accordance with Annex 2. Each mortar cartridge shall be marked with the identifying mark of the producer and with the trade name.

The two components of the Injection Mortar Pattex CF 900 are delivered in unmixed condition in mortar cartridges of 150 ml, 280 ml, 300 ml, 330 ml, 380 ml or 410 ml (coaxial type) or 345 ml (side-by-side type) according to Annex 4.

2.2 Methods of verification

The assessment of fitness of the anchor for the intended use in relation to the requirements for mechanical resistance and stability and safety in use in the sense of the Essential Requirements 1 and 4 has been made in accordance with the "Guideline for European Technical Approval of Metal Anchors for Use in Concrete", Part 1 "Anchors in general" and Part 5 "Bonded anchors", on the basis of Option 7.

In addition to the specific clauses relating to dangerous substances contained in this European Technical Approval, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the EU Construction Products Directive, these requirements need also to be complied with, when and where they apply.

3 Evaluation of Conformity and CE marking

3.1 Attestation of Conformity system

The system of attestation of conformity 2(i) (referred to as System 1) according to Council Directive 89/106/EEC Annex III laid down by the European Commission provides:

a) tasks for the manufacturer:

- (1) factory production control;
- (2) further testing of samples taken at the factory by the manufacturer in accordance with a control plan.

b) tasks for the approved body:

- (3) initial type-testing of the product;
- (4) initial inspection of factory and of factory production control;
- (5) continuous surveillance, assessment and approval of factory production control.

3.2 Responsibilities

3.2.1 Tasks of the manufacturer; factory production control

The manufacturer has established a factory production control system in the plant and exercises permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer are documented in a systematic manner in the form of written policies and procedures. The production control system ensures that the product is in conformity with the European Technical Approval.

⁷

The technical documentation of this European Technical Approval is deposited at the Deutsches Institut für Bautechnik and, as far as relevant for the tasks of the approved bodies involved in the attestation of conformity procedure, is handed over to the approved bodies.

The manufacturer shall only use raw materials supplied with the relevant inspection documents as laid down in the control plan⁸. The incoming raw materials shall be subject to controls and tests by the manufacturer before acceptance. Check of incoming materials such as anchor rods, nuts and washers, shall include control of the inspection documents presented by suppliers (comparison with nominal values) by verifying dimensions and determining material properties, e.g. tensile strength, hardness, surface finish.

The manufactured components of the anchor shall be subjected to the following tests:

- Dimensions of component parts:
 - anchor rod (diameter, length, thread);
 - hexagon nut (well running, wrench size across flats);
 - washer (diameter, thickness);
 - resin (fill quantity, fill weight);
 - hardener (fill quantity, fill weight).
- Material properties:
 - anchor rod (tensile strength, yield limit);
 - hexagon nut (proof load);
 - washer (hardness);
 - mortar (condition, curing time, viscosity);
 - hardener (condition, reactivity).
- Visual control of completeness of the anchor.

The frequency of controls and tests conducted during production is laid down in the control plan taking account of the automated manufacturing process of the anchor.

The results of factory production control are recorded and evaluated. The records include at least the following information:

- Designation of the product, raw material and components,
- Type of control or testing,
- Date of manufacture of the product and date of testing of the product or basic material and components,
- Result of control and testing and, if appropriate, comparison with requirements,
- Signature of person responsible for factory production control.

The records shall be presented to the inspection body involved in the continuous surveillance. On request they shall be presented to the Deutsches Institut für Bautechnik.

Details of the extent, nature and frequency of testing and controls to be performed within the factory production control shall correspond to the control plan which is part of the technical documentation of this European Technical Approval.

3.2.2 Tasks of approved bodies

3.2.2.1 Initial type-testing of the product

For initial type-testing the results of the tests performed as part of the assessment for the European Technical Approval shall be used unless there are changes in the production line or plant. In such cases the necessary initial type-testing has to be agreed between the Deutsches Institut für Bautechnik and the approved bodies involved.

3.2.2.2 Initial inspection of factory and of factory production control

The approved body shall ascertain that, in accordance with the control plan, the factory, in particular the staff and equipment, and the factory production control are suitable to ensure a continuous and orderly manufacturing of the anchor with the specifications mentioned in 2.1 as well as in the Annexes to the European Technical Approval.

⁸ The control plan is deposited at the Deutsches Institut für Bautechnik and is handed over only to the approved bodies involved in the conformity attestation procedure.

3.2.2.3 Continuous surveillance

The approved body shall visit the factory at least once a year for surveillance. It has to be verified that the system of factory production control and the specified automated manufacturing process are maintained taking account of the control plan.

Continuous surveillance and assessment of factory production control have to be performed according to the control plan.

The results of product certification and continuous surveillance shall be made available on demand by the certification body or inspection body, respectively, to the Deutsches Institut für Bautechnik.

In cases where the provisions of the European Technical Approval and the control plan are no longer fulfilled the conformity certificate shall be withdrawn.

3.3 CE marking

The CE marking shall be affixed on each packaging of anchors. The symbol "CE" shall be followed by the identification number of the certification body and shall be accompanied by the additional information:

- name or identifying mark of producer and manufacturing plant,
- the last two digits of the year in which the CE marking was affixed,
- number of the EC certificate of conformity,
- number of the European Technical Approval,
- use category (ETAG 001-1 Option 7),
- anchor size.

4 Assumptions under which the fitness of the product for the intended use was favourably assessed

4.1 Manufacturing

The anchor is manufactured in accordance with the provisions of the European Technical Approval using the automated manufacturing process as identified in the inspection of the plant by the Deutsches Institut für Bautechnik and the approved body and laid down in the technical documentation.

4.2 Installation

4.2.1 Design of anchorages

The fitness of the anchor for the intended use is given under the following conditions:

The anchorages are designed in accordance with the "Guideline for European Technical Approval of Metal Anchors for Use in Concrete", Annex C, Method A, for bonded anchors under the responsibility of an engineer experienced in anchorages and concrete work.

For the verifications given below according to Annex C the following shall be observed:

- For the verification 'concrete cone failure' (clause 5.2.2.4, Annex C of the Guideline) $N_{Rk,c}$ shall be determined according to (1) and (2): The smaller value of (1) or (2) is decisive.

(1) $N_{Rk,c}$ according to equation (5.2), Annex C of the Guideline

where: $N_{Rk,c}^0$ according to Table 5, Annex 6

$s_{cr,N}$ according to Table 5, Annex 6

$c_{cr,N}$ according to Table 5, Annex 6

$\psi_{ucr,N} = 1.0$

In the special cases given in ETAG 001 Annex C, 5.2.2.4g) the value $N_{Rk,c}^0$ according to Table 5, Annex 6 shall be reduced:

$$N_{Rk,c}^0 = N_{Rk,c}^0 \text{ (Table 5)} \times \frac{h'_{ef}}{h_{ef}}$$

(2) $N_{Rk,c}$ according to equation (5.2), Annex C of the Guideline

$$\text{where: } N_{Rk,c}^0 = 0.75 \times 15.5 \times h_{ef}^{1.5} \times f_{ck,cube}^{0.5}$$

$$s_{cr,N} = 3 h_{ef}$$

$$c_{cr,N} = 1.5 h_{ef}$$

$$\psi_{ucr,N} = 1.0$$

- For the verification 'splitting failure due to loading' (clause 5.2.2.6, Annex C of the Guideline) $N_{Rk,sp}$ shall be determined according to (3).

(3) $N_{Rk,sp}$ according to equation (5.3), Annex C of the Guideline

$$\text{where: } N_{Rk,c}^0 \text{ according to Table 5, Annex 6}$$

$$s_{cr,sp} \text{ according to Table 5, Annex 6}$$

$$c_{cr,sp} \text{ according to Table 5, Annex 6}$$

$$\psi_{ucr,N} = 1.0$$

$$\psi_{h,sp} = 1.0$$

- For the verification 'concrete pryout failure' (clause 5.2.3.3, Annex C of the Guideline) $N_{Rk,c}$ for equation (5.6), Annex C of the Guideline, shall be determined according to (1).

Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored.

The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).

4.2.2 Installation of anchors

The fitness for use of the anchor can only be assumed if the anchor is installed as follows:

- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site,
- Use of the anchor only as supplied by the manufacturer without exchanging the components of an anchor,
- Anchor installation in accordance with the manufacturer's specifications and drawings using the tools indicated in the technical documentation of this European Technical Approval,
- Checks before placing the anchor to ensure that the strength class of the concrete in which the anchor is to be placed is in the range given and is not lower than that of the concrete to which the characteristic loads apply,
- Check of concrete being well compacted, e.g. without significant voids,
- Edge distance and spacing not less than the specified values,
- Positioning of the drill holes without damaging the reinforcement,
- In case of aborted hole: The hole shall be filled with mortar,
- Cleaning of the drill hole by at least 4x blowing / 4x brushing / 4x blowing following the manufacturers installation instructions,
- The anchor must not be installed in flooded holes,

- anchor installation such that the effective anchorage depth is complied with. This compliance is ensured when the embedment mark of the anchor does not exceed the concrete surface,
- Mortar injection by using the equipment including the static mixer shown in Annex 1; discarding the first swings of mortar (the specific number is given in the manufacturer's installation instruction) of each new cartridge, the injection mortar is sufficiently mixed when the colour has turned into a uniform grey; taking from the manufacturer's installation instruction the admissible processing time (open time) of a cartridge including pressing-in of the anchor rod as a function of the anchor component installation temperature and the ambient temperature of the concrete; filling the drill hole uniformly starting from the drill hole bottom, in order to avoid entrapment of air; removing the mixer slowly bit by bit during pressing-out; filling the drill hole with the minimum quantity of the injection mortar given in the manufacturer's installation instruction (appr. 2/3 of the drill, pressing the anchor rod by manual turning into the mortar-filled drill hole up to the marked anchorage depth; achieving the anchorage depth (installation depth), injection mortar must be visible at the member surface; replacing the static mixer if work is interrupted for a time exceeding the indicated processing time of the cartridge; the anchor component installation temperature shall be at least +5 °C; during curing of the injection mortar the temperature of the concrete must not fall below -5 °C; observing the curing time according to Annex 3, Table 3 until the anchor may be loaded; after the curing time fixing the fixture to be anchored by using a calibrated torque wrench by not exceeding the torque moment given in Annex 5, Table 4.

4.2.3 Responsibility of the manufacturer

The manufacturer is responsible to ensure that the information on the specific conditions according to 1 and 2 including Annexes referred to and 4.2.1 and 4.2.2 as well as 5 is given to those who are concerned. This information may be made by reproduction of the respective parts of the European Technical Approval. In addition all installation data shall be shown clearly on the package and/or on an enclosed instruction sheet, preferably using illustration(s).

The minimum data required are:

- Diameter of drill bit,
- Hole depth,
- Diameter of anchor rod,
- Minimum effective anchorage depth,
- Maximum thickness of the fixture,
- Information on the installation procedure, including cleaning of the hole with the cleaning equipments, preferably by means of an illustration,
- Anchor component installation temperature,
- Ambient temperature of the concrete during installation of the anchor,
- Admissible processing time (open time) of a cartridge,
- Curing time until the anchor may be loaded as a function of the ambient temperature in the concrete during installation,
- Torque moment,
- Identification of the manufacturing batch.

All data shall be presented in a clear and explicit form.

5 Recommendations concerning packaging, transport and storage

The injection cartridges shall be protected against sun radiation and shall be stored according to the manufacturer's installation instructions in dry condition at temperatures of at least +5 °C to not more than +25 °C.

Mortar cartridges with expired shelf life must no longer be used.

The anchor shall only be packaged and supplied as a complete unit. Mortar cartridges may be packed separately from anchor rods, nuts and washers.

The manufacturer's installation instruction shall indicate that the Injection Mortar Pattex CF 900 can be used only with the corresponding anchor rods of the manufacturer.

Dipl.-Ing. E. Jasch

Beglaubigt:

Lange


Sealing cap





Cartridge: Injection Mortar Pattex CF 900

Imprint:
Pattex CF 900, processing notes, charge-code, storage-life, hazard-code, curing- and processing time (depending on the temperature), with as well as without travel scale

Static mixer



Anchor rod with washer and hexagon nut




- Use category 1:
- Installation in dry or wet concrete
 - Service in dry and wet concrete
 - No overhead installation

- Temperature range:
- 40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)
 - 40°C to +120°C (max. short term temperature +120°C and max. long term temperature +72°C)

Pattex CF 900 with Anchor Rod HC

Product and intended use

Annex 1
of European
Technical Approval
ETA-05/0135



Marking:
 Works symbol, anchor identity, anchor size,
 additional marking for high corrosion-resistant: HC
 e.g.: CVM M12 HC
 Designation of anchor parts is given in Annex 3 (Table 2).

Table 1: Anchor dimensions

Size	Anchor rod		
	$\varnothing d_1$ [mm]	h_{ef} [mm]	min L ¹⁾ [mm]
M 10	10	90	≥ 110
M 12	12	110	≥ 130
M 16	16	125	≥ 145

¹⁾ max L = 1500 mm

Pattex CF 900 with Anchor Rod HC	Annex 2 of European Technical Approval ETA-05/0135
Anchor dimensions	

Table 2: Materials

Part	Designation	Stainless steel
1	Anchor rod	EN 10088, 1.4529 / 1.4565 Property class 70 acc. to EN ISO 3506
2	Hexagon nut according to DIN 934	EN 10088, 1.4529 / 1.4565 Property class 70 acc. to EN ISO 3506
3	Washer	EN 10088 – 1.4529 / 1.4565
4	Chemical mortar	Bonding agent: vinylester-resin, styrene-free Additive: quartz sand Hardener: dibenzoyl peroxide

Table 3: Minimum curing time



Concrete temperature	Minimum curing time in dry concrete	Minimum curing time in wet concrete
$\geq -5\text{ °C}$	6 h	12 h
$\geq 0\text{ °C}$	3 h	6 h
$\geq +5\text{ °C}$	2 h	4 h
$\geq +10\text{ °C}$	80 min	160 min
$\geq +20\text{ °C}$	45 min	90 min
$\geq +30\text{ °C}$	25 min	50 min
$\geq +35\text{ °C}$	20 min	40 min

Pattex CF 900 with Anchor Rod HC


Materials,
Curing times depending on the temperature
Annex 3
of European
Technical Approval
ETA-05/0135

150 ml, 280 ml, 300 ml, 330 ml, 380 ml and 410 ml injection mortar cartridge (type: coaxial)


Sealing/Screw cap



Component B: Hardener (inner tube)





Component A: Injection mortar (outer tube)




Static Mixer, one-way tool, must be changed in case of working interruption

345 ml injection mortar cartridge (type: side-by-side)


Sealing/Screw cap



Component B: Hardener



Component A: Injection mortar




Static Mixer, one-way tool, must be changed in case of working interruption

Pattex CF 900 with Anchor Rod HC	<p>Annex 4 of European Technical Approval ETA-05/0135</p>
Mortar cartridges	

Table 4: Installation parameters

Anchor size		M 10	M 12	M 16
Nominal drill hole diameter	d_0 [mm] =	12	14	18
Cutting diameter of drill bit	d_{cut} [mm] ≤	12.5	14.5	18.5
Depth of drill hole	h_0 [mm] ≥	90	110	125
Diameter of clearance hole in the fixture	d_f [mm] ≤	12	14	18
Diameter of steel brush	d_b [mm] ≥	14	16	20
Torque moment	T_{inst} [Nm]	20	40	60
Thickness of fixture	$\min t_{fix}$ [mm] >	0		
	$\max t_{fix}$ [mm] <	1400	1380	1360
Minimum thickness of member	h_{min} [mm]	130	160	160
Minimum spacing	s_{min} [mm]	90	110	125
Minimum edge distance	c_{min} [mm]	45	55	62.5

Steel brush



Pattex CF 900 with Anchor Rod HC

Installation parameters

Annex 5
of European
Technical Approval
ETA-05/0135

**Table 5: Design method A:
Characteristic values for tension loads**

Anchor size		M 10	M 12	M 16
Steel failure				
Characteristic resistance	$N_{Rk,s}$ [kN]	41	59	110
Partial safety factor	$\gamma_{Ms}^{1)}$	1.87		
Pullout and Concrete cone failure				
Non-cracked concrete C20/25 (50 °C / 80 °C) ³⁾	$N_{Rk,c}^0 = N_{Rk,p}$ [kN]	20	25	35
Non-cracked concrete C20/25 (72 °C / 120 °C) ³⁾	$N_{Rk,c}^0 = N_{Rk,p}$ [kN]	16	20	30
Increasing factors for non-cracked concrete ψ_c	C30/37	1.22		
	C40/50	1.41		
	C50/60	1.55		
Effective anchorage depth	h_{ef} [mm]	90	110	125
Characteristic edge distance	$c_{cr,N}$	90	110	125
Characteristic spacing	$s_{cr,N}$	180	220	250
Partial safety factor	$\gamma_{Mc} = \gamma_{Mp}^{1)}$	1.8 ²⁾		
Splitting failure				
Spacing	$s_{cr,sp}$ [mm]	180	220	250
Edge distance	$c_{cr,sp}$ [mm]	90	110	125
Partial safety factor	$\gamma_{Msp}^{1)}$	1.8 ²⁾		

¹⁾ In absence of other national regulations

²⁾ The partial safety factor $\gamma_2 = 1.2$ is included.

³⁾ Maximum long term temperature/ maximum short term temperature

Table 6: Displacements for tension loads

Anchor size		M 10	M 12	M 16
Tension load	N [kN]	6.6	8.3	11.6
Displacement	δ_{N0} [mm]	0.3	0.5	0.4
	$\delta_{N\infty}$ [mm]	0.6	1.6	2.0

Pattex CF 900 with Anchor Rod HC

Design Method A:
Characteristic values for tension loads,
Displacements

Annex 6
of European
Technical Approval
ETA-05/0135

**Table 7: Design method A:
Characteristic values for shear loads**

Anchor size		M 10	M 12	M 16
Steel failure without lever arm				
Characteristic resistance	$V_{Rk,s}$ [kN]	20	30	55
Partial safety factor	$\gamma_{Ms}^{1)}$	1.56		
Steel failure with lever arm				
Characteristic resistance	$M^0_{Rk,s}$ [Nm]	52	92	233
Partial safety factor	$\gamma_{Ms}^{1)}$	1.56		
Concrete pryout failure				
Factor k in equation (5.6) of ETAG 001, Annex C, Section 5.2.3.3		2.0		
Partial safety factor	$\gamma_{Mc}^{1)}$	1.50 ²⁾		
Concrete edge failure				
Effective length of anchor in shear loading	ℓ_f [mm]	90	110	125
Outside diameter of anchor	d_{nom} [mm]	12	14	18
Partial safety factor	$\gamma_{Mc}^{1)}$	1.50 ²⁾		

¹⁾ If no other national regulations exist

²⁾ The partial safety factor $\gamma_2 = 1.0$ is included.

Table 8: Displacements for shear loads

Anchor size		M 10	M 12	M 16
Shear load	V [kN]	6.6	8.3	11.6
Displacement	δ_{V0} [mm]	0.4	1.1	1.3
	$\delta_{V\infty}$ [mm]	0.6	1.6	2.0

Pattex CF 900 with Anchor Rod HC

Design Method A:
Characteristic values for shear loads,
Displacements

Annex 7
of European
Technical Approval
ETA-05/0135