Deutsches Institut für Bautechnik

Anstalt des öffentlichen Rechts

Kolonnenstr. 30 L 10829 Berlin Germany

Tel.: +49(0)30 787 30 0 Fax: +49(0)30 787 30 320 E-mail: dibt@dibt.de Internet: www.dibt.de





Mitglied der EOTA

Member of EOTA

European Technical Approval ETA-03/0017

English translation prepared by DIBt - Original version in German language

M24 zur Verankerung im Beton

Handelsbezeichnung

Trade name

MKT Bolzenanker BZ plus

MKT Wedge anchor BZ plus

Zulassungsinhaber

Holder of approval

MKT

Metall-Kunststoff-Technik GmbH & Co. KG Auf dem Immel 2

M10, M12, M16, M20 and M24 for use in concrete

Kraftkontrolliert spreizender Dübel aus galvanisch

verzinktem Stahl in den Größen M8, M10, M12, M16, M20 und

Torque controlled expansion anchor made of galvanised steel of sizes M8,

67685 Weilerbach

Zulassungsgegenstand und Verwendungszweck

Generic type and use of construction product

Geltungsdauer: vom

Validity: from bis

to

30 June 2010

17 June 2013

Herstellwerke

Manufacturing plants

MKT

Metall-Kunststoff-Technik GmbH & Co. KG Auf dem Immel 2 67685 Weilerbach

Diese Zulassung umfasst This Approval contains 14 Seiten einschließlich 10 Anhänge 14 pages including 10 annexes

Diese Zulassung ersetzt This Approval replaces ETA-03/0017 mit Geltungsdauer vom 21.05.2008 bis 17.06.2013 ETA-03/0017 with validity from 21.05.2008 to 17.06.2013



I LEGAL BASES AND GENERAL CONDITIONS

- 1 This European technical approval is issued by Deutsches Institut für Bautechnik in accordance with:
 - Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of Member States relating to construction products¹, modified by Council Directive 93/68/EEC² and Regulation (EC) N° 1882/2003 of the European Parliament and of the Council³;
 - Gesetz über das In-Verkehr-Bringen von und den freien Warenverkehr mit Bauprodukten zur Umsetzung der Richtlinie 89/106/EWG des Rates vom 21. Dezember 1988 zur Angleichung der Rechts- und Verwaltungsvorschriften der Mitgliedstaaten über Bauprodukte und anderer Rechtsakte der Europäischen Gemeinschaften (Bauproduktengesetz - BauPG) vom 28. April 1998⁴, as amended by law of 31 October 2006⁵;
 - Common Procedural Rules for Requesting, Preparing and the Granting of European technical approvals set out in the Annex to Commission Decision 94/23/EC⁶;
 - Guideline for European technical approval of "Metal anchors for use in concrete Part 2: Torque controlled expansion anchors ", ETAG 001-02.
- Deutsches Institut für Bautechnik is authorized to check whether the provisions of this European technical approval are met. Checking may take place in the manufacturing plant. Nevertheless, the responsibility for the conformity of the products to the European technical approval and for their fitness for the intended use remains with the holder of the European technical approval.
- This European technical approval is not to be transferred to manufacturers or agents of manufacturers other than those indicated on page 1, or manufacturing plants other than those indicated on page 1 of this European technical approval.
- This European technical approval may be withdrawn by Deutsches Institut für Bautechnik, in particular pursuant to information by the Commission according to Article 5(1) of Council Directive 89/106/EEC.
- Reproduction of this European technical approval including transmission by electronic means shall be in full. However, partial reproduction can be made with the written consent of Deutsches Institut für Bautechnik. In this case partial reproduction has to be designated as such. Texts and drawings of advertising brochures shall not contradict or misuse the European technical approval.
- The European technical approval is issued by the approval body in its official language. This version corresponds fully to the version circulated within EOTA. Translations into other languages have to be designated as such.

¹ Official Journal of the European Communities L 40, 11 February 1989, p. 12

² Official Journal of the European Communities L 220, 30 August 1993, p. 1

³ Official Journal of the European Union L 284, 31 October 2003, p. 25

⁴ Bundesgesetzblatt Teil I 1998, p. 812

⁵ Bundesgesetzblatt Teil I 2006, p. 2407, 2416

⁶ Official Journal of the European Communities L 17, 20 January 1994, p. 34

II SPECIFIC CONDITIONS OF THE EUROPEAN TECHNICAL APPROVAL

1 Definition of product and intended use

1.1 Definition of the construction product

The MKT Wedge anchor BZ plus in the range of M8, M10, M12, M16, M20 and M24 is an anchor made of galvanised steel which is placed into a drilled hole and anchored by torque-controlled expansion.

An illustration of the product and intended use is given in Annex 1.

1.2 Intended use

The anchor is intended to be used for anchorages for which requirements for mechanical resistance and stability and safety in use in the sense of the Essential Requirements 1 and 4 of Council Directive 89/106 EEC shall be fulfilled and failure of anchorages made with these products would cause risk to human life and/or lead to considerable economic consequences.

The anchor may be used for anchorages with requirements related to resistance to fire.

The anchor is to be used only for anchorages subject to static or quasi-static loading in reinforced or unreinforced normal weight concrete of strength classes C20/25 at minimum and C50/60 at most according to EN 206:2000-12. It may be anchored in cracked and non-cracked concrete.

The anchor may only be used in structures subject to dry internal conditions.

The provisions made in this European technical approval are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

2 Characteristics of the product and methods of verification

2.1 Characteristics of the product

The anchor corresponds to the drawings and provisions given in Annexes 2 and 3. The characteristic material values, dimensions and tolerances of the anchor not given in Annexes 2 and 3 shall correspond to the respective values laid down in the technical documentation⁷ of this European technical approval.

Regarding the requirements concerning safety in case of fire it is assumed that the anchor meets the requirements of class A1 in relation to reaction to fire in accordance with the stipulations of the Commission decision 96/603/EC, amended by 2000/605/EC.

The characteristic values for the design of anchorages are given in Annexes 4 and 5.

The characteristic values for the design of anchorages regarding resistance to fire are given in Annexes 6 and 7. They are valid for use in a system that is required to provide a specific fire resistance class.

Z28429.10

The technical documentation of this European technical approval is deposited at the Deutsches Institut für Bautechnik and, as far as relevant for the tasks of the approved bodies involved in the attestation of conformity procedure, is handed over to the approved bodies.

Each anchor is marked with the identifying mark of the producer, the commercial name, the thread size and the maximum thickness of fixture according to Annex 2.

The anchor shall only be packaged and supplied as a complete unit.

2.2 Methods of verification

The assessment of fitness of the anchor for the intended use in relation to the requirements for mechanical resistance and stability and safety in use in the sense of the Essential Requirements 1 and 4 has been made in accordance with the "Guideline for European technical approval of Metal Anchors for Use in Concrete", Part 1 "Anchors in general" and Part 2 "Torque-controlled expansion anchors", on the basis of Option 1.

The assessment of the anchor for the intended use in relation to the requirements for resistance to fire has been made in accordance with the technical Report TR 020 "Evaluation of anchorages in concrete concerning resistance to fire".

In addition to the specific clauses relating to dangerous substances contained in this European technical approval, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Directive, these requirements need also to be complied with, when and where they apply.

3 Evaluation and attestation of conformity and CE marking

3.1 System of attestation of conformity

According to the decision 96/582/EG of the European Commission⁸ the system 2(i) (referred to as system 1) of attestation of conformity applies.

System 1: Certification of the conformity of the product by an approved certification body on the basis of:

- (a) Tasks for the manufacturer:
 - (1) factory production control;
 - (2) further testing of samples taken at the factory by the manufacturer in accordance with a prescribed control plan.
- (b) Tasks for the approved body:
 - (3) initial type-testing of the product;
 - (4) initial inspection of factory and of factory production control;
 - (5) continuous surveillance, assessment and approval of factory production control.

Note: Approved bodies are also referred to as "notified bodies".

3.2 Responsibilities

3.2.1 Tasks of the manufacturer

3.2.1.1 Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall insure that the product is in conformity with this European technical approval.

Official Journal of the European Communities L 254 of 08.10.1996.

The manufacturer may only use initial/ raw/ constituent materials stated in the technical documentation of this European technical approval.

The factory production control shall be in accordance with the control plan which is part of the technical documentation of this European technical approval. The control plan is laid down in the context of the factory production control system operated by the manufacturer and deposited at Deutsches Institut für Bautechnik⁹.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the control plan.

3.2.1.2 Other tasks of manufacturer

The manufacturer shall, on the basis of a contract, involve a body which is approved for the tasks referred to in section 3.1 in the field of anchors in order to undertake the actions laid down in section 3.2.2. For this purpose, the control plan referred to in sections 3.2.1.1 and 3.2.2 shall be handed over by the manufacturer to the approved body involved.

The manufacturer shall make a declaration of conformity, stating that the construction product is in conformity with the provisions of this European technical approval.

3.2.2 Tasks of approved bodies

The approved body shall perform the

- initial type-testing of the product,
- initial inspection of factory and of factory production control,
- continuous surveillance, assessment and approval of factory production control,

in accordance with the provisions laid down in the control plan.

The approved body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The approved certification body involved by the manufacturer shall issue an EC certificate of conformity of the product stating the conformity with the provisions of this European technical approval.

In cases where the provisions of the European technical approval and its control plan are no longer fulfilled the certification body shall withdraw the certificate of conformity and inform Deutsches Institut für Bautechnik without delay.

3.3 CE marking

The CE marking shall be affixed on each packaging of the anchor. The letters "CE" shall be followed by the identification number of the approved certification body, where relevant, and be accompanied by the following additional information:

- the name and address of the producer (legal entity responsible for the manufacturer),
- the last two digits of the year in which the CE marking was affixed,
- the number of the EC certificate of conformity for the product,
- the number of the European technical approval,
- the number of the guideline for European technical approval,
- use category (ETAG 001-1 Option 1),
- size.

The control plan is a confidential part of the documentation of the European technical approval, but not published together with the ETA and only handed over to the approved body involved in the procedure of attestation of conformity.

See section 3.2.2.

4 Assumptions under which the fitness of the product for the intended use was favourably assessed

4.1 Manufacturing

The European technical approval is issued for the product on the basis of agreed data/information, deposited with Deutsches Institut für Bautechnik, which identifies the product that has been assessed and judged. Changes to the product or production process, which could result in this deposited data/information being incorrect, should be notified to Deutsches Institut für Bautechnik before the changes are introduced. Deutsches Institut für Bautechnik will decide whether or not such changes affect the ETA and consequently the validity of the CE marking on the basis of the ETA and if so whether further assessment or alterations to the ETA shall be necessary.

4.2 Design of anchorages

The fitness of the anchor for the intended use is given under the following conditions:

The anchorages are designed in accordance with the "Guideline for European technical approval of Metal Anchors for Use in Concrete", Annex C, Method A, for torque controlled expansion anchors under the responsibility of an engineer experienced in anchorages and concrete work.

Verifiable calculation notes and drawings are taking account of the loads to be anchored.

The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports).

The design of anchorages under fire exposure has to consider the conditions given in the technical Report TR 020 "Evaluation of anchorages in concrete concerning resistance to fire". The relevant characteristic anchor values are given in Annexes 6 and 7. The design method covers anchors with a fire attack from one side only. If the fire attack is from more than one side, the design method may be taken only, if the edge distance of the anchor is $c \ge 300 \text{ mm}$.

4.3 Installation

The fitness for use of the anchor can only be assumed if the anchor is installed as follows:

- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site,
- Use of the anchor only as supplied by the manufacturer without exchanging the components of an anchor,
- Anchor installation in accordance with the manufacturer's specifications and drawings and using the appropriate tools,
- Checks before placing the anchor to ensure that the strength class of the concrete in which the anchor is to be placed is in the range given and is not lower than that of the concrete to which the characteristic loads apply,
- Check of concrete being well compacted, e.g. without significant voids.
- Edge distances and spacing not less than the specified values without minus tolerances,
- Positioning of the drill holes without damaging the reinforcement,
- In case of aborted hole: new drilling at a minimum distance away of twice the depth of the aborted hole or smaller distance if the aborted drill hole is filled with high strength mortar and if under shear or oblique tension load it is not in the direction of load application,
- Cleaning of the hole of drilling dust,

- Anchor installation such that the effective anchorage depth is complied with. This compliance is ensured when the embedment mark of the anchor does no more exceed the concrete surface.
- Application of the torque moment given in Annex 3 using a calibrated torque wrench.

5 Responsibility of the manufacturer


The manufacturer is responsible to ensure that the information on the specific conditions according to 1 and 2 including Annexes referred to and 4.2 and 4.3 is given to those who are concerned. This information may be made by reproduction of the respective parts of the European technical approval. In addition all installation data shall be shown clearly on the package and/or on an enclosed instruction sheet, preferably using illustration(s).


The minimum data required are:


- Diameter of drill bit.
- Thread diameter,
- Maximum thickness of the fixture,
- Minimum effective anchorage depth,
- Minimum hole depth,
- Torque moment,
- Information on the installation procedure, including cleaning of the hole, preferably by means of an illustration,
- Reference to any special installation equipment needed,
- Identification of the manufacturing batch.

All data shall be presented in a clear and explicit form.

Dipl.-Ing. Georg Feistel Head of Division Construction Engineering of Deutsches Institut für Bautechnik Berlin, 30 June 2010 *beglaubigt* Lange








MKT Wedge A	Anchor	BZ pl	us
-------------	--------	-------	----

Product and intended use

Annex 1

of European technical Approval



marking of length		С	D	E	F	G	Н	I	7	Κ	L	M
length of anchor min	2	63.5	76.2	88.9	101.6	114.3	127.0	139.7	152.4	165.1	177.8	190.5
length of anchor max	<	76.2	88.9	101.6	114.3	127.0	139.7	152.4	165.1	177.8	190.5	203.2



marking of length		N	0	Р	Q	R	S	T	U	٧	W	Х	Υ	Z
length of anchor min	≥	203.2	215.9	228.6	241.3	254.0	279.4	304.8	330.2	355.6	381.0	406.4	431.8	457.2
length of anchor max	<	215.9	228.6	241.3	254.0	279.4	304.8	330.2	355.6	381.0	406.4	431.8	457.2	483.0

Table 1: Anchor dimensions

bolt _	Thread ∅ d _k		M8	M10	M12	M16	M20	M24
	$\emptyset d_k$						14120	1712-7
_		=	7.9	9.8	11.8	15.7	19.7	24
	t _{fix} max	≤	3000	3000	3000	3000	3000	3000
	L max		3065	3080	3095	3120	3137	3161
ion sleeve	ls	=	14.5	18.5	22	24.3	28	32
	SW		13	17	19	24	30	36
	ion sleeve n nut	ion sleeve ls	ion sleeve ls =	ion sleeve Is = 14.5	ion sleeve Is = 14.5 18.5	ion sleeve Is = 14.5 18.5 22	ion sleeve Is = 14.5 18.5 22 24.3	ion sleeve Is = 14.5 18.5 22 24.3 28

Dimension in mm


Table 2: Materials

Part	Anchor size	M8 to M20	M24
1	Conical bolt	Cold formed or machined steel Cone plastic coated (M8 – M20)	Threaded bolt, steel, strength class 8.8, to EN ISO 898-1 Threaded cone, steel, strength class 8, to EN 20898-2
2	Expansion sleeve	Steel acc. to EN 10088, material No. Steel EN 10139 for M24	1.4301 or 1.4401 for M8 – M20;
3	Hexagon nut	Strength class 8 acc. to EN 20898-2,	galvanised, coating
4	Washer acc. to EN ISO 7089, or EN ISO 7093, or EN ISO 7094	Steel, galvanised	

MKT Wedge Anchor BZ plus	Annex 2
Anchor dimensions, Material	of European technical Approval
	ETA-03/0017

Table 3: Installation parameters

Anchor Size			M8	M10	M12	M16	M20	M24
Nominal drill hole diameter	d ₀	[mm]	8	10	12	16	20	24
Cutting diameter of drill bit	d _{cut} ≤	[mm]	8.45	10.45	12.5	16.5	20.55	24.55
Depth of drill hole	h ₁ ≥	[mm]	60	75	90	110	125	145
Effective anchorage depth	h _{ef}	[mm]	46	60	65	85	100	115
Installation torque	T _{inst}	[Nm]	20	25	45	90	160	200
Diameter of clearance hole in the fixture	d _f ≤	[mm]	9	12	14	18	22	26



- 1) Effective anchorage depth hef
- 2) Minimum thickness of concrete member h_{min}
- 3) Thickness of fixture t_{fix}

Table 4: Standard thickness of concrete member and respective minimum spacing and edge distance

Anchor Size			M8	M10	M12	M16	M20	M24
Minimum thickness of member	h _{std}	[mm]	100	120	130	170	200	230
Cracked concrete								
Minimum spacing	Smin	[mm]	40	45	60	60	95	100
	for c ≥	[mm]	70	70	100	100	150	180
Minimum edge distance	C _{min}	[mm]	40	45	60	60	95	100
The state of the s	for s ≥	[mm]	80	90	140	180	200	220
Non-cracked concrete								
Minimum spacing	Smin	[mm]	40	45	60	65	90	100
	for c ≥	[mm]	80	70	120	120	180	180
Minimum edge distance	C _{min}	[mm]	50	50	75	80	130	100
	for s ≥	[mm]	100	100	150	150	240	220

Intermediate values by linear interpolation.

Table 5: Minimum thickness of concrete member and respective minimum spacing and edge distance

Anchor Size			M8	M10	M12	M16	M20	M24
Minimum thickness of member	h _{min} _	[mm]	80	100	110	140	-	-
Cracked concrete								
Minimum spacing	Smin	[mm]	40	45	60	70	-	-
	for c ≥	[mm]	70	90	100	160		-
Minimum edge distance	C _{min}	[mm]	40	50	60	80		-
Tim in fact, or go are an in a	for s ≥	[mm]	80	115	140	180	-	-
Non-cracked concrete								
Minimum spacing	Smin	[mm]	40	60	60	80	-	-
· · · · · · · · · · · · · · · · · · ·	for c ≥	[mm]	80	140	120	180	-	-
Minimum edge distance	C _{min}	[mm]	50	90	75	90	-	-
	for s ≥	[mm]	100	140	150	200	-	

Intermediate values by linear interpolation.

MKT Wedge Anchor BZ plus

Installation parameters, Minimum thickness of member, minimum spacing and edge distance

Annex 3

of European technical Approval

Table 6: Design method A Characteristic values for tension loads

Anchor Size			М8	M10	M12	M16	M20	M24
Steel failure								
Characteristic resistance	$N_{Rk,s}$	[kN]	16	27	39	60	86	126
Partial safety factor	γ _{Ms} ³⁾	[-]		1.53		1.5	1.6	1.5
Pull-out						(Lastina and Control of Control o		
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p}$	[kN]	5	9	12	25	- 1)	- 1)
Characteristic resistance in non-cracked concrete C20/25		[kN]	12	16	20	35	- 1)	- 1)
Splitting for standard thicknes The higher one of the decisive v			e 2 is ap	plicable.				
Standard thickness of concrete	h _{std} ≥	[mm]	100	120	130	170	200	230
Case 1							***************************************	
Characteristic resistance in concrete C20/25	N ⁰ _{Rk,sp} ⁴⁾	[kN]	9	12	16	30	40	- 1)
Respective spacing	S _{cr,sp}	[mm]			3	h _{ef}		
Respective edge distance	C _{cr,sp}	[mm]			1.	5 h _{ef}		
Case 2								
Characteristic resistance in concrete C20/25	N ⁰ _{Rk,sp} 4)	[kN]	12	16	20	35	- 1)	- 1)
Respective spacing	S _{cr,sp} 5)	[mm]		4	h _{ef}		4.4 h _{ef}	3 h _{ef}
Respective edge distance	C _{cr,sp} ⁵⁾	[mm]		2	h _{ef}		2.2 h _{ef}	1.5 h _{ef}
Splitting for minimum thickne	ss of concrete n	nember						
Minimum thickness of concrete	h _{min} ≥	[mm]	80	100	110	140		
Characteristic resistance in concrete C20/25	N ⁰ _{Rk,sp} ⁴⁾	[kN]	12	16	20	35	1	duced ess of
Respective spacing	S _{cr,sp} 5)	[mm]		5	h _{ef}		cond	crete
Respective edge distance	C _{cr,sp} ⁵⁾	[mm]		2.5	5 h _{ef}			
Increasing factors	C30/37	[-]			1	.22		
for N _{Bk,p} and N ⁰ _{Bk,sp}	ψ _C C40/50	[-]	**************************************		1	.41		
· mode.	C50/60	[-]			1	.55		
Concrete cone failure	ayng pagagang namasan nag pana dalam ajadiyan panaligi dan dalah dalah dalah dalah dalah dalah dalah dalah dal							
Effective anchorage depth	h _{ef}	[mm]	46	60	65	85	100	115
Spacing	S _{cr,N}	[mm]		<u> </u>	3	h _{ef}	***************************************	
Edge distance	C _{cr,N}	[mm]		***************************************	1.	5 h _{ef}		
Eugo dictario								

MKT Wedge Anchor BZ plus Annex 4 of European Design method A, technical Approval Characteristic values for tension loads ETA-03/0017

 ¹⁾ Concrete cone failure is decisive
 2) The partial safety factor γ₂ = 1.0 is included
 3) In absence of other national regulations
 4) For the proof against splitting failure according to ETAG 001 Annex C, N⁰_{Rk,c} in equation (5.3) has to be replaced by $N_{Rk,sp}^0$ with consideration of the member thickness ($\psi_{ucr,sp} = 1.0$).

The values $s_{cr,sp}$ and $c_{cr,sp}$ may be linearly interpolated for member thicknesses $h_{min} < h < h_{std}$ (case 2) ($\psi_{h,sp}$ =1.0).

Displacements under tension loads Table 7:

Anchor Size			M8	M10	M12	M16	M20	M24
Tension load in cracked concrete	N	[kN]	2.4	4.3	5.7	11.9	17.1	21.1
Displacement	δ_{N0}	[mm]	0.6	1.0	0.7	1.0	0.9	0.7
,	δ _{N∞}	[mm]	1.4	1.2	1.0	1.3	1.0	1.2
Tension load in non-cracked concrete		[kN]	5.7	7.6	9.5	16.7	23.8	29.6
Displacement	δ_{No}	[mm]	0.4	0.5	0.3	0.3	0.4	0.5
•	δ _{N∞}	[mm]		C).8		0.	8

Design method A Table 8: Characteristic values for shear loads

Anchor Size			M8	M10	M12	M16	M20	M24
Steel failure without lever arm								
Characteristic resistance	$V_{Rk,s}$	[kN]	15	22	33	60	69	114
Partial safety factor	γ _{Ms} 1)	[-]		1	.25		1.33	1.25
Steel failure with lever arm								,
Characteristic bending resistance	$M^0_{Rk,s}$	[Nm]	23	47	82	209	363	898
Partial safety factor	γ _{Ms} 1)	[-]		1	.25		1.33	1.25
Concrete pryout failure								-y
Factor in equation (5.6) ETAG 001, Annex C, 5.2.3.3	k	[-]	2.0	2.0	2.0	2.0	2.0	2.0
Partial safety factor	γ _{Mcp} 1)	[-]			1.5	5 ²⁾		
Concrete edge failure								·
Effective length of anchor in shear loading	l _f	[mm]	46	60	65	85	100	115
Outside diameter of anchor	d _{nom}	[mm]	8	10	12	16	20	24
Partial safety factor	γ _{Mc} 1)	[-]			1.	o ²⁾	···	

Displacements under shear loads Table 9:

Anchor Size			М8	M10	M12	M16	M20	M24
Shear load in cracked and non-cracked concrete	٧	[kN]	8.6	12.6	18.9	34.3	36.8	64.9
Displacement	δ_{V0}	[mm]	2.3	2.2	3.0	4.0	1.8	3.5
	$\delta_{V_{\infty}}$	[mm]	3.5	3.3	4.6	6.0	2.7	5.3

MKT Wedge Anchor BZ plus	Annex 5
Design method A,	of European
Characteristic values for shear loads,	technical Approval
Displacements	ETA-03/0017

 $^{^{1)}}$ In absence of other national regulations $^{2)}$ The partial safety factors $~\gamma_1=\gamma_2=1.0$ are included

ind non-cracked concrete	
ension loads under fire exposure in cracked and non-cracked concrete	
Characteristic values to tension lo	C20/25 to C50/60
Table 10:	

n /	100	hor B	7 nli	ıe						Anne		
020/22 01 c2/020	Anchor size	Fire resistance duration	Steel failure:	Characteristic resistance	Pullout failure:	Characteristic resistance in concrete C20/25 to C50/60	Concrete cone failure:	Characteristic resistance in concrete C20/25 to C50/60	Spacing	Edge Distance	Minimum spacing and edge distance under fire exposure from one side	Minimum spacing and edge distance under fire exposure from more than one side
(C) (C)		R [min]		N _{Rk,s,fi} [KN]		N _{Rk,p,fi} [KN]		N ^o Rk,c,fi [KN]	Scr,N,fi	C _{or,N,fi}	dge sure	dge sure
		30		1,4								
	M8	09		1.		1.3		2.6				
	_	90 1		0.8								
f		120		0.7		1.0		2.1				
		30 6		2.2 1.		2		ည				
	M10	06 09		1.8 1.4		2.3		5.0				
		0 120		4 1.2		1.8	ı	4.0			'	
-		30		3.2								S
	Σ	9		2.8		3.0		6.1				min aC
	M12	06		2.4							аć	cordin
r		120		2.2		2.4		4.9			cordi	g to A
	-	30		6.0					4 x h _{ef}	2 x h _{ef}	ng to	vnnex
	M16	6 09		5.2 4		6.3		12.0	4	· 4-	according to Annex 3	3; c _{mi}
	_	90 120		4.4		5.0		9.6			က	S _{min} according to Annex 3; c _{min} ≥ 300 mm.
-	\dashv					0		9				00 mn
	}	30 60		9.4 8.2		9.0		18.0				Ċ.
	M20	06 0		2 6.9				0				
		120		6.3		7.2		4. 4.				
L	_	30		13.6								
		09		5 11.8		11.0		25.5				
	M24	06	ī	3 10.0				10				
	-			6		ού						

MKT Wedge Anchor BZ plus

Characteristic values of tension load resistance under fire exposure

of European technical Approval In absence of other national regulations the partial safety factor for resistance under fire exposure $\gamma_{M,fi} = 1.0$ is recommended.

4

Characterstic values to shear loads under fire exposure in cracked and non-cracked concrete C20/25 to C50/60 Table 11:

														ŀ				l				
Anchor size:		₩			Ž	M10			M12	2		M16				M20				M24	4	
Fire resistance R duration [min]	0	06	30 60 90 120 30	30	09	06	120	30	09	60 90 120	30	09	. 06	120	30	09	06	120	30	09	90	120

Steel failure without lever arm:

			_			-				_	-		_										
Characteristic resistance	V _{Rk,s,fi} [kN]	1.6	1.5	1.6 1.5 1.2	1.0	1.0 2.6 2.5	2.5	2.1	2.0	3.8	3.8 3.6 3.5	5 3.4	1 7.(7.0 6.8	6.5	6.5 6.4 11 11 10 10 16	Ξ	=	10	10	16	15	15
Steel failure with lever arm:	ith lever a	i.i.]		-			ł													
Characteristic M ⁰ Rk,s,fi 1.7 1.6 1.2	M ⁰ Rk,s,fi	1.7	1 6	12	1.1	33	3.2 2.7	2.7	2.5	6.6	.6	7,70	47		4	5.9 5.6 5.4 5.3 15 14 14 13	29	28	27	26	50	48	47

	Α	
Characteristic	Concrete pryout failure:	In Equation (5.6) of ETAG 001, A
M ^T Rk.s.fi 1.7 1.6 1.2 1.1 3.3 3.2 2.7 2.5 5.9 5.6 5.4 5.3 15 14 14 13 29 28 27 26 50 50 [Nm]	t failure:	of ETAG
1.7		001,
9.1		Ann
1.2		lex C
1.1		, 5.2
3.3		.3.31
3.2		ihe k
2.7		-fact
2.5		or 2.(
5.9) and
5.6		the r
5.4 5		eleva
E.:		ınt va
15		Annex C, 5.2.3.3 the k-factor 2.0 and the relevant values of $N_{\text{Pk,c,fi}}^{0}$ of Table 10 have to be considered.
4		of N°
4		³k,c,fi O
13		ıf Tab
59		le 10
28		have
27		o to be
26		Suoo e
50		sidere
48		Ö.

46

The initial value $V^0_{Rkc,fl}$ of the characteristic resistance in concrete C20/25 to C50/60 under fire exposure may be determined by: Concrete edge failure:

 $V_{Pk,c,fl} = 0,20 \times V_{Pk,c} \text{ (R120)}$ $V_{Rk,c,fi}^0 = 0,25 \times V_{Rk,c}^0$ (R30, R 60, R90) with $V^0_{
m Bk,c}$ initial value of the characteristic resistance in cracked concrete C20/25 under normal temperature.

In absence of other national regulations the partial safety factor for resistance under fire exposure $\gamma_{M,fi}=1.0$ is recommended.

MKT Wedge Anchor BZ plus

Characteristic values of shear load resistance under fire exposure

Annex 7

of European technical Approval