



## European Technical Approval ETA-04/0005

English translation prepared by DIBt - Original version in German language

Handelsbezeichnung  
*Trade name*

maxit Dämmsystem PS/ - PS Silence  
maxit Dämmsystem PS Speedy/ - PS Silence Speedy

Zulassungsinhaber  
*Holder of approval*

Franken Maxit Mauermörtel GmbH & Co.  
Azendorf 63  
95359 Kasendorf  
DEUTSCHLAND

Zulassungsgegenstand  
und Verwendungszweck  
*Generic type and use  
of construction product*

Außenseitige Wärmedämm-Verbundsysteme mit Putzschicht zur  
Wärmedämmung von Gebäuden  
*External Thermal Insulation Composite Systems with rendering for the  
use as external insulation of building walls*

Geltungsdauer:  
*Validity:* vom  
*from*  
bis  
*to*

12 June 2013  
12 June 2018

Herstellwerk  
*Manufacturing plant*

Franken Maxit Mauermörtel GmbH & Co.  
Azendorf 63  
95359 Kasendorf  
DEUTSCHLAND

Diese Zulassung umfasst  
*This Approval contains*

18 Seiten einschließlich 1 Anhang  
*18 pages including 1 annex*

Diese Zulassung ersetzt  
*This Approval replaces*

ETA-04/0005 mit Geltungsdauer vom 17.05.2011 bis 21.12.2014  
*ETA-04/0005 with validity from 17.05.2011 to 21.12.2014*

## I LEGAL BASES AND GENERAL CONDITIONS

- 1 This European technical approval is issued by Deutsches Institut für Bautechnik in accordance with:
  - Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of Member States relating to construction products<sup>1</sup>, modified by Council Directive 93/68/EEC<sup>2</sup> and Regulation (EC) N° 1882/2003 of the European Parliament and of the Council<sup>3</sup>;
  - *Gesetz über das In-Verkehr-Bringen von und den freien Warenverkehr mit Bauprodukten zur Umsetzung der Richtlinie 89/106/EWG des Rates vom 21. Dezember 1988 zur Angleichung der Rechts- und Verwaltungsvorschriften der Mitgliedstaaten über Bauprodukte und anderer Rechtsakte der Europäischen Gemeinschaften (Bauproduktengesetz - BauPG) vom 28. April 1998<sup>4</sup>, as amended by Article 2 of the law of 8 November 2011<sup>5</sup>;*
  - Common Procedural Rules for Requesting, Preparing and the Granting of European technical approvals set out in the Annex to Commission Decision 94/23/EC<sup>6</sup>;
  - Guideline for European technical approval of "External Thermal Insulation Composite Systems with Rendering", ETAG 004, edition March 2000.
- 2 Deutsches Institut für Bautechnik is authorized to check whether the provisions of this European technical approval are met. Checking may take place in the manufacturing plant. Nevertheless, the responsibility for the conformity of the products to the European technical approval and for their fitness for the intended use remains with the holder of the European technical approval.
- 3 This European technical approval is not to be transferred to manufacturers or agents of manufacturers other than those indicated on page 1, or manufacturing plants other than those laid down in the context of this European technical approval.
- 4 This European technical approval may be withdrawn by Deutsches Institut für Bautechnik, in particular pursuant to information by the Commission according to Article 5(1) of Council Directive 89/106/EEC.
- 5 Reproduction of this European technical approval including transmission by electronic means shall be in full. However, partial reproduction can be made with the written consent of Deutsches Institut für Bautechnik. In this case partial reproduction has to be designated as such. Texts and drawings of advertising brochures shall not contradict or misuse the European technical approval.
- 6 The European technical approval is issued by the approval body in its official language. This version corresponds fully to the version circulated within EOTA. Translations into other languages have to be designated as such.

<sup>1</sup> Official Journal of the European Communities L 40, 11 February 1989, p. 12  
<sup>2</sup> Official Journal of the European Communities L 220, 30 August 1993, p. 1  
<sup>3</sup> Official Journal of the European Union L 284, 31 October 2003, p. 25  
<sup>4</sup> *Bundesgesetzblatt Teil I 1998*, p. 812  
<sup>5</sup> *Bundesgesetzblatt Teil I 2011*, p. 2178  
<sup>6</sup> Official Journal of the European Communities L 17, 20 January 1994, p. 34



	Components (see clause 2.3 for further description, characteristics and performances)	Coverage [kg/m <sup>2</sup> ]	Thickness [mm]
<b>Insulation material with associated method of fixing</b>	<ul style="list-style-type: none"> <li><b>Anchors for insulation product</b> all anchors with ETA according to ETAG 014<sup>7</sup> with characteristics defined in clause 2.3.2</li> </ul>		
<b>Base coat</b>	<b>maxit multi Kleber und Armierungsmörtel FM</b> <b>maxit multi Kleber und Armierungsmörtel E</b> <b>maxit multi Kleber und Armierungsmörtel PS</b> Identical with the equally named adhesives given above.	} about 8.0 (prepared)	Mean (dry): 6
<b>Glass fibre mesh</b>	<b>maxit Armierungsgewebe PS</b> Alkali- and slide-resistant glass fibre mesh with mass per unit area of about 165 g/m <sup>2</sup> and mesh size of about 4.0 mm x 4.0 mm.	–	–
<b>Key coat</b>	Ready to use pigmented acrylic-resin dispersion liquids: <b>maxit Aufbrennsperre</b> <b>maxit Aufbrennsperre weiß</b> <b>maxit Edelputz Haftgrund</b> For the compatibility with the finishing coats see below.	} 0.12 to 0.13 l/m <sup>2</sup>	– – –
<b>Finishing coat</b>	<b>To use with key coat "maxit Edelputz Haftgrund" if applicable:</b> <ul style="list-style-type: none"> <li>Ready to use paste - acrylic binder: <b>maxit spectra Kunstharzputz K / R**</b> (particle size 1.5 – 2 and 3 mm)</li> </ul> <b>To use with key coat "maxit Aufbrennsperre" or "maxit Aufbrennsperre weiß" if applicable:</b> <ul style="list-style-type: none"> <li>Ready to use paste - acrylosiloxane binder: <b>maxit silco Siliconharzputz K / R**</b> (particle size 1.5 – 2 and 3 mm)</li> <li>Ready to use paste - silicate binder: <b>maxit sil Silikatputz K / R**</b> (particle size 1.5 – 2 and 3 mm)</li> <li>Thin layered cement based powder requiring addition of about 27 % of water: <b>maxit ip color K / R**</b> (particle size 1 – 2 – 3 and 4 mm)</li> </ul>	2.0 to 4.0  2.0 to 4.0  2.0 to 4.0  2.0 to 6.0 (prepared)	} Regulated by particle size

	Components (see clause 2.3 for further description, characteristics and performances)	Coverage [kg/m <sup>2</sup> ]	Thickness [mm]
Finishing coat	<b>maxit ip color plus K / R**</b> (particle size 2 – 3 and 4 mm)	3.0 to 6.0 (prepared)	Regulated by particle size
	<b>maxit ip Leichtoberputz K / R**</b> (particle size 1.5 – 2 – 3 and 4 mm)	2.0 to 5.0 (prepared)	
	<ul style="list-style-type: none"> <li>Thick layered cement based powder requiring addition of about 20 % of water:</li> </ul> <b>maxit ip Edelkratzputz FM</b>	10 to 24 (prepared)	5 to 12
Ancillary material	Description in accordance with clause 3.2.2.5 of ETAG 004 and decorative coatings compatible with the ETICS to be applied to the finishing coat. Remains the responsibility of the ETA-holder.		
<p>* The instruction to the installer concerning the use of a key coat remains the responsibility of the ETA-holder.</p> <p>** K / R indicates different structures of the finishing coats.</p>			

## 1.2 Intended use

These ETICS are intended to be used as external insulation to the walls of buildings made of masonry (bricks, blocks, stones ...) or concrete (cast on site or as prefabricated panels) with and without rendering (Class A1 or A2 – s1,d0 according to EN 13501-1:2007). They shall be designed to give the wall to which they are applied satisfactory thermal insulation.

The ETICS are non load-bearing construction elements. They do not contribute directly to the stability of the wall on which they are installed, but they can contribute to durability by providing enhanced protection from the effects of weathering.

The ETICS can be used on new or existing (retrofit) vertical walls.

The ETICS are not intended to ensure the air tightness of the building structure.

The choice of the method of fixing depends on the characteristics of the substrate, which could need preparation (see clause 7.2.1 of ETAG 004) and on the national instructions.

The provisions made in this European technical approval (ETA) based upon the assumed intended working life of the ETICS of at least 25 years, provided that the conditions laid down in clauses 4.2, 5.1 and 5.2 for the packaging, transport, storage, installation as well as appropriate use, maintenance and repair are met. The indications given on the working life cannot be interpreted as a guarantee given by the manufacturer or the Approval Body, but should only be regarded as a means to choosing the appropriate products in relation to the expected, economically reasonable working life of the works.

## 2 Characteristics of products and methods of verification

### 2.1 General

The assessment of the fitness for use of the ETICS for the intended use according to the Essential Requirements was carried out in compliance with ETAG 004, "Guideline for European Technical Approval of External Thermal Insulation Composite Systems with rendering", edition March 2000 (called ETAG 004 in this ETA).

Characteristics (of the components as well as of the ETICS), not mentioned in this ETA nor in the annexe/s shall correspond to the respective values laid down in the technical documentation of this ETA.

## 2.2 Characteristics of the ETICS

### 2.2.1 Reaction to fire

Rendering system: Base coat with finishing coat indicated hereafter	Maximum declared organic content	Class according to EN 13501-1:2007
maxit spectra Kunstharzputz K / R	Base coat ≤ 2.6 % Finishing coat ≤ 6.8 %	B – s2,d0
maxit silco Siliconharzputz K / R		
maxit ip color K / R, maxit ip color plus K / R, maxit ip Leichtoberputz K / R, maxit ip Edelkratzputz FM	Base coat ≤ 2.6 % Finishing coat ≤ 1.9 %	
maxit sil Silikatputz K / R particles size 1.5 mm	Base coat ≤ 2.6 % Finishing coat ≤ 4.9 %	B – s1,d0
maxit sil Silikatputz K / R particles size 2 and 3 mm		F

#### Mounting and fixing

(for all end use applications given in clause 1.2 of the ETA)

The assessment of reaction to fire is based on tests with a maximum insulation layer thickness of 180 mm (testing according to EN 13823:2002 – SBI-test), resp. 60 mm (testing according to EN ISO 11925-2:2002) and a maximum insulation material (EPS) density of 25 kg/m<sup>3</sup> as well as rendering systems with two different types of binder (silicate based and organic based) each with the highest organic content.

The manufacturer of the tested EPS is Rygol Dämmstoffwerk Werner Rygol GmbH Co. KG, D-93351 Painten. EPS with higher density than tested or with other chemical composition or of an other manufacturer, which fulfils the requirements of clause 2.3.1 and is deposited with the DIBt, can be used if it fulfils the requirements of Class E according to EN 13501-1:2007 by testing specimens with a thickness of 10 mm and with the highest possible density.

For rendering systems with silicate based finishing coats the assessment of reaction to fire is based on tests with particle sizes of 1.5 (lowest thickness).

For rendering systems with organic based and cement based finishing coats the assessment of reaction to fire is based on tests with finishing coats with particle sizes of 1.5 and 3 mm (lowest and highest thickness) and with the highest organic content.

For the SBI-test the ETICS was mounted directly to a calcium silicate substrate (class A2 - s1,d0) according to EN 13238:2001 with a thickness of 10 mm.

For testing according to EN ISO 11925-2:2002 no substrate was used.

The installation of the ETICS was carried out by the approval holder following his design and installation instructions using a single mesh all over the test specimen.

The tests specimens were prefabricated and did not include any joints.

For the SBI-test the lateral edges were covered with the rendering system.

For testing according to EN ISO 11925-2:2002 the edges were not covered with the rendering system (cut edges). The tests were performed with surface flaming of the front side and edge flaming turned by 90°.

Anchors were not included in the tested ETICS as they have no influence on the test result.

Note:

A European reference fire scenario for facades has not been laid down. In some Member States, the classification of ETICS according to EN 13501-1:2007 might not be sufficient for the use in facades. An additional assessment of ETICS according to national provisions (e.g. on the basis of a large scale test) might be necessary to comply with Member State regulations, until the existing European classification system has been completed.

**2.2.2 Water absorption (capillarity test)**

Base coat	Water absorption after 1 h < 1 kg/m <sup>2</sup>	Water absorption after 24 h < 0.5 kg/m <sup>2</sup>
maxit multi Kleber und Armierungsmörtel FM	x	x
maxit multi Kleber und Armierungsmörtel E	x	x
maxit multi Kleber und Armierungsmörtel PS	x	x

Rendering system: Base coat with finishing coat indicated hereafter	Water absorption after 24 h	
	< 0.5 kg/m <sup>2</sup>	≥ 0.5 kg/m <sup>2</sup>
maxit spectra Kunstharzputz	x	
maxit silco Siliconharzputz	x	
maxit sil Silikatputz	x	
maxit ip color K / R, maxit ip color plus K / R, maxit ip Leichtoberputz K / R	x	
maxit ip Edelkratzputz FM	x	

**2.2.3 Hygrothermal behaviour**

Hygrothermal cycles have been performed on rigs with all base coats.

None of the following defects occur during the testing:

- blistering or peeling of any finishing
- failure or cracking associated with joints between insulation product boards or profiles fitted with the system
- detachment of render
- cracking allowing water penetration to the insulation layer

The ETICS are so assessed resistant to hygrothermal cycles.

**2.2.4 Freeze/thaw behaviour**

The water absorption of the base coat as well as the rendering system is less than 0.5 kg/m<sup>2</sup> after 24 hours for all configurations of the ETICS. The ETICS are so assessed as freeze/thaw resistant.



### 2.2.5 Impact resistance

The verified resistance to hard body impact results in the classification into categories listed below. The resistance to perforation has not to be verified, because of a total render thickness of not less than 6 mm.

finishing coat \ base coat	maxit multi Kleber und Armierungsmörtel FM	maxit multi Kleber und Armierungsmörtel E	maxit multi Kleber und Armierungsmörtel PS
maxit spectra Kunstharzputz	Category I		
maxit silco Siliconharzputz	Category I		
maxit sil Silikatputz	Category I		
maxit ip color K / R, maxit ip color plus K / R, maxit ip Leichtoberputz K / R	Category II	Category III	Category III
maxit ip Edelkratzputz FM	Category II		

### 2.2.6 Water vapour permeability

Rendering system: Base coat with finishing coat indicated hereafter (evaluated without decorative coating or key coat)	Equivalent air thickness $s_d$
maxit spectra Kunstharzputz	$\leq 1.0$ m (Test result obtained with a layer thickness of 3 mm: 0.2 m)
maxit silco Siliconharzputz	$\leq 1.0$ m (Test result obtained with a layer thickness of 3 mm: 0.2 m)
maxit sil Silikatputz	$\leq 1.0$ m (Test result obtained with a layer thickness of 3 mm: 0.1 m)
maxit ip color K / R, maxit ip color plus K / R, maxit ip Leichtoberputz K / R	$\leq 1.0$ m (Test result obtained with a layer thickness of 5 mm: 0.1 m)
maxit ip Edelkratzputz FM	$\leq 1.0$ m (Test result obtained with a layer thickness of 12 mm: 0.2 m)

### 2.2.7 Emission of dangerous substances or radiation

The ETICS complies with the provisions of Guidance Paper H ("A harmonized approach related to dangerous substances under the construction product directives Revision August 2002").

In addition to the specific clauses relating to dangerous substances contained in this ETA, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Directive, these requirements need also to be complied with, when and where they apply.



## 2.2.8 Safety in use

### 2.2.8.1 Bond strengths

Bond strength between base coat and insulation product (EPS)

Base coat	Conditioning		
	Initial state	After hygrothermal cycles on the rig	After freeze/thaw test
maxit multi Kleber und Armierungsmörtel FM	≥ 0.08 MPa	≥ 0.08 MPa	Test not required because freeze/thaw cycles not necessary
maxit multi Kleber und Armierungsmörtel E	≥ 0.08 MPa	≥ 0.08 MPa	
maxit multi Kleber und Armierungsmörtel PS	≥ 0.08 MPa	≥ 0.08 MPa	

Bond strength between adhesive and substrate resp. insulation product (EPS)

Adhesive	Substrate resp. insulation product	Conditioning		
		Initial state	2 d immersion in water + 2 h drying	2 d immersion in water + 7 d drying
maxit multi Baukleber	Concrete	≥ 0.25 MPa	≥ 0.08 MPa	≥ 0.25 MPa
	EPS	≥ 0.08 MPa	≥ 0.03 MPa	≥ 0.08 MPa
maxit multi Kleber und Armierungsmörtel FM	Concrete	≥ 0.25 MPa	≥ 0.08 MPa	≥ 0.25 MPa
	EPS	≥ 0.08 MPa	≥ 0.03 MPa <sup>8</sup>	≥ 0.08 MPa <sup>8</sup>
maxit multi Kleber und Armierungsmörtel E	Concrete	≥ 0.25 MPa	≥ 0.08 MPa	≥ 0.25 MPa
	EPS	≥ 0.08 MPa	≥ 0.03 MPa <sup>8</sup>	≥ 0.08 MPa <sup>8</sup>
maxit multi Kleber und Armierungsmörtel PS	Concrete	≥ 0.25 MPa	≥ 0.08 MPa	≥ 0.25 MPa
	EPS	≥ 0.08 MPa	≥ 0.03 MPa	≥ 0.08 MPa

Bonded surface:

For bonded ETICS the calculated minimal bonded surface area, according to ETAG 004, clause 6.1.4.1.3 is 40 %.

### 2.2.8.2 Fixing strength (displacement test)

Test not required because the ETICS fulfils the following criteria to clause 5.1.4.2 of ETAG 004:

- the bonded area exceeds 20 %
- $E \cdot d < 50\,000 \text{ N/mm}$   
(E: modulus of elasticity of the base coat – d: mean dried thickness of the base coat)

### 2.2.8.3 Wind load resistance

Safety in use of mechanically fixed ETICS using anchors

The following failure loads only apply to the listed combination (EPS panel's characteristics) / (anchor plate's characteristics) and the characteristics of the insulation product given in clause 2.3.1.

<sup>8</sup>

According to the EOTA GD 004 existing data was used after EOTA consensus has been reached that the deviations of the test methods use from the EOTA test methods are not relevant or the results are on the safe side.

Apply to all anchors listed in the Table in clause 1.1 mounted on the insulation panels surface				
Characteristics of the EPS (standard EPS)	Thickness		≥ 60 mm	
	Tensile strength perpendicular to the faces		≥ 100 kPa	
	Shear modulus		≥ 1.0 N/mm <sup>2</sup>	
Plate diameter of anchor			Ø 60 mm	Ø 90 mm
Failure loads [N]	Anchors not placed at the panel joints (Static Foam Block Test)	R <sub>panel</sub>	Minimal: 510 Average: 520	Minimal: 720 Average: 730
	Anchors placed at the panel joints (Pull-through test)	R <sub>joint</sub>	Minimal: 400 Average: 430	Minimal: 430 Average: 470

Apply to all anchors listed in the Table in clause 1.1 mounted on the insulation panels surface				
Characteristics of the EPS (elastified EPS)	Thickness		≥ 60 mm	
	Tensile strength perpendicular to the faces		≥ 80 kPa	
	Shear modulus		≥ 0.3 N/mm <sup>2</sup>	
Plate diameter of anchor			Ø 60 mm	
Failure loads [N]	Anchors not placed at the panel joints (Static Foam Block Test)	R <sub>panel</sub>	Minimal: 350 Average: 360	
	Anchors placed at the panel joints (Pull-through test)	R <sub>joint</sub>	Minimal: 300 Average: 310	

The failure loads specified above only apply to the following anchors with a plate diameter of anchor of 60 mm with deep mounting under the following conditions of installation:

Anchor	Thickness of the EPS [d]	Conditions of installation *
ejotherm STR U ejotherm STR U 2G (ETA-04/0023)	100 mm > d ≥ 80 mm (for standard and elastified EPS)	– Maximum installation depth of the anchor plate: 15 mm (≙ thickness of insulation cover) – Maximum depth of die: 5 mm
	≥ 100 mm (for standard and elastified EPS)	– Maximum installation depth of the anchor plate: 15 mm (≙ thickness of insulation cover) – Maximum depth of die: 20 mm
IsoFux NDT8LZ (ETA-05/0080)	≥ 80 mm (for standard and elastified EPS)	– Maximum depth of countersink: 20 mm
TERMOZ 8 SV (ETA-06/0180)	≥ 80 mm (for standard EPS only)	– Maximum installation depth of the anchor plate: 15 mm (≙ thickness of insulation cover)

\* According to the appropriate ETA of anchor

The wind load resistance R<sub>d</sub> of the ETICS is calculated as follows:

$$R_d = \frac{R_{panel} \cdot n_{panel} + R_{joint} \cdot n_{joint}}{\gamma}$$

- n<sub>panel</sub>: number (per m<sup>2</sup>) of anchors not placed at the panel joints  
n<sub>joint</sub>: number (per m<sup>2</sup>) of anchors placed at the panel joint  
γ: national safety factor

### 2.2.9 Thermal resistance

The nominal value of the additional thermal resistance  $R$  provided by the ETICS to the substrate wall is calculated in accordance with EN ISO 6946:2007 from the nominal value of the insulation product's thermal resistance  $R_D$  given accompanied to the CE marking and from the thermal resistance of the rendering system  $R_{render}$  which is about  $0.02 \text{ (m}^2 \cdot \text{K)/W}$ .

$$R = R_D + R_{render}$$

The thermal bridges caused by anchors increase the thermal transmittance  $U$ . This influence had to take into account according to EN ISO 6946:2007.

$$U_c = U + \chi_p \cdot n$$

Corrected thermal transmittance

where:  $\chi_p \cdot n$  influence of thermal bridges

$n$  number of anchors per  $\text{m}^2$

$\chi_p$  local influence of thermal bridge caused by an anchor. The values listed below can be taken into account, if not specified in the anchor's technical approval

$\chi_p = 0.004 \text{ W/K}$  for anchors with a galvanized steel screw with the head covered by a plastic material

$\chi_p = 0.002 \text{ W/K}$  for anchors with a stainless steel screw with the head covered by plastic material, and for anchors with an air gap at the head of the screw

### 2.2.10 Aspects of durability and serviceability

#### 2.2.10.1 Experience on site of the ETICS

In addition to the hygrothermal cycle tests on the rig (see clause 2.2.3) an extensive experience on site has been assessed by the DIBt in Germany.

#### 2.2.10.2 Bond strength after ageing

The rendering system (base coat with each finishing coat indicated in the Table in clause 1.1) has proofed its bond strength after ageing by experience on site.

### 2.3 Characteristics of the components

Detailed information on the chemical composition and other identifying characteristics of the components, following Annex C of ETAG 004 have been deposited with the DIBt.

Further information can be observed from the product data sheets, which are part of the technical documentation for this ETA.

#### 2.3.1 Thermal insulation product

Factory-prefabricated, uncoated panels made of expanded polystyrene (EPS) to EN 13163:2008 shall be used, having the description and characteristics defined in the Table below.

Description and characteristics	For bonded ETICS	For mechanically with anchors and supplementary adhesive fixed ETICS
Reaction to fire; EN 13501-1:2007	Class E*	
Thermal resistance $[(\text{m}^2 \cdot \text{K)/W}]$	Defined in the CE marking in reference to EN 13163:2008	

Description and characteristics	For bonded ETICS	For mechanically with anchors and supplementary adhesive fixed ETICS
<b>Tolerances</b>		
Length; EN 822:1994	± 0.6 % or ± 3 mm whichever gives the greatest numerical tolerance (class L1 or class L2)	
Width [mm]; EN 822:1994	± 2 (class W2)	
Thickness [mm]; EN 823:1994	± 1 (class T2)	
Squareness [mm/m]; EN 824:1994	± 2 (class S2)	
Flatness [mm/m]; EN 825:1994	5 (class P4)	
<b>Dimensional stability under</b>		
- laboratory conditions [%]; EN 1603:1996	± 0.2 (class DS(N)2)	
- specified temperature and humidity conditions [%]; EN 1604:1996	2 (level DS(70,-)2 or level DS(70,-)1)	
Water absorption (long term partial immersion) [kg/m <sup>2</sup> ]; EN 12087:1997	$W_{ip} \leq 0.5$	
Water vapour diffusion resistance factor; EN 12086:1997	$\mu = 20 - 70$	
Tensile strength perpendicular to the faces in dry conditions** [kPa]; EN 1607:1996		
- standard EPS	$\sigma_{mt} \geq 80$	$\sigma_{mt} \geq 100$
- elastified EPS***	$\sigma_{mt} \geq 80$	$\sigma_{mt} \geq 80$
Bending strength** [kPa]; EN 12089:1997	$\sigma_b \geq 50$	
Apparent density [kg/m <sup>3</sup> ]; EN 1602:1996	$\rho_a \leq 30$	
Shear strength** [kPa]; EN 12090:1997	$20 \leq f_{tk} \leq 170$	
Shear modulus [MPa]; EN 12090:1997		
- standard EPS	$1.0 \leq G_m \leq 3.8$	
- elastified EPS***	$0.3 \leq G_m \leq 1.0$	
Testing of characteristics see EN 13163:2008.		
* See the conditions of clause 2.2.1 for the EPS.		
** Minimal value of all single values		
*** Elastified EPS is made from standard EPS by short time high load pressing to reduce the dynamic stiffness. The protection against noise of the entire wall is improved by the use of elastified EPS related to an ETICS with standard EPS.		

Thermal insulation materials for mechanically fixed ETICS with profiles must circumferentially at the edges, 24 mm from the inner surface, get an approx. 3 mm wide and 13 to 18 mm deep groove cut-in at the factory.

### 2.3.2 Anchors

All anchors with ETA according to ETAG 014<sup>7</sup> with characteristics having the description below shall be used in the mechanically fixed ETICS:

- plate diameter of anchor  $\geq 60$  mm resp.  $\geq 90$  mm
- plate stiffness  $\geq 0.3$  kN/mm
- load resistance of the anchor plate  $\geq 1.0$  kN

These characteristics and the characteristic tension resistance of the anchors shall be taken from the corresponding ETA.

### 2.3.3 Render (base coat)

The average value of crack width of the base coats reinforced with the glass fibre mesh "maxit Armierungsgewebe PS" measured at a render strain value of 1 % is:

Base coat	Average value of crack width $w_{m(1\%)}$
maxit multi Kleber und Armierungsmörtel FM	0.08 mm
maxit multi Kleber und Armierungsmörtel E	0.10 mm
maxit multi Kleber und Armierungsmörtel PS	0.10 mm

### 2.3.4 Reinforcement (glass fibre mesh)

Characteristics (alkali resistance): Pass

	"maxit Armierungsgewebe PS"	
	Warp	Weft
Residual strength after ageing [N/mm]	$\geq 20$	$\geq 20$
Relative residual resistance after ageing in % of the strength in the as-delivered state	$\geq 60$	$\geq 60$

## 3 Evaluation and attestation of conformity and CE-marking

### 3.1 System of attestation of conformity

According to the decision 97/556/EC of the European Commission<sup>9</sup> amended by 2001/596/EC<sup>10</sup> system 1 or 2+ of the attestation of conformity applies depending on reaction to fire.

Considering Class B for reaction to fire of the ETICS, the systems of attestation of conformity are system 1 regarding reaction to fire characteristic and system 2+ regarding other characteristics than reaction to fire.

These systems of attestation of conformity are defined as follows:

System 1: Certification of the conformity of the product by a notified certification body on the basis of:

- (a) Tasks for the manufacturer:
  - (1) factory production control;
  - (2) further testing of samples taken at the factory by the manufacturer in accordance with a prescribed test plan;

<sup>9</sup>  
<sup>10</sup>

Official Journal of the European Communities/Union L229/14 of 20.08.1997  
Official Journal of the European Communities/Union L 209/33 of 02.08.2001

- (b) Tasks for the notified body:
- (3) initial type-testing of the product;
  - (4) initial inspection of factory and of factory production control;
  - (5) continuous surveillance, assessment and approval of factory production control.

System 2+: Declaration of conformity of the product by the manufacturer on the basis of:

- (a) Tasks for the manufacturer:
- (1) initial type-testing of the product;
  - (2) factory production control;
  - (3) testing of samples taken at the factory in accordance with a prescribed test plan.
- (b) Tasks for the notified body:
- (4) certification of factory production control on the basis of:
    - initial inspection of factory and of factory production control;
    - continuous surveillance, assessment and approval of factory production control.

## 3.2 Responsibilities

### 3.2.1 Tasks for the manufacturer

#### 3.2.1.1 Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall insure that the ETICS and the components are in conformity with this ETA.

The manufacturer shall only use raw materials stated in the technical documentation of this ETA. The incoming raw materials are subjected to verifications by the manufacturer before acceptance.

The factory production control shall be in accordance with the "Control plan"<sup>11</sup> which is part of the technical documentation of this ETA. The "Control plan"<sup>11</sup> has been agreed between the manufacturer and the DIBt and is laid down in the context of the factory production control system operated by the manufacturer and deposited with the DIBt.

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the "Control plan"<sup>11</sup>. The records include at least the following information:

- designation of the product, the basic materials and components;
- type of control or testing;
- date of manufacture of the product and date of testing of the product or basic materials or components;
- result of control and testing and, if appropriate, comparison with requirements;
- signature of person responsible for factory production control.

The records shall be presented to the notified body involved in continuous surveillance. On request they shall be presented to the DIBt.

<sup>11</sup> The "Control plan" is a confidential part of the European technical approval and only handed over to the notified body involved in the procedure of attestation of conformity. See section 3.2.2.

### 3.2.1.2 Other tasks for the manufacturer

For initial type-testing of the ETICS and the components regarding other characteristics than reaction to fire the results of the tests performed as part of the assessment for the ETA shall be used unless there are changes in the production line or plant. In such cases the necessary initial type-testing has to be agreed with the DIBt.

The manufacturer shall, on the basis of a contract, involve a body which is notified for the tasks referred to in clause 3.1 in the field of ETICS in order to undertake the actions laid down in clause 3.2.2. For this purpose, the "Control plan"<sup>11</sup> referred to in clauses 3.2.1.1 and 3.2.2 shall be handed over by the manufacturer to the notified bodies involved.

The manufacturer shall make a declaration of conformity, stating that the ETICS is in conformity with the provisions of ETA-04/0005 issued on 12 June 2013.

### 3.2.2 Tasks for the notified bodies

The notified body shall perform the

- initial type-testing of the ETICS and the components regarding reaction to fire characteristic,
- initial inspection of factory and of factory production control,
- continuous surveillance, assessment and approval of factory production control,

in accordance with the provisions laid down in the "Control plan"<sup>11</sup>.

The notified body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The notified certification body involved by the manufacturer shall issue an EC certificate of conformity of the ETICS which includes the certification of factory production control stating the conformity with the provisions of this ETA.

In cases where the provisions of the ETA and its "Control plan"<sup>11</sup> are no longer fulfilled the notified certification body shall withdraw the certificate of conformity and inform the DIBt without delay.

## 3.3 Marking

### 3.3.1 CE marking

The CE marking shall be affixed on the accompanying commercial document. The letters "CE" shall be followed by the identification number of the notified certification body and be accompanied by the following additional information:

- the name and address of the ETA-holder (legal entity responsible for the manufacture),
- the last two digits of the year in which the CE marking was affixed,
- the number of the EC certificate of conformity for the ETICS,
- the number of the ETA,
- the number of the ETAG,
- the ETICS trade name.

### 3.3.2 Additional marking

The respective trade name of the individual components of the ETICS shall be given on the packaging.

In addition to the trade name the following information shall be given in the accompanying commercial document and/or on the packaging of the thermal insulation product:

- minimum value of the tensile strength perpendicular to the faces of the insulation product,
- shear modulus of the insulation product.



#### **4 Assumptions under which the fitness of the product for the intended use was favourably assessed**

##### **4.1 Manufacturing**

The composition and manufacturing process used for the components of the ETICS shall comply with those on which the approval tests were based. Composition and manufacturing process are deposited at the DIBt.

The ETA is issued for the ETICS on the basis of agreed data/information, deposited with the DIBt, which identifies the ETICS that has been assessed and judged. Changes to the ETICS or the components or their production process, which could result in this deposited data/information being incorrect, should be notified to the DIBt before the changes are introduced. DIBt will decide whether or not such changes affect the approval and consequently the validity of the CE marking on the basis of the approval and if so whether further assessment or alterations to the approval shall be necessary.

##### **4.2 Installation, design and execution**

###### **4.2.1 General**

The wall on which the ETICS is applied shall be sufficiently stable and airtight. Its stiffness shall be large enough to ensure that the ETICS is not subjected to deformations, which could lead to damage.

The requirements given in ETAG 004, chapter 7, have to be considered.

###### **4.2.2 Installation**

The ETICS is installed on site. The approval holder is obliged to instruct all those entrusted with the design and execution of the ETICS about the specific conditions of this ETA and all other details necessary for perfect execution.

Only the components whose trade name is given in clause 1.1 and which have the characteristics according to clause 2.3 may be used for the ETICS.

###### **4.2.3 Design**

###### **4.2.3.1 Requirements for the substrate**

As to the requirements for the substrate and its preparation, ETAG 004, clause 7.2.1 applies.

The substrate for mechanically fixed systems should have a sufficient resistance for the use of anchors according to clause 2.3.2. The conditions of the ETA for the anchor concerned apply.

###### **4.2.3.2 Resistance to wind load**

Judging of sufficient resistance to wind load should be on the basis of the resistance of the fixings according to clause 2.2.8.3 and of the characteristic tension resistance of the used anchor according to clause 2.3.2. Taking into account the national safety factors the design values of resistance are determined. The smaller one of the design resistances of the ETICS ( $R_d$ ) and of the anchor ( $N_{Rd}$ ) is decisive.

The determined design wind load suction  $S_d$  (taking into account the national safety factors) is compared with the design resistance.

###### **4.2.4 Execution**

The manufacturer's design and installation instructions, which are part of the technical documentation for this ETA, shall be observed with respect to the installation of the ETICS and drying times of rendering products.

## 5 Indications to the manufacturer

### 5.1 Packaging, transport and storage

Packaging of the components has to be such that they are protected against moisture during transport and storage, unless other measures are foreseen by the manufacturer for this purpose.


The components are to be protected against damage.

### 5.2 Use, maintenance, repair

To the indications on use, maintenance and repair ETAG 004, clause 7.3 applies.

Dirk Brandenburger  
Head of Department

*beglaubigt:*  
Wachner



Electronic copy of the ETA by DIBt: ETA-04/0005

maxit Dämmsystem PS/ - PS Silence  
maxit Dämmsystem PS Speedy/ - PS Silence Speedy

Surface structure of insulation panels used in  
"maxit Dämmsystem PS Speedy/ - PS Silence Speedy"

Annex 1