

## European Technical Approval ETA-05/0023

English translation prepared by DIBt - Original version in German language

Handelsbezeichnung <i>Trade name</i>	Chemofast Injektionssystem STV / ALV <i>Chemofast Injection System STV / ALV</i>
Zulassungsinhaber <i>Holder of approval</i>	CHEMOFAST Anchoring GmbH Hanns-Martin-Schleyer-Straße 23 47877 Willich DEUTSCHLAND
Zulassungsgegenstand und Verwendungszweck <i>Generic type and use of construction product</i>	Verbunddübel mit Ankerstange in den Größen M10, M12 und M16 zur Verankerung im ungerissenen Beton <i>Bonded anchor with anchor rod of sizes M10, M12 and M16 for use in non-cracked concrete</i>
Geltungsdauer: <i>Validity:</i>	vom <i>from</i> bis <i>to</i> 9 April 2013 9 April 2018
Herstellwerk <i>Manufacturing plant</i>	CHEMOFAST Anchoring GmbH

Diese Zulassung umfasst  
*This Approval contains*

16 Seiten einschließlich 7 Anhänge  
*16 pages including 7 annexes*

Diese Zulassung ersetzt  
*This Approval replaces*

ETA-05/0023 mit Geltungsdauer vom 08.03.2010 bis 25.02.2015  
*ETA-05/0023 with validity from 08.03.2010 to 25.02.2015*

## I LEGAL BASES AND GENERAL CONDITIONS

- 1 This European technical approval is issued by Deutsches Institut für Bautechnik in accordance with:
  - Council Directive 89/106/EEC of 21 December 1988 on the approximation of laws, regulations and administrative provisions of Member States relating to construction products<sup>1</sup>, modified by Council Directive 93/68/EEC<sup>2</sup> and Regulation (EC) N° 1882/2003 of the European Parliament and of the Council<sup>3</sup>;
  - *Gesetz über das In-Verkehr-Bringen von und den freien Warenverkehr mit Bauprodukten zur Umsetzung der Richtlinie 89/106/EWG des Rates vom 21. Dezember 1988 zur Angleichung der Rechts- und Verwaltungsvorschriften der Mitgliedstaaten über Bauprodukte und anderer Rechtsakte der Europäischen Gemeinschaften (Bauproduktengesetz - BauPG) vom 28. April 1998<sup>4</sup>, as amended by Article 2 of the law of 8 November 2011<sup>5</sup>;*
  - Common Procedural Rules for Requesting, Preparing and the Granting of European technical approvals set out in the Annex to Commission Decision 94/23/EC<sup>6</sup>;
  - Guideline for European technical approval of "Metal anchors for use in concrete - Part 5: Bonded anchors", ETAG 001-05.
- 2 Deutsches Institut für Bautechnik is authorized to check whether the provisions of this European technical approval are met. Checking may take place in the manufacturing plant. Nevertheless, the responsibility for the conformity of the products to the European technical approval and for their fitness for the intended use remains with the holder of the European technical approval.
- 3 This European technical approval is not to be transferred to manufacturers or agents of manufacturers other than those indicated on page 1, or manufacturing plants other than those indicated on page 1 of this European technical approval.
- 4 This European technical approval may be withdrawn by Deutsches Institut für Bautechnik, in particular pursuant to information by the Commission according to Article 5(1) of Council Directive 89/106/EEC.
- 5 Reproduction of this European technical approval including transmission by electronic means shall be in full. However, partial reproduction can be made with the written consent of Deutsches Institut für Bautechnik. In this case partial reproduction has to be designated as such. Texts and drawings of advertising brochures shall not contradict or misuse the European technical approval.
- 6 The European technical approval is issued by the approval body in its official language. This version corresponds fully to the version circulated within EOTA. Translations into other languages have to be designated as such.

<sup>1</sup> Official Journal of the European Communities L 40, 11 February 1989, p. 12  
<sup>2</sup> Official Journal of the European Communities L 220, 30 August 1993, p. 1  
<sup>3</sup> Official Journal of the European Union L 284, 31 October 2003, p. 25  
<sup>4</sup> *Bundesgesetzblatt Teil I 1998*, p. 812  
<sup>5</sup> *Bundesgesetzblatt Teil I 2011*, p. 2178  
<sup>6</sup> Official Journal of the European Communities L 17, 20 January 1994, p. 34

## II SPECIFIC CONDITIONS OF THE EUROPEAN TECHNICAL APPROVAL

### 1 Definition of product and intended use

#### 1.1 Definition of the construction product

The Chemofast Injection system STV / ALV with anchor rod is a bonded anchor consisting of a mortar cartridge with Chemofast Injection mortar "STV / ALV" or "STV / ALV Express" and a steel element. The steel element (including nut and washer) is a commercial threaded rod according to Annex 3 in the range of M10, M12 and M16 made of galvanised steel, hot-dip galvanised steel, stainless steel or made of high corrosion resistant steel.

The anchor rod is anchored via the bond between anchor rod, chemical mortar and concrete.

An illustration of the product and intended use is given in Annex 1.

#### 1.2 Intended use

The anchor is intended to be used for anchorages for which requirements for mechanical resistance and stability and safety in use in the sense of the Essential Requirements 1 and 4 of Council Directive 89/106 EEC shall be fulfilled and failure of anchorages made with these products would cause risk to human life and/or lead to considerable economic consequences. Safety in case of fire (Essential Requirement 2) is not covered in this European technical approval. The anchor is to be used only for anchorages subject to static or quasi-static loading in reinforced or unreinforced normal weight concrete of strength classes C20/25 at minimum and C50/60 at most according to EN 206:2000-12.

The anchor may be anchored in non-cracked concrete only.

It may be installed in dry or wet concrete. It must not be installed in flooded holes.

Overhead installation is not admissible.

The anchor may be used in the following temperature ranges:

Temperature range I:	-40 °C to +80 °C	(max short term temperature +80 °C and max long term temperature +50 °C)
Temperature range II:	-40 °C to +120 °C	(max short term temperature +120 °C and max long term temperature +72 °C)

#### Elements made of zinc coated steel:

The elements made of zinc plated or hot-dip galvanised steel may only be used in structures subject to dry internal conditions.

#### Elements made of stainless steel:

The elements made of stainless steel 1.4401, 1.4404 or 1.4571 may be used in structures subject to dry internal conditions and also in structures subject to external atmospheric exposure (including industrial and marine environment), or exposure in permanently damp internal conditions, if no particular aggressive conditions exist. Such particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

Elements made of high corrosion resistant steel:

The elements made of high corrosion resistant steel 1.4529 or 1.4565 may be used in structures subject to dry internal conditions and also in structures subject to external atmospheric exposure, in permanently damp internal conditions or in other particular aggressive conditions. Such particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

The provisions made in this European technical approval are based on an assumed working life of the anchor of 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

## 2 Characteristics of product and methods of verification

### 2.1 Characteristics of product

The anchor corresponds to the drawings and provisions given in Annexes 1 to 4. The characteristic material values, dimensions and tolerances of the anchor not indicated in Annexes 1 to 4 shall correspond to the respective values laid down in the technical documentation<sup>7</sup> of this European technical approval.

The characteristic values for the design of anchorages are given in Annexes 6 and 7.

Each mortar cartridge shall be marked with the imprint "STV / ALV" or "STV / ALV Express", the size of the cartridge, processing notes, charge code, storage-life, hazard code and curing- and processing time in accordance with Annex 4.

The two components of the Chemofast Injection Mortar "STV / ALV" or "STV / ALV Express" are delivered in unmixed condition in mortar cartridges of 150 ml, 280 ml, 300 ml, 330 ml, 380 ml or 410 ml (coaxial type), 235 ml or 345 ml (side-by-side type) or 165 ml or 300 ml (Foil tube type) according to Annex 4.

### 2.2 Methods of verification

The assessment of fitness of the anchor for the intended use in relation to the requirements for mechanical resistance and stability and safety in use in the sense of the Essential Requirements 1 and 4 has been made in accordance with the "Guideline for European technical approval of Metal Anchors for Use in Concrete", Part 1 "Anchors in general" and Part 5 "Bonded anchors", on the basis of Option 7.

In addition to the specific clauses relating to dangerous substances contained in this European technical approval, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Construction Products Directive, these requirements need also to be complied with, when and where they apply.

<sup>7</sup> The technical documentation of this European technical approval is deposited at the Deutsches Institut für Bautechnik and, as far as relevant for the tasks of the approved bodies involved in the attestation of conformity procedure, is handed over to the approved bodies.

### 3 Evaluation and attestation of conformity and CE marking

#### 3.1 System of attestation of conformity

According to the decision 96/582/EG of the European Commission<sup>8</sup> the system 2(i) (referred to as System 1) of attestation of conformity applies.

This system of attestation of conformity is defined as follows:

System 1: Certification of the conformity of the product by an approved certification body on the basis of:

(a) Tasks for the manufacturer:

- (1) factory production control;
- (2) further testing of samples taken at the factory by the manufacturer in accordance with a control plan;

(b) Tasks for the approved body:

- (3) initial type-testing of the product;
- (4) initial inspection of factory and of factory production control;
- (5) continuous surveillance, assessment and approval of factory production control.

Note: Approved bodies are also referred to as "notified bodies".

#### 3.2 Responsibilities

##### 3.2.1 Tasks of the manufacturer

###### 3.2.1.1 Factory production control

The manufacturer shall exercise permanent internal control of production. All the elements, requirements and provisions adopted by the manufacturer shall be documented in a systematic manner in the form of written policies and procedures, including records of results performed. This production control system shall insure that the product is in conformity with this European technical approval.

The manufacturer may only use initial/raw/constituent materials stated in the technical documentation of this European technical approval.

The factory production control shall be in accordance with the control plan which is part of the technical documentation of this European technical approval. The control plan is laid down in the context of the factory production control system operated by the manufacturer and deposited at Deutsches Institut für Bautechnik.<sup>9</sup>

The results of factory production control shall be recorded and evaluated in accordance with the provisions of the control plan.

###### 3.2.1.2 Other tasks of manufacturer

The manufacturer shall, on the basis of a contract, involve a body which is approved for the tasks referred to in section 3.1 in the field of anchors in order to undertake the actions laid down in section 3.2.2. For this purpose, the control plan referred to in sections 3.2.1.1 and 3.2.2 shall be handed over by the manufacturer to the approved body involved.

The manufacturer shall make a declaration of conformity, stating that the construction product is in conformity with the provisions of this European technical approval.

<sup>8</sup> Official Journal of the European Communities L 254 of 08.10.1996

<sup>9</sup> The control plan is a confidential part of the European technical approval and only handed over to the approved body involved in the procedure of attestation of conformity. See section 3.2.2.

### 3.2.2 Tasks of approved bodies

The approved body shall perform the following tasks in accordance with the provisions laid down in the control plan:

- initial type-testing of the product,
- initial inspection of factory and of factory production control,
- continuous surveillance, assessment and approval of factory production control.

The approved body shall retain the essential points of its actions referred to above and state the results obtained and conclusions drawn in a written report.

The approved certification body involved by the manufacturer shall issue an EC certificate of conformity of the product stating the conformity with the provisions of this European technical approval.

In cases where the provisions of the European technical approval and its control plan are no longer fulfilled the certification body shall withdraw the certificate of conformity and inform Deutsches Institut für Bautechnik without delay.

### 3.3 CE marking

The CE marking shall be affixed on each packaging of anchors. The letters "CE" shall be followed by the identification number of the approved certification body, where relevant, and be accompanied by the following additional information:

- the name and address of the producer (legal entity responsible for the manufacturer),
- the last two digits of the year in which the CE marking was affixed,
- the number of the EC certificate of conformity for the product,
- the number of the European technical approval,
- the number of the guideline for European technical approval,
- use category (ETAG 001-1, Option 7),
- size.

## 4 Assumptions under which the fitness of the product for the intended use was favourably assessed

### 4.1 Manufacturing

The European technical approval is issued for the product on the basis of agreed data/information, deposited with Deutsches Institut für Bautechnik, which identifies the product that has been assessed and judged. Changes to the product or production process, which could result in this deposited data/information being incorrect, should be notified to Deutsches Institut für Bautechnik before the changes are introduced. Deutsches Institut für Bautechnik will decide whether or not such changes affect the approval and consequently the validity of the CE marking on the basis of the approval and if so whether further assessment or alterations to the approval shall be necessary.

#### 4.2 Design of anchorages

The fitness of the anchor for the intended use is given under the following conditions:

The anchorages are designed in accordance with the "Guideline for European technical approval of Metal Anchors for Use in Concrete", Annex C, Method A, for bonded anchors under the responsibility of an engineer experienced in anchorages and concrete work.

For the verifications given below according to Annex C the following shall be observed:

- For the verification 'concrete cone failure' (clause 5.2.2.4, Annex C of the Guideline)  $N_{Rk,c}$  shall be determined according to (1) and (2): The smaller of the values according to (1) and (2) is decisive.

- $N_{Rk,c}$  according to equation (5.2), Annex C of the Guideline

where:  $N_{Rk,c}^0$  according to Annex 6

$S_{cr,N}$  according to Annex 6

$C_{cr,N}$  according to Annex 6

$\Psi_{ucr,N} = 1,0$

In special cases according to clause 5.2.2.4 g, Annex C of the Guideline the method given there is valid. However, the value  $N_{Rk,c}^0$  shall be calculated according to the following equation:

$$N_{Rk,c}^0 = N_{Rk,c}^0 \text{ (Annex 6)} \times \frac{h'_{ef}}{h_{ef}}$$

- $N_{Rk,c}$  according to equation (5.2), Annex C of the Guideline

where:  $N_{Rk,c}^0 = 0,75 \times 15,5 \times h_{ef}^{1,5} \times f_{ck,cube}^{0,5}$

$S_{cr,N} = 3 h_{ef}$

$C_{cr,N} = 1,5 h_{ef}$

$\Psi_{ucr,N} = 1,0$

- For the verification 'splitting failure due to loading' (clause 5.2.2.6, Annex C of the Guideline)  $N_{Rk,sp}$  shall be determined according to (3).

- $N_{Rk,sp}$  according to equation (5.3), Annex C of the Guideline

where:  $N_{Rk,c}^0$  according to Annex 6

$S_{cr,sp}$  according to Annex 6

$C_{cr,sp}$  according to Annex 6

$\Psi_{ucr,N} = 1,0$

$\Psi_{h,sp} = 1,0$

- For the verification 'concrete pryout failure' (clause 5.2.3.3, Annex C of the Guideline)  $N_{Rk,c}$  for equation (5.6), Annex C of the Guideline, shall be determined according to (1).

Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored.

The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).



### 4.3 Installation of anchors

The fitness for use of the anchor can only be assumed if the anchor is installed as follows:

- anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site,
- use of the anchor only as supplied by the manufacturer without exchanging the components of an anchor, commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:
  - Material and mechanical properties according to Annex 2,
  - Confirmation of material and mechanical properties by inspection certificate according to EN 10204:2004,
  - Identifying mark of the producer and marking of embedment depth according to Annex 2.
- anchor installation in accordance with the manufacturer's specifications and drawings using the tools indicated in the technical documentation of this European technical approval,
- checks before placing the anchor to ensure that the strength class of the concrete in which the anchor is to be placed is in the range given and is not lower than that of the concrete to which the characteristic loads apply,
- check of concrete being well compacted, e.g. without significant voids,
- Edge distance and spacing not less than the specified values without minus tolerances,
- positioning of the drill holes without damaging the reinforcement,
- in case of aborted drill hole: the drill hole shall be filled with mortar,
- cleaning the drill hole by at least 4x blowing / 4x brushing / 4x blowing according to Annex 5,
- the anchor must not be installed in flooded holes,
- keeping the effective anchorage depth,
- the anchor component installation temperature shall be at least +5 °C,
- the temperature of the concrete during installation and curing of the chemical mortar must not fall below -5 °C;
- the curing time according to Annex 3 shall be observed before the anchor may be loaded,
- after the curing time fixing the member to be anchored by using a calibrated torque wrench by not exceeding the torque moment given in Annex 5.



## 5 Indications to the manufacturer

### 5.1 Responsibility of the manufacturer

The manufacturer is responsible to ensure that the information on the specific conditions according to 1 and 2 including Annexes referred to as well as sections 4.2, 4.3 and 5.2 is given to those who are concerned. This information may be made by reproduction of the respective parts of the European technical approval. In addition all installation data shall be shown clearly on the package and/or on an enclosed instruction sheet, preferably using illustration(s).

The minimum data required are:

- drill bit diameter,
- hole depth,
- minimum effective anchorage depth,
- information on the installation procedure, including cleaning of the hole with the cleaning equipments, preferably by means of an illustration,
- anchor component installation temperature,
- ambient temperature of the concrete during installation of the anchor,
- admissible processing time (open time) of the mortar,
- curing time until the anchor may be loaded as a function of the ambient temperature in the concrete during installation,
- torque moment,
- identification of the manufacturing batch.

All data shall be presented in a clear and explicit form.

### 5.2 Recommendations concerning packaging, transport and storage

The injection cartridges shall be protected against sun radiation and shall be stored according to the manufacture's installation instructions in dry condition at temperatures of at least +5 °C to not more than +25 °C.

Mortar cartridges with expired shelf life must no longer be used.

Georg Feistel  
Head of Department

*beglaubigt:*  
Baderschneider

**Cartridge: STV / ALV or STV / ALV Express**

Sealing cap





Imprint:  
STV / ALV or STV / ALV Express, processing notes,  
charge-code, storage-life, hazard-code, curing- and  
processing time (depending on the temperature), with as  
well as without travel scale

**Static mixer**



**Anchor rod with washer and  
hexagon nut**




Use category: - Installation in dry or wet concrete, it must not be installed in flooded holes.  
- No overhead installation

Temperature range: - 40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)  
- 40°C to +120°C (max. short term temperature +120°C and max. long term temperature +72°C)

Chemofast Injection system STV / ALV

Product and intended use

**Annex 1**



Commercial standard rod with:

- Mechanical properties acc. specifications annex 3, table 2
- Inspection certificate acc. to EN 10204:2004
- Identifying mark of the producer, e.g.: CVM
- Marking of embedment depth

Designation of anchor parts is given in Annex 3 (Table 2).

**Table 1: Anchor dimensions**

Size	Anchor rod		
	$\varnothing d_1$ [mm]	$h_{ef}$ [mm]	min $L^{1)}$ [mm]
M 10	10	90	$\geq 110$
M 12	12	110	$\geq 130$
M 16	16	125	$\geq 145$

<sup>1)</sup> max L = 1500 mm

**Table 2: Materials**

Part	Designation	Material
<b>Steel, zinc plated <math>\geq 5 \mu\text{m}</math> acc. to EN ISO 4042 or Steel, hot-dip <math>\geq 40 \mu\text{m}</math> acc. to EN ISO 1461</b>		
1	Anchor rod	Steel acc. DIN EN 10087 or DIN EN 10263 Property class 5.8, 8.8 acc. EN ISO 898-1:1999
2	Hexagon nut according to DIN 934 or DIN EN 24032	Property class 5 (for class 5.8 rod) EN ISO 898-2, Property class 8 (for class 8.8 rod) EN ISO 898-2
3	Washer acc. to EN ISO 7089, EN ISO 7093, or EN ISO 7094	Steel, zinc plated
<b>Stainless steel</b>		
1	Anchor rod	Material 1.4401 / 1.4571 acc. EN 10088-1:2005, Property class 50, 70 or 80 acc. EN ISO 3506
2	Hexagon nut according to DIN 934 or DIN EN 24032	Material 1.4401 / 1.4571 EN 10088, Property class 50 (for class 50 rod) EN ISO 3506 Property class 70 (for class 70 rod) EN ISO 3506 Property class 80 (for class 80 rod) EN ISO 3506
3	Washer acc. to EN ISO 7089, EN ISO 7093, or EN ISO 7094	Material 1.4401 or 1.4571 acc. EN 10088
<b>High corrosion resistance steel</b>		
1	Anchor rod	Material 1.4529 / 1.4565 acc. EN 10088-1:2005, Property class 50, 70 or 80 acc. EN ISO 3506
2	Hexagon nut according to DIN 934 or DIN EN 24032	Material 1.4529 / 1.4565 EN 10088, Property class 50 (for class 50 rod) EN ISO 3506 Property class 70 (for class 70 rod) EN ISO 3506 Property class 80 (for class 80 rod) EN ISO 3506
3	Washer acc. to EN ISO 7089, EN ISO 7093, or EN ISO 7094	Material 1.4529 / 1.4565 acc. EN 10088

**Table 3: Minimum curing time**

Concrete temperature	STV / ALV		STV / ALV Express	
	dry concrete	wet concrete	dry concrete	wet concrete
$\geq -5 \text{ }^\circ\text{C}$	6 h	12 h	4 h	8 h
$\geq 0 \text{ }^\circ\text{C}$	3 h	6 h	2 h	4 h
$\geq +5 \text{ }^\circ\text{C}$	2 h	4 h	1 h	2 h
$\geq +10 \text{ }^\circ\text{C}$	80 min	160 min	40 min	80 min
$\geq +20 \text{ }^\circ\text{C}$	45 min	90 min	20 min	40 min
$\geq +30 \text{ }^\circ\text{C}$	25 min	50 min	10 min	20 min
$\geq +35 \text{ }^\circ\text{C}$	20 min	40 min		


Chemofast Injection system STV / ALV

Materials,  
Curing times depending on the temperature

**Annex 3**


**150 ml, 280 ml, 300 ml, 330 ml, 380 ml and 410 ml injection mortar cartridge (type: coaxial)**

Sealing/Screw cap



Imprint:  
STV / ALV or STV / ALV Express, processing notes,  
charge-code, storage-life, hazard-code, curing- and  
processing time (depending on the temperature), with as  
well as without travel scale



Component B: Hardener  
(inner tube)



Component A: Injection mortar  
(outer tube)


**235 ml, 345 ml injection mortar cartridge (type: side-by-side)**

Sealing/Screw cap



Imprint:  
STV / ALV or STV / ALV Express, processing notes, charge-  
code, storage-life, hazard-code, curing- and processing time  
(depending on the temperature),  
with as well as without travel scale


Component B: Hardener



Component A: Injection mortar



**165 ml, 300 ml injection mortar cartridge (type: Foil tube)**

Sealing/Screw cap



Imprint:  
STV / ALV or STV / ALV Express, processing notes, charge-  
code, storage-life, hazard-code, curing- and processing time  
(depending on the temperature),  
with as well as without travel scale

Component B: Hardener  
and Component A: Injection  
mortar in a foil package



Static Mixer,  
one-way tool, must be changed  
in case of working interruption

Chemofast Injection system STV / ALV

Mortar cartridges

**Annex 4**


**Table 4: Installation parameters**

Anchor size		M 10	M 12	M 16
Nominal drill hole diameter	$d_0$ [mm] =	12	14	18
Cutting diameter of drill bit	$d_{cut}$ [mm] ≤	12.5	14.5	18.5
Depth of drill hole	$h_0$ [mm] ≥	90	110	125
Diameter of clearance hole in the fixture	$d_f$ [mm] ≤	12	14	18
Diameter of steel brush	$d_b$ [mm] ≥	14	16	20
Torque moment	$T_{inst}$ [Nm]	20	40	60
Thickness of fixture	$\min t_{fix}$ [mm] >	0		
	$\max t_{fix}$ [mm] <	1400	1380	1360
Minimum thickness of member	$h_{min}$ [mm]	130	160	160
Minimum spacing	$s_{min}$ [mm]	90	110	125
Minimum edge distance	$c_{min}$ [mm]	45	55	62.5

**Steel brush**



**Hand blowout pump**



Chemofast Injection system STV / ALV

Installation parameters  
Installation instruction

**Annex 5**

**Table 5: Design method A: Characteristic values for tension loads**

Anchor size			M 10	M 12	M 16
<b>Steel failure</b>					
Property class 5.8 acc. to EN ISO 898-1	Characteristic resistance	$N_{Rk,s}$ [kN]	29	42	78
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,50		
Property class 8.8 acc. to EN ISO 898-1	Characteristic resistance	$N_{Rk,s}$ [kN]	46	67	126
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,50		
Property class 50 acc. to EN ISO 3506	Characteristic resistance	$N_{Rk,s}$ [kN]	29	42	78
	Partial safety factor	$\gamma_{Ms}^{1)}$	2,86		
Property class 70 acc. to EN ISO 3506	Characteristic resistance	$N_{Rk,s}$ [kN]	40	59	110
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,87		
Property class 80 acc. to EN ISO 3506	Characteristic resistance	$N_{Rk,s}$ [kN]	46	67	126
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,60		
<b>Pullout and Concrete cone failure</b>					
Non-cracked concrete C20/25 (50 °C / 80 °C) <sup>3)</sup>		$N_{Rk,c}^0 = N_{Rk,p}$ [kN]	20	25	35
Non-cracked concrete C20/25 (72 °C / 120 °C) <sup>3)</sup>		$N_{Rk,c}^0 = N_{Rk,p}$ [kN]	16	20	30
Increasing factors for non-cracked concrete $\Psi_c$		C30/37	1.22		
		C40/50	1.41		
		C50/60	1.55		
Effective anchorage depth		$h_{ef}$ [mm]	90	110	125
Characteristic edge distance		$c_{cr,N}$ [mm]	90	110	125
Characteristic spacing		$s_{cr,N}$ [mm]	180	220	250
Partial safety factor		$\gamma_{Mc} = \gamma_{Mp}^{1)}$	1.8 <sup>2)</sup>		
<b>Splitting failure</b>					
Spacing		$s_{cr,sp}$ [mm]	180	220	250
Edge distance		$c_{cr,sp}$ [mm]	90	110	125
Partial safety factor		$\gamma_{Msp}^{1)}$	1.8 <sup>2)</sup>		

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> The partial safety factor  $\gamma_2 = 1.2$  is included.

<sup>3)</sup> Maximum long term temperature/ maximum short term temperature

**Table 6: Displacements for tension loads**

Anchor size		M 10	M 12	M 16
Tension load	N [kN]	6.6	8.3	11.6
Displacement	$\delta_{N0}$ [mm]	0.3	0.5	0.4
	$\delta_{N\infty}$ [mm]	0.6	1.6	2.0

Chemofast Injection system STV / ALV

Design Method A:  
Characteristic values for tension loads, Displacements

**Annex 6**



**Table 7: Design method A: Characteristic values for shear loads**

Anchor size			M 10	M 12	M 16
<b>Steel failure without lever arm</b>					
Property class 5.8 acc. to EN ISO 898-1	Characteristic resistance	$V_{Rk,s}$ [kN]	14	21	39
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,25		
Property class 8.8 acc. to EN ISO 898-1	Characteristic resistance	$V_{Rk,s}$ [kN]	23	33	63
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,25		
Property class 50 acc. to EN ISO 3506	Characteristic resistance	$V_{Rk,s}$ [kN]	14	21	39
	Partial safety factor	$\gamma_{Ms}^{1)}$	2,38		
Property class 70 acc. to EN ISO 3506	Characteristic resistance	$V_{Rk,s}$ [kN]	20	29	55
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,56		
Property class 80 acc. to EN ISO 3506	Characteristic resistance	$V_{Rk,s}$ [kN]	23	33	62
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,33		
<b>Steel failure with lever arm</b>					
Property class 5.8 acc. to EN ISO 898-1	Characteristic resistance	$M^0_{Rk,s}$ [Nm]	37	65	166
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,25		
Property class 8.8 acc. to EN ISO 898-1	Characteristic resistance	$M^0_{Rk,s}$ [Nm]	60	105	266
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,25		
Property class 50 acc. to EN ISO 3506	Characteristic resistance	$M^0_{Rk,s}$ [Nm]	37	65	166
	Partial safety factor	$\gamma_{Ms}^{1)}$	2,38		
Property class 70 acc. to EN ISO 3506	Characteristic resistance	$M^0_{Rk,s}$ [Nm]	52	92	233
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,56		
Property class 80 acc. to EN ISO 3506	Characteristic resistance	$M^0_{Rk,s}$ [Nm]	60	105	266
	Partial safety factor	$\gamma_{Ms}^{1)}$	1,33		
<b>Concrete pryout failure</b>					
Factor k in equation (5.6) of ETAG 001, Annex C, Section 5.2.3.3			2.0		
Partial safety factor			$\gamma_{Mc}^{1)}$ 1.50 <sup>2)</sup>		
<b>Concrete edge failure</b>					
Effective length of anchor in shear loading		$\ell_f$ [mm]	90	110	125
Outside diameter of anchor		$d_{nom}$ [mm]	12	14	18
Partial safety factor			$\gamma_{Mc}^{1)}$ 1.50 <sup>2)</sup>		

<sup>1)</sup> If no other national regulations exist

<sup>2)</sup> The partial safety factor  $\gamma_2 = 1.0$  is included.

**Table 8: Displacements for shear loads**

Anchor size		M 10	M 12	M 16
Shear load	V [kN]	6.6	8.3	11.6
Displacement	$\delta_{v0}$ [mm]	0.4	1.1	1.3
	$\delta_{v\infty}$ [mm]	0.6	1.6	2.0

Chemofast Injection system STV / ALV

Design Method A:  
Characteristic values for shear loads, Displacements

**Annex 7**