

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments

★ ★ ★
★ Designated
according to
Article 29 of Regula-
tion (EU) No 305/2011
and member of EOTA
(European Organi-
sation for Technical
Assessment)
★ ★ ★
★ ★

European Technical Assessment

ETA-11/0033
of 3 November 2015

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Trade name of the construction product

Product family
to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment
contains

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

Deutsches Institut für Bautechnik

BERNER multicompound system MCS Diamond

Bonded anchor for use in concrete

Berner Trading Holding GmbH
Bernerstraße 6
74653 Künzelsau
DEUTSCHLAND

Berner Herstellwerk 6
Berner manufacturing plant 6

40 pages including 3 annexes which form an integral part
of this assessment

Guideline for European technical approval of "Metal
anchors for use in concrete", ETAG 001 Part 5: "Bonded
anchors", April 2013,
used as European Assessment Document (EAD)
according to Article 66 Paragraph 3 of Regulation (EU)
No 305/2011.

European Technical Assessment

ETA-11/0033

English translation prepared by DIBt

Page 2 of 40 | 3 November 2015

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part**1 Technical description of the product**

The BERNER multicomponent system MCS Diamond is a bonded anchor consisting of a cartridge with injection mortar MCS Diamond and a steel element. The steel element consists of

- an anchor rod MCS Plus A with washer and hexagon nut of sizes M8 to M30 or
- an internal threaded anchor MCS Plus I of sizes M8 to M20 or
- a reinforcing bar of sizes $\phi = 8$ to 40 mm or
- a rebar anchor BRA of sizes M12 to M24

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment**3.1 Mechanical resistance and stability (BWR 1)**

Essential characteristic	Performance
Characteristic values under static and quasi-static action for design according to TR 029 or CEN/TS 1992-4:2009, Displacements	See Annex C 1 to C 19
Characteristic values for seismic performance categories C1 and C2 for design according to Technical Report TR 045, Displacements	See Annex C 20 to C 23

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorages satisfy requirements for Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with guideline for European technical approval ETAG 001, April 2013, used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011, the applicable European legal act is: [98/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document


Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 3. November 2015 by Deutsches Institut für Bautechnik

Uwe Bender
Head of Department

beglaubigt:
Baderschneider

Installation conditions



Anchor rod MCS Plus A
Pre-positioned anchorage

Anchor rod MCS Plus A
Push-through anchorage
(annular gap filled with mortar)

Internal threaded anchor MCS Plus I
Only pre-positioned anchorage

Reinforcing bar

Rebar anchor BRA
Pre-positioned anchorage

Rebar anchor BRA
Push-through anchorage
(annular gap filled with mortar)

BERNER multicomponent system MCS Diamond

Product description
Installation conditions

Annex A 1




Table A1: Materials

Part	Designation	Material		
1	Mortar cartridge	Mortar, hardener, filler		
		Steel, zinc plated	Stainless steel A4	High corrosion-resistant steel C
2	Anchor rod	Property class 5.8 or 8.8; EN ISO 898-1: 2013 zinc plated $\geq 5\mu\text{m}$, EN ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_s > 12\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_s > 12\%$ fracture elongation	Property class 50 or 80 EN ISO 3506:2009 or property class 70 with $f_{yk}= 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_s > 12\%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5\mu\text{m}$, EN ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	1.4565; 1.4529 EN 10088-1:2014
4	Hexagon nut	Property class 5 or 8; EN ISO 898-2:2013 zinc plated $\geq 5\mu\text{m}$, ISO 4042:1999 A2K or hot-dip galvanised EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506:2009 1.4565; 1.4529 EN 10088-1:2014
5	Internal threaded anchor MCS Plus I	Property class 5.8 or 8.8; ISO 898-1:2013 zinc plated $\geq 5\mu\text{m}$, ISO 4042:1999 A2K	Property class 70 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
6	Screw or threaded rod/ anchor rod for internal threaded anchor MCS Plus I	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5\mu\text{m}$, ISO 4042:1999 A2K	Property class 70 EN ISO 3506:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529 EN 10088-1:2014
7	Reinforcing bar EN 1992-1-1:2004 and AC:2010, Annex C	Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$		
8	Rebar anchor BRA	Rebar part: Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$	Threaded part: Property class 70 ISO 3506:2009 1.4565; 1.4529 EN 10088-1:2014	
BERNER multicompound system MCS Diamond				
Product description Materials			Annex A 3	

Specifications of intended use (part 1)

Table B1: Overview use categories and performance categories

Anchorage subject to		MCS Diamond with ...										
		Anchor rod MCS Plus A	Internal threaded anchor MCS Plus I	Reinforcing bar	Rebar anchor BRA							
Hammer drilling		all sizes										
Diamond drilling		all sizes										
Static and quasi static load, in	un- cracked concrete cracked concrete	all sizes	Tables: C1, C2, C9, C10	all sizes	Tables: C3, C4, C11, C12	all sizes	Tables: C5, C6, C13, C14	all sizes				
Seismic performance category (only hammer drilling)	C1	M10 – M30	Table C17	-----	Ø10 – Ø 32	Table C18	-----	-----				
	C2	M12, M16, M20, M24	Table C19		-----							
Use category	Dry or wet concrete	all sizes										
	Flooded hole	all sizes										
Installation temperature		+5°C to +40°C										
Service tempe- rature	Temperature range I	-40°C to +60°C		(max. long term temperature +35°C and max. short term temperature +60°C)								
	Temperature range II	-40°C to +72°C		(max. long term temperature +50°C and max. short term temperature +72°C)								

Base materials:

- Reinforced or unreinforced normal weight concrete according to EN 206:2013
- Strength classes C20/25 to C50/60 according to EN 206:2013

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel)
 - Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel)
 - Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions exist (high corrosion resistant steel)
- Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used)

BERNER multicompound system MCS Diamond

Intended Use
Specifications (part 1)

Annex B 1

Specifications of intended use (part 2)

Design:

- Anchorages have to be designed under the responsibility of an engineer experienced in anchorages and concrete work
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages under static or quasi-static actions are designed in accordance with EOTA Technical Report TR 029 "Design of bonded anchors" Edition September 2010 or CEN/TS 1992-4:2009
- Anchorages under seismic actions (cracked concrete) have to be designed in accordance with:
 - EOTA Technical Report TR 045 "Design of Metal Anchors under Seismic Action", Edition February 2013
 - Anchorages shall be positioned outside of critical regions (e.g. plastic hinges) of the concrete structure.
 - Fastenings in stand-off installation or with a grout layer are not allowed.

Installation:

- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- In case of aborted hole: The hole shall be filled with mortar
- Marking and keeping the effective anchorage depth
- Overhead installation is allowed

BERNER multicompound system MCS Diamond

Intended Use
Specifications (part 2)


Annex B 2

Table B2: Installation parameters for anchor rods

Size	[-]	M8	M10	M12	M14	M16	M20	M22	M24	M27	M30
Width across flat	SW	13	17	19	22	24	30	32	36	41	46
Nominal drill bit diameter	d_0 [mm]	12	14	14	16	18	24	25	28	30	35
Depth of drill hole	h_0 [mm]						$h_0 = h_{ef}$				
Effective anchorage depth	$h_{ef,min}$ [mm]	60	60	70	75	80	90	93	96	108	120
	$h_{ef,max}$ [mm]	160	200	240	280	320	400	440	480	540	600
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$ [mm]	40	45	55	60	65	85	95	105	120	140
Diameter of clearance hole in the fixture ¹⁾	pre-positioned anchorage d_f [mm]	9	12	14	16	18	22	24	26	30	33
	Push through anchorage d_f [mm]	14	16	16	18	20	26	28	30	33	40
Minimum thickness of concrete member	h_{min} [mm]			$h_{ef} + 30 \geq 100$					$h_{ef} + 2d_0$		
Maximum torque moment	$T_{inst,max}$ [Nm]	10	20	40	50	60	120	135	150	200	300

¹⁾ For larger clearance holes in the fixture see TR 029, 4.2.2.1 or CEN/TS 1992-4-1:2009, 5.2.3.1

Anchor rod MCS Plus A:



Marking (on random place):

Property class 8.8, stainless steel, property class 80 or high corrosion-resistant steel, property class 80: •
Stainless steel A4, property class 50 and high corrosion-resistant steel, property class 50: ••

Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:

- Materials, dimensions and mechanical properties according Annex A 3, Table A1
- Inspection certificate 3.1 according to EN 10204:2004, the documents should be stored
- Marking of embedment depth

BERNER multicompound system MCS Diamond

Intended Use
Installation parameters anchor rods


Annex B 3

Table B3: Installation parameters internal threaded anchors MCS Plus I


Size	M8	M10	M12	M16	M20
Diameter of anchor d_H [mm]	12	16	18	22	28
Nominal drill bit diameter d_0 [mm]	14	18	20	24	32
Drill hole depth h_0 [mm]			$h_0 = h_{ef}$		
Effective anchorage depth ($h_{ef} = L_H$) h_{ef} [mm]	90	90	125	160	200
Maximum torque moment $T_{inst,max}$ [Nm]	10	20	40	80	120
Minimum spacing and minimum edge distance $s_{min} = c_{min}$ [mm]	55	65	75	95	125
Diameter of clearance hole in the fixture ¹⁾ d_f [mm]	9	12	14	18	22
Minimum thickness of concrete member h_{min} [mm]	120	125	165	205	260
Maximum screw-in depth $l_{E,max}$ [mm]	18	23	26	35	45
Minimum screw-in depth $l_{E,min}$ [mm]	8	10	12	16	20

¹⁾ For larger clearance holes in the fixture see TR 029, 4.2.2.1 or CEN/TS 1992-4-1:2009, 5.2.3.1

Internal threaded anchor MCS Plus I



Marking



Marking: Anchor size

e.g.: **M10**

Stainless steel additional **A4**

e.g.: **M10 A4**

High corrosion-resistant steel additional **C**

e.g.: **M10 C**

Fastening screw or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Table A1

BERNER multicompound system MCS Diamond

Intended Use

Installation parameters internal threaded anchors MCS Plus I

Annex B 4

Table B4: Installation parameters reinforcing bars

Reinforcing bar	ϕ	8	10	12	14	16	18	20	22	24
Nominal drill bit diameter	d_0 [mm]	12	14	16	18	20	25	25	30	30
Drill hole depth	h_0 [mm]						$h_0 = h_{ef}$			
Effective anchorage depth	$h_{ef,min}$ [mm]	60	60	70	75	80	85	90	94	98
	$h_{ef,max}$ [mm]	160	200	240	280	320	360	400	440	480
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$ [mm]	40	45	55	60	65	75	85	95	105
Minimum thickness of concrete member	h_{min} [mm]	$h_{ef} + 30$ ≥ 100		$h_{ef} + 2d_0$						
Reinforcing bar	ϕ	25	26	28	30	32	34	36	40	
Nominal drill bit diameter	d_0 [mm]	30	35	35	40	40	40	45	55	
Drill hole depth	h_0 [mm]						$h_0 = h_{ef}$			
Effective anchorage depth	$h_{ef,min}$ [mm]	100	104	112	120	128	136	144	160	
	$h_{ef,max}$ [mm]	500	520	560	600	640	680	720	800	
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$ [mm]	110	120	130	140	160	170	180	200	
Minimum thickness of concrete member	h_{min} [mm]						$h_{ef} + 2d_0$			

Reinforcing bar



- The minimum value of related rip area $f_{R,min}$ according to EN 1992-1-1:2004+AC:2010
- The maximum outer rebar diameter over the rips shall be:
 - The nominal diameter of the rip $\phi + 2 * h$ ($h \leq 0,07 * \phi$)
 - (ϕ : Nominal diameter of the bar; h : rip height of the bar)

BERNER multicomponent system MCS Diamond

Intended Use
Installation parameters reinforcing bars


Annex B 5

Table B5: Installation parameters rebar anchor BRA

Thread diameter		M12	M16	M20	M24
Nominal bar size	ϕ [mm]	12	16	20	25
Width across flat	SW [mm]	19	24	30	36
Nominal drill bit diameter	d_0 [mm]	16	20	25	30
Depth of drill hole ($h_0 = l_{ges}$)	h_0 [mm]			$h_{ef} + l_e$	
Effective anchorage depth	$h_{ef,min}$ [mm]	70	80	90	96
	$h_{ef,max}$ [mm]	140	220	300	380
Distance concrete surface to welded join	l_e [mm]			100	
Minimum spacing and minimum edge distance	$s_{min} = c_{min}$ [mm]	55	65	85	105
Diameter of clearance hole in the fixture ¹⁾	$pre-positioned\ anchorage \leq d_f$ [mm]	14	18	22	26
	$push\ through\ anchorage \leq d_f$ [mm]	18	22	26	32
Minimum thickness of concrete member	h_{min} [mm]	$h_0 + 30 \geq 100$		$h_0 + 2d_0$	
Maximum torque moment	$T_{inst,max}$ [Nm]	40	60	120	150

¹⁾ For larger clearance holes in the fixture see TR 029, 4.2.2.1 or CEN/TS 1992-4-1:2009, 5.2.3.1

Rebar anchor BRA



Marking: on head e.g.: BRA (for stainless steel);
BRA C (for high corrosion-resistant steel)

BERNER multicomponent system MCS Diamond

Intended Use
Installation parameters rebar anchor BRA

Annex B 6

Table B6: Parameters of steel brush

Drill bit diameter [mm]	12	14	16	18	20	24	25	28	30	32	35	40	45	55
Steel brush diameter d_b [mm]	14	16		20	25	26	27	30		40		42	47	58




Table B7: Maximum processing time of the mortar and minimum curing time

System temperature [°C]	Maximum processing time t_{work} [minutes]	Minimum curing time ¹⁾ t_{cure} [hours]
+5 to +10	120	40
≥ +10 to +20	30	18
≥ +20 to +30	14	10
≥ +30 to +40	7	5

¹⁾ In wet concrete or flooded holes the curing times must be doubled.





BERNER multicomponent system MCS Diamond

Intended Use
Cleaning tools
Processing times and curing times







Annex B 7

Installation instructions part 1

Drilling and cleaning the hole (hammer drill)

1		Drill the hole. Drill hole diameter d_0 and drill hole depth h_0 see Tables B2, B3, B4, B5 .
2		Clean the drill hole: Blow out the drill hole two times, using oil-free compressed air ($p \geq 6$ bar)
3		Brush the drill hole two times. For drill hole diameter ≥ 30 mm use a power drill. For deep holes use an extension. Corresponding brushes see Table B6
4		Clean the drill hole: Blow out the drill hole two times, using oil-free compressed air ($p \geq 6$ bar)

Drilling and cleaning the hole (drilling with diamond drill bit)

1		Drill the hole. Drill hole diameter d_0 and drill hole depth h_0 see Tables B2, B3, B4, B5 .		Break the drill core and draw it out.	
2		Flush the drill hole until the water comes clear.			
3		Blow out the drill hole two times, using oil-free compressed air ($p > 6$ bar)	4		Brush the drill hole two times using a power drill. Corresponding brushes see Table B6
5		Blow out the drill hole two times, using oil-free compressed air ($p > 6$ bar)			



BERNER multicomponent system MCS Diamond

Intended use
Installation instructions part 1




Annex B 8

Installation instructions part 2

Preparing the cartridge






6		Twist off the sealing cap Twist on the static mixer (the spiral in the static mixer must be clearly visible).
7		Place the cartridge into the dispenser.
8		Press approximately 10 cm of material out until the resin is evenly grey in colour. Don't use mortar that is not uniformly grey.

Injection of the mortar




9	 Fill approximately 2/3 of the drill hole with mortar. Always begin from the bottom of the hole and avoid bubbles.	 For drill hole depth ≥ 150 mm use an extension tube.	 For overhead installation, deep holes $h_0 > 250$ mm or drill hole diameter $d_0 \geq 40$ mm use an injection-adapter.
---	--	---	--

Installation instructions part 3

Installation anchor rods or internal threaded anchors MCS Plus I

10			Only use clean and oil-free anchor elements. Mark the setting depth of the anchor. Press the threaded rod or internal threaded anchor down to the bottom of the hole, turning it slightly while doing so. After inserting the anchor element, excess mortar must emerge around the anchor element.	
		For overhead installation fasten the anchor rod with wedges until the mortar begins to harden		For push-through installation fill the annular gap also with mortar
11		Wait for the specified curing time t_{cure} see Table B7.		Mounting the fixture $T_{inst,max}$ see Tables B2 and B3.

Installation reinforcing bars and rebar anchor BRA

9		Only use clean and oil-free reinforcing bars or BRA. Mark the setting depth. Using a turning movement, push the reinforcing bar or the BRA vigorously into the filled hole up to the insertion depth marking.		
		When reaching the setting depth mark, excess mortar must emerge from the mouth of the drill hole.		
10		Wait for the specified curing time t_{cure} see Table B7.		Mounting the fixture $T_{inst,max}$ see Table B5.

BERNER multicomponent system MCS Diamond

Intended use
Installation instructions part 3

Annex B 10

Table C1: Characteristic values of resistance for anchor rods under tension load (un-cracked concrete)

Size			M8	M10	M12	M14	M16	M20	M22	M24	M27	M30						
Installation safety factor	dry and wet concrete	$\gamma_2 =$	[-]			1,0			1,2									
	flooded hole	γ_{inst}	[-]			1,4												
Steel failure																		
Characteristic resistance $N_{Rk,s}$ [kN]			$A_s \cdot f_{uk}$															
Combined pullout and concrete cone failure																		
Diameter of calculation d [mm]			8	10	12	14	16	20	22	24	27	30						
Characteristic bond resistance in un-cracked concrete C20/25																		
Hammer-drilling (dry and wet concrete)																		
Temperature range I ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			16	16	15	14	14	13	13	13	12	12						
Temperature range II ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			15	14	14	13	13	12	12	12	11	11						
Hammer-drilling (flooded hole)																		
Temperature range I ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			16	16	15	13	13	11	11	10	10	9						
Temperature range II ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			15	14	14	13	12	11	10	10	9	9						
Diamond-drilling (dry and wet concrete)																		
Temperature range I ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			16	15	13	12	12	10	10	10	9	9						
Temperature range II ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			15	14	12	11	11	10	9	9	8	8						
Diamond-drilling (flooded hole)																		
Temperature range I ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			16	15	13	12	12	10	10	10	9	9						
Temperature range II ¹⁾ $\tau_{Rk,ucr}$ [N/mm ²]			15	14	12	11	11	10	9	9	8	8						
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1																		
Increasing factor for τ_{Rk}	k_{ucr}		[-]			10,1												
	Ψ_c		C25/30			1,02												
			C30/37			1,04												
			C35/45			1,06												
			C40/50			1,07												
			C45/55			1,08												
Splitting failure																		
Edge distance $c_{cr,sp}$	$h / h_{ef} \geq 2,0$		[mm]			1,0 h_{ef}												
	$2,0 > h / h_{ef} > 1,3$		[mm]			4,6 $h_{ef} - 1,8 h$												
	$h / h_{ef} \leq 1,3$		[mm]			2,26 h_{ef}												
Axial distance $s_{cr,sp}$			[mm]			2 $c_{cr,sp}$												

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values for static or quasi-static action under tension load for threaded rods (un-cracked concrete)

Annex C 1

Table C1.1: Characteristic values of resistance for anchor rods under tension load (cracked concrete)

Size		M8	M10	M12	M14	M16	M20	M22	M24	M27	M30								
Installation safety factor	dry and wet concrete	$\gamma_2 = \gamma_{\text{inst}}$	[-]	1,0				1,2											
	flooded hole			1,2				1,4											
Steel failure																			
Characteristic resistance	N _{Rk,s}	[kN]	$A_s \cdot f_{uk}$																
Combined pullout and concrete cone failure																			
Diameter of calculation	d	[mm]	8	10	12	14	16	20	22	24	27	30							
Characteristic bond resistance in cracked concrete C20/25																			
Hammer-drilling and diamond drilling (dry and wet concrete)																			
Temperature range I ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	7	7	7	7	6	6	7	7	7	7							
Temperature range II ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	7	7	7	7	6	6	7	7	7	7							
Hammer-drilling and diamond drilling (flooded hole)																			
Temperature range I ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	6	7,5	7,5	7	6	6	6	6	6	6							
Temperature range II ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	6	7	7	7	6	6	6	6	6	6							
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k _{cr}	[-]	7,2																
Increasing factor for τ_{Rk}	C25/30	[-]	1,02																
	C30/37	[-]	1,04																
	C35/45	[-]	1,06																
	C40/50	[-]	1,07																
	C45/55	[-]	1,08																
	C50/60	[-]	1,09																
Splitting failure																			
Edge distance c _{cr,sp}	$h / h_{ef} \geq 2,0$		[mm]	1,0 h _{ef}															
	2,0 > h / h _{ef} > 1,3		[mm]	4,6 h _{ef} - 1,8 h															
	$h / h_{ef} \leq 1,3$		[mm]	2,26 h _{ef}															
Axial distance s _{cr,sp}			[mm]	2 c _{cr,sp}															

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values for static or quasi-static action under tension load for anchor rods (cracked concrete)

Annex C 2

Table C2: Characteristic values of resistance for anchor rods under shear load

Size		M8	M10	M12	M14	M16	M20	M22	M24	M27	M30	
Installation safety factor	$\gamma_2 = \gamma_{\text{inst}}$	[\cdot]									1,0	
Steel failure without lever arm												
Characteristic steel resistance	$V_{Rk,s}$	[kN]									$0,5 \cdot A_s \cdot f_{uk}$	
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	k_2	[\cdot]									0,8	
Steel failure with lever arm												
Characteristic bending moment ¹⁾	$M_{Rk,s}^0$	[Nm]									$1,2 \cdot W_{el} \cdot f_{uk}$	
Concrete prout failure												
Factor k acc. to TR029 Section 5.2.3.3 resp. k_3 acc. to CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$	[\cdot]									2,0	
Concrete edge failure												
The value of h_{ef} for calculation in equations (5.8a) and (5.8b) of Technical Report TR 029 is limited by:											$\min(h_{ef}, 8d)$	
Diameter of calculation	d	[mm]	8	10	12	14	16	20	22	24	27	30

BERNER multicompound system MCS Diamond

Performances

Characteristic values for static or quasi-static action under shear load for anchor rods

Annex C 3

**Table C3: Characteristic values of resistance for internal threaded anchors
MCS Plus I under tension load (un-cracked concrete)**

Size			M8	M10	M12	M16	M20		
Installation safety factor	dry and wet concrete	$\gamma_2 =$	[$-$]	1,0		1,2			
	flooded hole	γ_{inst}	[$-$]	1,2		1,4			
Steel failure									
Characteristic resistance with screw		$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$					
Combined pullout and concrete cone failure									
Diameter of calculation		d	[mm]	12	16	18	22		
Characteristic bond resistance in un-cracked concrete C20/25									
Hammer-drilling (dry and wet concrete)									
Temperature range I ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	15	14	14	13		
Temperature range II ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	14	13	13	12		
Hammer-drilling (flooded hole)									
Temperature range I ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	14	12	12	11		
Temperature range II ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	13	12	11	10		
Diamond-drilling (dry and wet concrete)									
Temperature range I ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	13	12	11	10		
Temperature range II ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	12	11	10	9		
Diamond-drilling (flooded hole)									
Temperature range I ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	13	12	11	10		
Temperature range II ¹⁾		$\tau_{Rk,ucr}$	[N/mm ²]	12	11	10	9		
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1									
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[$-$]	10,1					
		C30/37	[$-$]	1,02					
		C35/45	[$-$]	1,04					
		C40/50	[$-$]	1,06					
		C45/55	[$-$]	1,07					
		C50/60	[$-$]	1,08					
				1,09					
Splitting failure									
Edge distance	$c_{cr,sp}$	$h / h_{ef} \geq 2,0$	[mm]	1,0 h_{ef}					
		$2,0 > h / h_{ef} > 1,3$	[mm]	4,6 $h_{ef} - 1,8 h$					
		$h / h_{ef} \leq 1,3$	[mm]	2,26 h_{ef}					
Axial distance		$s_{cr,sp}$	[mm]	2 $c_{cr,sp}$					

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values for static or quasi-static action under tension load for internal threaded anchors MCS Plus I (un-cracked concrete)

Annex C 4

**Table C3.1: Characteristic values of resistance for internal threaded anchors
MCS Plus I under tension load (cracked concrete)**

Size				M8	M10	M12	M16	M20
Installation safety factor	dry and wet concrete		$\gamma_2 =$	[-]				1,0
	flooded hole		γ_{inst}	[-]				1,2
Steel failure								
Characteristic resistance with screw		$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$				
Combined pullout and concrete cone failure								
Diameter of calculation		d_H	[mm]	12	16	18	22	28
Characteristic bond resistance in cracked concrete C20/25								
Hammer-drilling and diamond drilling (dry and wet concrete)								
Temperature range I ¹⁾		$\tau_{Rk,cr}$	[N/mm ²]	7	6	6	7	7
Temperature range II ¹⁾		$\tau_{Rk,cr}$	[N/mm ²]	7	6	6	7	7
Hammer-drilling and diamond drilling (flooded hole)								
Temperature range I ¹⁾		$\tau_{Rk,cr}$	[N/mm ²]	7	6,5	6	6	6
Temperature range II ¹⁾		$\tau_{Rk,cr}$	[N/mm ²]	7	6	6	6	6
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1		k_{cr}	[-]	7,2				
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[-]	1,02				
		C30/37	[-]	1,04				
		C35/45	[-]	1,06				
		C40/50	[-]	1,07				
		C45/55	[-]	1,08				
		C50/60	[-]	1,09				
Splitting failure								
Edge distance	$c_{cr,sp}$	$h / h_{ef} \geq 2,0$	[mm]	1,0 h_{ef}				
		$2,0 > h / h_{ef} > 1,3$	[mm]	4,6 $h_{ef} - 1,8 h$				
		$h / h_{ef} \leq 1,3$	[mm]	2,26 h_{ef}				
Axial distance		$s_{cr,sp}$	[mm]	2 $c_{cr,sp}$				

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values for static or quasi-static action under tension load for internal threaded anchors MCS Plus I (cracked concrete)

Annex C 5

**Table C4: Characteristic values of resistance for internal threaded anchors
MCS Plus I under shear load**

Size		M8	M10	M12	M16	M20
Installation safety factor	$\gamma_2 = \gamma_{\text{inst}}$	[\cdot]			1,0	
Steel failure without lever arm						
Characteristic resistance with screw	$V_{Rk,s}$	[\cdot]			0,5 $\cdot A_s \cdot f_{uk}$	
Ductility factor acc. to CEN/TS 1992-4-5: 2009 Section 6.3.2.1	k_2	[\cdot]			0,8	
Steel failure with lever arm						
Characteristic bending moment with screw	$M_{Rk,s}^0$	[Nm]			1,2 $\cdot W_{el} \cdot f_{uk}$	
Concrete pyrolysis failure						
Factor k acc. to TR029 Section 5.2.3.3 resp. k_3 acc. to CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$	[\cdot]			2,0	
Concrete edge failure						
The value of h_{ef} for calculation in equations (5.8a) and (5.8b) of Technical Report TR 029 is limited by:					min ($h_{ef}; 8d$)	
Diameter of calculation	d	[mm]	12	16	18	22
					28	

BERNER multicompound system MCS Diamond

Performances

Characteristic values for static or quasi-static action under shear load for internal threaded anchors MCS Plus I

Annex C 6

Table C5: Characteristic values of resistance for reinforcing bars under tension loads (hammer-drilling; un-cracked concrete; ϕ 8- ϕ 24)

Reinforcing bar	ϕ	8	10	12	14	16	18	20	22	24
Installation safety factor	dry and wet concrete	γ_2 =	[$-$]		1,0					1,2
	flooded hole	γ_{inst}	[$-$]				1,4			
Steel failure										
Characteristic resistance $N_{Rk,s}$ [kN]										
Combined pullout and concrete cone failure										
Diameter of calculation	d [mm]	8	10	12	14	16	18	20	22	24
Characteristic bond resistance in un-cracked concrete										
Hammer-drilling (dry and wet concrete)										
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	16	16	15	14	14	14	13	13	13
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	15	14	14	13	13	13	12	12	12
Hammer-drilling (flooded hole)										
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	16	16	14	13	12	12	11	11	10
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	15	14	13	12	11	12	11	10	10
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{ucr}	[$-$]						10,1		
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[$-$]					1,02		
		C30/37	[$-$]					1,04		
		C35/45	[$-$]					1,06		
		C40/50	[$-$]					1,07		
		C45/55	[$-$]					1,08		
		C50/60	[$-$]					1,09		
Splitting failure										
Edge distance $c_{cr,sp}$		$h / h_{ef} \geq 2,0$	[mm]					1,0 h_{ef}		
		$2,0 > h / h_{ef} > 1,3$	[mm]					4,6 $h_{ef} - 1,8 h$		
		$h / h_{ef} \leq 1,3$	[mm]					2,26 h_{ef}		
Axial distance $s_{cr,sp}$			[mm]					2 $c_{cr,sp}$		

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebars (hammer-drilling; un-cracked concrete; ϕ 8- ϕ 24)

Annex C 7

Table C5.1: Characteristic values of resistance for reinforcing bars under tension loads (hammer-drilling; un-cracked concrete ϕ 25- ϕ 40)

Reinforcing bar	ϕ	25	26	28	30	32	34	36	40						
Installation safety factor	dry and wet concrete	γ_2 =	[$-$]	1,2											
	flooded hole	γ_{inst}	[$-$]	1,4											
Steel failure															
Characteristic resistance $N_{Rk,s}$ [kN]															
Combined pullout and concrete cone failure															
Diameter of calculation	d [mm]	25	26	28	30	32	34	36	40						
Characteristic bond resistance in un-cracked concrete															
Hammer-drilling (dry and wet concrete)															
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	13	13	13	12	12	12	12	12						
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	12	11	11	11	11	11	11	10						
Hammer-drilling (flooded hole)															
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	10	10	10	9	9	9	8	8						
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	9	9	9	9	8	8	8	8						
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{ucr}	[$-$]	10,1												
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[$-$]	1,02											
		C30/37	[$-$]	1,04											
		C35/45	[$-$]	1,06											
		C40/50	[$-$]	1,07											
		C45/55	[$-$]	1,08											
		C50/60	[$-$]	1,09											
Splitting failure															
Edge distance $c_{cr,sp}$		$h / h_{ef} \geq 2,0$	[mm]	1,0 h_{ef}											
		$2,0 > h / h_{ef} > 1,3$	[mm]	4,6 $h_{ef} - 1,8 h$											
		$h / h_{ef} \leq 1,3$	[mm]	2,26 h_{ef}											
Axial distance $s_{cr,sp}$			[mm]	2 $c_{cr,sp}$											

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebars (hammer-drilling; un-cracked concrete; ϕ 25- ϕ 40)

Annex C 8

Table C5.2: Characteristic values of resistance for reinforcing bars under tension loads (diamond-drilling; un-cracked concrete ϕ 8- ϕ 24)

Reinforcing bar	ϕ	8	10	12	14	16	18	20	22	24							
Installation safety factor	dry and wet concrete	γ_2 =	[$-$]	1,0					1,2								
	flooded hole	γ_{inst}	[$-$]	1,4													
Steel failure																	
Characteristic resistance $N_{Rk,s}$ [kN]																	
Combined pullout and concrete cone failure																	
Diameter of calculation	d [mm]	8	10	12	14	16	18	20	22	24							
Characteristic bond resistance in un-cracked concrete																	
Diamond-drilling (dry and wet concrete)																	
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	16	15	13	12	12	11	10	10	10							
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	15	14	12	11	11	10	10	9	9							
Diamond-drilling (flooded hole)																	
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	16	15	13	12	12	11	10	10	10							
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm^2]	15	14	12	11	11	10	10	9	9							
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{ucr}	[$-$]	10,1														
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[$-$]	1,02													
		C30/37	[$-$]	1,04													
		C35/45	[$-$]	1,06													
		C40/50	[$-$]	1,07													
		C45/55	[$-$]	1,08													
		C50/60	[$-$]	1,09													
Splitting failure																	
Edge distance	$c_{cr,sp}$	$h / h_{ef} \geq 2,0$ [mm]		1,0 h_{ef}													
		$2,0 > h / h_{ef} > 1,3$ [mm]		4,6 $h_{ef} - 1,8 h$													
		$h / h_{ef} \leq 1,3$ [mm]		2,26 h_{ef}													
Axial distance	$s_{cr,sp}$	[mm]		2 $c_{cr,sp}$													

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebars (diamond-drilling; un-cracked concrete; ϕ 8- ϕ 24)

Annex C 9

Table C5.3: Characteristic values of resistance for reinforcing bars under tension loads (diamond-drilling; un-cracked concrete ϕ 25- ϕ 40)

Reinforcing bar		ϕ	25	26	28	30	32	34	36	40								
Installation safety factor	dry and wet concrete	γ_2 =	[-]		1,2													
	flooded hole	γ_{inst}	[-]		1,4													
Steel failure																		
Characteristic resistance $N_{Rk,s}$ [kN] $A_s \cdot f_{uk}$																		
Combined pullout and concrete cone failure																		
Diameter of calculation	d	[mm]	25	26	28	30	32	34	36	40								
Characteristic bond resistance in un-cracked concrete C20/25																		
Diamond-drilling (dry and wet concrete)																		
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	9	9	9	9	8	8	8	7								
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	9	8	8	8	8	7	7	7								
Diamond-drilling (flooded hole)																		
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	9	9	9	9	8	8	8	7								
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	9	8	8	8	8	7	7	7								
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{ucr}	[-]	10,1															
Increasing factor for τ_{Rk}	Ψ_c	C25/30 [-]	1,02															
		C30/37 [-]	1,04															
		C35/45 [-]	1,06															
		C40/50 [-]	1,07															
		C45/55 [-]	1,08															
		C50/60 [-]	1,09															
Splitting failure																		
Edge distance	$c_{cr,sp}$	$h / h_{ef} \geq 2,0$ [mm]	1,0 h_{ef}															
		$2,0 > h / h_{ef} > 1,3$ [mm]	4,6 $h_{ef} - 1,8 h$															
		$h / h_{ef} \leq 1,3$ [mm]	2,26 h_{ef}															
Axial distance	$s_{cr,sp}$	[mm]	2 $c_{cr,sp}$															

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond	Annex C 10
Performances Characteristic values in static or quasi-static action under tension load for rebars (diamond-drilling; un-cracked concrete; ϕ 25- ϕ 40)	

Table C5.4: Characteristic values of resistance for reinforcing bars under tension loads (hammer-drilling and diamond-drilling; cracked concrete ϕ 8- ϕ 24)

Reinforcing bar	ϕ	8	10	12	14	16	18	20	22	24
Installation safety factor	dry and wet concrete	γ_2 =	[$-$]	1,0						1,2
	flooded hole	γ_{inst}	[$-$]	1,2						1,4
Steel failure										
Characteristic resistance $N_{Rk,s}$ [kN] $A_s \cdot f_{uk}$										
Combined pullout and concrete cone failure										
Diameter of calculation	d [mm]	8	10	12	14	16	18	20	22	24
Characteristic bond resistance in cracked concrete										
Hammer-drilling and diamond-drilling (dry and wet concrete)										
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm ²]	7	7	7	7	6	6	6	7	7
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm ²]	7	7	7	7	6	6	6	7	7
Hammer-drilling and diamond-drilling (flooded hole)										
Temperature range I ¹⁾	$\tau_{Rk,ucr}$ [N/mm ²]	6	7,5	6,5	6,5	6,5	6	6	6	6
Temperature range II ¹⁾	$\tau_{Rk,ucr}$ [N/mm ²]	6	6,5	6,5	6	6	6	6	6	6
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{cr}	[$-$]								7,2
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[$-$]							1,02
		C30/37	[$-$]							1,04
		C35/45	[$-$]							1,06
		C40/50	[$-$]							1,07
		C45/55	[$-$]							1,08
		C50/60	[$-$]							1,09
Splitting failure										
Edge distance $c_{cr,sp}$	$h / h_{ef} \geq 2,0$	[mm]								1,0 h_{ef}
	$2,0 > h / h_{ef} > 1,3$	[mm]								4,6 $h_{ef} - 1,8 h$
	$h / h_{ef} \leq 1,3$	[mm]								2,26 h_{ef}
Axial distance $s_{cr,sp}$		[mm]								2 $c_{cr,sp}$

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebars (hammer-drilling and diamond-drilling; cracked concrete; ϕ 8- ϕ 24)

Annex C 11

Table C5.5: Characteristic values of resistance for reinforcing bars under tension loads (hammer-drilling and diamond-drilling; cracked concrete ϕ 25- ϕ 40)

Reinforcing bar		ϕ	25	26	28	30	32	34	36	40					
Installation safety factor	dry and wet concrete	γ_2 =	[$-$]			1,2									
	flooded hole	γ_{inst}	[$-$]			1,4									
Steel failure															
Characteristic steel resistance		$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$											
Combined pullout and concrete cone failure															
Diameter of calculation		d	[mm]	25	26	28	30	32	34	36	40				
Characteristic bond resistance in cracked concrete C20/25															
Hammer-drilling and diamond drilling (dry and wet concrete)															
Temperature range I ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	7	7	7	7	5	5	5	5					
Temperature range II ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	7	7	7	7	5	5	5	5					
Hammer-drilling and diamond drilling (flooded hole)															
Temperature range I ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	6	6	6	6	5	5	5	5					
Temperature range II ¹⁾	$\tau_{Rk,cr}$	[N/mm ²]	6	6	6	6	5	5	5	5					
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{cr}	[$-$]	7,2												
Increasing factor for τ_{Rk}	C25/30	[$-$]	1,02												
	C30/37	[$-$]	1,04												
	C35/45	[$-$]	1,06												
	C40/50	[$-$]	1,07												
	C45/55	[$-$]	1,08												
	C50/60	[$-$]	1,09												
Splitting failure															
Edge distance $c_{cr,sp}$	$h / h_{ef} \geq 2,0$	[mm]	1,0 h_{ef}												
	$2,0 > h / h_{ef} > 1,3$	[mm]	4,6 $h_{ef} - 1,8 h$												
	$h / h_{ef} \leq 1,3$	[mm]	2,26 h_{ef}												
Axial distance	$s_{cr,sp}$	[mm]	2 $c_{cr,sp}$												

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebars (hammer-drilling and diamond-drilling; cracked concrete; ϕ 25- ϕ 40)

Annex C 12

Table C6: Characteristic values of resistance for reinforcing bars under shear load (ϕ 8- ϕ 24)

Reinforcing bar	ϕ	8	10	12	14	16	18	20	22	24
Installation safety factor	$\gamma_2 = \gamma_{inst}$	[$-$]								1,0
Steel failure without lever arm										
Characteristic steel resistance	$V_{Rk,s}$ [kN]									$0,5 \cdot A_s \cdot f_{uk}$
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	k_2	[$-$]								0,8
Steel failure with lever arm										
Characteristic bending moment	$M^0_{Rk,s}$ [kN]									$1,2 \cdot W_{el} \cdot f_{uk}$
Concrete prout failure										
Factor k acc. to TR029 Section 5.2.3.3 resp. k_3 acc. to CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$	[$-$]								2,0
Concrete edge failure										
The value of h_{ef} for calculation in equations (5.8a) and (5.8b) of Technical Report TR 029 is limited by:										$\min(h_{ef}; 8d)$
Diameter of calculation	d [mm]	8	10	12	14	16	18	20	22	24

Table C6.1: Characteristic values of resistance for reinforcing bars under shear load (ϕ 25- ϕ 40)

Reinforcing bar	ϕ	25	26	28	30	32	34	26	40
Installation safety factor	γ_2	[$-$]							1,0
Steel failure without lever arm									
Characteristic steel resistance	$V_{Rk,s}$ [kN]								$0,5 \cdot A_s \cdot f_{uk}$
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	K_2	[$-$]							0,8
Steel failure with lever arm									
Characteristic bending moment	$M^0_{Rk,s}$ [kN]								$1,2 \cdot W_{el} \cdot f_{uk}$
Concrete prout failure									
Factor k acc. to TR029 Section 5.2.3.3 resp. k_3 acc. to CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$	[$-$]							2,0
Concrete edge failure									
The value of h_{ef} for calculation in equations (5.8a) and (5.8b) of Technical Report TR 029 is limited by:									$\min(h_{ef}; 8d)$
Diameter of calculation	d [mm]	25	26	28	30	32	34	26	40

BERNER multicompound system MCS Diamond	Annex C 13
Performances Characteristic values in static or quasi-static action of rebars under shear loads	

Table C7: Characteristic values of resistance for rebar anchors BRA under tension loads (un-cracked concrete)

Size		M12	M16	M20	M24
Installation safety factor	dry and wet concrete	$\gamma_2 =$ [-]		1,0	1,2
	flooded hole	γ_{inst} [-]		1,2	1,4
Steel failure					
Characteristic steel resistance	$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$		
Partial safety factor	$\gamma_{Ms,N}^{2)}$	[-]	1,4		
Combined pullout and concrete cone failure					
Diameter of calculation	d	[mm]	12	16	20
Characteristic bond resistance in un-cracked concrete C20/25					
Hammer-drilling (dry and wet concrete)					
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	15	14	13
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	14	13	12
Hammer-drilling (flooded hole)					
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	15	13	11
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	14	12	11
Diamond-drilling (dry and wet concrete)					
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	13	12	10
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	12	11	10
Diamond-drilling (flooded hole)					
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	13	12	10
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	12	11	9
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{ucr}	[-]	10,1		
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[-]	1,02	
		C30/37	[-]	1,04	
		C35/45	[-]	1,06	
		C40/50	[-]	1,07	
		C45/55	[-]	1,08	
		C50/60	[-]	1,09	
Splitting failure					
Edge distance $c_{cr,sp}$	$h / h_{ef} \geq 2,0$		[mm]	1,0 h_{ef}	
	$2,0 > h / h_{ef} > 1,3$		[mm]	4,6 $h_{ef} - 1,8 h$	
	$h / h_{ef} \leq 1,3$		[mm]	2,26 h_{ef}	
Axial distance $s_{cr,sp}$			[mm]	2 $c_{cr,sp}$	

¹⁾ See Annex B 1

²⁾ In absence of other national regulations

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebar anchors BRA (un-cracked concrete)

Annex C 14

Table C7.1: Characteristic values of resistance for rebar anchors BRA under tension load (hammer and diamond-drilling; cracked concrete)

Size		M12	M16	M20	M24		
Installation safety factor	dry and wet concrete	γ_2 =	[-]	1,0	1,2		
	flooded hole	γ_{inst}	[-]	1,2	1,4		
Steel failure							
Characteristic steel resistance	$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$				
Partial safety factor	$\gamma_{Ms,N}^{2)}$	[-]	1,4				
Combined pullout and concrete cone failure							
Diameter of calculation	d	[mm]	12	16	20		
Characteristic bond resistance in un-cracked concrete C20/25							
Hammer and diamond-drilling (dry and wet concrete)							
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	7	6	6		
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	7	6	7		
Hammer and diamond-drilling (flooded hole)							
Temperature range I ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	8	8	6		
Temperature range II ¹⁾	$\tau_{Rk,ucr}$	[N/mm ²]	8	7	6		
Factor acc. CEN/TS 1992-4:2009 Section 6.2.3.1	k_{cr}	[-]	7,2				
Increasing factor for τ_{Rk}	Ψ_c	C25/30	[-]	1,02			
		C30/37	[-]	1,04			
		C35/45	[-]	1,06			
		C40/50	[-]	1,07			
		C45/55	[-]	1,08			
		C50/60	[-]	1,09			
Splitting failure							
Edge distance $c_{cr,sp}$	$h / h_{ef} \geq 2,0$	[mm]	1,0 h_{ef}				
	$2,0 < h / h_{ef} > 1,3$	[mm]	4,6 $h_{ef} - 1,8 h$				
	$h / h_{ef} \leq 1,3$	[mm]	2,26 h_{ef}				
Axial distance $s_{cr,sp}$		[mm]	2 $c_{cr,sp}$				

¹⁾ See Annex B 1

²⁾ In absence of other national regulations.

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under tension load for rebar anchors BRA (hammer and diamond-drilling; cracked concrete)

Annex C 15

Table C8: Characteristic values of resistance for rebar anchors BRA under shear load

Size		M12	M16	M20	M24
Installation safety factor	$\gamma_2 = \gamma_{\text{inst}}$	[\cdot]		1,0	
Steel failure without lever arm					
Characteristic steel resistance	$V_{Rk,s}$	[kN]		0,5 $\cdot A_s \cdot f_{uk}$	
Partial safety factor	$\gamma_{Ms,V}^{1)}$	[\cdot]		1,56	
Ductility factor acc. to CEN/TS 1992-4-5:2009 Section 6.3.2.1	k_2	[\cdot]		0,8	
Steel failure with lever arm					
Characteristic bending moment	$M_{Rk,s}^0$	[Nm]		1,2 $\cdot W_{el} \cdot f_{uk}$	
Partial safety factor	$\gamma_{Ms,V}^{1)}$	[\cdot]		1,56	
Concrete prout failure					
Factor k acc. to TR029 Section 5.2.3.3 resp. k_3 acc. to CEN/TS 1992-4-5:2009 Section 6.3.3	$k_{(3)}$	[\cdot]		2,0	
Concrete edge failure					
The value of h_{ef} for calculation in equations (5.8a) and (5.8b) of Technical Report TR 029 is limited by:				min (h_{ef} ; 8d)	
Diameter of calculation	d	[mm]	12	16	20
					25

¹⁾ In absence of other national regulations

BERNER multicompound system MCS Diamond

Performances

Characteristic values in static or quasi-static action under shear load
rebar anchors BRA

Annex C 16

Table C9: Displacements under tension load for anchor rods¹⁾

Size	M8	M10	M12	M16	M20	M24	M27	M30
Un-cracked and cracked concrete; temperature range I, II								
Displacement δ_{N0} - factor [mm/(N/mm ²)]	0,07	0,08	0,09	0,10	0,11	0,12	0,13	0,13
Displacement $\delta_{N\infty}$ - factor [mm/(N/mm ²)]	0,13	0,14	0,15	0,17	0,17	0,18	0,19	0,19

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0} - \text{factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty} - \text{factor} \cdot \tau$$

(τ : design bond strength)

Table C10: Displacements under shear load for anchor rods¹⁾

Size	M8	M10	M12	M16	M20	M24	M27	M30
Un-cracked and cracked concrete; temperature range I, II								
Displacement δ_{V0} - factor [mm/kN]	0,18	0,15	0,12	0,09	0,07	0,06	0,05	0,05
Displacement $\delta_{V\infty}$ - factor [mm/kN]	0,27	0,22	0,18	0,14	0,11	0,09	0,08	0,07

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0} - \text{factor} \cdot V$$

$$\delta_{V\infty} = \delta_{V\infty} - \text{factor} \cdot V$$

(V : design shear resistance)

Table C11: Displacements under tension load for internal threaded anchors MCS Plus I¹⁾

Size	M8	M10	M12	M16	M20
Un-cracked and cracked concrete; temperature range I, II					
Displacement δ_{N0} - factor [mm/(N/mm ²)]	0,09	0,10	0,10	0,11	0,19
Displacement $\delta_{N\infty}$ - factor [mm/(N/mm ²)]	0,13	0,15	0,15	0,17	0,19

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0} - \text{factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty} - \text{factor} \cdot \tau$$

(τ : design bond strength)

Table C12: Displacements under shear load for internal threaded anchors MCS Plus I¹⁾

Size	M8	M10	M12	M16	M20
Un-cracked and cracked concrete; temperature range I, II					
Displacement δ_{V0} - factor [mm/kN]	0,12	0,09	0,08	0,07	0,05
Displacement $\delta_{V\infty}$ - factor [mm/kN]	0,18	0,14	0,12	0,10	0,08

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0} - \text{factor} \cdot V$$

$$\delta_{V\infty} = \delta_{V\infty} - \text{factor} \cdot V$$

(V : design shear resistance)

BERNER multicompound system MCS Diamond

Performances

Displacements anchor rods and internal threaded anchor MCS Plus I

Annex C 17

Table C13: Displacements under tension load for reinforcing bars ¹⁾

Size	ϕ	8	10	12	14	16	18	20	22	24
Un-cracked and cracked concrete; temperature range I, II										
Displacement	δ_{N0} - factor	[mm/(N/mm ²)]	0,07	0,08	0,09	0,09	0,10	0,10	0,11	0,11
Displacement	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,11	0,12	0,13	0,14	0,15	0,16	0,16	0,17
Size	ϕ	25	26	28	30	32	34	36	40	
Un-cracked and cracked concrete; temperature range I, II										
Displacement	δ_{N0} - factor	[mm/(N/mm ²)]	0,12	0,12	0,13	0,13	0,13	0,14	0,14	0,15
Displacement	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,18	0,18	0,19	0,19	0,20	0,20	0,21	0,22

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0} \text{- factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty} \text{- factor} \cdot \tau$$

(τ : design bond strength)

Table C14: Displacements under shear load for reinforcing bars ¹⁾

Size	ϕ	8	10	12	14	16	18	20	22	24
Un-cracked and cracked concrete; temperature range I, II										
Displacement	δ_{V0} - factor	[mm/kN]	0,18	0,15	0,12	0,10	0,09	0,08	0,07	0,07
Displacement	$\delta_{V\infty}$ - factor	[mm/kN]	0,27	0,22	0,18	0,16	0,14	0,12	0,11	0,10
Size	ϕ	25	26	28	30	32	34	36	40	
Un-cracked and cracked concrete; temperature range I, II										
Displacement	δ_{V0} - factor	[mm/kN]	0,06	0,06	0,05	0,05	0,05	0,05	0,05	0,04
Displacement	$\delta_{V\infty}$ - factor	[mm/kN]	0,09	0,08	0,08	0,07	0,07	0,06	0,06	0,05

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0} \text{- factor} \cdot V$$

$$\delta_{V\infty} = \delta_{V\infty} \text{- factor} \cdot V$$

(V : design shear resistance)

BERNER multicomponent system MCS Diamond

Performances
Displacements reinforcing bars

Annex C 18

Table C15: Displacements under tension load for rebar anchors BRA¹⁾

Size	φ	12	16	20	24
Un-cracked and cracked concrete; temperature range I, II					
Displacement	δ_{N0} - factor	[mm/(N/mm ²)]	0,09	0,10	0,11
Displacement	$\delta_{N\infty}$ - factor	[mm/(N/mm ²)]	0,13	0,16	0,18

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0} - \text{factor} \cdot \tau$$

$$\delta_{N\infty} = \delta_{N\infty} - \text{Factor} \cdot \tau$$

(τ: design bond strength)

Table C16: Displacements under shear load for rebar anchors BRA¹⁾

Size	φ	12	16	20	24
Un-cracked and cracked concrete; temperature range I, II					
Displacement	δ_{V0} - factor	[mm/kN]	0,12	0,09	0,07
Displacement	$\delta_{V\infty}$ - factor	[mm/kN]	0,18	0,14	0,11

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0} - \text{factor} \cdot V$$

$$\delta_{V\infty} = \delta_{V\infty} - \text{factor} \cdot V$$

(V: design shear resistance)

BERNER multicompound system MCS Diamond

Performances
Displacements rebar anchor BRA

Annex C 19

Table C17A: Characteristic values of resistance for anchor rods MCS Plus A under seismic action performance category C1 in hammer drilled hole

Size			M10	M12	M14	M16	M20	M22	M24	M27	M30	
Installation safety factor	dry and wet concrete	$\gamma_2 =$	[-]			1,0			1,2			
	flooded hole	γ_{inst}	[-]			1,4						
Characteristic resistance tension load, steel failure												
$N_{Rk,s,C1}$ [kN]	Zinc plated steel	Property class	5,8	29	43	58	79	123	152	177	230	281
			8,8	47	68	92	126	196	243	282	368	449
$\gamma_{M,s,C1}^{(1)}$ [-]	Stainless steel A4 and steel C	Property class	50	29	43	58	79	123	152	177	230	281
			70	41	59	81	110	172	212	247	322	393
	Zinc plated steel	Property class	80	47	68	92	126	196	243	282	368	449
	Stainless steel A4 and steel C	Property class	50					1,50				
Characteristic bond resistance, combined pullout and concrete cone failure												
(dry and wet concrete)												
Temperature range I ⁽³⁾	$\tau_{Rk,C1}$	[N/mm ²]	7,0	7,0	6,7	5,7	5,7	6,7	6,7	6,7	6,7	
Temperature range II ⁽³⁾	$\tau_{Rk,C1}$	[N/mm ²]	7,0	7,0	6,7	5,7	5,7	6,7	6,7	6,7	6,7	
(flooded hole)												
Temperature range I ⁽³⁾	$\tau_{Rk,C1}$	[N/mm ²]	7,5	7,5	6,5	6,5	5,7	6,7	5,7	5,7	5,7	
Temperature range II ⁽³⁾	$\tau_{Rk,C1}$	[N/mm ²]	6,8	6,8	6,5	5,7	5,7	5,7	5,7	5,7	5,7	
Characteristic resistance shear load, steel failure without lever arm												
$V_{Rk,s,C1}$ [kN]	Zinc plated steel	Property class	5,8	15	21	29	39	61	76	89	115	141
			8,8	23	34	46	63	98	122	141	184	225
Installation safety factor	Stainless steel A4 and steel C	Property class	50	15	21	29	39	61	76	89	115	141
			70	20	30	40	55	86	107	124	161	197

⁽¹⁾ For threaded rods MCS Plus A the factor for steel ductility is 1,0

⁽²⁾ $f_{uk} = 700 \text{ N/mm}^2$; $f_{yk} = 560 \text{ N/mm}^2$

⁽³⁾ See Annex B 1

BERNER multicompound system MCS Diamond	Annex C 20
Performances Characteristic values under seismic action (performances C1) for anchor rods MCS Plus A	

Table C17B: Characteristic values of resistance for standard threaded rods under seismic action performance category C1 in hammer drilled hole

Size	M10	M12	M14	M16	M20	M22	M24	M27	M30			
Installation safety factor	See Table C17A											
Characteristic resistance tension load, steel failure	See Table C17A											
Characteristic bond resistance, combined pullout and concrete cone failure	See Table C17A											
Characteristic resistance shear load, steel failure without lever arm												
$V_{Rk,s,C1}$ [kN]	Zinc plated steel	Property class	5.8 8.8	11 16	15 24	20 32	27 44	43 69	53 85	62 99	81 129	99 158
	Stainless steel A4 and steel C	Property class	50 70 80	11 14 16	15 21 24	20 28 32	27 39 44	43 60 69	53 75 85	62 87 99	81 113 129	99 138 158
	Installation safety factor	$\gamma_2 = \gamma_{inst}$	[-]								1,0	

BERNER multicompound system MCS Diamond

Performances

Characteristic values under seismic action (performances C1) for standard threaded rods

Annex C 21

Table C18: Characteristic values of resistance for reinforcing bars under seismic action performance category C1 in hammer drilled hole

Reinforcing bar		ϕ	10	12	14	16	18	20	22	24
Installation safety factor	dry and wet concrete	$\gamma_2 =$	[-]		1,0				1,2	
	flooded hole	γ_{inst}	[-]		1,2				1,4	
Characteristic resistance tension load, steel failure										
$N_{RK,s,C1}$		[kN]	44	63	85	111	140	173	209	249
Characteristic bond resistance, combined pullout and concrete cone failure										
(dry and wet concrete)										
Temperature range I ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	7,0	7,0	6,7	5,7	5,7	5,7	6,7	6,7
Temperature range II ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	7,0	7,0	6,7	5,7	5,7	5,7	6,7	6,7
(flooded hole)										
Temperature range I ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	7,5	7,0	6,5	5,7	5,7	5,7	6,7	5,7
Temperature range II ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	6,8	6,8	5,8	5,8	5,7	5,7	5,7	5,7
Characteristic resistance shear load, steel failure without lever arm										
$V_{RK,s,C1}$		[kN]	15	22	30	39	49	61	74	88
Installation safety factor	$\gamma_2 = \gamma_{inst}$	[-]	1,0							

Reinforcing bar		ϕ	25	26	28	30	32	
Installation safety factor	dry and wet concrete	$\gamma_2 =$	[-]		1,2			
	flooded hole	γ_{inst}	[-]		1,4			
Characteristic resistance tension load, steel failure								
$N_{RK,s,C1}$		[kN]	270	292	339	389	443	
Characteristic bond resistance, combined pullout and concrete cone failure								
(dry and wet concrete)								
Temperature range I ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	6,7	6,7	6,7	6,7	4,8	
Temperature range II ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	6,7	6,7	6,7	6,7	4,8	
(flooded hole)								
Temperature range I ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	5,7	5,7	5,7	5,7	5,7	
Temperature range II ¹⁾	$\tau_{RK,s,C1}$	[N/mm ²]	5,7	5,7	5,7	5,7	4,8	
Characteristic resistance shear load, steel failure without lever arm								
$V_{RK,s,C1}$		[kN]	95	102	119	137	155	
Installation safety factor	$\gamma_2 = \gamma_{inst}$	[-]	1,0					

¹⁾ See Annex B 1

BERNER multicompound system MCS Diamond

Performances

Characteristic values under seismic action (performances C1) for rebars

Annex C 22

Table C19: Characteristic values of resistance for anchor rods MCS Plus A and standard threaded rods under seismic action performance category C2 in hammer drilled hole

Size				M12	M16	M20	M24
Installation safety factor	dry and wet concrete	$\gamma_2 = \gamma_{inst}$	[-]	1,0			1,2
	flooded hole		[-]	1,2		1,4	
Characteristic resistance tension load, steel failure							
$N_{Rk,s, C2}$ [kN]	Zinc plated steel	Property class	5.8 8.8	39 61	72 116	108 173	177 282
	Stainless steel A4 and steel C	Property class	50 70 80	39 53 61	72 101 116	108 152 173	177 247 282
Characteristic bond resistance, combined pullout and concrete cone failure (dry and wet concrete)							
Temperature range I ¹⁾	$\tau_{Rk, C2}$ [N/mm ²]	2,2	3,5	1,8	2,4		
Temperature range II ¹⁾ $\tau_{Rk, C2}$ [N/mm ²]							
Characteristic bond resistance, combined pullout and concrete cone failure (flooded hole)							
Temperature range I ¹⁾ Temperature range II ¹⁾	$\tau_{Rk, C2}$ [N/mm ²]	2,3	3,5	1,8	2,1		
	$\tau_{Rk, C2}$ [N/mm ²]	2,3	3,5	1,8	2,1		
Displacements							
$\delta_{N,(DLS)}$ - factor ³⁾	[mm/(N/mm ²)]	0,09	0,10	0,11	0,12		
$\delta_{N,(ULS)}$ - factor ³⁾	[mm/(N/mm ²)]	0,15	0,17	0,17	0,18		
Characteristic resistance shear load, steel failure without lever arm							
$V_{Rk,s, C2}$ ²⁾ [kN]	Zinc plated steel	Property class	5.8 8.8	14 22	27 44	43 69	62 99
	Stainless steel A4 and steel C	Property class	50 70 80	14 20 22	27 39 44	43 60 69	62 87 99
	Installation safety factor	$\gamma_2 = \gamma_{inst}$ [-]				1,0	
Displacements							
$\delta_{V,(DLS)}$ - factor ⁴⁾	[mm/kN]	0,18	0,10	0,07	0,06		
$\delta_{V,(ULS)}$ - factor ⁴⁾	[mm/kN]	0,25	0,14	0,11	0,09		

¹⁾ See Annex B 1

²⁾ For anchor rods MCS Plus A the factor for steel ductility is 1,0

³⁾ Calculation for displacement

$$\delta_{N(DLS)} = \delta_{N(DLS)}\text{-Factor} \cdot \tau; \\ \delta_{N(ULS)} = \delta_{N(ULS)}\text{-Factor} \cdot \tau;$$

(τ : design bond strength)

⁴⁾ Calculation for displacement

$$\delta_{V(DLS)} = \delta_{V(DLS)}\text{-Factor} \cdot V; \\ \delta_{V(ULS)} = \delta_{V(ULS)}\text{-Factor} \cdot V;$$

(V : design shear resistance)

BERNER multicompound system MCS Diamond

Performances

Characteristic values under seismic action (performances C2) for anchor rods MCS Plus A and standard anchor rods

Annex C 23