



Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and Laender Governments



European Technical Assessment

ETA-11/0322 of 23 November 2016

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the Deutsches Institut für Bautechnik **European Technical Assessment:** Trade name of the construction product Prefabricated structural components made of steel grades Q235B, Q235D, Q345B and Q345D Product family Prefabricated structural components from hot rolled products made of steel grades Q235B, Q235D, Q345B to which the construction product belongs and Q345D Manufacturer ANDRITZ AG Stattegger Straße 18 8045 GRAZ **ÖSTERREICH** Manufacturing plant Plant 1 Plant 2 Plant 3 Plant 4 Plant 5 This European Technical Assessment 9 pages including 4 annexes which form an integral part contains of this assessment This European Technical Assessment is European Assessment Document (EAD) 200017-00-0302 Version March 2015 issued in accordance with Regulation (EU) No 305/2011, on the basis of This version replaces ETA-11/0322 issued on 24 September 2012

Deutsches Institut für Bautechnik Kolonnenstraße 30 B | 10829 Berlin | GERMANY | Phone: +49 30 78730-0 | Fax: +49 30 78730-320 | Email: dibt@dibt.de | www.dibt.de



European Technical Assessment ETA-11/0322 English translation prepared by DIBt

Page 2 of 9 | 23 November 2016

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.



Page 3 of 9 | 23 November 2016

European Technical Assessment ETA-11/0322 English translation prepared by DIBt

Specific part

1 Technical description of the product

The construction products are prefabricated structural steel components made of uncoated hotrolled plates or profiles made of the weldable steel grades Q235B, Q235D, Q345B and Q345D. The maximum thickness for profiles is 80 mm. The maximum thickness for plates made of Q235B and Q235D is 80 mm and for plates made of Q345B and Q345D is 250 mm.

The steel grades are similar to the structural steel grades according to EN 10025-2 listed in Table 1.

	Comparable according E	
Steel grade	Designation according EN 10027-1	Designation according EN 10027-2
Q235B	S235JR	1.0038
Q235D	S235J2	1.0117
Q345B	S355JR	1.0045
Q345D	S355J2	1.0577

Table 1 – Comparison of steel grades

Due to the manufacturing process the steel grades deviate from EN 10025-2 as follows:

- The minimum yield strengths R_{eH} and the ultimate strengths R_m differ from those specified in EN 10025-2.
- The chemical analysis differs from the analysis specified in EN 10025-2.

The product characteristics must be identified on the basis of the Inspection certificate "type 3.1" according to EN 10204 (to be furnished by the supplier).

Specification of the intended use in accordance with the applicable European Assessment Document

The prefabricated structural steel components made of the steel grades Q235B, Q235D, Q345B, Q345D are intended for use in welded, bolted or riveted steel or composite structures.

Concerning product packaging, transport, storage, maintenance, replacement and repair it is the responsibility of the manufacturer to undertake the appropriate measures and to advise his clients on the transport, storage, maintenance, replacement and repair of the product as he considers necessary. The thermo-mechanically hot-rolled long steel products made of weldable fine grain structural steel can be dismantled and recycled, but are normally not intended for re-use.

It is assumed that the product will be installed according to the manufacturer's instructions or (in absence of such instructions) according to the usual practice of the building professionals, notably in accordance with the provisions of EN 1090-2:2008+A1:2011.

2



European Technical Assessment

ETA-11/0322

Page 4 of 9 | 23 November 2016

English translation prepared by DIBt

The performances given in Section 3 are only valid if the hot-rolled products of the steel grades Q235B, Q235D, Q345B and Q345D are used in compliance with the specifications and conditions given in Annex (1 to 4).

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of Hot rolled products and therewith executed structural parts made of the steel grades Q235B, Q235D, Q345B, Q345D of at least 100 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Chemical composition	see Annex 1, Table 2 and 3

The chemical analysis shall be carried out in accordance with EN 10025-2:2004, clause 8.3.3 and 9.1. The test method shall be in accordance with EN 10025-2:2004, clause 10.1.

Yield strength	
Tensile strength	see Annex 2, Table 4.1 and 4.2
Elongation at fracture	

Location and orientation including preparation of samples and test pieces shall be in accordance with EN 10025-1 and EN 10025-2. The test method shall be in accordance with EN 10025-1, clause 10.2.1 and EN 10025-2.

Impact toughness value	see Annex 2, Table 4.1 and 4.2
------------------------	--------------------------------

Location and orientation of samples and test specimen shall be in accordance with EN 10025-2:2004, clause 9.2. The impact properties shall be determined according to EN 10025-2, clause 7.3.2.

Weldability	see Annex 1, Table 2 and 3 see Annex 3, Table 5
Improved deformation properties perpendicular to the surface	no performance assessed
Formability	no performance assessed
Suitability for hot-dip zinc-coating	no performance assessed
Surface properties	no performance assessed
Internal soundness	no performance assessed
Dimensions, tolerances on dimensions and shape, mass	no performance assessed



Page 5 of 9 | 23 November 2016

European Technical Assessment

ETA-11/0322

English translation prepared by DIBt

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class (A1) according to EN 13501-1:2007+A1:2009

The Hot rolled products and therewith executed structural parts made of the steel grades Q235B, Q235D, Q345B, Q345D satisfy the requirements for performance class A1 of the characteristic reaction to fire, in accordance with the provisions of EC decision 96/603/EC (as amended).

3.3 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dang substances	erous no performance assessed

3.4 Sustainable use of natural resources (BWR 7)

Essential characteristic	Performance
Durability	no performance assessed

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

According to EAD No. 200017-00-0302, the applicable European legal act is: 1998/214/EC amended by 2001/596/EC.

The system to be applied is: 2+

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 23 November 2016 by Deutsches Institut für Bautechnik

Uwe Bender Head of Department *beglaubigt:* Hahn



Steel						Pe	rcent by	weight	[%]						
grade	С	Si	Mn	Р	S	Nb	V	Ti	Cr	Ni	Cu	Ν	Мо	AI	
0	Ч	≤	≤	≤	≤	≤	≤	≤	≤	≤	≤	≤	≤	≥	
Q235B	0,20	0,35	1,40	0,045	0,045				0.30	0,30	0.30	0,008			
Q235D	0,17	0,55	1,40	0,035	0,035				0,30	0,30	0,30	0,000		0,015	
Q345B	0,20	0,50	1,70	0,035	0,035	0.07	0,15	0.20	0.20	0,50	0,30	0,012	0,10		
Q345D	0,18	0,50	1,70	0,030	0,025	0,07	0,15	0,20	0,30	0,30	0,50	0,30	0,012	0,10	0,015

Table 3 A	Acceptable tolerances of product analyses compared to ladle analyses
-----------	--

Steel					Pe	ercent b	y weigł	nt [%]						
grade	С	Si	Mn	Ρ	S	Nb	V	Ti	Cr	Ni	Cu	N ≤	Мо	AI
Q235B		.0.02												
Q235D	. 0. 02	±0,03	≤ 0,8:±0,03	-0,005	-0,005				.0.05	.0.05	· 0.05	.0.005		±0,003
Q345B	±0,02	≤ 0,37:±0,03	>0,8- 1,7:±0,06	+0,000	+0,000		-0,02	-0,02	±0,05	±0,05	±0,05	±0,005		
Q345D		>0,37- 0,50:±0,05				±0,005	+0,01	+0,01					±0,01	±0,003

Hot rolled products and therewith executed structural parts made of the steel grades Q235B, Q235D, Q345B, Q345D

Annex 1

Chemical Composition



able 4.1	ambient tem	-		e steel grades (Q235B and Q235D		
Steel grade	Nominal thickness t [mm]	Yield strength R _{eL} [MPa]	Tensile strength R _m [MPa]	Elongation at fracture L ₀ = 5,65 • √S0 [%]	Impact toughness value K _v [J]		
	t ≤ 16	235		00			
Q235B	16 < t ≤ 40	225	370 - 500	26	≥ 27		
Q235D	40 < t ≤ 60	215	370-300	25	at +20 °C		
	60 < t ≤ 80	215	-	24			
	$t \leq 16$	235		26			
Q235D	16 < t ≤ 40	225	370 - 500	20	≥ 27		
	40 < t ≤ 60	215		25	at -20 °C		
	60 < t ≤ 80	215		24			
able 4.2	•	-	I products of th	e steel grades (Q345B and Q345D		
	ambient tem	perature					
Steel grade Nominal thickness t ¹⁾ Yie		Yield strength R _{e∟} [MPa]	Tensile strength R _m [MPa]	Elongation at fracture L₀ = 5,65 • √S0 [%]	Impact toughness value K _v [J]		
	t ≤ 16	345		20			
	16 < t ≤ 40	335					
	40 < t ≤ 63	325	470 - 630		≥ 34		
Q345B	63 < t ≤ 80	315		19	at +20 °C		
Q040D	80 < t ≤ 100	305					
	100 < t ≤ 150	285		18			
	150 < t ≤ 200	275	450 - 600	17	≥ 27		
	$200 < t \le 250$	265			at +20 °C		
	t ≤ 16	345		21			
	16 < t ≤ 40	335		21			
	40 < t ≤ 63	325	470 - 630		≥ 34		
Q345D	63 < t ≤ 80	315		20	at -20 °C		
QUHUD	80 < t ≤ 100	305					
	100 < t ≤ 150	285		19			
	150 < t ≤ 200	275	450 - 600	18	≥ 27		
	200 < t ≤ 250	265	1		at -20 °C		

Hot rolled products and therewith executed structural parts made of the steel grades Q235B, Q235D, Q345B, Q345D

Yield strength, tensile strength and elongation at fracture

Annex 2



The carbon equivalent value CEV shall be determined according to EN 10025-1. CEV shall comply with the values specified in Table 5.

Table 5 Maximum for Carbon Equivalent Value (CE					
	Stool grada	Nominal thickness t [mm]			
	Steel grade	t ≤ 63	63 < t ≤ 250		
	Q235B, Q235D	0,37	0,40		
	Q345B, Q345D	0,44	0,48		

Annex 3

Weldability



	Steel grade	Product thickness t [mm]	Yield strength f _{v.k} [N/mm²]	Tensile strength f _{u.k} [N/mm²]
1	Q235B Q235D	$t \leq 40$	235	- 360
3		40 < t ≤ 80	215	
4	Q345B Q345D	$t \leq 40$	335	470
5		40 < t ≤ 80	315	450
6		80 < t ≤ 150	285	430
7		150 < t ≤ 250	265	430

Table 6 - Characteristic values of yield strength and tensile strength

Hot rolled products and therewith executed structural parts made of the steel grades Q235B, Q235D, Q345B, Q345D

Characteristic values of yield strength and tensile strength

Annex 4