

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-04/0095
of 11 May 2017

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

Würth Injection System W-VIZ

Product family
to which the construction product belongs

Torque controlled bonded anchor with
anchor rod W-VIZ-A and internal threaded rod W-VIZ-IG
for use in concrete

Manufacturer

Adolf Würth GmbH & Co. KG
Reinhold Würth Straße 12-17
74653 Künzelsau

Manufacturing plant

Würth Herstellwerk W1, Deutschland

This European Technical Assessment
contains

35 pages including 3 annexes which form an integral part
of this assessment

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

Guideline for European technical approval of "Metal
anchors for use in concrete", ETAG 001 Part 5: "Bonded
anchors", April 2013,
used as European Assessment Document (EAD)
according to Article 66 Paragraph 3 of Regulation (EU)
No 305/2011.

This version replaces

ETA-04/0095 issued on 23 April 2015

European Technical Assessment

ETA-04/0095

English translation prepared by DIBt

Page 2 of 35 | 11 May 2017

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The Injection System W-VIZ is a torque controlled bonded anchor consisting of a cartridge with injection mortar WIT-VM 100, WIT-VIZ, WIT-EXPRESS, WIT-VM 100 express or WIT-VIZ express and an anchor rod with expansion cones and external connection thread (type W-VIZ-A) or with internal connection thread (type W-VIZ-IG).

The load transfer is realised by mechanical interlock of several cones in the bonding mortar and then via a combination of bonding and friction forces in the anchorage ground (concrete).

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance of W-VIZ-A	See Annex C1 to C7
Displacements under tension and shear loads for W-VIZ-A	See Annex C8 and C9
Characteristic resistance of W-VIZ-IG	See Annex C10 to C12
Displacements under tension and shear loads for W-VIZ-IG	See Annex C12

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchorage satisfy requirements for Class A1
Resistance to fire	No performance assessed

3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply. (Nur bei Injektionssysteme)

3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with guideline for European technical approval ETAG 001, April 2013, used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document



Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 11 May 2017 by Deutsches Institut für Bautechnik

Andreas Kummerow
Head of Department



beglaubigt:
Baderschneider

Anchor rod W-VIZ-A




Pre-setting installation

(and through-setting
installation
W-VIZ-A 75 M12,
see Annex B11)



Through-setting installation

Anchor rod W-VIZ-IG ¹⁾



¹⁾ Illustration with hexagon head screw exemplified; other screws or threaded rods also permitted (see Annex A5, requirements of the fastening screw or threaded rod)

Anchor version	Product description	Intended use	Performance
W-VIZ-A	Annex A1 – Annex A4	Annex B1 – Annex B11	Annex C1 – Annex C9
W-VIZ-IG	Annex A1 – Annex A2; Annex A5	Annex B1 – Annex B3; Annex B12 – Annex B14	Annex C10 – Annex C12

Injection System W-VIZ

Product description
Installation situation



Annex A1

Injection System W-VIZ


Mortar cartridge



Imprint: Injection Adhesive WIT-VM 100, WIT-VIZ, WIT-EXPRESS, WIT-VM 100 express, WIT-VIZ express, processing notes, shelf-life, hazard code, storage temperature, curing time and processing time (depending on temperature)




Imprint: Injection Adhesive WIT-VM 100, WIT-VIZ, WIT-EXPRESS, WIT-VM 100 express, WIT-VIZ express, processing notes, shelf-life, hazard code, storage temperature, curing time and processing time (depending on temperature)




Sealing cap




Reducing adapter



Static mixer




Blow-out pump



Air Blower

Cleaning Brush




Anchor rod W-VIZ-A




Washer
(optional:
washer with
bore)

Hexagon nut



Anchor rod W-VIZ-IG




Injection System W-VIZ

Product description

Cartridges, Cleaning tools, Anchor types

Annex A2

Marking



Marking: e.g. ◇ 95 VMZ 12-25 ...

- ◇ Identifying mark of manufacturing plant
- 95 Anchorage depth
- VMZ Trade name
- 12 Size of thread
- 25 Maximum thickness of fixture (when using washer 2a)
- A4 additional marking of stainless steel A4
- HCR additional marking of high corrosion resistant

Marking of length	B	C	D	E	F	G	H	I	J	K	L	M
Length of anchor min \geq	50.8	63.5	76.2	88.9	101.6	114.3	127.0	139.7	152.4	165.1	177.8	190.5
Length of anchor max $<$	63.5	76.2	88.9	101.6	114.3	127.0	139.7	152.4	165.1	177.8	190.5	203.2

Marking of length	N	O	P	Q	R	S	T	U	V	W	X	Y	Z	>Z
Length of anchor min \geq	203.2	215.9	228.6	241.3	254.0	279.4	304.8	330.2	355.6	381.0	406.4	431.8	457.2	482.6
Length of anchor max $<$	215.9	228.6	241.3	254.0	279.4	304.8	330.2	355.6	381.0	406.4	431.8	457.2	482.6	

Table A1: Dimensions of anchor rod, W-VIZ-A M8 – M12

Anchor size W-VIZ-A		40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Additional marking		1	2	1	2	1	2	3	4	5	6	7
1	Anchor rod	M8		M10		M12						
	Thread	M8		M10		M12						
	Number of cones	2	3	3	3	3	3	4	4	6	6	6
	$d_k =$	8.0	8.0	9.7	9.7	10.7	12.5	12.5	12.5	12.5	12.5	12.5
	Length L (washer 2a)	52+ t_{fix}	63+ t_{fix}	75+ t_{fix}	90+ t_{fix}	95+ t_{fix}	90+ t_{fix}	100+ t_{fix}	115+ t_{fix}	120+ t_{fix}	130+ t_{fix}	145+ t_{fix}
3	Reduction $t_{fix}^{(1)}$ (washer with bore 2b)	3,4	3,4	3	3	2,5	2,5	2,5	2,5	2,5	2,5	2,5
	Hexagon nut SW	13	13	17	17	19	19	19	19	19	19	19

¹⁾ When using washer with bore (2b) the thickness of fixture is reduced by the specified value

Dimensions in mm

Injection System W-VIZ

Product description

Anchor parts, Marking, Anchor dimensions **W-VIZ-A** M8 – M12

Annex A3

Table A2: Dimensions of anchor rod, W-VIZ-A M16 – M24

Anchor size W-VIZ-A	90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Additional marking	1	2	3	4	5	1	2	3	1	2	3
1 Anchor rod	M16					M20			M24		
Thread	M16					M20			M24		
Number of cones	3	4	6	6	6	3	6	6	6	6	6
$d_k =$	16.5	16.5	16.5	16.5	16.5	19.7	22.0	22.0	24.0	24.0	24.0
Length L (washer 2a)	114	129	150	170	185	143	203	223	210	240	265
Reduction $t_{fix}^{1)}$ (washer with bore 2b)	2	2	2	2	2	2	2	2	1	1	1
3 Hexagon nut SW	24	24	24	24	24	30	30	30	36	36	36

¹⁾ When using washer with bore (2b) the thickness of fixture is reduced by the specified value

Dimensions in mm

Table A3: Materials W-VIZ-A

Part	Designation	Steel, zinc plated			Stainless steel A4	High corrosion resistant steel (HCR)
		galvanised	hot-dip galvanised \geq 40µm	sherardized \geq 40µm		
1	Anchor rod	Steel acc. to EN 10087:1998, galvanised and coated	Steel acc. to EN 10087:1998, hot-dip galvanised and coated	Steel acc. to EN 10087:1998, sherardized and coated	Stainless steel, 1.4401, 1.4404, 1.4571, 1.4362, EN 10088:2005, coated	High corrosion resistant steel 1.4529, 1.4565 acc. to EN 10088:2005, coated
2a	Washer	Steel, zinc plated	Steel, zinc plated	Steel, zinc plated	Stainless steel, 1.4401, 1.4571, EN 10088:2005	High corrosion resistant steel 1.4529 or 1.4565, acc. to EN 10088:2005
2b	Washer with bore					
3	Hexagon nut	Property class 8 acc. to EN ISO 898-2:2012-08, galvanised	Property class 8 acc. to EN ISO 898-2:2012-08, hot-dip galvanised	Property class 8 acc. to EN ISO 898-2:2012-08, sherardized or hot-dip galvanised	ISO 3506:2009, A4-70, 1.4401, 1.4571, EN 10088:2005	ISO 3506:2009, Property class 70, high corrosion resistant steel 1.4529 or 1.4565, EN 10088:2005
4	Mortar cartridge	Vinylester resin, styrene free, mixing ratio 1:10				

Injection System W-VIZ

Product description

Anchor dimensions **W-VIZ-A** M16 – M24, Materials **W-VIZ-A**

Annex A4

Marking: e.g. \diamond 80 VMZ M10



Identifying mark of
manufacturing plant

80


Anchorage depth

VMZ

Trade name

M10

Size of internal thread



A4 additional marking
of stainless steel A4

HCR additional marking of
high corrosion resistant steel HCR

Table A4: Dimensions of anchor rod W-VIZ-IG

Anchor size W-VIZ-IG		40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20
Internal thread	-	M6		M8		M10		M12		M16		M20	
Number of cones	-	2	3	3	3	3	4	3	4	6	3	6	6
Outer diameter	d_k [mm]	8.0	8.0	9.7	10.7	12.5	12.5	16.5	16.5	16.5	19.7	22.0	24.0
Thread length	L_{th} [mm]	12	15	16	19	20	23	24	27	30	32	32	40
Total length	L [mm]	41	52	63	78	74	84	94	109	130	120	180	182
Length identifier	[mm]	L_{dh} < 18	L_{dh} > 19	L_{dh} < 22.5	L_{dh} > 23.5	L_{dh} < 27	L_{dh} > 28	L_{dh} < 31.5	32.5 < L_{dh} < 34.5	L_{dh} > 35.5	d_k < 21	d_k > 21	-

Table A5: Materials W-VIZ-IG

Part	Designation	Steel, zinc plated		Stainless steel A4	High corrosion resistant steel (HCR)
		galvanized	sherardized $\geq 40\mu m$		
1	Anchor rod	Steel acc. to EN 10087:1998, galvanized and coated	Steel acc. to EN 10087:1998, sherardized and coated	Stainless steel, 1.4401, 1.4404, 1.4571, 1.4362, EN 10088:2005, coated	High corrosion resistant steel 1.4529, 1.4565 acc. to EN 10088:2005, coated
4	Mortar cartridge	Vinylester resin, styrene free, mixing ratio 1:10			

Requirements of the fastening screw or the threaded rod and nut

- Minimum screw-in depth L_{sdmin} see Table B7:
- The length of screw or the threaded rod must depending on the thickness of fixture t_{fix} , available thread length L_{th} (=maximum available thread length, see Table B7:) and the minimum screw-in depth L_{sdmin} be established.
- $A_5 > 8\%$ ductility

Steel, zinc plated:

Minimum property class 8.8 according to EN ISO 898-1:2013 or EN ISO 898-2:2012

Stainless steel A4: Material 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362 according to EN 10088:2005

Minimum property class 70 according to EN ISO 3506:2009

High corrosion resistant steel (HCR): Material 1.4529; 1.4565 according to EN 10088:2005

Minimum property class 70 according to EN ISO 3506:2009

Injection System W-VIZ

Product description

Anchor parts, anchor dimensions, Materials W-VIZ-IG

Annex A5

Specifications of intended use

Injection System W-VIZ-A		M8	M10	M12	M16	M20	M24
Static or quasi-static action				✓			
Seismic action (Category C1 + C2)		-	✓	✓	✓	✓	✓
Cracked and uncracked concrete				✓			
Strength classes acc. to EN 206-1:2000 C20/25 to C50/60				✓			
Reinforced or unreinforced normal weight concrete acc. to EN 206-1:2000				✓			
Temperature Range I	-40 °C to +80 °C	max. short term temperature +80 °C and max. long term temperature +50 °C					
Temperature Range II	-40 °C to +120 °C	max. short term temperature +120 °C and max. long term temperature +72 °C					
Making of drill hole	Hammer drill bit			✓			
	Vacuum drill bit ¹⁾	-	✓	✓	✓	✓	✓
	Diamond drill bit (seismic action excluded)	-	✓	✓	✓	✓	✓
Installation allowable in	dry concrete			✓			
	wet concrete			✓			
	water-filled hole	-	-	✓ ²⁾	✓	✓	✓
Overhead installation admissible		✓	✓	✓	✓	✓	✓

¹⁾ e.g. Würth hammer drill bit with suction, MKT vacuum drill bit or Heller Duster Expert

²⁾ exception: W-VIZ-A 75M12 (Installation in water-filled drill hole is not allowed)

Injection System W-VIZ-IG		M6	M8	M10	M12	M16	M20
Static or quasi-static action					✓		
Seismic action (Category C1 + C2)					-		
Cracked and uncracked concrete					✓		
Strength classes acc. to EN 206-1:2000 C20/25 to C50/60					✓		
Reinforced or unreinforced normal weight concrete acc. to EN 206-1:2000					✓		
Temperature Range I	-40 °C to +80 °C	max short term temperature +80 °C and max long term temperature +50 °C					
Temperature Range II	-40 °C to +120 °C	max short term temperature +120 °C and max long term temperature +72 °C					
Making of drill hole	Hammer drill bit				✓		
	Vacuum drill bit ¹⁾	-	✓	✓	✓	✓	✓
	Diamond drill bit (seismic action excluded)	-	✓	✓	✓	✓	✓
Installation allowable in	dry concrete				✓		
	wet concrete				✓		
	water-filled hole	-	-	✓	✓	✓	✓
Overhead installation admissible		✓	✓	✓	✓	✓	✓

¹⁾ e.g. Würth hammer drill bit with suction, MKT vacuum drill bit or Heller Duster Expert

Injection System W-VIZ

Intended use
Specifications, installation conditions

Annex B1

Specifications of intended use

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc plated steel, stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure including industrial and marine environment or exposure to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other particular aggressive conditions (high corrosion resistant steel).

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages under static or quasi-static actions are designed in accordance with:
 - ETAG 001, Annex C, design method A, Edition August 2010 or
 - CEN/TS 1992-4:2009, design method A
- Anchorages under seismic actions (cracked concrete) are designed in accordance with:
 - EOTA Technical Report TR 045, Edition February 2013
 - Anchorages shall be positioned outside of critical regions (e.g. plastic hinges) of the concrete structure.
 - Fastenings in stand-off installation or with a grout layer are not allowed.

Installation:

- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- In case of aborted drill hole: the drill hole shall be filled with mortar.
- Drill hole must be cleaned directly prior to installation of the anchor or the drill hole has to be protected against re-contamination in an appropriate way until dispensing the mortar in the drill hole.
- Water filled drill holes (where admissible) must not be polluted – otherwise the cleaning of the drill hole must be repeated.
- The anchor component installation temperature shall be at least +5 °C; during curing of the injection mortar the temperature of the concrete must not fall below -5 °C. Curing time must be observed prior to loading the anchor.
- It must be ensured that icing does not occur in the drill hole.
- Optionally, the annular gap between anchor rod and fixture may be filled with injection adhesive WIT-VM 100, WIT-VIZ, WIT-EXPRESS, WIT-VM 100 express, WIT-VIZ express using the washer with bore (Part 2b, Annex A3) instead of the washer (Part 2a, Annex A3).

Injection System W-VIZ

Intended use
Specifications

Annex B2

Table B1: Processing and curing time WIT-VM 100, WIT-VIZ

Temperature in the drill hole	Maximum processing time	Minimum curing time	
		dry concrete	wet concrete
+ 40 °C	1.4 min	15 min	30 min
+ 35 °C to + 39 °C	1.4 min	20 min	40 min
+ 30 °C to + 34 °C	2 min	25 min	50 min
+ 20 °C to + 29 °C	4 min	45 min	1:30 h
+ 10 °C to + 19 °C	6 min	1:20 h	2:40 h
+ 5 °C to + 9 °C	12 min	2:00 h	4:00 h
0 °C to + 4 °C	20 min	3:00 h	6:00 h
- 4 °C to - 1 °C	45 min	6:00 h	12:00 h
- 5 °C	1:30 h	6:00 h	12:00 h

Table B2: Processing and curing time WIT-EXPRESS, WIT-VM 100 express, WIT-VIZ express

Temperature in the drill hole	Maximum processing time	Minimum curing time	
		dry concrete	wet concrete
+ 30 °C	1 min	10 min	20 min
+ 20 °C to + 29 °C	1 min	20 min	40 min
+ 10 °C to + 19 °C	3 min	40 min	80 min
+ 5 °C to + 9 °C	6 min	1:00 h	2:00 h
+ 0 °C to + 4 °C	10 min	2:00 h	4:00 h
- 4 °C to - 1 °C	20 min	4:00 h	8:00 h
- 5 °C	40 min	4:00 h	8:00 h

Injection System W-VIZ

Intended use
Processing and curing time

Annex B3

Table B3: Installation parameters, W-VIZ-A M8 – M12

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Effective anchorage depth	$h_{ef} \geq$	[mm]	40	50	60	75	75	70	80	95	100	110	125
Nominal diameter of drill hole	$d_0 =$	[mm]	10	10	12	12	12	14	14	14	14	14	14
Depth of drill hole	$h_0 \geq$	[mm]	42	55	65	80	80	75	85	100	105	115	130
Diameter of cleaning brush	$D \geq$	[mm]	10.8	10.8	13.0	13.0	13.0	15.0	15.0	15.0	15.0	15.0	15.0
Installation torque	$T_{inst} \leq$	[Nm]	10	10	15	15	25	25	25	25	30	30	30
Diameter of clearance hole in the fixture													
Pre-setting installation	$d_f \leq$	[mm]	9	9	12	12	14	14	14	14	14	14	14
Through-setting installation	$d_f \leq$	[mm]	-	-	14	14	14 ¹⁾ / 16	16	16	16	16	16	16

¹⁾ see Annex B11

Table B4: Installation parameters, W-VIZ-A M16 – M24



Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Effective anchorage depth	$h_{ef} \geq$	[mm]	90	105	125	145	160	115	170	190	170	200	225
Nominal diameter of drill hole	$d_0 =$	[mm]	18	18	18	18	18	22	24	24	26	26	26
Depth of drill hole	$h_0 \geq$	[mm]	98	113	133	153	168	120	180	200	185	215	240
Diameter of cleaning brush	$D \geq$	[mm]	19.0	19.0	19.0	19.0	19.0	23.0	25.0	25.0	27.0	27.0	27.0
Installation torque	$T_{inst} \leq$	[Nm]	50	50	50	50	50	80	80	80	100	120	120
Diameter of clearance hole in the fixture													
Pre-setting installation	$d_f \leq$	[mm]	18	18	18	18	18	22	24 (22)	24 (22)	26	26	26
Through-setting installation	$d_f \leq$	[mm]	20	20	20	20	20	24	26	26	28	28	28

Pre-setting installation

Through-setting installation

size M20 + M24
 $\geq 0.5 t_{fix}$

size M20 + M24
 $\geq 0.5 t_{fix}$



The annular gap in the clearance hole in the fixture has to be filled completely by excess mortar!

Injection System W-VIZ

Intended use
Installation parameters W-VIZ-A

Annex B4

Table B5: Minimum spacing and edge distance, W-VIZ-A M8 – M12

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Minimum thickness of concrete	h_{min}	[mm]	80	80	100	110 100 ¹⁾	110	110	110	130 125 ¹⁾	130	140	160
Cracked concrete													
Minimum spacing	s_{min}	[mm]	40	40	40	40	50	55	40	40	50	50	50
Minimum edge distance	c_{min}	[mm]	40	40	40	40	50	55	50	50	50	50	50
Uncracked concrete													
Minimum spacing	s_{min}	[mm]	40	40	50	50	50	55	55	55	80 ²⁾	80 ²⁾	80 ²⁾
Minimum edge distance	c_{min}	[mm]	40	40	50	50	50	55	55	55	55 ²⁾	55 ²⁾	55 ²⁾

Table B6: Minimum spacing and edge distance, W-VIZ-A M16 – M24

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Minimum thickness of concrete	h_{min}	[mm]	130	150	170 160 ¹⁾	190 180 ¹⁾	205 200 ¹⁾	160	230 220 ¹⁾	250 240 ¹⁾	230 220 ¹⁾	270 260 ¹⁾	300 290 ¹⁾
Cracked concrete													
Minimum spacing	s_{min}	[mm]	50	50	60	60	60	80	80	80	80	80	80
Minimum edge distance	c_{min}	[mm]	50	50	60	60	60	80	80	80	80	80	80
Uncracked concrete													
Minimum spacing	s_{min}	[mm]	50	60	60	60	60	80	80	80	80	105	105
Minimum edge distance	c_{min}	[mm]	50	60	60	60	60	80	80	80	80	105	105

¹⁾ The remote face of the concrete member shall be inspected to ensure there has been no break-through by drilling. In case of break-through, the ground of the drill hole shall be closed with high strength mortar. The full bonded length h_{ef} shall be achieved and any potential loss of injection mortar shall be compensated.

²⁾ For an edge distance $c \geq 80$ mm a minimum spacing $s_{min} = 55$ mm is applicable.

Injection System W-VIZ

Intended use
Minimum spacing and edge distance, W-VIZ-A

Annex B5

Installation instructions W-VIZ-A

Hole drilling and cleaning (hammer drill bit)

1	Pre-setting installation V		Use Hammer drill or air drill with drill bit and depth gauge. Drill perpendicular to concrete surface.
	Through-setting installation D		
2	V		W-VIZ-A M8 - M16: Blow out drill hole from the bottom with Blow-out pump at least two times. The Extension Tube with reduced diameter must be added to the Blow-out pump for the diameter M8.
			W-VIZ-A M20 - M24: Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.
	D		W-VIZ-A M10 - M16: Blow out drill hole from the bottom with Blow-out pump at least two times.
			W-VIZ-A M20 - M24: Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.
3	V		Check diameter of cleaning brush. If the brush can be pushed into the drill hole without any resistance, it must be replaced. Chuck brush into drill machine. Turn on drill machine. Brush drill hole back and forth along the entire drill hole depth at least two times while rotated by drill machine.
	D		
4	V		W-VIZ-A M8 - M16: Blow out drill hole from the bottom with Blow-out pump at least two times. The Extension Tube with reduced diameter must be added to the Blow-out pump for the diameter M8.
			W-VIZ-A M20 - M24: Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.
	D		W-VIZ-A M10 - M16: Blow out drill hole from the bottom with Blow-out pump at least two times.
			W-VIZ-A M20 - M24: Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.



Injection System W-VIZ

Intended use

Installation instructions **W-VIZ-A**
Hole drilling and cleaning (hammer drill bit)

Annex B6

Hole drilling and cleaning (vacuum drill bit)









1	Pre-setting installation V		Drill hole perpendicular to concrete surface by using a vacuum drill bit (see Annex B1).
	Through-setting installation D		The nominal underpressure of the vacuum cleaner must be at least 230 mbar / 23kPa. Make sure the dust extraction is working properly throughout the whole drilling process.
Additional cleaning is not necessary - continue with step 5!			

Injection System W-VIZ

Intended use
Installation instructions **W-VIZ-A**
Hole drilling and cleaning (vacuum drill bit)

Annex B7

Hole drilling and cleaning (diamond drill bit)





1	Pre-setting installation V		Use diamond drill with diamond drill bit and depth gauge. Drill perpendicular to concrete surface.
	Through-setting installation D		
2	V		Remove drill core at least up to the nominal hole depth and check drill hole depth.
	D		
3	V		Flushing of drill hole: Flush drill hole with water, starting from the bottom, until clear water gets out of the drill hole.
	D		
4	V		Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.
	D		

Injection System W-VIZ

Intended use
Installation instructions **W-VIZ-A**
Hole drilling and cleaning (diamond drill bit)

Annex B8

Injection









5	D + V		Check expiration date on cartridge. Never use when expired. Remove cap from cartridge. Screw Mixer Nozzle on cartridge. When using a new cartridge always use a new Mixer Nozzle. Never use cartridge without Mixer Nozzle and never use Mixer Nozzle without helix inside.
6	D + V		Insert cartridge in Dispenser. Before injecting discard mortar (at least 2 full strokes or a line of 10 cm) until it shows a consistent grey colour. Never use this mortar.
7	V		Prior to injection, check if Mixer Nozzle reaches the bottom of the drill hole. If it does not reach the bottom, plug Mixer Extension onto Mixer Nozzle in order to fill the drill hole properly. Fill hole with a sufficient quantity of injection mortar. Start from the bottom of the drill hole and work out to avoid trapping air pockets.
	D		

Injection System W-VIZ

Intended use
Installation instructions **W-VIZ-A**
Injection

Annex B9

Insertion of anchor rod

8	V		Insert the anchor rod W-VIZ-A by hand, rotating slightly up to the full embedment depth as marked on the anchor rod. The anchor rod is properly set when excess mortar seeps from the hole. If the hole is not completely filled, pull out anchor rod, let mortar cure, drill out hole and repeat entire cleaning process.
	D		Insert the anchor rod W-VIZ-A by hand, rotating slightly up to the full embedment depth. After the installation, the annular gap in the clearance hole in the fixture has to be filled completely by excess mortar. If the hole is not completely filled, pull out anchor rod, let mortar cure, drill out hole and repeat entire cleaning process.
9	V		Follow minimum curing time shown in Table B1 or Table B2 During curing time, anchor rod must not be moved or loaded.
	D		
10	V		Remove excess mortar.
	D		
11	D + V		The fixture can be mounted after curing time. Apply installation torque T_{inst} according to Table B3 or Table B4 by using torque wrench.
Optional	V		Annular gap between anchor rod and attachment may optionally be filled with mortar. Therefore replace regular washer by washer with bore and plug on reducing adapter on static mixer. Annular gap is completely filled, when excess mortar seeps out.

Injection System W-VIZ

Intended use
Installation instructions **W-VIZ-A**
Anchor installation





Annex B10

Installation instructions W-VIZ-A 75 M12

Through-setting installation with clearance between concrete and anchor plate

Work step 1-7 as illustrated in Annexes B6 – B9

Requirement: Diameter of clearance hole in the fixture $d_f \leq 14$ mm

8		Insert the anchor rod W-VIZ-A by hand, rotating slightly up to the full embedment depth.
9		Check if excess mortar seeps from the hole. If the hole is not completely filled, pull out anchor rod, let mortar cure, drill out hole and repeat the entire cleaning process. The annular gap in the fixture does not have to be filled.
10		During curing time according to Table B1 or Table B2 anchor rod must not be moved or loaded.
11		Washer and nut can be mounted after curing time and backfilling of anchor plate. Apply installation torque T_{inst} according to Table B3 by using torque wrench.

Injection System W-VIZ

Intended use

Installation instructions **W-VIZ-A 75 M12**


Through-setting installation with clearance between concrete and anchor plate

Annex B11

Table B7: Installation parameters W-VIZ-IG

Anchor size W-VIZ-IG			40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20
Effective anchorage depth	$h_{ef} =$	[mm]	40	50	60	75	70	80	90	105	125	115	170	170
Nominal diameter of drill hole	$d_0 =$	[mm]	10	10	12	12	14	14	18	18	18	22	24	26
Depth of drill hole	$h_0 \geq$	[mm]	42	55	65	80	80	85	98	113	133	120	180	185
Diameter of cleaning brush	$D \geq$	[mm]	10.8	10.8	13.0	13.0	15.0	15.0	19.0	19.0	19.0	23.0	25.0	27.0
Installation torque	$T_{inst} \leq$	[Nm]	8	8	10	10	15	15	25	25	25	50	50	80
Diameter of clearance hole in the fixture	$d_f \leq$	[mm]	7	7	9	9	12	12	14	14	14	18	18	22
Available thread length	L_{th}	[mm]	12	15	16	19	20	23	24	27	30	32	32	40
Minimum screw-in depth	L_{sdmin}	[mm]	7	7	9	9	12	12	14	14	14	18	18	22
Minimum thickness of concrete	h_{min}	[mm]	80	80	100	110	110	110	130	150	170 160 ¹⁾	160	230 220 ¹⁾	230 220 ¹⁾
Cracked concrete														
Minimum spacing	s_{min}	[mm]	40	40	40	40	55	40	50	50	60	80	80	80
Minimum edge distance	c_{min}	[mm]	40	40	40	40	55	50	50	50	60	80	80	80
Uncracked concrete														
Minimum spacing	s_{min}	[mm]	40	40	50	50	55	55	50	60	60	80	80	80
Minimum edge distance	c_{min}	[mm]	40	40	50	50	55	55	50	60	60	80	80	80

¹⁾ The remote face of the concrete member shall be inspected to ensure there has been no break-through by drilling. In case of break-through the ground of the drill hole shall be closed with high strength mortar. The full bonded length h_{ef} shall be achieved and any potential loss of injection mortar shall be compensated.








Injection System W-VIZ

Intended use
Installation parameters **W-VIZ-IG**


Annex B12

Installation instructions W-VIZ-IG

Hole drilling and cleaning (hammer drill bit)

1		Use Hammer drill or air drill with drill bit and depth gauge. Drill perpendicular to concrete surface.
2		W-VIZ-IG M6 - M12: Blow out drill hole from the bottom with Blow-out pump at least two times. The Extension Tube with reduced diameter must be added to the Blow-out pump for the diameter M6.
3		W-VIZ-IG M16 - M20: Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.
4		W-VIZ-IG M6 - M12: Blow out drill hole from the bottom with Blow-out pump at least two times. The Extension Tube with reduced diameter must be added to the Blow-out pump for the diameter M6.
4		W-VIZ-IG M16 - M20: Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.

Hole drilling and cleaning (vacuum drill bit)





1		Drill hole perpendicular to concrete surface by using a vacuum drill bit (see Annex B1). The nominal underpressure of the vacuum cleaner must be at least 230 mbar / 23kPa. Make sure the dust extraction is working properly throughout the whole drilling process.
Additional cleaning is not necessary, go to step 5.		

Injection System W-VIZ




Intended use
Installation instructions **W-VIZ-IG**
Drilling and cleaning (hammer drill bit or a vacuum drill bit)

Annex B13





Hole drilling and cleaning (diamond drill bit)

1		Use diamond drill with diamond drill bit and depth gauge. Drill perpendicular to concrete surface.
2		Remove drill core at least up to the nominal hole depth and check drill hole depth.
3		Flushing of drill hole: Flush drill hole with water, starting from the bottom, until clear water gets out of the drill hole.
4		Connect Air Blower to compressed air (min. 6 bar, oil-free). Open air valve and blow out drill hole along the entire depth with back and forth motion at least two times.

Injection

5		Check expiration date on cartridge. Never use when expired. Remove cap from cartridge. Screw Mixer Nozzle on cartridge. When using a new cartridge always use a new Mixer Nozzle. Never use cartridge without Mixer Nozzle and never use Mixer Nozzle without helix inside.
6		Insert cartridge in dispenser. Before injecting discard mortar (at least 2 full strokes or a line of 10 cm) until it shows a consistent grey colour. Never use this mortar.
7		Prior to injection, check if Mixer Nozzle reaches the bottom of the drill hole. If it does not reach the bottom, plug Mixer Extension onto Mixer Nozzle in order to fill the drill hole properly. Fill cleaned drill hole with a sufficient quantity of injection mortar. Start from the bottom of the drill hole and work out to avoid trapping air pockets.

Setting of anchor

8		Insert the anchor rod W-VIZ-IG by hand, rotating slightly up to about 1mm below the concrete surface in the drill hole. The anchor rod is properly set when excess mortar seeps from the hole. If the hole is not completely filled, pull out anchor rod, let mortar cure, drill out hole and repeat the entire cleaning process.
9		Follow minimum curing time shown in Table B1 and Table B2. During curing time anchor rod must not be moved or loaded.
10		Remove excess mortar.
11		The fixture can be mounted after curing time. Apply installation torque T_{inst} according to Table B7 by using torque wrench.

Injection System W-VIZ

Intended use

Installation instructions **W-VIZ-IG**
Drilling and cleaning (diamond drill bit)
Anchor installation

Annex B14

Table C1: Characteristic values for **tension loads, W-VIZ-A M8 – M12, cracked concrete**, static and quasi-static action

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12		
Installation safety factor		$\gamma_2=\gamma_{inst}$	[-]		1.0										
Steel failure															
Characteristic tension resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	15	18	25	35	49	54	57						
	A4, HCR	[kN]	15	18	25	35	49	54	57						
Partial safety factor		γ_{Ms}	[-]		1.5										
Pull-out															
Characteristic resistance $N_{Rk,p}$ in concrete C20/25	50°C / 80°C ²⁾	[kN]	1)												
	72°C / 120°C ²⁾	[kN]	5	7.5	12	12	12	16	20	20	30	30	30		
Increasing factor		ψ_c	[-]		$\left(\frac{f_{ck,cube}}{25}\right)^{0,5}$										
Concrete cone failure															
Effective anchorage depth		$h_{ef} \geq$	[mm]		40	50	60	75	75	70	80	95	100	110	125
Factor acc. to CEN/TS 1992-4		k_{cr}	[-]		7.2										

¹⁾ Pull-out failure is not decisive

²⁾ Maximum long term temperature / Maximum short term temperature

Table C2: Characteristic values for **tension loads, W-VIZ-A M16 – M24, cracked concrete**, static and quasi-static action

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)	
Installation safety factor		$\gamma_2=\gamma_{inst}$	[-]	1.0										
Steel failure														
Characteristic tension resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	88	95	111		97	96	188		222			
	A4, HCR	[kN]	88	95	111		97	114	165		194			
Partial safety factor		γ_{Ms}	[-]	1.5				1.68	1.5		1.5			
Pull-out														
Characteristic resistance $N_{Rk,p}$ in concrete C20/25	50°C / 80°C ²⁾	[kN]	1)											
	72°C / 120°C ²⁾	[kN]	25	30	50		51	30	60		75			
Increasing factor		ψ_C	[-]	$\left(\frac{f_{ck,cube}}{25}\right)^{0,5}$										
Concrete cone failure														
Effective anchorage depth		$h_{ef} \geq$	[mm]	90	105	125	145	160	115	170	190	170	200	225
Factor acc. to CEN/TS 1992-4		k_{cr}	[-]	7.2										

¹⁾ Pull-out failure is not decisive

²⁾ Maximum long term temperature / Maximum short term temperature

Injection System W-VIZ

Performance

Characteristic values for **tension loads, W-VIZ-A** in **cracked concrete**, static and quasi-static action

Annex C1

Table C3: Characteristic values for **tension loads, W-VIZ-A M8 – M12**
in **uncracked concrete**, static and quasi-static action

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12	
Installation safety factor		$\gamma_2=\gamma_{inst}$	[-]		1.0									
Steel failure														
Characteristic tension resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	15	18	25	35	49	54	57					
	A4, HCR	[kN]	15	18	25	35	49	54	57					
Partial safety factor		γ_{Ms}	[-]		1.5									
Pull-out														
Characteristic resistance $N_{Rk,p}$ in uncracked concrete C20/25	50°C / 80°C ²⁾	[kN]	9	1 ¹⁾	1 ¹⁾	1 ¹⁾			40	1 ¹⁾	50	50		
	72°C / 120°C ²⁾	[kN]	6	9	16	16	16	25	25	30	30	30		
Splitting														
Splitting for standard thickness of concrete member (The higher resistance of Case 1 and Case 2 may be applied.)														
Standard thickness of concrete		$h_{std} \geq 2 h_{ef}$	[mm]	100	120	150	150	140	160	190	200	220	250	
Case 1 ($N^0_{Rk,c}$ has to be replaced by $N^0_{Rk,sp}$)														
Characteristic resistance in uncracked concrete C20/25		$N^0_{Rk,sp}$	[kN]	7.5	9	16	20	20	20	1 ¹⁾	30	40	40	40
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$	[mm]	3 h_{ef}										
Case 2														
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$	[mm]	6 h_{ef}	5 h_{ef}	7 h_{ef}	7 h_{ef}	5 h_{ef}	3 h_{ef}	5 h_{ef}	4 h_{ef}	6 h_{ef}	5 h_{ef}	
Splitting for minimum thickness of concrete member (The higher resistance of Case 1 and Case 2 may be applied.)														
Minimum thickness of concrete		$h_{min} \geq$	[mm]	80	100	110	110	110	125	130	140	160		
Case 1 ($N^0_{Rk,c}$ has to be replaced by $N^0_{Rk,sp}$)														
Characteristic resistance in uncracked concrete C20/25		$N^0_{Rk,sp}$	[kN]	7.5	-	16	16	20	25	25	30	30	30	
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$	[mm]	3 h_{ef}	-	3 h_{ef}	3 h_{ef}							
Case 2														
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$	[mm]	6 h_{ef}	7 h_{ef}	6 h_{ef}	7 h_{ef}	7 h_{ef}	7 h_{ef}	6 h_{ef}	7 h_{ef}	6 h_{ef}	6 h_{ef}	
Increasing factor for $N_{Rk,p}$ and $N^0_{Rk,sp}$		ψ_C	[-]	$\left(\frac{f_{ck,cube}}{25}\right)^{0,5}$										
Concrete cone failure														
Effective anchorage depth		$h_{ef} \geq$	[mm]	40	50	60	75	75	70	80	95	100	110	125
Factor acc. to CEN/TS 1992-4		k_{ucr}	[-]	10.1										

¹⁾ Pull-out failure is not decisive

²⁾ Maximum long term temperature / Maximum short term temperature

Injection System W-VIZ

Performance

Characteristic values for **tension loads, W-VIZ-A M8 – M12**,
uncracked concrete, static and quasi-static action

Annex C2

Table C4: Characteristic values for **tension loads, W-VIZ-A M16 – M24, uncracked concrete**, static and quasi-static action

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Installation safety factor		$\gamma_2=\gamma_{inst}$ [-]	1.0										
Steel failure													
Characteristic tension resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	88	95	111	111	97	96	188	188	222	222	222
	A4, HCR	[kN]	88	95	111	111	97	114	165	165	194	194	194
Partial safety factor		γ_{Ms} [-]	1.5					1.68	1.5		1.5		
Pull-out													
Characteristic resistance $N_{Rk,p}$ in uncracked concrete C20/25	50°C / 80°C ²⁾	[kN]	1)			75	90	1)			1)		
	72°C / 120°C ²⁾	[kN]	25	35	50	50	53	40	75	75	95	95	95
Splitting													
Splitting for standard thickness of concrete (The higher resistance of Case 1 and Case 2 may be applied.)													
Standard thickness of concrete		$h_{std} \geq 2 h_{ef}$ [mm]	180	200	250	290	320	230	340	380	340	400	450
Case 1 ($N^0_{Rk,c}$ has to be replaced by $N^0_{Rk,sp}$)													
Characteristic resistance in uncracked concrete C20/25		$N^0_{Rk,sp}$ [kN]	40	50	50	60	80	1)		115	1)		140
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$ [mm]	3 h_{ef}										
Case 2													
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$ [mm]	4 h_{ef}	4 h_{ef}	4 h_{ef}	4 h_{ef}	4 h_{ef}	3 h_{ef}	3 h_{ef}	4 h_{ef}	3 h_{ef}	3 h_{ef}	3.6 h_{ef}
Splitting for minimum thickness of concrete (The higher resistance of Case 1 and Case 2 may be applied.)													
Minimum thickness of concrete		$h_{min} \geq$ [mm]	130	150	160	180	200	160	220	240	220	260	290
Case 1 ($N^0_{Rk,c}$ has to be replaced by $N^0_{Rk,sp}$)													
Characteristic resistance in uncracked concrete C20/25		$N^0_{Rk,sp}$ [kN]	35	50	40	50	71	-	75	75	1)	115	115
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$ [mm]	3 h_{ef}										
Case 2													
Spacing (edge distance)		$s_{cr,sp} (= 2 c_{cr,sp})$ [mm]	5 h_{ef}	5 h_{ef}	6 h_{ef}	5 h_{ef}	5 h_{ef}	5 h_{ef}	5.2 h_{ef}	4.4 h_{ef}	5.2 h_{ef}	4.4 h_{ef}	4.4 h_{ef}
Increasing factor for $N_{Rk,p}$ and $N^0_{Rk,sp}$		ψ_C [-]	$\left(\frac{f_{ck,cube}}{25}\right)^{0.5}$										
Concrete cone failure													
Effective anchorage depth		$h_{ef} \geq$ [mm]	90	105	125	145	160	115	170	190	170	200	225
Factor acc. to CEN/TS 1992-4		k_{Ucr} [-]	10.1										

¹⁾ Pull-out failure is not decisive

²⁾ Maximum long term temperature / Maximum short term temperature

Injection System W-VIZ

Performance
Characteristic values for **tension loads, W-VIZ-A M16 – M24, uncracked concrete**, static and quasi-static action

Annex C3

Table C5: Characteristic values for **shear load, W-VIZ-A M8 – M12, cracked and uncracked concrete**, static and quasi-static action

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Installation safety factor $\gamma_2=\gamma_{inst}$		[-]	1.0										
Steel failure without lever arm													
Characteristic shear resistance $V_{Rk,s}$	Steel, zinc plated	[kN]	14		21		34						
	A4, HCR	[kN]	15		23		34						
Partial safety factor γ_{Ms}		[-]	1.25										
Factor for ductility k_2		[-]	1.0										
Steel failure with lever arm													
Characteristic bending moments $M^0_{Rk,s}$	Steel, zinc plated	[Nm]	30		60		105						
	A4, HCR	[Nm]	30		60		105						
Partial safety factor γ_{Ms}		[-]	1.25										
Concrete pry-out failure													
Factor k acc. ETAG 001, Annex C or k_3 acc. CEN/TS 1992-4		$k_{(3)}$ [-]	2										
Concrete edge failure													
Effective length of anchor in shear load l_f		[mm]	40	50	60	75	75	70	80	95	100	110	125
Diameter of anchor d_{nom}		[mm]	10		12		12	14					

Injection System W-VIZ

Performance


Characteristic values for **shear load, W-VIZ-A M8 – M12, cracked and uncracked concrete**, static and quasi-static action

Annex C4

Table C6: Characteristic values for **shear load, W-VIZ-A M16 – M24, cracked and uncracked concrete, static and quasi-static action**

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Installation safety factor $\gamma_2=\gamma_{inst}$		[-]	1.0										
Steel failure without lever arm													
Characteristic shear resistance $V_{Rk,s}$	Steel, zinc plated	[kN]	63					70	149 ¹⁾ (98)		178 ¹⁾ (141)		
	A4, HCR	[kN]	63					86	131 ¹⁾ (86)		156 ¹⁾ (123)		
Partial safety factor γ_{Ms}		[-]	1.25					1.4	1.25		1.25		
Factor for ductility k_2		[-]	1.0										
Steel failure with lever arm													
Characteristic bending moments $M^0_{Rk,s}$	Steel, zinc plated	[Nm]	266					392	519		896		
	A4, HCR	[Nm]	266					454		784			
Partial safety factor γ_{Ms}		[-]	1.25					1.4	1.25		1.25		
Concrete pry-out failure													
Factor k acc. ETAG 001, Annex C or k_3 acc. CEN/TS 1992-4		$k_{(3)}$ [-]	2										
Concrete edge failure													
Effective length of anchor in shear load l_f		[mm]	90	105	125	145	160	115	170	190	170	200	225
Diameter of anchor d_{nom}		[mm]	18					22	24		26		

¹⁾ This value may only be applied if $l_t \geq 0.5 t_{fix}$



Injection System W-VIZ

Performance

Characteristic values for **shear load, W-VIZ-A M16 – M24, cracked and uncracked concrete, static and quasi-static action**

Annex C5

Table C7: Characteristic resistances for **seismic loading**
W-VIZ-A M10 – M12 performance category C1 and C2

Anchor size W-VIZ-A			60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Tension loads											
Installation safety factor		$\gamma_2=\gamma_{inst}$ [-]	1.0								
Steel failure, steel zinc plated											
Characteristic resistance C1	$N_{Rk,s,seis,C1}$	[kN]	25		35	49	54			57	
Characteristic resistance C2	$N_{Rk,s,seis,C2}$	[kN]	25		35	49	54			57	
Steel failure, stainless steel A4, HCR											
Characteristic resistance C1	$N_{Rk,s,seis,C1}$	[kN]	25		35	49	54			57	
Characteristic resistance C2	$N_{Rk,s,seis,C2}$	[kN]	25		35	49	54			57	
Partial safety factor		$\gamma_{Ms,seis}$ [-]	1.5								
Pull-out											
Characteristic resistance C1	$N_{Rk,p,seis,C1}$	50°C / 80°C ¹⁾	[kN]	14.5		14.5	30.6	36.0	41.5	42.8	
		72°C / 120°C ¹⁾	[kN]	10.9		10.9	20.0		30.0		
Characteristic resistance C2	$N_{Rk,p,seis,C2}$	50°C / 80°C ¹⁾	[kN]	7.4		7.4	8.7		17.6		
		72°C / 120°C ¹⁾	[kN]	5.1		5.1	6.5		12.3		

Shear loads				
Steel failure without lever arm, steel zinc plated				
Characteristic resistance C1	$V_{Rk,s,seis,C1}$	[kN]	11.8	27.2
Characteristic resistance C2	$V_{Rk,s,seis,C2}$	[kN]	12.6	27.2
Partial safety factor	$\gamma_{Ms,seis}$	[-]	1.25	
Steel failure without lever arm, stainless steel A4, HCR				
Characteristic resistance C1	$V_{Rk,s,seis,C1}$	[kN]	12.9	27.2
Characteristic resistance C2	$V_{Rk,s,seis,C2}$	[kN]	13.8	27.2
Partial safety factor	$\gamma_{Ms,seis}$	[-]	1.25	
Steel failure with lever arm				
Characteristic bending moment C1	$M^0_{Rk,s,seis,C1}$	[Nm]	no performance determined	
Characteristic bending moment C2	$M^0_{Rk,s,seis,C2}$	[Nm]	no performance determined	

¹⁾ Maximum long term temperature / Maximum short term temperature

Injection System W-VIZ

Performance

Characteristic resistances for **seismic loading**, W-VIZ-A M10 – M12, performance category **C1** and **C2**

Annex C6

Table C8: Characteristic resistances for **seismic loading**
W-VIZ-A M16 – M24 performance category **C1** and **C2**

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Tension loads													
Installation safety factor		$\gamma_2=\gamma_{inst}$	[-]	1.0									
Steel failure, steel zinc plated													
Characteristic resistance C1		$N_{Rk,s,seis,C1}$	[kN]	88	95	111	97	96	188	222			
Characteristic resistance C2		$N_{Rk,s,seis,C2}$	[kN]	88	95	111	97	96	188	222			
Steel failure, stainless steel A4, HCR													
Characteristic resistance C1		$N_{Rk,s,seis,C1}$	[kN]	88	95	111	97	114	165	194			
Characteristic resistance C2		$N_{Rk,s,seis,C2}$	[kN]	88	95	111	97	114	165	194			
Partial safety factor		$\gamma_{Ms,seis}$	[-]	1.5				1.68	1.5	1.5			
Pull-out													
Characteristic resistance C1	$N_{Rk,p,seis,C1}$	50°C / 80°C ¹⁾	[kN]	30.7	38.7	43.7	44.4	88.2	90.7				
		72°C / 120°C ¹⁾	[kN]	25.0	30.0	38.5	29.4	55.8	59.3				
Characteristic resistance C2	$N_{Rk,p,seis,C2}$	50°C / 80°C ¹⁾	[kN]	16.3	22.1	26.1	30.9	59.7	59.7				
		72°C / 120°C ¹⁾	[kN]	10.5	14.4	19.5	16.2	44.4	44.4				

Shear loads						
Steel failure without lever arm, steel zinc plated						
Characteristic resistance C1	$V_{Rk,s,seis,C1}$	[kN]	39.1	39.1	82.3	107
Characteristic resistance C2	$V_{Rk,s,seis,C2}$	[kN]	50.4	51.0	108.8 ¹⁾ (71.5)	154.9 ¹⁾ (122.7)
Partial safety factor	$\gamma_{Ms,seis}$	[-]	1.25	1.4	1.25	1.25
Steel failure without lever arm, stainless steel A4, HCR						
Characteristic resistance C1	$V_{Rk,s,seis,C1}$	[kN]	39.1	39.1	72.2	93
Characteristic resistance C2	$V_{Rk,s,seis,C2}$	[kN]	50.4	62.6	95.6 ¹⁾ (62.8)	135.7 ¹⁾ (107)
Partial safety factor	$\gamma_{Ms,seis}$	[-]	1.25	1.4	1.25	1.25
Steel failure with lever arm						
Characteristic bending moment C1	$M^0_{Rk,s,seis,C1}$	[Nm]	no performance determined			
Characteristic bending moment C2	$M^0_{Rk,s,seis,C2}$	[Nm]	no performance determined			

¹⁾ This value may only be applied if $l_t \geq 0,5 t_{fix}$, (see Annex C5)

Injection System W-VIZ

Performance

Characteristic resistances for **seismic loading**, W-VIZ-A M16 – M24,
performance category **C1** and **C2**

Annex C7

Table C9: Displacements under tension loads, W-VIZ-A M8 – M12

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Tension load in cracked concrete	N	[kN]	4.3	6.1	8.0	11.1	11.1	10.0	12.3	15.9	17.1	19.8	24.0
Displacement	δ_{N0}	[mm]	0.5	0.5	0.5	0.6	0.6	0.6	0.6	0.6	0.6	0.7	0.7
	$\delta_{N\infty}$	[mm]	1.3										
Tension load in uncracked concrete	N	[kN]	4.3	8.5	11.1	15.6	15.6	14.1	17.2	19.0	24.0	23.8	23.8
Displacement	δ_{N0}	[mm]	0.2	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.6	0.6
	$\delta_{N\infty}$	[mm]	1.3										
Displacements under seismic tension loads C2													
Displacements for DLS	$\delta_{N,seis,C2(DLS)}$	[mm]	-	-	1.0	1.0		1.3		1.1			
Displacements for ULS	$\delta_{N,seis,C2(ULS)}$	[mm]	-	-	3.0	3.0		3.9		3.0			

Table C10: Displacements under tension loads, W-VIZ-A M16 – M24

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Tension load in cracked concrete	N	[kN]	14.6	18.4	24.0	30.0	34.7	21.1	38.0	44.9	38.0	48.5	57.9
Displacement	δ_{N0}	[mm]	0.7	0.7	0.7	0.8	1.2	0.7	0.8	0.8	0.8	0.9	0.9
	$\delta_{N\infty}$	[mm]	1.3				1.6	1.1	1.3		1.3		
Tension load in uncracked concrete	N	[kN]	20.5	25.9	33.0	35.7	48.1	29.6	53.3	63.0	53.3	67.9	81.1
Displacement	δ_{N0}	[mm]	0.6	0.6	0.6	0.6	0.8	0.5	0.6	0.6	0.6	0.6	0.6
	$\delta_{N\infty}$	[mm]	1.3				1.6	1.1	1.3		1.3		
Displacements under seismic tension loads C2													
Displacements for DLS	$\delta_{N,seis,C2(DLS)}$	[mm]	1.6		1.5			1.7	1.9		1.9		
Displacements for ULS	$\delta_{N,seis,C2(ULS)}$	[mm]	3.7		4.4			4.0	4.5		4.5		

Injection System W-VIZ

Performance
Displacements under tension loads, **W-VIZ-A**

Annex C8

Table C11: Displacements under shear loads W-VIZ-A M8 – M12

Anchor size W-VIZ-A			40 M8	50 M8	60 M10	75 M10	75 M12	70 M12	80 M12	95 M12	100 M12	110 M12	125 M12
Shear load	V	[kN]	8.3		13.3		19.3						
Displacements	δ_{V0}	[mm]	2.4	2.5	2.9		3.3						
	$\delta_{V\infty}$	[mm]	3.6	3.8	4.4		5.0						
Displacements under seismic shear loads C2													
Displacements for DLS	$\delta_{V,seis,C2(DLS)}$	[mm]	-	-	2.1		2.5						
Displacements for ULS	$\delta_{V,seis,C2(ULS)}$	[mm]	-	-	3.7		5.1						

Table C12: Displacements under shear loads W-VIZ-A M16 – M24

Anchor size W-VIZ-A			90 M16	105 M16	125 M16	145 M16	160 M16	115 M20	170 M20 (LG)	190 M20 (LG)	170 M24 (LG)	200 M24 (LG)	225 M24 (LG)
Shear load	V	[kN]	36					44	75 (49)	89 (71)			
Displacements	δ_{V0}	[mm]	3.8					3.0	4.3 (3.0)	4.6 (3.5)			
	$\delta_{V\infty}$	[mm]	5.7					4.5	6.5 (4.5)	6.9 (5.3)			
Displacements under seismic shear loads C2													
Displacements for DLS	$\delta_{V,seis,C2(DLS)}$	[mm]	2.9					3.5		3.7			
Displacements for ULS	$\delta_{V,seis,C2(ULS)}$	[mm]	6.8					9.3		9.3			

Injection System W-VIZ

Performance
Displacements under shear loads, **W-VIZ-A**

Annex C9

Table C13: Characteristic values for **tension load, W-VIZ-IG**, cracked concrete

Anchor size W-VIZ-IG			40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20	
Installation safety factor		$\gamma_2=\gamma_{inst}$	[-]	1.0											
Steel failure															
Characteristic tension resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	15	16	19	29	35		67		52	125	108		
	A4, HCR	[kN]	11		19	21	33		47		65	88	94		
Partial safety factor		γ_{Ms}	[-]	1.5											
Pull-out															
Characteristic resistance $N_{Rk,p}$ in cracked concrete C20/25	50°C / 80°C ²⁾	[kN]	1)												
	72°C / 120°C ²⁾	[kN]	5	7.5	12		16	20	20	30	50	30	60	75	
Increasing factor		ψ_c	[-]	$\left(\frac{f_{ck,cube}}{25}\right)^{0,5}$											
Concrete cone failure															
Effective anchorage depth		h_{ef}	[mm]	40	50	60	75	70	80	90	105	125	115	170	170
Factor according to CEN/TS 1992-4		k_{cr}	[-]	7.2											

¹⁾ Pull-out failure is not decisive

²⁾ Maximum long term temperature / Maximum short term temperature

Injection System W-VIZ

Performance

Characteristic values for **tension load, W-VIZ-IG**, cracked concrete

Annex C10

Table C14: Characteristic values for **tension load, W-VIZ-IG, uncracked concrete**

Anchor size W-VIZ-IG			40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20
Installation safety factor $\gamma_2=\gamma_{inst}$		[-]	1-0											
Steel failure														
Characteristic tension resistance $N_{Rk,s}$	Steel, zinc plated	[kN]	15	16	19	29	35		67		52	125	108	
	A4, HCR	[kN]	11		19	21	33		47		65	88	94	
Partial safety factor γ_{Ms}		[-]	1.5											
Pull-out														
Characteristic resistance $N_{Rk,p}$ in uncracked concrete C20/25	50°C / 80°C ²⁾	[kN]	9	1 ¹⁾	1 ¹⁾									
	72°C / 120°C ²⁾	[kN]	6	9	16		16	25	25	35	50	40	75	95
Splitting														
Splitting for standard thickness of concrete (The higher resistance of Case 1 and Case 2 may be applied.)														
Standard thickness of concrete $h_{std} \geq 2h_{ef}$		[mm]	100		120	150	140	160	180	200	250	230	340	340
Case 1 ($N^0_{Rk,c}$ has to be replaced by $N^0_{Rk,sp}$)														
Characteristic resistance in concrete C20/25		$N^0_{Rk,sp}$ [kN]	7.5	9	16	20	20	1 ¹⁾	40	50	50	1 ¹⁾		1 ¹⁾
Spacing (edge distance) $s_{cr,sp} (= 2 C_{cr,sp})$		[mm]	3 h_{ef}											
Case 2														
Spacing (edge distance) $s_{cr,sp} (= 2 C_{cr,sp})$		[mm]	6 h_{ef}	6 h_{ef}	5 h_{ef}	7 h_{ef}	5 h_{ef}	3 h_{ef}	4 h_{ef}	4 h_{ef}	4 h_{ef}	3 h_{ef}	3 h_{ef}	3 h_{ef}
Splitting for minimum thickness of concrete (The higher resistance of Case 1 and Case 2 may be applied.)														
Minimum thickness of concrete $h_{min} \geq$		[mm]	80		100	110	110		130	150	160	160	220	220
Case 1 ($N^0_{Rk,c}$ has to be replaced by $N^0_{Rk,sp}$)														
Characteristic resistance in concrete C20/25		$N^0_{Rk,sp}$ [kN]	7.5	-	16		20	25	35	50	40	-	75	1 ¹⁾
Spacing (edge distance) $s_{cr,sp} (= 2 C_{cr,sp})$		[mm]	3 h_{ef}											
Case 2														
Spacing (edge distance) $s_{cr,sp} (= 2 C_{cr,sp})$		[mm]	6 h_{ef}	7 h_{ef}	6 h_{ef}	7 h_{ef}	7 h_{ef}	6 h_{ef}	5 h_{ef}	5 h_{ef}	6 h_{ef}	5 h_{ef}	5.2 h_{ef}	5.2 h_{ef}
Increasing factor for $N_{Rk,p}$ and $N^0_{Rk,sp}$		ψ_c [-]	$\left(\frac{f_{ck,cube}}{25}\right)^{0,5}$											
Concrete cone failure														
Effective anchorage depth h_{ef}		[mm]	40	50	60	75	70	80	90	105	125	115	170	170
Factor according to CEN/TS 1992-4 k_{Ucr}		[-]	10.1											

¹⁾ Pull-out failure is not decisive

²⁾ Maximum long term temperature / Maximum short term temperature

Injection System W-VIZ

Performance

Characteristic values for tension loads, **W-VIZ-IG**, uncracked concrete

Annex C11

Table C15: Characteristic values for **shear load, W-VIZ-IG, cracked and uncracked concrete**

Anchor size W-VIZ-IG			40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20	
Installation safety factor		$\gamma_2=\gamma_{inst}$	[-]		1.0										
Steel failure without lever arm															
Characteristic shear resistance $V_{Rk,s}$	Steel, zinc plated	[kN]	8.0		9.5	15	18		34		26		63	54	
	A4, HCR	[kN]	5.5		9.5	10	16		24		32		44	47	
Partial safety factor		γ_{Ms}	[-]		1.25										
Factor for ductility		k_2	[-]		1.0										
Steel failure with lever arm															
Characteristic bending moments $M^0_{Rk,s}$	Steel, zinc plated	[kN]	12		30		60		105		212		266	519	
	A4, HCR	[kN]	8.5		21		42		74		187		187	365	
Partial safety factor		γ_{Ms}	[-]		1.25										
Concrete pry-out failure															
Factor k acc. ETAG 001, Annex C or k_3 acc. CEN/TS 1992-4		$k_{(3)}$	[-]		2										
Concrete edge failure															
Effective length of anchor in shear load		l_f	[mm]	40	50	60	75	70	80	90	105	125	115	170	170
Diameter of anchor		d_{nom}	[mm]	10		12		14		18		22		24	26

Table C16: Displacements under **tension loads, W-VIZ-IG**

Anchor size W-VIZ-IG			40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20
Tension load in cracked concrete	N	[kN]	4.3	6.1	8.0	11.1	10.0	12.3	14.6	18.4	24.0	21.1	38.0	38.0
Displacement	δ_{N0}	[mm]	0.5		0.5	0.6	0.6		0.7			0.7	0.8	0.8
	$\delta_{N\infty}$	[mm]					1.3					1.1	1.3	1.3
Tension load in uncracked concrete	N	[kN]	4.3	8.5	11.1	15.6	14.1	17.2	20.5	25.9	33.0	29.6	53.3	53.3
Displacement	δ_{N0}	[mm]	0.2	0.4	0.4		0.4		0.6			0.5	0.6	0.6
	$\delta_{N\infty}$	[mm]					1.3					1.1	1.3	1.3

Table C17: Displacements under **shear loads, W-VIZ-IG**

Anchor size W-VIZ-IG			40 M6	50 M6	60 M8	75 M8	70 M10	80 M10	90 M12	105 M12	125 M12	115 M16	170 M16	170 M20
Shear load	V	[kN]	4.6		5.4	8.4	10.1		19.3			14.8	35.8	30.7
Displacement	δ_{V0}	[mm]	0.4		0.5	0.4	0.5		1.2			0.8	1.9	1.2
	$\delta_{V\infty}$	[mm]	0.7		0.8	0.7	0.8		1.9			1.2	2.8	1.9
Shear load	V	[kN]	3.2		5.4	5.9	9.3		13.5			18.5	25.2	26.9
Displacement	δ_{V0}	[mm]	0.3		0.5	0.3	0.5		0.9			1.0	1.4	1.1
	$\delta_{V\infty}$	[mm]	0.4		0.7	0.5	0.7		1.4			1.5	2.1	1.6

Injection System W-VIZ

Performance

Characteristic values for **shear load, W-VIZ-IG, cracked and uncracked concrete, Displacements**

Annex C12