

Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-16/0580

of 11 September 2017

English translation prepared by DIBt – Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:	Deutsches Institut für Bautechnik
Trade name of the construction product	ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink
Product family to which the construction product belongs	Microprismatic retro-reflective sheetings
Manufacturer	ORAFOL Europe GmbH Orafolstraße 2 16515 Oranienburg DEUTSCHLAND
Manufacturing plant	ORAFOL Europe GmbH Orafolstraße 2 16515 Oranienburg DEUTSCHLAND
This European Technical Assessment contains	21 pages including 4 annexes which form an integral part of this assessment
This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of	EAD 120001-01-0106
This version replaces	ETA-16/0580 issued on 20 October 2016

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part**1 Technical description of the product**

The product consists of retro-reflective sheeting on the basis of microprisms, which consist of optical elements, where the retro-reflection is created by total internal reflection on prisms. The microprisms are moulded in a transparent polymer enclosed in air capsules and provided with an adhesive, which can connect the sheeting with a substrate. The sheeting has a smooth surface and a regular structure visible on the surface forming the air capsules and serving to identify the orientation.

The product is delivered as reflective sheeting, the types of which are stated in Table 1.

Trade name	Component	Colour/Code		Properties
ORALITE® 6710 Engineer Prismatic Grade	Self-adhesive retro-reflective sheeting on the basis of microprisms	White	6710-010	Sheeting thickness (without protective paper and adhesive): 0,23 mm Dimension of the roll: 1,22 m x 50 m or customized
ORALITE® 5018 Screen Printing Ink	Printing ink for screen printing	Yellow Red Blue Green Black	5018-020 5018-030 5018-050 5018-060 5018-070	Solvent based, quick curing one-component ink-system Consumption: appr. 800ml / 55 m² full covered surface

Tab. 1: Types of reflective sheeting "ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink"

The indications of the manufacturer regarding the definition of the colours comply with the colour boxes of the CIE system (according to class CR2 of EN 12899-1) and are shown in Table 2.

Colour		Daylight chromaticity				Luminance factors
		1	2	3	4	
Yellow	x	0,494	0,470	0,513	0,545	$\geq 0,27$
	y	0,505	0,480	0,437	0,454	
Red	x	0,735	0,700	0,610	0,660	$\geq 0,05$
	y	0,265	0,250	0,340	0,340	
Green	x	0,110	0,170	0,170	0,110	$\geq 0,04$
	y	0,415	0,415	0,500	0,500	
Blue	x	0,130	0,160	0,160	0,130	$\geq 0,01$
	y	0,090	0,090	0,140	0,140	
Black*	x	0,385	0,300	0,260	0,345	$\leq 0,03$
	y	0,355	0,270	0,310	0,395	

* Class NR1 of EN 12899-1 for Black

Tab. 2: Daylight chromaticity and luminance factors according to the indications of the manufacturer which comply with class CR2 of EN 12899-1

2 Specification of the intended use in accordance with the applicable European Assessment Document

The construction product described here is used to manufacture signal aspects of fixed, vertical traffic signs (see also EN 12899-1:2007). The further intended applications are all other traffic signs and traffic installations, route guidance with retro-reflective elements and variable message signs.

However, the intended use excludes the manufacture of road marking elements according to EN 1436. The intended sign support material is aluminium, galvanised steel, polycarbonate or other materials. Tests within the framework of this assessment were carried out on aluminium-based samples.

The performances given in section 3 are only valid if the conditions laid down in the accompanying product data sheets and in the processing instructions given by the manufacturer have been respected throughout the production, processing, packaging, transport and storage of "ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink" (essential specifications acc. to manufacturer's instructions are given in Annex 4).

The verifications and assessment methods as well as the product information of the manufacturer on which this European Technical Assessment is based lead to the assumption of a working life of this product of at least 10 years. The indications given on the working life cannot be interpreted as a guarantee given by the manufacturer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Safety and accessibility in use (BWR 4)

For the preparation of the specimens, the test pieces of the reflective sheeting were applied by the manufacturer on a plane aluminium plate with a thickness of 2,0 mm ($\pm 0,05$ mm).

Essential characteristic	Performance
Visibility of "ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink"	
Daylight chromaticity and luminance factors	See Annex 1
Night-time colour	No performance assessed
Coefficient of retro-reflection and rotational symmetry	See Annex 2
Durability of "ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink"	
Impact resistance	Passed according to EN 12899-1
Temperature resistance	No performance assessed
Visibility after artificial weathering	See Annex 3
Visibility after natural weathering	No performance assessed
Adhesion	No performance assessed

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with EAD No 120001-01-0106, the applicable European legal act is: Decision 96/579/EC.

The system(s) to be applied is: 1

European Technical Assessment

ETA-16/0580

English translation prepared by DIBt

Page 5 of 21 | 11 September 2017

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

6 Reference list

This European Technical Assessment is based on the following test report:

- Interims test report No. V3-031/2015 of 29 April 2016 by Federal Highway Research Institute (Bundesanstalt für Straßenwesen - BASt) on the testing of microparticulate reflective sheetings
- Interims test report No. V3-013/2016 of 30 November 2016 by Federal Highway Research Institute (Bundesanstalt für Straßenwesen - BASt) on the testing of microparticulate reflective sheetings

Issued in Berlin on 11 September 2017 by Deutsches Institut für Bautechnik

Dr.-Ing. Karsten Kathage
Head of Department

beglaubigt:
Petrik

Annex 1

Daylight chromaticity and luminance factors according to clause 2.2.1 of the EAD

Colour	Sample	x	y	β
Yellow	1	0,508	0,476	0,36
	2	0,508	0,476	0,36
	3	0,508	0,476	0,36
Red	1	0,665	0,316	0,05
	2	0,663	0,316	0,05
	3	0,666	0,316	0,05
Blue	1	0,134	0,117	0,05
	2	0,133	0,117	0,05
	3	0,134	0,114	0,05
Green	1	0,132	0,444	0,10
	2	0,134	0,441	0,10
	3	0,132	0,443	0,10
Black	1	0,288	0,309	0,00
	2	0,287	0,308	0,00
	3	0,287	0,309	0,00

Annex 2

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Coefficient of retro-reflection for "Yellow" (Part 1)

Note: # Indicates a value greater than zero but not significant or applicable.

α	β_1	β_2	ε	Colour	Yellow			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer		
					Sample	Single test result of each sample	1	2	3		
0,2°	5°	0°	0°	5°	117	189	133	146	50		
					38	58	41	46	22		
					12,2	14,9	12,7	13,3	7,0		
	30°			30°	76	111	82	90	35		
					33	48	35	39	16,0		
					10,8	13,0	10,7	11,5	6,0		
	40°			40°	13,3	11,6	13,1	12,7	3,0		
					8,7	9,8	9,3	9,3	1,5		
					3,5	3,4	3,9	3,6	1,0		

Coefficient of retro-reflection started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour	Yellow			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer			
					Sample	Single test result of each sample	1	2	3			
0,33°	5°	0°	30°	5°	108	180	122	137	50			
					35	63	40	46	22			
					17,2	27	18,1	21	7,0			
	30°		40°	30°	64	103	69	79	35			
					30	50	33	38	16,0			
					15,7	24	16,4	18,7	6,0			
	40°				9,8	8,8	9,6	9,4	3,0			
					8,9	7,6	8,5	8,3	1,5			
					3,8	4,0	3,9	3,9	1,0			

Coefficient of retro-reflection started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour	Yellow			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer			
					Sample	Single test result of each sample	1	2	3			
0,33°	5°	0°	45°	5°	109	178	122	136	50			
					56	94	65	72	22			
					8,3	12,2	9,2	9,9	7,0			
	30°			30°	65	104	70	80	35			
					47	69	51	56	16,0			
					7,5	10,3	8,1	8,6	6,0			
	40°				9,3	8,1	8,8	8,7	3,0			
					6,2	5,2	5,2	5,5	1,5			
					3,4	3,0	3,2	3,2	1,0			

Coefficient of retro-reflection started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Yellow" (Part 1 continued)

α	β_1	β_2	ε	Colour		Yellow Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,2°	5°	0°	60°	111	181	125	139	50
				38	67	46	50	22
				20	35	25	27	7,0
	30°	0°	60°	68	106	74	83	35
				33	54	39	42	16,0
				19,0	31	23	24	6,0
2°	5°	0°	60°	12,2	9,6	10,8	10,9	3,0
				7,4	5,9	6,9	6,7	1,5
				4,3	4,6	4,3	4,4	1,0

Coefficient of retro-reflection started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour		Yellow Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,33 °	5°	0°	90°	122	191	139	151	50
				36	58	41	45	22
				11,3	17,7	11,8	13,6	7,0
	30°	0°	90°	84	117	92	98	35
				33	50	37	40	16,0
				10,3	15,9	10,5	12,2	6,0
2°	5°	0°	90°	17,5	13,3	16,4	15,7	3,0
				9,7	9,9	10,6	10,1	1,5
				3,4	5,0	3,3	3,9	1,0

Coefficient of retro-reflection started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Rotational symmetry for "Yellow" (Part 1)

Colour Sample				Yellow		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	97	130	105
			-50	105	143	117
			-25	94	132	106
			0*	76	111	82
			25	64	103	70
			50	65	105	71
			Ratio	1,64	1,39	1,67

* Rotational symmetry started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Yellow		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	87	124	97
			-50	70	106	76
			-25	64	103	70
			0*	68	106	74
			25	81	114	87
			50	100	136	112
			Ratio	1,56	1,32	1,60

* Rotational symmetry started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Yellow		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	104	143	117
			-50	91	128	101
			-25	72	108	78
			0*	64	103	69
			25	67	105	72
			50	78	112	83
			Ratio	1,63	1,39	1,70

* Rotational symmetry started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Yellow		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	67	105	74
			-50	64	103	70
			-25	70	106	76
			0*	84	117	92
			25	102	140	116
			50	104	146	120
			Ratio	1,63	1,42	1,71

* Rotational symmetry started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Yellow		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	98	136	110
			-50	79	115	87
			-25	66	103	71
			0*	65	104	70
			25	72	107	78
			50	89	121	96
			Ratio	1,51	1,32	1,57

* Rotational symmetry started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Red" (Part 2)

α	β_1	β_2	ε	Colour			Red Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer		
				Sample	1	2					
0,2°	5°	0°	$\varepsilon=0^\circ$	35	35	35	35	35	14,5		
				10,5	10,2	10,6	10,4	10,4	6,0		
				2,9	3,0	3,1	3,0	3,0	2,0		
	30°			24	24	23	24	24	10,0		
				9,5	9,3	9,6	9,5	9,5	4,0		
				2,9	2,7	2,9	2,8	2,8	1,8		
	40°			5,7	5,6	5,9	5,7	5,7	1,0		
				3,2	2,9	3,2	3,1	3,1	0,5		
				1,0	1,1	1,1	1,1	1,1	0,5		

Coefficient of retro-reflection started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour			Red Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer		
				Sample	1	2					
0,33°	5°	0°	$\varepsilon=30^\circ$	31	32	32	32	32	14,5		
				10,1	9,9	10,4	10,1	10,1	6,0		
				4,4	4,3	4,7	4,5	4,5	2,0		
	30°			19,2	19,5	19,3	19,3	19,3	10,0		
				8,6	8,4	8,9	8,6	8,6	4,0		
				4,2	4,1	4,4	4,2	4,2	1,8		
	40°			3,6	3,6	3,8	3,7	3,7	1,0		
				2,4	2,6	2,7	2,6	2,6	0,5		
				1,1	1,1	1,2	1,1	1,1	0,5		

Coefficient of retro-reflection started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour			Red Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer		
				Sample	1	2					
0,33°	5°	0°	$\varepsilon=45^\circ$	31	32	31	31	31	14,5		
				13,7	14,5	14,4	14,2	14,2	6,0		
				1,8	1,9	1,9	1,9	1,9	2,0		
	30°			18,3	18,9	18,5	18,6	18,6	10,0		
				11,7	12,2	12,2	12,0	12,0	4,0		
				1,7	1,8	1,8	1,8	1,8	1,8		
	40°			3,1	3,2	3,3	3,2	3,2	1,0		
				2,6	2,4	2,6	2,5	2,5	0,5		
				1,0	1,0	1,1	1,0	1,0	0,5		

Coefficient of retro-reflection started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Red" (Part 2 continued)

α	β_1	β_2	Colour Sample	Red Single test result of each sample			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				1	2	3		
0,2°	5°	0°	Red	31	32	31	31	14,5
				7,9	9,3	8,8	8,7	6,0
				3,9	4,6	4,5	4,3	2,0
0,33 °	5°	60°	Red	18,3	19,1	18,7	18,7	10,0
				6,9	8,0	7,7	7,5	4,0
				3,7	4,2	4,2	4,0	1,8
2°	5°	0°	Red	3,7	3,8	4,0	3,8	1,0
				2,2	2,2	2,3	2,2	0,5
				1,1	1,2	1,2	1,2	0,5

Coefficient of retro-reflection started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	Colour Sample	Red Single test result of each sample			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				1	2	3		
0,2°	5°	0°	Red	34	35	34	34	14,5
				8,8	9,9	9,3	9,3	6,0
				2,6	2,8	2,7	2,7	2,0
0,33 °	5°	90°	Red	22	23	22	22	10,0
				8,0	8,9	8,6	8,5	4,0
				2,4	2,6	2,5	2,5	1,8
2°	5°	0°	Red	5,4	5,6	5,7	5,6	1,0
				2,6	3,0	3,0	2,9	0,5
				0,8	0,9	0,9	0,9	0,5

Coefficient of retro-reflection started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Rotational symmetry for "Red" (Part 2)

Colour Sample				Red		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	26	27	26
			-50	31	31	30
			-25	29	29	28
			0*	24	24	23
			25	19,6	19,9	19,6
			50	18,2	18,9	18,5
Ratio				1,70	1,64	1,62

* Rotational symmetry started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Red		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	27	27	26
			-50	21	22	21
			-25	18,8	19,3	18,9
			0*	18,3	19,1	18,7
			25	21	22	22
			50	28	29	28
Ratio				1,53	1,52	1,50

* Rotational symmetry started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Red		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	31	31	30
			-50	28	28	27
			-25	23	23	22
			0*	19,2	19,5	19,3
			25	18,2	19	18,6
			50	20	21	21
Ratio				1,70	1,63	1,61

* Rotational symmetry started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Red		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	21	21	21
			-50	18,6	19,1	18,7
			-25	18,7	19,5	19
			0*	22	23	22
			25	29	30	29
			50	31	32	31
Ratio				1,67	1,68	1,66

* Rotational symmetry started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Red		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	30	30	29
			-50	25	25	24
			-25	20	20	20
			0*	18,3	18,9	18,5
			25	19,1	20	19,3
			50	24	25	24
Ratio				1,64	1,59	1,57

* Rotational symmetry started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Blue" (Part 3)

α	β_1	β_2	ε	Colour		Blue Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer	
				Sample	1	2	3		
0,2°	5°	0°	$\varepsilon=0^\circ$	16,0	16,0	12,9	15,0	4,0	
				5,0	5,0	3,9	4,6	1,7	
				0,8	0,8	0,6	0,7	0,5	
	30°	0°		7,0	7,0	5,5	6,5	2,0	
				3,1	3,1	2,4	2,9	1,0	
				0,9	0,7	0,5	0,7	#	
	40°	0°		0,4	0,4	0,3	0,4	#	
				0,2	0,1	0,1	0,1	#	
				0,0	0,0	0,0	0,0	#	

Coefficient of retro-reflection started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour		Blue Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer	
				Sample	1	2	3		
0,33°	5°	0°	$\varepsilon=30^\circ$	17,1	17,5	14,1	16,2	4,0	
				6,8	6,9	5,4	6,4	1,7	
				3,0	3,1	2,5	2,9	0,5	
	30°	30°		8,6	8,8	7,1	8,2	2,0	
				5,0	5,0	4,0	4,7	1,0	
				2,6	2,6	2,0	2,4	#	
	40°	30°		0,2	0,2	0,2	0,2	#	
				0,3	0,3	0,3	0,3	#	
				0,1	0,1	0,1	0,1	#	
2°	5°	0°	$\varepsilon=45^\circ$	17,3	17,6	14,2	16,4	4,0	

Coefficient of retro-reflection started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour		Blue Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer	
				Sample	1	2	3		
0,2°	5°	0°	$\varepsilon=45^\circ$	17,3	17,6	14,2	16,4	4,0	
				8,5	8,6	6,8	8,0	1,7	
				1,2	1,2	0,9	1,1	0,5	
	30°	45°		8,9	9,1	7,4	8,5	2,0	
				4,6	4,6	3,6	4,3	1,0	
				0,8	0,7	0,6	0,7	#	
	40°	45°		0,3	0,3	0,2	0,3	#	
				0,2	0,2	0,2	0,2	#	
				0,0	0,0	0,0	0,0	#	
2°	5°	0°	$\varepsilon=45^\circ$	17,3	17,6	14,2	16,4	4,0	

Coefficient of retro-reflection started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Blue" (Part 3 continued)

α	β_1	β_2	ε	Colour		Blue Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,2°	5°	0°	60°	17,0	17,4	14,1	16,2	4,0
				7,5	7,6	5,9	7,0	1,7
				3,2	3,3	2,5	3,0	0,5
0,33 °	5°	30°	60°	8,7	9,0	7,4	8,4	2,0
				4,8	4,9	3,9	4,5	1,0
				2,6	2,6	2,0	2,4	#
2°	5°	30°	40°	0,3	0,3	0,2	0,3	#
				0,2	0,2	0,2	0,2	#
				0,1	0,1	0,1	0,1	#

Coefficient of retro-reflection started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour		Blue Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,2°	5°	0°	90°	15,9	16,2	13,1	15,1	4,0
				5,8	5,8	4,5	5,4	1,7
				2,6	2,6	2,0	2,4	0,5
0,33 °	5°	30°	90°	7,1	7,3	6,0	6,8	2,0
				4,3	4,3	3,4	4,0	1,0
				2,0	2,2	1,7	2,0	#
2°	5°	30°	40°	0,2	0,2	0,1	0,2	#
				0,3	0,3	0,3	0,3	#
				0,2	0,2	0,2	0,2	#

Coefficient of retro-reflection started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Rotational symmetry for "Blue" (Part 3)

Colour Sample				Blue		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	6,7	6,7	5,5
			-50	6,4	6,4	5,2
			-25	6,5	6,4	5,1
			0*	7,0	7,0	5,5
			25	8,4	8,6	6,9
			50	8,8	9,1	7,4
Ratio				1,38	1,42	1,45

* Rotational symmetry started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Blue		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	6,5	6,4	5,1
			-50	7,7	7,7	6,2
			-25	8,8	9,0	7,3
			0*	8,7	9,0	7,4
			25	7,5	7,7	6,3
			50	6,2	6,1	5,0
Ratio				1,42	1,48	1,48

* Rotational symmetry started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Blue		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	6,6	6,4	5,3
			-50	6,5	6,5	5,1
			-25	7,4	7,5	5,9
			0*	8,6	8,8	7,1
			25	8,8	9,1	7,4
			50	7,8	8,0	6,6
Ratio				1,35	1,42	1,45

* Rotational symmetry started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Blue		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	8,0	8,0	6,5
			-50	8,8	9,1	7,4
			-25	8,6	8,9	7,3
			0*	7,1	7,3	6,0
			25	6,2	6,1	4,9
			50	6,8	6,7	5,4
Ratio				1,42	1,49	1,51

* Rotational symmetry started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Blue		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	6,6	6,5	5,3
			-50	6,8	6,7	5,3
			-25	8,2	8,4	6,7
			0*	8,9	9,1	7,4
			25	8,4	8,7	7,1
			50	6,8	6,9	5,6
Ratio				1,35	1,40	1,40

* Rotational symmetry started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Green" (Part 4)

α	β_1	β_2	ε	Colour		Green Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,2°	5°	0°	41	41	43	42	9,0	
			13,2	13,0	13,7	13,3	3,5	
			2,1	1,9	2,2	2,1	1,5	
	30°	0°	18,6	18,9	19,6	19,0	7,0	
			8,4	8,1	8,7	8,4	3,0	
			1,6	1,7	1,6	1,6	1,2	
	40°	0°	1,0	1,0	1,0	1,0	0,5	
			0,4	0,4	0,4	0,4	0,3	
			0,1	0,2	0,2	0,2	0,2	
0,33°	5°	0°	1,0	1,0	1,0	1,0	0,5	
			0,4	0,4	0,4	0,4	0,3	
			0,1	0,2	0,2	0,2	0,2	
	30°	0°	1,0	1,0	1,0	1,0	0,5	
			0,4	0,4	0,4	0,4	0,3	
			0,1	0,2	0,2	0,2	0,2	
	40°	0°	1,0	1,0	1,0	1,0	0,5	
			0,4	0,4	0,4	0,4	0,3	
			0,1	0,2	0,2	0,2	0,2	

Coefficient of retro-reflection started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour		Green Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,2°	5°	0°	44	45	46	45	9,0	
			17,8	18,2	19,1	18,4	3,5	
			8,0	8,3	8,9	8,4	1,5	
	30°	0°	23	24	25	24	7,0	
			13,4	13,9	14,5	13,9	3,0	
			6,9	7,1	7,7	17,2	1,2	
	40°	0°	0,7	0,6	0,7	0,7	0,5	
			0,8	0,8	0,9	0,8	0,3	
			0,4	0,4	0,5	0,4	0,2	
0,33°	5°	30°	0,7	0,6	0,7	0,7	0,5	
			13,4	13,9	14,5	13,9	3,0	
			6,9	7,1	7,7	17,2	1,2	
	30°	30°	0,7	0,6	0,7	0,7	0,5	
			0,8	0,8	0,9	0,8	0,3	
			0,4	0,4	0,5	0,4	0,2	
	40°	30°	0,7	0,6	0,7	0,7	0,5	
			13,4	13,9	14,5	13,9	3,0	
			6,9	7,1	7,7	17,2	1,2	
2°	5°	0°	0,7	0,6	0,7	0,7	0,5	
			0,8	0,8	0,9	0,8	0,3	
			0,4	0,4	0,5	0,4	0,2	
	30°	0°	0,7	0,6	0,7	0,7	0,5	
			0,8	0,8	0,9	0,8	0,3	
			0,4	0,4	0,5	0,4	0,2	
	40°	0°	0,7	0,6	0,7	0,7	0,5	
			13,4	13,9	14,5	13,9	3,0	
			6,9	7,1	7,7	17,2	1,2	

Coefficient of retro-reflection started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	ε	Colour		Green Single test result of each sample	Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
				Sample	1	2	3	
0,2°	5°	0°	45	46	47	46	9,0	
			23	23	24	23	3,5	
			3,1	3,3	3,2	3,2	1,5	
	30°	0°	25	25	26	25	7,0	
			12,9	13,0	13,3	13,1	3,0	
			2,1	2,3	2,2	2,2	1,2	
	40°	0°	0,8	0,8	0,8	0,8	0,5	
			0,6	0,5	0,6	0,6	0,3	
			0,1	0,1	0,1	0,1	0,2	
0,33°	5°	45°	0,8	0,8	0,8	0,8	0,5	
			12,9	13,0	13,3	13,1	3,0	
			2,1	2,3	2,2	2,2	1,2	
	30°	45°	0,8	0,8	0,8	0,8	0,5	
			0,6	0,5	0,6	0,6	0,3	
			0,1	0,1	0,1	0,1	0,2	
	40°	45°	0,8	0,8	0,8	0,8	0,5	
			12,9	13,0	13,3	13,1	3,0	
			2,1	2,3	2,2	2,2	1,2	
2°	5°	0°	0,8	0,8	0,8	0,8	0,5	
			0,6	0,5	0,6	0,6	0,3	
			0,1	0,1	0,1	0,1	0,2	
	30°	0°	0,8	0,8	0,8	0,8	0,5	
			0,6	0,5	0,6	0,6	0,3	
			0,1	0,1	0,1	0,1	0,2	
	40°	0°	0,8	0,8	0,8	0,8	0,5	
			12,9	13,0	13,3	13,1	3,0	
			2,1	2,3	2,2	2,2	1,2	

Coefficient of retro-reflection started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Coefficient of retro-reflection for "Green" (Part 4 continued)

α	β_1	β_2	Colour Sample	Green Single test result of each sample			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer	
				1	2	3			
0,2°	5°	0°	60°	45	46	47	46	9,0	
				19,4	19,9	20	19,8	3,5	
				8,6	8,4	8,7	8,6	1,5	
	30°	60°		25	25	26	25	7,0	
				13,1	13,0	13,3	13,1	3,0	
				6,8	6,7	6,8	6,8	1,2	
0,33 °	5°	0°		0,9	0,8	0,8	0,8	0,5	
				0,4	0,4	0,5	0,4	0,3	
				0,4	0,4	0,4	0,4	0,2	
	30°	60°							
2°	5°	0°							
	30°	60°							
40°	5°	0°							
	30°	60°							

Coefficient of retro-reflection started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

α	β_1	β_2	Colour Sample	Green Single test result of each sample			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer	
				1	2	3			
0,2°	5°	0°	90°	43	44	45	44	9,0	
				15,2	15,3	16,1	15,5	3,5	
				6,9	6,8	7,2	7,0	1,5	
	30°	90°		21	21	22	21	7,0	
				11,5	11,6	12,1	11,7	3,0	
				5,8	5,9	6,2	6,0	1,2	
0,33 °	5°	0°		0,8	0,7	0,7	0,7	0,5	
				0,7	0,7	0,8	0,7	0,3	
				0,5	0,5	0,5	0,5	0,2	
	30°	90°							
2°	5°	0°							
	30°	90°							
40°	5°	0°							
	30°	90°							

Coefficient of retro-reflection started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Rotational symmetry for "Green" (Part 4)

Colour Sample				Green		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	19,1	19,1	20
			-50	18,1	18,0	19,1
			-25	17,6	17,5	18,4
			0*	18,6	18,9	19,6
			25	23	23	24
			50	25	25	26
			Ratio	1,42	1,43	1,41

* Rotational symmetry started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Green		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	17,5	17,6	18,3
			-50	20	21	21
			-25	24	24	25
			0*	25	25	26
			25	22	22	23
			50	18,3	18,2	19,0
			Ratio	1,43	1,42	1,42

* Rotational symmetry started at $\varepsilon=60^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Green		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	18,2	18,1	19,1
			-50	17,5	17,5	18,3
			-25	19,4	19,5	20
			0*	23	24	25
			25	25	25	26
			50	23	23	24
			Ratio	1,43	1,43	1,42

* Rotational symmetry started at $\varepsilon=30^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Green		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	21	21	22
			-50	24	25	26
			-25	25	25	26
			0*	21	21	22
			25	18,1	17,8	18,9
			50	18,5	18,2	19,2
			Ratio	1,38	1,40	1,38

* Rotational symmetry started at $\varepsilon=90^\circ$ [cd m⁻² lx⁻¹]

Colour Sample				Green		
α	β_1	β_2	ε	1	2	3
0,33	5	0	-75	17,8	17,8	18,7
			-50	18,0	18,2	18,9
			-25	22	22	23
			0*	25	25	26
			25	24	25	25
			50	20	20	21
			Ratio	1,40	1,40	1,39

* Rotational symmetry started at $\varepsilon=45^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Coefficient of retro-reflection and rotational symmetry according to clause 2.2.3 of the EAD

Annex 2

Annex 3

Visibility after accelerated artificial weathering according to clause 2.2.6 of the EAD:

Acc. to ISO 4892-2:1994 samples have been artificially weathered 2000 hours by using a non-insulated black panel thermometer.

Sample size: 5,5 x 11 cm.

Daylight chromaticity and luminance factors after accelerated artificial weathering

Colour	Sample	x	y	β
Yellow	1	0,504	0,480	0,39
	2	0,504	0,480	0,38
	3	0,503	0,481	0,38
Red	1	0,661	0,317	0,05
	2	0,660	0,317	0,05
	3	0,660	0,317	0,05
Blue	1	0,133	0,114	0,04
	2	0,133	0,116	0,05
	3	0,133	0,113	0,04
Green	1	0,131	0,444	0,10
	2	0,132	0,444	0,11
	3	0,132	0,443	0,10
Black	1	0,289	0,309	0,00
	2	0,288	0,309	0,00
	3	0,288	0,308	0,00

Coefficients of retro-reflection after accelerated artificial weathering

Colour	Sample	Yellow			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
		1	2	3		
α 0,2°	5°	214	148	247	203	40
		65	43	83	64	17,6
	30°	117	84	133	111	28
		51	36	65	51	12,8

Coefficient of retro-reflection after accelerated artificial weathering started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour	Sample	Red			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
		1	2	3		
α 0,2°	5°	46	57	40	48	11,6
		13,2	16,6	14,5	14,8	4,8
	30°	28	34	25	29	8,0
		11,0	13,6	9,3	11,3	3,2

Coefficient of retro-reflection after accelerated artificial weathering started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour	Sample	Blue			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
		1	2	3		
α 0,2°	5°	12,0	12,9	12,6	12,5	3,2
		3,9	4,2	3,7	3,9	1,4
	30°	5,2	5,7	5,3	5,4	1,6
		2,4	2,5	1,8	2,2	0,8

Coefficient of retro-reflection after accelerated artificial weathering started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

Colour	Sample	Green			Average of the three samples tested	Minimum values acc. to the specification of the manufacturer
		1	2	3		
α 0,2°	5°	40	37	39	39	7,2
		12,7	13,4	13,0	13,0	2,8
	30°	18,6	18,2	18,5	18,4	5,6
		7,9	10,0	8,9	8,9	2,4

Coefficient of retro-reflection after accelerated artificial weathering started at $\varepsilon=0^\circ$ [cd m⁻² lx⁻¹]

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen Printing Ink

Visibility after accelerated artificial weathering according to clause 2.2.6 of the EAD

Annex 3

Annex 4

Essential specifications concerning manufacturing, packaging, transport and storage according to manufacturer's instruction:

Application

The envisaged substrates are aluminium, galvanized steel, polycarbonate or other.

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination, which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material.

For the application of the retro-reflective film and its additional components described in Chapter 1 detailed information have been published by the manufacturer. In the following only the most important aspects of the application are given:

Cutting, die cutting, plotting

The product can be cut by means of a commercial stack cutter. The holding-down clamp should be set to very low pressure and, as an additional measure, the film be protected from compression. It is recommended to limit the stacking height 40 sheets to 50 sheets.

Commercial cutting plotters with tangential blades, preferably of the flatbed type, should be used as plotter systems.

Adhesive bonding and laminating

The self-adhesive retro-reflective material can only be used for dry application.

Bonding should not be carried out at air and material temperatures of less than 15 °C. The optimum bonding temperature is about 21 °C. The films should be stored for a period of at least 48 hours in the premises designated for their processing.

In order to achieve good adhesion of the films, the substrate must be dry and free of dust, oil, fats, silicon or other contamination. If the substrate needs to be treated with a solvent, the next processing step cannot be carried out until the solvent is completely evaporated. When bonding films to metallic substrate, slight grinding of the surfaces is advantageous.

When several film webs need to be bonded side by side, they should always overlap. Depending on the format, the overlap should be 3 mm to 5 mm. Please make sure that a right side of the film web is always bonded to a left side, thus ensuring the uniform orientation of the film's honeycomb structure.

Packaging, transport and storage

The product should be stored in a cool and dry place (temperature range from 20 °C to 24 °C; relative air humidity of 40 % to 60 %) that is protected from direct sunlight.

Rolled material should be handled and stored in the original carton. The rolls have standard spacers that prevent contact between the roll surface and the carton and thus the formation of pressure marks and surface damage. Please make sure that partly processed rolls, too, are never stored or handled without spacer.

When making the rolls available for processing, it is advisable to use a horizontal suspension system (such as a paternoster system or a rack). Even if the rolls are stored in a vertical, freestanding position, a negative influence on the film's characteristics is generally not expected. Here again, it is crucial to place the roll on the spacer so as to avoid breakage of the edges. In practice it was shown, however, that this type of storage complicates the handling of the films.

Blank or printed film sheets are supplied in cartons that have been designed especially for the sheet dimensions, 50 sheets per carton. If the sheets are stored outside the carton, please make sure to put individual sheets on a flat and stable support so that they do not adjoin or overlap at the edges. Sheets may be stacked. In order to limit the weight load, not more than 40 sheets to 50 sheets should be stacked.

ORALITE® 6710 Engineer Prismatic Grade screen printed with ORALITE® 5018 Screen
Printing Ink

Essential specifications concerning manufacturing, packaging, transport and storage
according to manufacturer's instruction

Annex 4