

Approval body for construction products  
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and  
Laender Governments



## European Technical Assessment

**ETA-16/0696**  
**of 6 October 2017**

English translation prepared by DIBt - Original version in German language

### General Part

Technical Assessment Body issuing the  
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

S&P - ResEP-16 Epoxy Injection System

Product family  
to which the construction product belongs

Bonded anchor for use in concrete

Manufacturer

S&P Clever Reinforcement Company AG  
Seewernstrasse 127  
6423 SEEWEN  
SCHWEIZ

Manufacturing plant

Simpson Strong-Tie® Manufacturing Facilities

This European Technical Assessment  
contains

21 pages including 3 annexes which form an integral part  
of this assessment

This European Technical Assessment is  
issued in accordance with Regulation (EU)  
No 305/2011, on the basis of

ETAG 001 Part 5: "Bonded anchors", April 2013,  
used as EAD according to Article 66 Paragraph 3 of  
Regulation (EU) No 305/2011.

This version replaces

ETA-16/0696 issued on 21 October 2016

**European Technical Assessment**

**ETA-16/0696**

English translation prepared by DIBt

**Page 2 of 21 | 6 October 2017**

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

## Specific Part

### 1 Technical description of the product

The S&P – ResEP-16 Epoxy Injection System is a bonded anchor consisting of a cartridge with injection mortar ResEP-16 and a steel element. The steel elements are either

- Threaded rods in the range of M 12 to M 27 or
- Reinforcing bar in the range of  $\phi$  12 to  $\phi$  25 mm

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance tension and shear loads	See Annex C 1 to C 4
Displacements under tension and shear loads	See Annex C 5 to C 6

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Anchors satisfy requirements for Class A1
Resistance to fire	No performance assessed

#### 3.3 Hygiene, health and the environment (BWR 3)

Regarding dangerous substances there may be requirements (e.g. transposed European legislation and national laws, regulations and administrative provisions) applicable to the products falling within the scope of this European Technical Assessment. In order to meet the provisions of Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

#### 3.4 Safety in use (BWR 4)

The essential characteristics regarding Safety in use are included under the Basic Works Requirement Mechanical resistance and stability.

**4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base**

In accordance with guideline for European technical approval ETAG 001, April 2013 used as European Assessment Document (EAD) according to Article 66 Paragraph 3 of Regulation (EU) No 305/2011 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

**5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document**

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 6 October 2017 by Deutsches Institut für Bautechnik

BD Dipl.-Ing. Andreas Kummerow  
Head of Department


*Beglaubigt:*  
Baderschneider

**S&P**

## ResEP-16 Epoxy Injection System

**ResEP-16 Injection mortar cartridges:**

250 ml, 400 ml, 600 ml, 650 ml, 1500 ml and 1656 ml



Imprints:  
Commercial name,  
Manufacturer identification,  
Installation instructions,  
Shelf-life, Expiration date,  
Batch-no., Hazard codes

Illustration: 650 ml Injection mortar cartridge (side-by-side)

**Mixing nozzle: CTG-NZ2**



**Mixing nozzle: CTG-NZ2m**



**Extension tubes:**



Flexible plastic hose:  $\varnothing 8,0 - \varnothing 8,5$  mm




Rigid plastic tube: CTG-NZ-EXT



**Threaded rod M12, M16, M20, M24 or M27**



**Reinforcing bar  $\varnothing 12$ ,  $\varnothing 14$ ,  $\varnothing 16$ ,  $\varnothing 20$  or  $\varnothing 25$**





**S&P - ResEP-16 Epoxy Injection System**

**Product description**

Injection mortar / Components / Anchoring parts

**Annex A1**

S&P  
ResEP-16 Epoxy Injection System



S&P - ResEP-16 Epoxy Injection System

Product description  
Installation

Annex A2

## S&P

### ResEP-16 Epoxy Injection System

**Table A1: Threaded rods**

Designation	Material
<b>Steel, zinc plated <math>\geq 5\mu\text{m}</math> according EN ISO 4042:1999, (A2), passivated Steel, hot-dip galvanised <math>&gt; 40\mu\text{m}</math> according EN ISO 10684:2004 + AC:2009</b>	
Threaded rod	Carbon steel: Property class 5.8 and 8.8 acc. EN ISO 898-1:2013; A5 $\geq 8\%$ ductile
Washer	Steel: DIN 125-1:1990-03 (EN ISO 7089:2000), DIN 440:1990-05 (EN ISO 7094:2000), DIN 9021:1990-03 (EN ISO 7093-1:2000)
Hexagon nut	Steel: DIN 934:1987-10 (EN ISO 4032:2012), property class 8 acc. EN ISO 898-2:2012
<b>Stainless steel</b>	
Threaded rod	Stainless steel: 1.4362; 1.4401; 1.4404; 1.4439; 1.4571; 1.4578 acc. EN 10088-1:2014 $\leq M24$ : Property class 70, EN ISO 3506-1:2009; A5 $\geq 8\%$ ductile $> M24$ : Property class 50, EN ISO 3506-1:2009; A5 $\geq 8\%$ ductile
Washer	DIN 125-1:1990-03 (EN ISO 7089:2000), DIN 440:1990-05 (EN ISO 7094:2000), DIN 9021:1990-03 (EN ISO 7093-1:2000) Stainless steel: 1.4362; 1.4401; 1.4404; 1.4439; 1.4571; 1.4578 acc. EN 10088-1:2014
Hexagon nut	DIN 934:1987-10 (EN ISO 4032:2012), $\leq M24$ : Property class 70, EN ISO 3506-2:2009 $> M24$ : Property class 50 or 70, EN ISO 3506-2:2009 Stainless steel: 1.4362; 1.4401; 1.4404; 1.4439; 1.4571; 1.4578 acc. EN 10088-1:2014
<b>Stainless steel - High corrosion resistance steel</b>	
Threaded rod	Stainless steel: 1.4529; 1.4565 acc. EN 10088-1:2014 $\leq M24$ : Property class 70, EN ISO 3506-2:2009 ; A5 $\geq 8\%$ ductile $> M24$ : Property class 50, EN ISO 3506-2:2009 ; A5 $\geq 8\%$ ductile
Washer	DIN 125-1:1990-03 (EN ISO 7089:2000), DIN 440:1990-05 (EN ISO 7094:2000), DIN 9021:1990-03 (EN ISO 7093-1:2000) Stainless steel: 1.4529; 1.4565 acc. EN 10088-1:2014
Hexagon nut	DIN 934:1987-10 (EN ISO 4032:2012) $\leq M24$ : Property class 70, EN ISO 3506-2:2009 $> M24$ : Property class 50 or 70, EN ISO 3506-2:2009 Stainless steel: 1.4529; 1.4565 acc. EN 10088-1:2014
<b>Commercial threaded rods with:</b>	
Inspection certificate 3.1 according to EN 10204:2004	
Marking of embedment depth (This may be done by the manufacturer of the rod or by the worker on job site)	

**S&P - ResEP-16 Epoxy Injection System**

**Product description**  
Materials - Threaded rod

**Annex A3**



**S&P**

**ResEP-16 Epoxy Injection System**

**Table A2: Reinforcing bar**

Designation	Material
Rebar according EN 1992-1-1:2004 + AC:2010, Annex C	Bars and de-coiled rods class B or C $f_{yk}$ and $k$ according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$

**S&P - ResEP-16 Epoxy Injection System**

**Product description**

Materials - Reinforcement bar

**Annex A4**



## Specification of intended use

### Anchorage subject to:

- Static or quasi-static action
- Cracked concrete
- Non-cracked concrete

### Base materials:

- Reinforced and unreinforced normal weight concrete according to EN 206-1: 2000
- Strength classes C20/25 to C50/60 according to EN 206-1: 2000

### Temperature Range:

- **Installation:**  $\geq 10^{\circ}\text{C}$
- **Use conditions:**
  - Temperatur Range I:  $-40^{\circ}\text{C}$  to  $+43^{\circ}\text{C}$  (max. long term temperature  $+24^{\circ}\text{C}$  and max. short term temperature  $+43^{\circ}\text{C}$ )
  - Temperatur Range II:  $-40^{\circ}\text{C}$  to  $+65^{\circ}\text{C}$  (max. long term temperature  $+43^{\circ}\text{C}$  and max. short term temperature  $+65^{\circ}\text{C}$ )

### Use conditions (Environmental conditions)

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (stainless steel or high corrosion resistant steel).
- Structures subject to external atmospheric exposure and to permanently damp internal conditions, if other particular aggressive conditions exist (high corrosion resistant steel).

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used).

### Design:

- Anchorages are to be designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings prepared are taking account of the loads to be anchored. The position of the anchor is indicated on the designed drawings (e.g. position of the anchor relative to reinforcement or to supports).
- Anchorages under static or quasi-static actions are designed in accordance with:
  - EOTA Technical Report TR 029 "Design of Bonded Anchors"; Edition September 2010
  - CEN/TS 1992-4:2009, "Design of Fastenings for use in concrete" part 4-1 and part 4-5,

### Installation

- Use categorie: Dry or wet concrete (must not be installed in flooded holes).
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- Drilling by hammer-drilling.
- Overhead installation is allowed.

## S&P - ResEP-16 Epoxy Injection System

### Intended use Specifications

## Annex B1

**Table B1: Installation data for threaded rods**

S&P ResEP-16 Epoxy Injection System			Threaded rod				
			M12	M16	M20	M24	M27
Nom. threaded rod diameter	d	[mm]	12	16	20	24	27
Drill hole diameter	d <sub>o</sub>	[mm]	14	18	24	28	30
Effective anchorage depth	h <sub>ef, min</sub>	[mm]	70	80	90	100	110
	h <sub>ef, max</sub>		240	320	400	480	540
Diameter of clearance hole in the fixture	d <sub>f</sub> ≤	[mm]	14	18	22	26	30
Installation torque	T <sub>inst, max</sub>	[Nm]	40	60	80	100	120
Minimum thickness of concrete member	h <sub>min</sub>	[mm]	h <sub>ef</sub> + 30 mm ≥ 100 mm		h <sub>ef</sub> + 2d <sub>0</sub>		
Minimum allowable spacing	s <sub>min</sub>	[mm]	80	100	115	135	155
Minimum allowable edge distance	c <sub>min</sub>	[mm]	45	60	70	80	90

**Table B2: Installation data for reinforcing bar**

S&P ResEP-16 Epoxy Injection System			Reinforcing bar				
			Ø12	Ø14	Ø16	Ø20	Ø25
Nom. rebar diameter	d	[mm]	12	14	16	20	25
Drill hole diameter	d <sub>o</sub>	[mm]	16	18	20	25	32
Effective anchorage depth	h <sub>ef, min</sub>	[mm]	70	75	80	90	100
	h <sub>ef, max</sub>		240	280	320	400	500
Minimum thickness of concrete member	h <sub>min</sub>	[mm]	h <sub>ef</sub> + 30 mm ≥ 100 mm		h <sub>ef</sub> + 2d <sub>0</sub>		
Minimum allowable spacing	s <sub>min</sub>	[mm]	80	90	100	115	135
Minimum allowable edge distance	c <sub>min</sub>	[mm]	45	50	60	70	80


S&P - ResEP-16 Epoxy Injection System

Intended use  
Installation data

**Annex B2**


## HOLE PREPARATION

1.




Drill hole to specified diameter and embedment depth.

2.




Blow dust from hole 2 times with oil-free compressed air (min. 5.5 bar) starting from the bottom of the hole.

3.



Brush 4 times with specified brush diameter (Annex B7).

4.



Blow 2 times with oil-free compressed air (min. 5.5 bar) and verify that the threaded rod and rebar can achieve the required embedment depth.

S&P - ResEP-16 Epoxy Injection System

Intended use  
Installation instructions

Annex B3

## CARTRIDGE PREPARATION AND HOLE FILLING


1. Check cartridge expiration date. **Do not use expired product.** Product is usable until end of printed expiration month. Open cartridge per package instructions.

2.




Attach proper mixing nozzle supplied by the manufacturer to the cartridge. Do not modify nozzle.

3.




Insert cartridge into the appropriate dispensing tool.

4.



Dispense adhesive to the side until properly mixed, min. 3 strokes (uniform teal color). Discard initial adhesive!

5.



Fill hole approximately 2/3 full, starting from bottom or back of the cleaned drilled hole. Withdraw the nozzle slowly to avoid creating air pockets.

For drilled holes deeper than 150 mm (when  $d_0 \leq 16\text{mm}$ ) and drilled holes deeper than 250 mm (when  $16 < d_0 \leq 30\text{ mm}$ ) an extension tube shall be used. Adhesive retaining caps shall be used in overhead and horizontal installations (Annex B6).


S&P - ResEP-16 Epoxy Injection System

Intended use  
Installation instructions

Annex B4


**ANCHOR INSTALLATION (vertical downward anchorage)**

1.




Insert clean, oil free anchor, turning slowly until the anchor contacts the bottom of the hole.  
Setting control: Excess mortar flows out of the borehole.

2.



Do not disturb the anchor until fully cured. The curing time  $t_{cure}$  is given in table B3.

3.



After required curing time  $t_{cure}$  anchor can be loaded. Apply the installation torque  $T_{inst}$  using calibrated torque-wrench.

**S&P - ResEP-16 Epoxy Injection System**

**Intended use**  
Installation instructions

**Annex B5**



## ANCHOR INSTALLATION (horizontal and overhead anchorage)





1.  Install adhesive retaining cap.
2.  Insert clean, oil free anchor, turning slowly until the anchor contacts the bottom of the hole.
3.  Do not disturb the anchor until fully cured. The curing time  $t_{\text{cure}}$  is given in table B3.
4.  After required curing time  $t_{\text{cure}}$  anchor can be loaded. Apply the installation torque  $T_{\text{inst}}$  using calibrated torque-wrench.

Table B3: Maximum working and minimum curing time

Temperature in the anchorage base $T_{\text{anchorage base}}$	Working time $t_{\text{gel}}$	Curing time <sup>1)</sup> $t_{\text{cure}}$
$T_{\text{anchorage base}} \geq 10^{\circ}$	$\leq 60$ minutes	$\geq 72$ hours
$T_{\text{anchorage base}} \geq 21^{\circ}$	$\leq 45$ minutes	$\geq 24$ hours
$T_{\text{anchorage base}} \geq 32^{\circ}$	$\leq 20$ minutes	$\geq 24$ hours
$T_{\text{anchorage base}} \geq 43^{\circ}$	$\leq 12$ minutes	$\geq 24$ hours

<sup>1)</sup> For installation in wet concrete, the curing times shall be doubled (installation in water-filled drilled holes is not allowed).

S&P - ResEP-16 Epoxy Injection System

Intended use  
Installation instructions

Annex B6

**Table B4: Cleaning equipment**

S&P ResEP-16 Epoxy Injection System		Threaded rod				
		M12	M16	M20	M24	M27
Drill bit	Diameter $d_0$ [mm]	14	18	24	28	30
Cleaning brush	Diameter $d_b$ [mm]	19,1	19,1	25,4	31,8	31,8
	Length $l_b$ [mm]	100	100	100	100	100
	Part number	ETB6	ETB6	ETB8	ETB10	ETB10

**Table B5: Cleaning equipment**

S&P ResEP-16 Epoxy Injection System		Reinforcing bar				
		Ø12	Ø14	Ø16	Ø20	Ø25
Drill bit	Diameter $d_0$ [mm]	16	18	20	25	32
Cleaning brush	Diameter $d_b$ [mm]	19,1	19,1	25,4	31,8	41,3
	Length $l_b$ [mm]	100	100	100	100	150
	Part number	ETB6	ETB6	ETB8	ETB10	ETB12

**Cleaning brush (Nylon):**



**Compressed air cleaning tool**



Air pressure: **min. 5,5 bar**  
Orifice opening: **min. Ø3,5 mm**

**S&P - ResEP-16 Epoxy Injection System**

**Intended use**  
Installation equipment

**Annex B7**



**Table C1: Characteristic values of resistance to tension loads.**  
**Design method TR 029 or CEN/TS 1992-4-5**

S&P ResEP-16 Epoxy Injection System			Threaded rod				
			M12	M16	M20	M24	M27
Steel failure							
Characteristic resistance, Steel grade 5.8	$N_{Rk,s}$	[kN]	42	79	123	177	230
Characteristic resistance, Steel grade 8.8	$N_{Rk,s}$	[kN]	67	126	196	282	367
Partial safety factor	$\gamma_{Ms}^{1)}$	[-]	1,5				
Characteristic resistance, Stainless steel A4 and HCR, property class 50 (>M24) and 70 (≤M24)	$N_{Rk,s}$	[kN]	59	110	172	247	230
Partial safety factor	$\gamma_{Ms}^{1)}$	[-]	1,87				2,86
Combined pull-out and concrete cone failure							
Nom. threaded rod diameter	d	[mm]	12	16	20	24	27
Characteristic bond resistance in <b>non-cracked</b> concrete C20/25							
Temperature range I: 43°C / 24°C <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	17	10	10	9	7
Temperature range II: 65°C / 43°C <sup>2)</sup>	$\tau_{Rk,ucr}$	[N/mm <sup>2</sup> ]	16	9,5	9,5	8,5	6,5
Factor according to CEN/TS 1992-4-5: 6.2.2.3	$k_8$	[-]	10,1				
Characteristic bond resistance in <b>cracked</b> concrete C20/25							
Temperature range I: 43°C / 24°C <sup>2)</sup>	$\tau_{Rk,cr}$	[N/mm <sup>2</sup> ]	6	4,5	3	3	3
Temperature range II: 65°C / 43°C <sup>2)</sup>	$\tau_{Rk,cr}$	[N/mm <sup>2</sup> ]	5,5	4,5	3	3	3
Factor according to CEN/TS 1992-4-5: 6.2.2.3	$k_8$	[-]	7,2				
Increasing factor for $\tau_{Rk,p}$ in non-cracked and cracked concrete	$\Psi_c$	C30/37	1,0				
		C40/50	1,0				
		C50/60	1,0				
Installation safety factor	$\gamma_2 = \gamma_{inst}$	[-]	1,4				
Concrete cone failure							
Factor according to CEN/TS 1992-4-5: 6.2.3.1	$k_{cr}$	[-]	7,2				
Factor according to CEN/TS 1992-4-5: 6.2.3.1	$k_{ucr}$	[-]	10,1				
Edge distance	$c_{cr,N}$	[mm]	1,5x $h_{ef}$				
Center spacing	$s_{cr,N}$	[mm]	3x $h_{ef}$				
Installation safety factor	$\gamma_2 = \gamma_{inst}$	[-]	1,4				
Splitting failure							
Edge distance (splitting)	$c_{cr,sp}^{3)4)}$	[mm]	$c_{cr,sp} = h_{ef} * \left(\frac{\tau_{k,ucr}}{8}\right)^{0,4} * \left(3,1 - 0,7 \frac{h}{h_{ef}}\right)$				
Center spacing (splitting)	$s_{cr,sp}$	[mm]	2x $c_{cr,sp}$				
Installation safety factor	$\gamma_2 = \gamma_{inst}$	[-]	1,4				

1) In absence of other national regulations

2) Maximum short and long term temperatures

3) Ratio value  $[h/h_{ef}] \leq 2,4$

$$4) \quad \tau_{k,ucr} \leq \frac{k_{ucr} * \sqrt{h_{ef} * f_{ck}}}{\pi * d}$$

**S&P - ResEP-16 Epoxy Injection System**

**Performances**

Characteristic values of resistance to tension loads - Threaded rods  
Design method: EOTA TR 029:09/2010 or CEN/TS 1992-4-5:2009

**Annex C1**

**Table C2: Characteristic values of resistance to shear loads.**  
**Design method TR 029 or CEN/TS 1992-4-5**

S&P ResEP-16 Epoxy Injection System			Threaded rod				
			M12	M16	M20	M24	M27
Steel failure without lever arm <sup>3)</sup>							
Characteristic shear resistance, Steel grade 5.8	V <sub>Rk,s</sub>	[kN]	21	39	61	88	115
Characteristic shear resistance, Steel grade 8.8	V <sub>Rk,s</sub>	[kN]	34	63	98	141	184
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,25				
Steel failure without lever arm <sup>3)</sup>							
Characteristic shear resistance, Stainless steel A4 and HCR, property class 50 (>M24) and 70 (≤M24)	V <sub>Rk,s</sub>	[kN]	30	55	86	124	115
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,56				2,38
Steel failure with lever arm <sup>3)</sup>							
Characteristic bending moment, Steel grade 5.8	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	66	166	325	561	832
Characteristic bending moment, Steel grade 8.8	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	105	266	519	898	1332
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,25				
Steel failure with lever arm <sup>3)</sup>							
Characteristic bending moment, Stainless steel A4 and HCR, property class 50 (>M24) and 70 (≤M24)	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	92	233	454	786	832
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,56				2,38
Concrete pry-out failure							
Factor in equation ( 5.7 ) of TR 029 or in equation (27) to CEN/TS 1992-4-5	k / k <sub>3</sub>	[ - ]	2				
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,0				
Concrete edge failure							
Effective anchor length	l <sub>f</sub>	[ - ]	h <sub>ef</sub> <sup>2)</sup>				
Anchor diameter	d = d <sub>nom</sub>	[ - ]	12	16	20	24	27
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,0				

<sup>1)</sup> In absence of other national regulations

<sup>2)</sup> CEN/TS 1992-4-5:  $h_{ef} \leq 8 d_{nom}$

<sup>3)</sup> Ductility factor according to CEN/TS 1992-4-5: 6.3.2.1:  $k_2 = 1,0$

**S&P - ResEP-16 Epoxy Injection System**

**Performances**

Characteristic values of resistance to shear loads - Threaded rod  
Design method: **EOTA TR 029:09/2010** or **CEN/TS 1992-4-5:2009**

**Annex C2**

**Table C3: Characteristic values of resistance to tension loads.**  
**Design method TR 029 or CEN/TS 1992-4-5**

S&P ResEP-16 Epoxy Injection System			Reinforcing bar				
			Ø12	Ø14	Ø16	Ø20	Ø25
Steel failure							
Characteristic tension resistance B500B acc. DIN 488-2:2009-08 <sup>4)</sup>	N <sub>Rk,s</sub>	[kN]	62	85	111	173	270
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,4				
Combined pull-out and concrete cone failure							
Nom. rebar diameter	d	[mm]	12	14	16	20	25
Characteristic bond resistance in <b>non-cracked</b> concrete C20/25							
Temperature range I: 43°C / 24°C <sup>2)</sup>	τ <sub>Rk,ucr</sub>	[N/mm²]	13,5	8	8	7	5,5
Temperature range II: 65°C / 43°C <sup>2)</sup>	τ <sub>Rk,ucr</sub>	[N/mm²]	12,5	7,5	7,5	6,5	5
Factor according to CEN/TS 1992-4-5: 6.2.2.3	k <sub>8</sub>	[ - ]	10,1				
Characteristic bond resistance in <b>cracked</b> concrete C20/25							
Temperature range I: 43°C / 24°C <sup>2)</sup>	τ <sub>Rk,cr</sub>	[N/mm²]	5	3,5	2,5	2,5	2,5
Temperature range II: 65°C / 43°C <sup>2)</sup>	τ <sub>Rk,cr</sub>	[N/mm²]	4,5	3,5	2,5	2,5	2,5
Factor according to CEN/TS 1992-4-5: 6.2.2.3	k <sub>8</sub>	[ - ]	7,2				
Increasing factor for τ <sub>Rk,p</sub> in non-cracked and cracked concrete	Ψ <sub>c</sub>	C30/37	1,0				
		C40/50	1,02				
		C50/60	1,04				
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,4				
Concrete cone failure							
Factor according to CEN/TS 1992-4-5: 6.2.3.1	k <sub>cr</sub>	[ - ]	7,2				
Factor according to CEN/TS 1992-4-5: 6.2.3.1	k <sub>ucr</sub>	[ - ]	10,1				
Edge distance (splitting)	c <sub>cr,N</sub>	[mm]	1,5x h <sub>ef</sub>				
Center spacing (splitting)	s <sub>cr,N</sub>	[mm]	3x h <sub>ef</sub>				
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,4				
Splitting failure							
Edge distance (splitting)	c <sub>cr,sp</sub> <sup>3)5)</sup>	[mm]	$c_{cr,sp} = h_{ef} * \left(\frac{\tau_{k,ucr}}{8}\right)^{0,4} * \left(3,1 - 0,7 \frac{h}{h_{ef}}\right)$				
Center spacing (splitting)	s <sub>cr,sp</sub>	[mm]	2x c <sub>cr,sp</sub>				
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,4				

1) In absence of other national regulations

2) Maximum short and long term temperatures

3) Ratio value  $[h/h_{ef}] \leq 2,4$

4) For reinforcement bars that do not comply with DIN 488: The characteristic tension resistance  $N_{Rk,s}$  shall be determined acc. Technical Report TR 029, equation (5.5) or CEN/TS 1992-4-1, equation (B5).

$$5) \quad \tau_{k,ucr} \leq \frac{k_{ucr} * \sqrt{h_{ef} * f_{ck}}}{\pi * d}$$

**S&P - ResEP-16 Epoxy Injection System**

**Performances**

Characteristic values of resistance to tension loads - Reinforcing bar  
Design method: EOTA TR 029:09/2010 or CEN/TS 1992-4-5:2009

**Annex C3**

**Table C4: Characteristic values of resistance to shear loads.**  
**Design method TR 029 or CEN/TS 1992-4**

S&P ResEP-16 Epoxy Injection System			Reinforcing bar				
			Ø12	Ø14	Ø16	Ø20	Ø25
Steel failure without lever arm <sup>5)</sup>							
Characteristic resistance B500B acc. DIN 488-2:2009-08 <sup>3)</sup>	V <sub>Rk,s</sub>	[kN]	31	42	55	86	135
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,5				
Steel failure with lever arm <sup>5)</sup>							
Characteristic bending moment B500B acc. DIN 488-2:2009-08 <sup>4)</sup>	M <sup>0</sup> <sub>Rk,s</sub>	[Nm]	112	178	265	518	1012
Partial safety factor	γ <sub>Ms</sub> <sup>1)</sup>	[ - ]	1,5				
Concrete pry-out failure							
Factor in equation ( 5.7 ) of TR 029 or in equation (27) to CEN/TS 1992-4-5	k / k <sub>3</sub>	[ - ]	2				
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,0				
Concrete edge failure							
Effectiv anchor length	l <sub>f</sub>	[ - ]	h <sub>ef</sub> <sup>2)</sup>				
Anchor diameter	d = d <sub>nom</sub>	[ - ]	12	14	16	20	25
Installation safety factor	γ <sub>2</sub> = γ <sub>inst</sub>	[ - ]	1,0				

1) In absence of other national regulations

2) CEN/TS 1992-4-5:  $h_{ef} \leq 8 d_{nom}$

3) For reinforcing bars that do not comply with DIN 488: The characteristic resistance  $V_{Rk,s}$  shall be determined acc. Technical report TR 029, equation (5.5) or CEN/TS 1992-4-1, equation (B8).

4) For reinforcing bars that do not comply with DIN 488: The characteristic bending moment  $M^0_{Rk,s}$  shall be determined with:  $M^0_{Rk,s} = 1,2 \times W_{el} \times f_{uk}$

5) Ductility factor according to CEN/TS 1992-4-5: 6.3.2.1:  $k_2 = 1,0$

**S&P - ResEP-16 Epoxy Injection System**

**Performances**

Characteristic values of resistance to shear loads - Reinforcing bar  
Design method: EOTA TR 029:09/2010 or CEN/TS 1992-4-5:2009

**Annex C4**

**Table C5: Displacements under tension loads <sup>1)</sup>**

S&P			Threaded rod				
ResEP-16 Epoxy Injection System			M12	M16	M20	M24	M27
<b>Non-cracked concrete</b>							
<b>Temperature range I: 43°C / 24°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,020	0,030	0,010	0,010	0,030
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,024	0,040	0,040	0,044	0,064
<b>Temperature range II: 65°C / 43°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,020	0,030	0,010	0,012	0,031
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,025	0,042	0,042	0,047	0,070
<b>Cracked concrete</b>							
<b>Temperature range I: 43°C / 24°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,100	0,100	0,230	0,200	0,170
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,133	0,180	0,270	0,300	0,300
<b>Temperature range II: 65°C / 43°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,100	0,130	0,230	0,200	0,170
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,145	0,180	0,270	0,300	0,300

<sup>1)</sup> Calculation of the displacement:

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau \quad \tau = \text{action bond stress for tension}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$$

<sup>2)</sup>

Maximum short and long term temperatures

**Table C6: Displacements under shear loads <sup>3)</sup>**

S&P			Threaded rod				
ResEP-16 Epoxy Injection System			M12	M16	M20	M24	M27
Factor for displacement	$\delta_{V0}$ -factor	[mm/kN]	0,022	0,015	0,012	0,005	0,005
	$\delta_{V\infty}$ -factor	[mm/kN]	0,033	0,022	0,018	0,010	0,010

<sup>3)</sup> Calculation of the displacement:

$$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V \quad V = \text{action shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$$

**S&P - ResEP-16 Epoxy Injection System**

**Performances**  
Displacements - Threaded rod

**Annex C5**



**Table C7: Displacements under tension loads <sup>1)</sup>**

S&P ResEP-16 Epoxy Injection System			Reinforcing bar				
			Ø12	Ø14	Ø16	Ø20	Ø25
<b>Non-cracked concrete</b>							
<b>Temperature range I: 43°C / 24°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,015	0,030	0,040	0,043	0,055
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,033	0,056	0,063	0,071	0,090
<b>Temperature range II: 65°C / 43°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,020	0,030	0,040	0,045	0,050
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,036	0,060	0,066	0,077	0,100
<b>Cracked concrete</b>							
<b>Temperature range I: 43°C / 24°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,100	0,170	0,280	0,240	0,200
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,160	0,220	0,320	0,440	0,440
<b>Temperature range II: 65°C / 43°C <sup>2)</sup></b>							
Factor for displacement	$\delta_{N0}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,110	0,170	0,280	0,240	0,200
	$\delta_{N\infty}$ -factor	[mm/(N/mm <sup>2</sup> )]	0,178	0,228	0,320	0,440	0,440

<sup>1)</sup> Calculation of the displacement:

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau \quad \tau = \text{action bond stress for tension}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$$

<sup>2)</sup>

Maximum short and long term temperatures

**Table C8: Displacements under shear loads <sup>3)</sup>**

S&P ResEP-16 Epoxy Injection System			Reinforcing bar				
			Ø12	Ø14	Ø16	Ø20	Ø25
Factor for displacement	$\delta_{V0}$ -factor	[mm/kN]	0,010	0,010	0,013	0,015	0,015
	$\delta_{V\infty}$ -factor	[mm/kN]	0,013	0,015	0,019	0,023	0,023

<sup>3)</sup> Calculation of the displacement:

$$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V \quad V = \text{action shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$$

**S&P - ResEP-16 Epoxy Injection System**

**Performances**  
Displacements - Reinforcing bar

**Annex C6**