

Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-02/0030 of 10 July 2018

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:	Deutsches Institut für Bautechnik
Trade name of the construction product	Highload Anchor SZ
Product family to which the construction product belongs	Mechanical anchor for use in concrete
Manufacturer	MKT Metall-Kunststoff-Technik GmbH & Co. KG Auf dem Immel 2 67685 Weilerbach
Manufacturing plant	MKT Metall-Kunststoff-Technik GmbH & Co. KG Auf dem Immel 2 67685 Weilerbach
This European Technical Assessment contains	22 pages including 3 annexes which form an integral part of this assessment
This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of	EAD 330232-00-0601
This version replaces	ETA-02/0030 issued on 27 February 2018

European Technical Assessment
ETA-02/0030

English translation prepared by DIBt

Page 2 of 22 | 10 July 2018

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part**1 Technical description of the product**

The Highload Anchor SZ is an anchor made of galvanised steel or made of stainless steel which is placed into a drilled hole and anchored by torque-controlled expansion. The following anchor types are covered:

- Anchor type SZ-B with threaded bolt,
- Anchor type SZ-S with hexagon head screw,
- Anchor type SZ-SK with countersunk washer and countersunk screw.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment**3.1 Mechanical resistance and stability (BWR 1)**

Essential characteristic	Performance
Characteristic values for static and quasi-static loading	See Annex C1 to C6
Characteristic values for seismic performance category C1 and C2	See Annex C7 to C8
Displacements	See Annex C10 to C11

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C9

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD 330232-00-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

European Technical Assessment
ETA-02/0030
English translation prepared by DIBt

Page 4 of 22 | 10 July 2018

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.


Issued in Berlin on 10 July 2018 by Deutsches Institut für Bautechnik

BD Dipl.-Ing. Andreas Kummerow
Head of Department

beglaubigt:
Lange


Highload Anchor SZ

Fastener type SZ-B with threaded bolt




SZ-B (M6-M24)
SZ-B (M8-M16) A4

Fastener type SZ-S with hexagon head screw




SZ-S (M6-M24)
SZ-S (M8-M16) A4

Fastener type SZ-SK with countersunk washer and countersunk screw



SZ-SK (M6-M12)
SZ-SK (M8-M12) A4

Installation situation




Highload Anchor SZ

Product description


Product and installation situation

Annex A1


SZ-B



SZ-S



SZ-SK



Marking:

expansion sleeve:

- Identifying mark of manufacturing plant
- additional marking of stainless steel A4 A4
- Anchor identity (alternatively on distance sleeve) SZ
- size of thread (alternatively M10 on distance sleeve)



Distance sleeve:

- Diameter 15
- max. thickness of fixture $t_{fix,max}$ 25
- additional marking for countersunk version SK

marking on the washer of anchor size SZ 24/M16L

L

Table A1: Designation of fastener parts and materials

Part	Designation	Materials galvanized $\geq 5 \mu\text{m}$, acc. to EN ISO 4042:1999	Stainless steel A4
1	Threaded bolt	Steel, Strength class 8.8, EN ISO 898-1:2013	Stainless steel, 1.4401, 1.4404 or 1.4571, EN 10088:2014
2	Washer	Steel, EN 10139:2016	Stainless steel, EN 10088:2014
3	Distance sleeve	Steel tube EN 10305-2:2016, EN 10305-3:2016;	Steel tube stainless steel, 1.4401, 1.4404 or 1.4571; EN 10217-7:2014, EN 10216-5:2013
4	Ring	Polyethylene	Polyethylene
5	Expansion sleeve	Steel, EN 10139:2016	Stainless steel, 1.4401, 1.4404 or 1.4571, EN 10088:2014
6	Threaded cone	Steel EN 10083-2:2006	Stainless steel, 1.4401, 1.4404 or 1.4571, EN 10088:2014
7	Hexagon nut	Steel, Strength class 8, EN ISO 898-2:2012	Stainless steel, strength class 70, EN ISO 3506-2:2009
8	Hexagon head screw	Steel, Strength class 8.8, EN ISO 898-1:2013	Stainless steel, strength class 70, EN ISO 3506-1:2009
9	Countersunk screw	Steel, Strength class 8.8, EN ISO 898-1:2013	Stainless steel, strength class 70, EN ISO 3506-1:2009
10	Countersunk washer	Steel, EN 10083-2:2006	Stainless steel, 1.4401, 1.4404 or 1.4571, EN 10088:2014, zinc plated

Highload Anchor SZ

Product description
Marking and materials

Annex A2

Specification of intended use

Highload Anchor SZ, steel zinc plated	10/M6	12/M8	15/M10	18/M12	24/M16	24/ M16L	28/M20	32/M24
Static or quasi-static action						✓		
Seismic action (SZ-B and SZ-S)	-				C1 + C2			
Seismic action (SZ-SK)	-		C1 + C2				-	
Fire exposure				R 30 ... R 120				
Highload Anchor SZ, stainless steel A4	12/M8	15/M10	18/M12	24/M16				
Static or quasi-static action					✓			
Seismic action (SZ-B and SZ-S)			C1 + C2					
Seismic action (SZ-SK)		C1 + C2				-		
Fire exposure			R30 ... R120					

Base materials:

- Cracked and uncracked concrete
- Compacted, reinforced or unreinforced normal weight concrete (without fibers) according to EN 206:2013
- Strength classes C20/25 to C50/60 according to EN 206:2013

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc plated steel or stainless steel).
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal conditions, if no particular aggressive conditions exist (stainless steel).

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere of indoor pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used.)

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the fastener is indicated on the design drawings (e.g. position of the fastener relative to reinforcement or to supports, etc.).
- Anchorages under static or quasi-static actions, seismic actions and under fire exposure are designed in accordance with FprEN 1992-4:2016 and TR 055.

Installation:

- Fastener installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters on site.
- In case of aborted hole: new drilling at a minimum distance away of twice the depth of the aborted hole or smaller distance if the aborted drill hole is filled with high strength mortar and if under shear or oblique tension load it is not in the direction of load application.
- Compliance with the effective anchorage depth. For fastenings with anchorage depths $h_{ef} > h_{ef,min}$ the usable thickness of fixture is reduced by $h_{ef} - h_{ef,min}$.
- Use as supplied by the manufacturer without replacing individual parts.
- Drilling of hole only by hammer drilling (use of vacuum drill bits is admissible)


Highload Anchor SZ

Intended use


Specification of intended use

Annex B1

Installation instructions



Installation situation



Highload Anchor SZ

Intended use
Installation situation

Annex B3

Table B1: Installation parameters, steel zinc plated

Fastener size		10/M6	12/M8	15/M10	18/M12	24/M16	24/ M16L	28/M20	32/M24
Size of thread	[-]	M6	M8	M10	M12	M16	M16	M20	M24
Minimum effective anchorage depth	$h_{\text{ef},\min}$ [mm]	50	60	71	80	100	115	125	150
Maximum effective anchorage depth	$h_{\text{ef},\max}$ [mm]	76	100	110	130	114	150	185	210
Nominal diameter of drill bit	$d_0 =$ [mm]	10	12	15	18	24	24	28	32
Cutting diameter of drill bit	$d_{\text{cut}} \leq$ [mm]	10,45	12,5	15,5	18,5	24,55	24,55	28,55	32,7
Depth of drill hole	$h_1 \geq$ [mm]	$h_{\text{ef}} + 15$	$h_{\text{ef}} + 20$	$h_{\text{ef}} + 25$	$h_{\text{ef}} + 25$	$h_{\text{ef}} + 30$	$h_{\text{ef}} + 30$	$h_{\text{ef}} + 35$	$h_{\text{ef}} + 30$
Diameter of clearance hole in the fixture	$d_f \leq$ [mm]	12	14	17	20	26	26	31	35
Thickness of countersunk washer SZ-SK	t_{sk} [mm]	4	5	6	7	-	-	-	-
Minimum thickness of fixture SZ-SK	$t_{\text{fix min}}^{(2)}$ [mm]	8	10	14	18	-	-	-	-
Installation torque	T_{inst} (SZ-B, SZ-S) [Nm]	15	30	50	80	160	160	280	280
	T_{inst} (SZ-SK) [Nm]	10	25	55	70	-	-	-	-
Minimum thickness of member	h_{\min} [mm]	$h_{\text{ef}} + 50$	$h_{\text{ef}} + 60$	$h_{\text{ef}} + 69$	$h_{\text{ef}} + 80$	$h_{\text{ef}} + 100$	$h_{\text{ef}} + 115$	$h_{\text{ef}} + 125$	$h_{\text{ef}} + 150$
Minimum spacing ^{1) 3)} cracked concrete	s_{\min} [mm]	50	50	60	70	100	100	125	150
Minimum edge distance ^{1) 3)} cracked concrete	c_{\min} [mm]	50	55	60	70	100	100	180	150
Minimum spacing ^{1) 3)} uncracked concrete	s_{\min} [mm]	50	60	60	70	100	100	125	150
for $c \geq$ [mm]		80	100	120	140	180	180	300	300
Minimum edge distance ^{1) 3)} uncracked concrete	c_{\min} [mm]	50	60	60	70	100	100	180	150
for $s \geq$ [mm]		100	120	120	160	220	220	540	300

¹⁾ Intermediate values by linear interpolation

²⁾ Depending on the existing shear load, the thickness of the fixture may be reduced to the thickness of the countersunk washer t_{sk} (see Annex A2). It must be verified that the present shear load can be transferred completely into the distance sleeve (bearing of hole).

³⁾ For fire exposure from more than one side $c \geq 300$ mm or $c_{\min} \geq 300$ mm applies.

Highload Anchor SZ

Intended use
Installation parameters, steel zinc plated

Annex B4

Table B2: Installation parameters, stainless steel A4

Fastener size		12/M8	15/M10	18/M12	24/M16
Size of thread	[-]	M8	M10	M12	M16
Minimum effective anchorage depth	$h_{\text{ref},\min}$ [mm]	60	71	80	100
Maximum effective anchorage depth	$h_{\text{ref},\max}$ [mm]	100	110	130	150
Nominal diameter of drill bit	$d_0 =$ [mm]	12	15	18	24
Cutting diameter of drill bit	$d_{\text{cut}} \leq$ [mm]	12,5	15,5	18,5	24,55
Depth of drill hole	$h_1 \geq$ [mm]	$h_{\text{ref}} + 20$	$h_{\text{ref}} + 25$	$h_{\text{ref}} + 25$	$h_{\text{ref}} + 30$
Diameter of clearance hole in the fixture	$d_f \leq$ [mm]	14	17	20	26
Thickness of countersunk washer SZ-SK	t_{sk} [mm]	5	6	7	-
Minimum thickness of fixture SZ-SK	$t_{\text{fix min}}^{\text{2)}} [mm]$	10	14	18	-
Installation torque	$T_{\text{inst}} (\text{SZ-B})$ [Nm]	35	55	90	170
	$T_{\text{inst}} (\text{SZ-S})$ [Nm]	30	50	80	170
	$T_{\text{inst}} (\text{SZ-SK})$ [Nm]	17,5	42,5	50	-
Minimum thickness of member	h_{\min} [mm]	$h_{\text{ref}} + 60$	$h_{\text{ref}} + 69$	$h_{\text{ref}} + 80$	$h_{\text{ref}} + 100$
Minimum spacing ^{1) 3)}	s_{\min} [mm]	50	60	70	80
cracked concrete	for $c \geq$ [mm]	80	120	140	180
Minimum edge distance ^{1) 3)}	c_{\min} [mm]	50	60	70	80
cracked concrete	for $s \geq$ [mm]	80	120	160	200
Minimum spacing ^{1) 3)}	s_{\min} [mm]	50	60	70	80
uncracked concrete	for $c \geq$ [mm]	80	120	140	180
Minimum edge distance ^{1) 3)}	c_{\min} [mm]	50	85	70	180
uncracked concrete	for $s \geq$ [mm]	80	185	160	80

¹⁾ Intermediate values by linear interpolation

²⁾ Depending on the existing shear load, the thickness of the fixture may be reduced to the thickness of the countersunk washer t_{sk} (see Annex A2). It must be verified that the present shear load can be transferred completely into the distance sleeve (bearing of hole).

³⁾ For fire exposure from more than one side $c \geq 300$ mm or $c_{\min} \geq 300$ mm applies.

Highload Anchor SZ

Intended use
Installation parameters, stainless steel A4

Annex B5

Table C1: Characteristic values for **tension load, cracked concrete, static or quasi-static action, steel zinc plated**

Fastener size		10/M6	12/M8	15/M10	18/M12	24/M16	24/ M16L	28/M20	32/M24
Installation factor	γ_{inst} [-]						1,0		
Steel failure									
Characteristic resistance	$N_{Rk,s}$ [kN]	16	29	46	67	126	126	196	282
Partial factor	γ_{Ms} [-]						1,5		
Pull-out failure									
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p}$ [kN]	5	12	16	25	36	44	50	65
Increasing factor for $N_{Rk,p}$	ψ_c [-]						$\left(\frac{f_{ck}}{20}\right)^{0,5}$		
Concrete cone failure									
Minimum effective anchorage depth	$h_{\text{ef},\text{min}}$ [mm]	50	60	71	80	100	115	125	150
Maximum effective anchorage depth	$h_{\text{ef},\text{max}}$ [mm]	76	100	110	130	114	150	185	210
Factor for cracked concrete	$k_1 = k_{cr,N}$	[-]				7,7			

Highload Anchor SZ

Performance

Characteristic values for **tension load, cracked concrete, static or quasi-static action, steel zinc plated**

Annex C1

Table C2: Characteristic values for **tension load, cracked concrete, static or quasi-static action, stainless steel A4**

Fastener size			12/M8	15/M10	18/M12	24/M16
Installation factor	γ_{inst}	[-]			1,0	
Steel failure						
SZ-B						
Characteristic resistance	$N_{Rk,s}$	[kN]	26	41	60	110
Partial factor	γ_{Ms}	[-]			1,5	
SZ-S and SZ-SK						
Characteristic resistance	$N_{Rk,s}$	[kN]	26	41	60	110
Partial factor	γ_{Ms}	[-]			1,87	
Pull-out failure						
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p}$	[kN]	9	16	25	36
Increasing factor for $N_{Rk,p}$	ψ_c	[-]			$\left(\frac{f_{ck}}{20}\right)^{0,5}$	
Concrete cone failure						
Minimum effective anchorage depth	$h_{\text{ef,min}}$	[mm]	60	71	80	100
Maximum effective anchorage depth	$h_{\text{ef,max}}$	[mm]	100	110	130	150
Factor for cracked concrete	$k_1 = k_{cr,N}$	[-]			7,7	

Highload Anchor SZ

Performance

Characteristic values for **tension load, cracked concrete, static or quasi-static action, stainless steel A4**

Annex C2

Table C3: Characteristic values for **tension load, uncracked concrete, static or quasi-static action, steel zinc plated**

Fastener size		10/M6	12/M8	15/M10	18/M12	24/M16	24/ M16L	28/M20	32/M24	
Installation factor	γ_{inst}	[-]					1,0			
Steel failure										
Characteristic resistance	$N_{Rk,s}$	[kN]	16	29	46	67	126	126	196	282
Partial factor	γ_{Ms}	[-]					1,5			
Pull-out failure										
Characteristic resistance in uncracked concrete C20/25	$N_{Rk,p}$	[kN]	17	20	30	36	50	¹⁾	70	¹⁾
Increasing factor for $N_{Rk,p}$	ψ_c	[-]			$\left(\frac{f_{ck}}{20}\right)^{0,5}$		-	$\left(\frac{f_{ck}}{20}\right)^{0,5}$	-	
Splitting failure (The higher resistance of case 1 and case 2 may be applied)										
Case 1										
Characteristic resistance in uncracked concrete C20/25	$N^0_{Rk,sp}$	[kN]	12	16	25	30	40	70	50	70
Edge distance	$c_{cr,sp}$	[mm]					1,5 h_{ef}			
Increasing factor for $N^0_{Rk,sp}$	ψ_c	[-]			$\left(\frac{f_{ck}}{20}\right)^{0,5}$					
Case 2										
Characteristic resistance in uncracked concrete	$N^0_{Rk,sp}$	[kN]					$\min(N_{Rk,p}; N^0_{Rk,c})$			
Edge distance	$c_{cr,sp}$	[mm]				2,5 h_{ef}		1,5 h_{ef}	2,5 h_{ef}	2 h_{ef}
Concrete cone failure										
Minimum effective anchorage depth	$h_{\text{ef},\text{min}}$	[mm]	50	60	71	80	100	115	125	150
Maximum effective anchorage depth	$h_{\text{ef},\text{max}}$	[mm]	76	100	110	130	114	150	185	210
Edge distance	$c_{cr,N}$	[mm]					1,5 h_{ef}			
Factor for uncracked concrete	$k_1 = k_{ucr,N}$	[-]					11,0			

¹⁾ $N_{Rk,p} = N^0_{Rk,c}$ calculated with $h_{\text{ef},\text{min}}$

Highload Anchor SZ

Performance

Characteristic values for **tension load, uncracked concrete, static or quasi-static action, steel zinc plated**

Annex C3

Table C4: Characteristic values for **tension load, uncracked concrete**, static or quasi-static action, **stainless steel A4**

Fastener size		12/M8	15/M10	18/M12	24/M16
Installation factor	γ_{inst}	[$-$]		1,0	
Steel failure					
SZ-B					
Characteristic resistance	$N_{Rk,s}$	[kN]	26	41	60
Partial factor	γ_{Ms}	[$-$]		1,5	
SZ-S and SZ-SK					
Characteristic resistance	$N_{Rk,s}$	[kN]	26	41	60
Partial factor	γ_{Ms}	[$-$]		1,87	
Pull-out failure					
Characteristic resistance in uncracked concrete C20/25	$N_{Rk,p}$	[kN]	16	25	35
Increasing factor for $N_{Rk,p}$	ψ_c	[$-$]		$\left(\frac{f_{ck}}{20}\right)^{0,5}$	
Splitting failure					
Edge distance	$c_{cr,sp}$	[mm]	180	235	265
Concrete cone failure					
Minimum effective anchorage depth	$h_{ef,min}$	[mm]	60	71	80
Maximum effective anchorage depth	$h_{ef,max}$	[mm]	100	110	130
Edge distance	$c_{cr,N}$	[mm]		1,5 h_{ef}	
Factor for uncracked concrete	$k_1 = k_{ucr,N}$	[$-$]		11,0	

Highload Anchor SZ

Performance

Characteristic values for **tension loads, uncracked concrete**, static or quasi-static action, **stainless steel A4**

Annex C4

Table C5: Characteristic values of **shear load**, static or quasi-static action,
steel zinc plated

Fastener size	10/M6	12/M8	15/M10	18/M12	24/M16	24/ M16L	28/M20	32/M24	
Steel failure without lever arm									
SZ-B									
Characteristic resistance $V^0_{Rk,s}$	[kN]	16	25	36	63	91	91	122	200
Ductility factor k_7	[-]				1,0				
SZ-S and SZ-SK									
Characteristic resistance $V^0_{Rk,s}$	[kN]	18	30	48	73	126	126	150	200
Ductility factor k_7	[-]				1,0				
Partial factor γ_{Ms}	[-]				1,25				
Steel failure with lever arm									
Characteristic resistance $M^0_{Rk,s}$	[Nm]	12	30	60	105	266	266	519	898
Partial factor γ_{Ms}	[-]				1,25				
Concrete pry-out failure									
Pry-out factor k_8	[-]	1,8 ¹⁾				2,0			
Concrete edge failure									
Effective length of fastener in shear loading l_f	[mm]					h_{ef}			
Outside diameter of fastener d_{nom}	[mm]	10	12	15	18	24	24	28	32

¹⁾ $k_8 = 2,0$ for $h_{ef} \geq 60$ mm

Highload Anchor SZ

Performance

Characteristic values for **shear load**, static or quasi-static action,
steel zinc plated

Annex C5

Table C6: Characteristic values for **shear load**, static or quasi-static action,
stainless steel A4

Fastener size		12/M8	15/M10	18/M12	24/M16
Steel failure without lever arm					
Characteristic resistance	$V^0_{Rk,s}$ [kN]	24	37	62	92
SZ-B					
Ductility factor	k_7 [-]		1,0		
Partial factor	γ_{Ms} [-]		1,25		
SZ-S					
Ductility factor	k_7 [-]		1,0		
Partial factor	γ_{Ms} [-]		1,36		
SZ-SK					
Ductility factor	k_7 [-]		0,8		-
Partial factor	γ_{Ms} [-]		1,36		-
Steel failure with lever arm					
Characteristic bending resistance	$M^0_{Rk,s}$ [Nm]	26	52	92	232
SZ-B					
Partial factor	γ_{Ms} [-]		1,25		
SZ-S and SZ-SK					
Partial factor	γ_{Ms} [-]		1,56		
Concrete pry-out failure					
Pry-out factor	k_8 [-]		2,0		
Concrete edge failure					
Effective length of fastener in shear loading	l_f [mm]			h_{ef}	
Outside diameter of fastener	d_{nom} [mm]	12	15	18	24

Highload Anchor SZ

Performance

Characteristic values for **shear load**, static or quasi-static action,
stainless steel A4

Annex C6

Table C7: Characteristic values for **seismic action, Category C1 and C2, steel zinc plated**

Fastener size		12/M8	15/M10	18/M12	24/M16	24/M16L	28/M20	32/M24	
Tension load									
Installation factor	γ_{inst}	[\cdot]				1,0			
Steel failure									
Characteristic resistance category C1	$N_{Rk,s,eq,C1}$	[kN]	29	46	67	126	126	196	280
Characteristic resistance category C2	$N_{Rk,s,eq,C2}$	[kN]	29	46	67	126	126	196	280
Partial factor	γ_{Ms}	[\cdot]				1,5			
Pull-out failure									
Characteristic resistance category C1	$N_{Rk,p,eq,C1}$	[kN]	12	16	25	36	44,4	50,3	63,3
Characteristic resistance category C2	$N_{Rk,p,eq,C2}$	[kN]	5,4	16,4	22,6	29,0	41,2	43,6	63,3
Shear load									
Steel failure without lever arm									
SZ-B									
Characteristic resistance category C1	$V_{Rk,s,eq,C1}$	[kN]	18,0	27,1	43,4	51,9	51,9	96,4	160,1
Characteristic resistance category C2	$V_{Rk,s,eq,C2}$	[kN]	12,7	20,5	31,5	50,1	50,1	67,1	108,1
SZ-S									
Characteristic resistance category C1	$V_{Rk,s,eq,C1}$	[kN]	18,0	27,1	43,4	51,9	51,9	96,4	160,1
Characteristic resistance category C2	$V_{Rk,s,eq,C2}$	[kN]	12,7	20,5	31,5	69,3	69,3	67,1	108,1
SZ-SK									
Characteristic resistance category C1	$V_{Rk,s,eq,C1}$	[kN]	25,2	36,5	50,4	-	-	-	-
Characteristic resistance category C2	$V_{Rk,s,eq,C2}$	[kN]	19,2	29,3	39,4	-	-	-	-
Factor for annular gap	α_{gap}	[\cdot]				0,5			
Partial factor	γ_{Ms}	[\cdot]				1,25			
Highload Anchor SZ									
Performance Characteristic values for seismic action, steel zinc plated								Annex C7	

Table C8: Characteristic values for **seismic action, Category C1 and C2, stainless steel A4**

Fastener size		12/M8	15/M10	18/M12	24/M16
Tension load					
Installation factor	γ_{inst}	[-]		1,0	
Steel failure					
Characteristic resistance, category C1	$N_{Rk,s,\text{eq},C1}$	[kN]	26	41	60
Characteristic resistance, category C2	$N_{Rk,s,\text{eq},C2}$	[kN]	26	41	60
Partial factor SZ-B	γ_{Ms}	[-]		1,5	
Partial factor SZ-S and SZ-SK	γ_{Ms}	[-]		1,87	
Pull-out failure					
Characteristic resistance, category C1	$N_{Rk,p,\text{eq},C1}$	[kN]	9	16	26
Characteristic resistance, category C2	$N_{Rk,p,\text{eq},C2}$	[kN]	4,8	16,5	24,8
Shear load					
Steel failure without lever arm					
SZ-B					
Characteristic resistance, category C1	$V_{Rk,s,\text{eq},C1}$	[kN]	9,6	13,3	25,4
Characteristic resistance, category C2	$V_{Rk,s,\text{eq},C2}$	[kN]	9,7	14,0	18,0
Partial factor	γ_{Ms}	[-]		1,25	
SZ-S					
Characteristic resistance, category C1	$V_{Rk,s,\text{eq},C1}$	[kN]	9,6	13,3	25,4
Characteristic resistance, category C2	$V_{Rk,s,\text{eq},C2}$	[kN]	9,7	14,0	18,0
Partial factor	γ_{Ms}	[-]		1,36	
SZ-SK					
Characteristic resistance, category C1	$V_{Rk,s,\text{eq},C1}$	[kN]	11,5	23,3	31,6
Characteristic resistance, category C2	$V_{Rk,s,\text{eq},C2}$	[kN]	10,8	17,4	15,4
Partial factor	γ_{Ms}	[-]		1,36	-
Highload Anchor SZ					
Performance Characteristic values for seismic action, stainless steel A4					
Annex C8					

English translation prepared by DIBt

Table C9: Characteristic values under **fire exposure** in cracked and uncracked concrete C20/25 to C50/60

Fastener size		10/M6	12/M8	15/M10	18/M12	24/M16	24/ M16L	28/M20	32/M24
Tension load									
Steel failure									
Steel zinc plated									
Characteristic resistance	R30 R60 R90 R120	N _{Rk,s,fi} [kN]	1,0 0,8 0,6 0,4	1,9 1,5 1,0 0,8	4,3 3,2 2,1 1,5	6,3 4,6 3,0 2,0	11,6 8,6 5,0 3,1	18,3 13,5 7,7 4,9	26,3 19,5 12,6 9,2
Stainless steel A4									
Characteristic resistance	R30 R60 R90 R120	N _{Rk,s,fi} [kN]	- - - -	6,1 4,4 2,6 1,8	10,2 7,3 4,3 2,8	15,7 11,1 6,4 4,1	29,2 20,6 12,0 7,7	- - - -	- - - -
Shear load									
Steel failure without lever arm									
Steel zinc plated									
Characteristic resistance	R30 R60 R90 R120	V _{Rk,s,fi} [kN]	1,0 0,8 0,6 0,4	1,9 1,5 1,0 0,8	4,3 3,2 2,1 1,5	6,3 4,6 3,0 2,0	11,6 8,6 5,0 3,1	18,3 13,5 7,7 4,9	26,3 19,5 12,6 9,2
Stainless steel A4									
Characteristic resistance	R30 R60 R90 R120	V _{Rk,s,fi} [kN]	- - - -	14,3 11,1 7,9 6,3	22,7 17,6 12,6 10,0	32,8 25,5 18,3 14,6	61,0 47,5 34,0 27,2	- - - -	- - - -
Steel failure with lever arm									
Steel zinc plated									
Characteristic bending resistance	R30 R60 R90 R120	M ⁰ _{Rk,s,fi} [Nm]	0,8 0,6 0,4 0,3	2,0 1,5 1,0 0,8	5,6 4,1 2,7 1,9	9,7 7,2 4,7 3,1	24,8 18,3 11,9 6,6	42,4 29,8 17,1 10,7	83,6 61,9 40,1 29,2
Stainless steel A4									
Characteristic bending resistance	R30 R60 R90 R120	M ⁰ _{Rk,s,fi} [Nm]	- - - -	6,2 4,5 2,7 1,8	13,2 9,4 5,6 3,6	24,4 17,2 10,0 6,4	61,8 43,6 25,3 16,2	- - - -	- - - -

If pull-out is not decisive in equation D.4 and D.5, FprEN 1992-4:2016 N_{Rk,p} must be replaced by N⁰_{Rk,c}.

Highload Anchor SZ

Performance
Characteristic values under **fire exposure**

Annex C9

Table C10: Displacements under tension and shear load, **steel zinc plated**

Fastener size		10/ M6	12/ M8	15/ M10	18/ M12	24/ M16	24/ M16L	28/ M20	32/ M24	
Tension load										
Tension load in cracked concrete	N	[kN]	2,4	5,7	7,6	12,3	17,1	21,1	24	26,2
Displacement	δ_{N0}	[mm]	0,5	0,5	0,5	0,7	0,8	0,7	0,9	1,4
	$\delta_{N\infty}$	[mm]	2,0	2,0	1,3	1,3	1,3	1,3	1,4	1,9
Tension load in uncracked concrete	N	[kN]	8,5	9,5	14,3	17,2	24	29,6	34	43
Displacement	δ_{N0}	[mm]	0,8	1,0		1,1		1,3	0,3	0,7
	$\delta_{N\infty}$	[mm]		3,4		1,7		2,3	1,4	0,7
Seismic action C2										
Displacement for DLS	$\delta_{N,\text{eq}}(\text{DLS})$	[mm]	-	3,3	3,0	5,0	3,0	3,0	4,0	5,3
Displacement for ULS	$\delta_{N,\text{eq}}(\text{ULS})$	[mm]	-	12,2	11,3	16,0	9,2	9,2	13,8	12,4
Shear load										
SZ-B										
Shear load in cracked and uncracked concrete	V	[kN]	9,1	14	20,7	35,1	52,1	52,1	77	86,6
Displacement	δ_{V0}	[mm]	2,5	2,1	2,7	3,0	5,1	5,1	4,3	10,5
	$\delta_{V\infty}$	[mm]	3,8	3,1	4,1	4,5	7,6	7,6	6,5	15,8
Seismic action C2										
Displacement for DLS	$\delta_{V,\text{eq}}(\text{DLS})$	[mm]	-	2,3	3,1	3,0	2,6	2,6	1,6	6,1
Displacement for ULS	$\delta_{V,\text{eq}}(\text{ULS})$	[mm]	-	4,8	6,4	6,1	6,6	6,6	4,8	9,5
SZ-S										
Shear load in cracked and uncracked concrete	V	[kN]	10,1	17,1	27,5	41,5	72	72	77	86,6
Displacement	δ_{V0}	[mm]	2,9	2,5	3,6	3,5	7,0	7,0	4,3	10,5
	$\delta_{V\infty}$	[mm]	4,4	3,8	5,4	5,3	10,5	10,5	6,5	15,8
Seismic action C2										
Displacement for DLS	$\delta_{V,\text{eq}}(\text{DLS})$	[mm]	-	2,3	3,1	3,0	3,3	3,3	1,6	6,1
Displacement for ULS	$\delta_{V,\text{eq}}(\text{ULS})$	[mm]	-	4,8	6,4	6,1	8,2	8,2	4,8	9,5
SZ-SK										
Shear load in cracked and uncracked concrete	V	[kN]	10,1	17,1	27,5	41,5	-	-	-	-
Displacement	δ_{V0}	[mm]	2,9	2,5	3,6	3,5	-	-	-	-
	$\delta_{V\infty}$	[mm]	4,4	3,8	5,4	5,3	-	-	-	-
Seismic action C2										
Displacement for DLS	$\delta_{V,\text{eq}}(\text{DLS})$	[mm]	-	3,1	3,9	3,9	-	-	-	-
Displacement for ULS	$\delta_{V,\text{eq}}(\text{ULS})$	[mm]	-	10,2	11,8	13,0	-	-	-	-
Highload Anchor SZ										
Performance Displacements under tension and shear load, steel zinc plated								Annex C10		

Table C11: Displacements under tension and shear load, **stainless steel A4**

Fastener size		12/M8	15/M10	18/M12	24/M16
Tension load					
Tension load in cracked concrete	N	[kN]	4,3	7,6	12,1
Displacement	δ_{N0}	[mm]	0,5	0,5	1,3
	$\delta_{N\infty}$	[mm]	1,2	1,6	1,8
Tension load in uncracked concrete	N	[kN]	7,6	11,9	16,7
Displacement	δ_{N0}	[mm]	0,2	0,3	1,2
	$\delta_{N\infty}$	[mm]	1,1	1,1	1,1
Seismic action C2					
Displacement for DLS	$\delta_{N,\text{eq}}(\text{DLS})$	[mm]	4,7	4,5	4,3
Displacement for ULS	$\delta_{N,\text{eq}}(\text{ULS})$	[mm]	13,3	12,7	9,7
Shear load					
Shear load in cracked concrete	V	[kN]	13,9	21,1	34,7
Displacement	δ_{V0}	[mm]	3,4	4,9	4,8
	$\delta_{V\infty}$	[mm]	5,1	7,4	7,1
Seismic action C2					
SZ-B, SZ-S					
Displacement for DLS	$\delta_{V,\text{eq}}(\text{DLS})$	[mm]	2,8	3,1	2,6
Displacement for ULS	$\delta_{V,\text{eq}}(\text{ULS})$	[mm]	5,6	5,8	5,0
SZ-SK					
Displacement for DLS	$\delta_{V,\text{eq}}(\text{DLS})$	[mm]	2,5	2,8	2,9
Displacement for ULS	$\delta_{V,\text{eq}}(\text{ULS})$	[mm]	5,8	5,9	6,9