

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-18/0261
of 17 July 2018

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

Styrisol

Product family
to which the construction product belongs

Extruded polystyrene foam boards as load bearing layer
and thermal insulation outside the waterproofing

Manufacturer

ABRISO
Protective Packaging & Insulation
Gijzelbrechtegemstraat 8-10
8570 ANZEGEM
BELGIEN

Manufacturing plant

ABRISO
Gijzelbrechtegemstraat 8-10
8570 ANZEGEM

This European Technical Assessment
contains

7 pages including 1 annex which form an integral part of
this assessment

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

EAD 040650-00-1201

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The extruded polystyrene foam boards are made of rigid cellular plastics material extruded from polystyrene or one of its copolymers and which has a closed cell structure. The blowing agent mixture is of HFC-134a, HFC-152a and carbon dioxide (CO₂). The extruded polystyrene foam boards have a skin on both surfaces and a special edge treatment (shiplap).

The extruded polystyrene foam boards do not contain Hexabromocyclododecane (HBCD).

The extruded polystyrene foam boards have the following designation:

"Styrisol".

The extruded polystyrene foam boards are manufactured with the following dimensions:

Nominal thicknesses:	50 mm to 120 mm
Nominal length:	1250 mm
Nominal widths:	600 mm

The European Technical Assessment has been issued for the product on the basis of agreed data/information, deposited with Deutsches Institut für Bautechnik, which identifies the product that has been assessed. The European Technical Assessment applies only to products corresponding to this agreed data/information.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The extruded polystyrene foam boards are intended to be used as load bearing layer and/or thermal insulation outside the waterproofing. The boards are laid uniformly on the substrate to which they are applied. In particular the following applications are intended:

- Load bearing and thermal insulation underneath foundation slabs
- External horizontal and vertical thermal insulation of in-ground constructions in non-structural applications (also in case of groundwater)
- Inverted roof insulation (including park deck and green roof applications)

The performance according to section 3 only applies if the thermal insulation boards are installed according to the manufacturer's installation instructions and if they are protected from precipitation, wetting or weathering during transport and storage before installation.

Concerning the application of the thermal insulation boards, also the respective national regulations shall be observed.

Where the thermal insulation boards are fixed by using adhesives, only such adhesions shall be used, which are suitable for this purpose. The assessment of these fixings is not subject of this European Technical Assessment.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the extruded polystyrene foam boards of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

For sampling, conditioning and testing the provisions of the EAD No 040650-00-1201 "Extruded polystyrene foam boards as load bearing layer and/or thermal insulation outside the waterproofing" apply.

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Compressive stress at 10 % deformation or compressive strength test acc. to EN 826:2013 Slip deformation Compressive stress or compressive strength in the transverse and longitudinal directions	Level (individual values may fall below this level up to 10 %): ≥ 300 kPa No performance assessed No performance assessed
Characteristic value of compressive stress or compressive strength 5 %-fractile value for a one-sided confidence level of 75 % under unknown or known variance using ISO 12491:1997 thickness $50 \text{ mm} \leq d \leq 80 \text{ mm}$ thickness $80 \text{ mm} < d \leq 120 \text{ mm}$	$\sigma_{0,05} = 353 \text{ kPa}$ ($n = 50$; $\sigma_{\text{mean}} = 435 \text{ kPa}$; $s_{\sigma} = 48 \text{ kPa}$) $\sigma_{0,05} = 444 \text{ kPa}$ ($n = 50$; $\sigma_{\text{mean}} = 504 \text{ kPa}$; $s_{\sigma} = 33 \text{ kPa}$)
Compressive creep	See Annex A
Behaviour under shear load (large-sized specimen)	No performance assessed
Creep under shear load	No performance assessed
Creep under combined compressive and shear load	No performance assessed
Compressive modulus of elasticity	No performance assessed
Adhesion behaviour under compressive and shear load on large-sized samples	No performance assessed
Shear strength	No performance assessed
Density test acc. to EN 1602:2013	density range: 33 kg/m ³ - 37 kg/m ³

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire test acc. to EN ISO 11925-2:2010	Class E acc. to EN 13501-1:2007 + A1:2009

3.3 Energy economy and heat retention (BWR 6)

Essential characteristic	Performance
<p>Thermal conductivity at mean reference temperature of 10 °C test acc. to EN 12667:2001 or EN 12939:2001 and aging procedure acc. EN 13164:2012+A1:2015, Annex C with deviating storage time period (sliced specimen) of (90 +2/-2) days prior to testing</p> <p>thickness 50 mm ≤ d ≤ 60 mm thickness 60 mm < d ≤ 120 mm</p> <p>Moisture conversion coefficient</p>	<p>$\lambda_{D(90d)} = 0,034 \text{ W/(m} \cdot \text{K)}$ $\lambda_{D(90d)} = 0,035 \text{ W/(m} \cdot \text{K)}$</p> <p>No performance assessed</p>
<p>Water absorption</p> <p>Long term water absorption by total immersion test acc. to EN 12087:2013 (method 2A)</p> <p>Long term water absorption by diffusion test acc. to EN 12088:2013</p>	<p>WL(T)0,7 ($W_{it} \leq 0,7 \text{ Vol.}\%$)</p> <p>WD(V)3 ($W_{dv} \leq 3,0 \text{ Vol.}\%$)</p>
<p>Freeze-thaw resistance test acc. to EN 12091:2013</p> <p>using the wet test specimens from having done the water diffusion test in accordance with EN 12088</p> <p>Reduction in compressive stress at 10 % deformation or in compressive strength of the re-dried specimens, when tested in accordance with EN 826:2013</p>	<p>FTCD1 ($W_v \leq 1,0 \text{ Vol.}\%$)</p> <p>≤ 10 %</p>
<p>Water vapour diffusion resistance factor</p>	<p>No performance assessed</p>
<p>Geometrical properties</p> <p>Thickness test acc. EN 823:2013 (clause 7.2, figure 2, measuring set-up 3)</p> <p>Length, width test acc. EN 822:2013</p> <p>Squareness in direction of length and width; in direction of thickness test acc. EN 824:2013</p> <p>Flatness in direction of length and width test acc. EN 825:2013</p>	<p>tolerance</p> <p>-2/+3 mm</p> <p>± 8 mm</p> <p>5 mm/m</p> <p>2 mm</p>

Essential characteristic	Performance
Deformation under specified compressive load and temperature conditions test acc. to EN 1605:2013	load: 40 kPa; temperature: (70 ± 1) °C; time: (168 ± 1) h $\leq 5 \%$
Dimensional stability under specified conditions test acc. to EN 1604:2013	temperature: 70 °C and 90 % R.H. DS(70,90) ($\Delta\epsilon_l \leq 5 \%$, $\Delta\epsilon_b \leq 5 \%$, $\Delta\epsilon_d \leq 5 \%$)
Tensile strength perpendicular to faces	No performance assessed
Volume percentage of closed cells test acc. to EN ISO 4590:2016 (method 1 with correction)	$\geq 95 \%$

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with EAD No. 040650-00-1201, the applicable European legal acts are: 1995/467/EC and 1999/91/EC ¹.

The systems to be applied are:

- System 1 for Essential characteristics concerning Mechanical resistance and stability (BWR 1)
- System 3 all other Essential characteristics

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 17 July 2018 by Deutsches Institut für Bautechnik

Prof. Gunter Hoppe
Head of Department

beglaubigt:
Wendler

¹ as amended

Styrisol

Annex A

1. Compressive creep

1.1 Compressive creep (single-layer board)

Styrisol ¹	thickness 50 mm			thickness 120 mm		
density (kg/m ³)	35,5	35,5	36	36,5	36,43	36,43
compressive stress/ deformation acc. EN 826 (kPa / %)	396/10			580/10		
load stage (kPa)	100	125	150	100	125	150
X ₀ (mm)	0,27	0,3	0,37	0,43	0,61	0,61
X _{ct} (mm)	0,195	0,279	0,344	0,279	0,336	0,365
X _{ct50} (mm)	0,48	0,71	0,83	0,82	0,86	1,06
X_{t50}(mm)	0,75	1,01	1,2	1,25	1,47	1,67

Styrisol	thickness 50 mm		thickness 120 mm	
density (kg/m ³)	33,7	33,7	35,9	35,6
compressive stress/ deformation acc. EN 826 (kPa / %)	472/10		413/10	
load stage (kPa)	100	125	100	125
X ₀ (mm)	0,37	0,24	0,19	0,25
X _{ct} (mm)	0,50	0,39	0,25	0,64
X _{ct50} (mm)	0,546	0,43	0,868	1,045
X_{t50}(mm)	0,914	0,67	1,056	1,295

¹ Differing flame retardant