

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-18/0643
of 1 November 2018

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

ICCONS ThunderBolt® Pro - XTM

Product family
to which the construction product belongs

Mechanical fasteners for use in concrete

Manufacturer

ICCONS Pty Ltd (New Zealand)
c/o - 5E Piermark Drive
Rosedale
AUCKLAND 0632
NEUSEELAND

Manufacturing plant

Factory Plant 1

This European Technical Assessment
contains

18 pages including 3 annexes which form an integral part
of this assessment

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

EAD 330232-00-0601

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The ICCONS ThunderBolt® Pro - XTM of sizes IC 8, IC 10 and IC 12 is an anchor made of galvanized or stainless steel. The anchor is screwed into a predrilled cylindrical drill hole. The special thread of the anchor cuts an internal thread into the member while setting. The anchorage is characterised by mechanical interlock in the special thread.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the concrete screw is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the concrete screw of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	see Annex C 1 and C 2
Characteristic resistance to shear load (static and quasi-static loading)	see Annex C 4
Displacements (static and quasi-static loading)	see Annex C 3 and C 5
Characteristic resistance and displacements for seismic performance categories C1 and C2	No performance assessed

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 6 and C 7

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Documents EAD No. 330232-00-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

English translation prepared by DIBt

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document


Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin 1 November 2018 by Deutsches Institut für Bautechnik

Dr.-Ing. Lars Eckfeldt
p.p. Head of Department

beglaubigt:
Baderschneider


Product in the installed condition




Steel 10B21




Stainless steel A4




Hexagon Head : IC-H, IC-HF
10B21 (IC8, IC10, IC12)
A4 (IC8, IC10, IC12)



Countersunk Head : IC-CS
10B21 (IC8, IC10)
A4 (IC8, IC10)



Pan Head : IC-PH
10B21 (IC8, IC10)
A4 (IC8, IC10)



Hanger Bolt : IC-HB
A4 (IC10-M12)


ICCONS ThunderBolt® Pro - XTM

Product description
Installed condition


Annex A1

Table A1: Materials and screw types

Name		Material								
Screw fastener	Head marking	material								
	IC	Steel 10B21 acc. to SAE-J403 zinc coating: electroplated (> 5 µm) or mechanical plated (> 30 µm) (only head type –H and –HF)								
	IC A4	Stainless steel 1.4401, 1.4404 (both A4)								
Anchor size / head types		IC 8			IC 10			IC 12		
		-H -HF -CS -PH	-H -HF	-CS -PH	-H -HF -CS -PH	-H -HF -PH	-CS -PH	-H -HF -CS -PH		
Material		10B21	A4		10B21	A4		10B21	A4	
Characteristic yield strength	f _{yk}	N/mm ²	780	640	432	750	640	432	750	640
Characteristic tensile strength	f _{uk}	N/mm ²	870	800	540	850	800	540	850	800
Elongation at rupture	A _s	[%]	≤ 8							



Hexagon washer head
1) IC-H size 8,10,12 (10B21 steel)
2) IC-H A4 size 8,10,12 (stainless A4)



Hexagon washer head
3) IC-HF size 8,10,12 (10B21 steel)
4) IC-HF A4 size 8,10,12 (stainless A4)



Countersunk head
5) IC-CS size 8,10 (10B21 steel)
6) IC-CS A4 size 8,10 (stainless A4)



Pan head
7) IC-PH size 8,10 (10B21 steel)
8) IC-PH A4 size 8,10 (stainless A4)



Hanger Bolt head
9) IC-HB A4 size 10 with M12 internal thread (stainless A4)

ICCONS ThunderBolt® Pro - XTM



Product description
Materials and screw types

Annex A2

Table A2: Dimensions and markings

Fastener size			IC 8				IC 10				IC 12	
Head type			H, HF, PH		CS		H, HF, PH, HB		CS		H, HF	
Material			10B21	A4	10B21	A4	10B21	A4	10B21	A4	10B21	A4
Embedment depth	h_{nom}	[mm]	65	85	65	85	75	100	75	100	95	120
Length of fastener	min L	[mm]	70	90	75	95	80	105	85	110	100	125
	max L	[mm]	150				150				150	
Thread diameter	D	[mm]	9,9				12,5				14,3	
Shaft diameter	d	[mm]	7,4				9,4				11,3	
Thread pitch	p	[mm]	5,8				7,7				8,1	




Steel
10B21



Reverse Locking
Serrations

Head marking:
Identifying mark of producer: IC
Nominal size: e.g. 12 mm
Length L: e.g. 120 mm

Stainless Steel
A4



Reverse Locking
Serrations

Head marking:
Identifying mark of producer: IC
Nominal size: e.g. 12mm
Length L: 120mm
Material: A4

ICCONS ThunderBolt® Pro - XTM

Product description
Dimensions and markings

Annex A3

Specifications of Intended use

Anchorage subject to:

- Static and quasi-static loads: All sizes.
- Fire exposure: All sizes

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013,
- Strength classes C20/25 to C50/60 according to EN 206:2013,
- Uncracked or cracked concrete: all sizes.

Use conditions (Environmental conditions)

- Anchorages subject to dry internal conditions. (zinc plated steel and stainless steel)
- Anchorages subject to external atmospheric exposure (including industrial and marine environment) or exposure in permanently damp internal conditions if no particular aggressive conditions exist. (Stainless steel)

Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of seawater, chloride atmosphere or indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in desulphurization plants or road tunnels where de-icing materials are used)

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed in accordance with FprEN 1992-4:2016 and TR 055, Edition December 2016

Installation:

- Hammer drilling only: all sizes and all embedment depths.
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- In case of aborted hole: new drilling at a minimum distance away of twice the depth of the aborted hole or smaller distance if the aborted hole is filled with high strength mortar and if under shear or oblique tension load it is not the direction of the load application.
- After installation further turning of the anchor shall not be possible.
- The head of the anchor must be fully engaged on the fixture and show no signs of damage.

ICCONS ThunderBolt® Pro - XTM

**Intended Use
Specifications**

Annex B1

Table B1: Installation parameters (Steel 10B21)

Fastener size			IC 8			IC 10			IC 12
Head type			H HF	CS	PH	H HF	CS	PH	H HF
Material			Steel 10B21						
Diameter of drill bit	d ₀	[mm]	8			10			12
Embedment depth	h _{nom}	[mm]	65			75			95
Min. hole depth in concrete	h ₁ ≥	[mm]	75			85			105
Effective anchorage depth	h _{ef}	[mm]	50,6			58,1			75,4
Clearance hole in the fixture	d _f	[mm]	11			13			15
Thickness of fixture	t _{fix}	[mm]	5-85	10-85	5-85	5-75	10-75	5-75	5-55
Installation torque	T _{inst}	[Nm]	40	- ¹⁾	- ¹⁾	60	- ¹⁾	- ¹⁾	80
Wrench size (types: H, HF)	WS	[mm]	13	-	-	17	-	-	19
Torx size (types: CS, PH)	TX	-	-	45		-	50		-
Max. power output, machine setting	T _{max} ≤	[Nm]	185	120	120	350	120	120	350

1) For the installation of the C and B head types only impact screw driver can be used.

Table B2: Installation parameters (Stainless Steel A4)

Fastener size			IC8			IC 10			IC 12	
Head type			H HF	CS	PH	H HF	HB	CS	PH	H HF
Material			Stainless A4							
Diameter of drill bit	d ₀	[mm]	8			10			12	
Embedment depth	h _{nom}	[mm]	85			100			120	
Min. hole depth in concrete	h ₁ ≥	[mm]	95			110			130	
Effective anchorage depth	h _{ef}	[mm]	51,9			58,7			75,6	
Clearance hole	d _f	[mm]	11			13			15	
Thickness of fixture	t _{fix}	[mm]	5-65	10-65	5-65	5-50	5-50	10-50	5-50	5-30
Installation torque	T _{inst}	[Nm]	- ¹⁾	- ¹⁾	- ¹⁾	- ¹⁾	- ¹⁾	- ¹⁾	- ¹⁾	- ¹⁾
Wrench size (types: H, HF, HB)	WS	[mm]	13	-	-	17	19	-	-	19
Torx size (types: CS, PH)	TX	-	-	45		-	-	50		-
Max. torque moment, machine setting	T _{max} ≤	[Nm]	120	120	120	185	185	185	185	185

1) For the installation of the C and B head types only impact screw driver can be used.

ICCONS ThunderBolt® Pro - XTM

Intended Use
Installation parameters

Annex B2

Table B3: Minimum thickness of member, Minimum spacing and edge distance

Fastener size			IC 8		IC 10		IC 12	
Head type			H, HF, CS, PH		H, HF, CS, PH, HB		H, HF	
Material			10B21	A4	10B21	A4	10B21	A4
Minimum member thickness	h_{min}	[mm]	110	125	130	140	160	170
Minimum edge distance	c_{min}	[mm]	50	50	60	60	70	70
Minimum spacing	s_{min}	[mm]	50	50	60	60	70	70


ICCONS ThunderBolt® Pro - XTM

Intended Use


Minimum member thickness, minimum edge distance and anchor spacing

Annex B3


Installation instruction




Drill the hole to the bore hole depth h_1 .



Clean the hole.



Screw in the anchor by using a torque wrench or an impact screw driver.
In case of using torque wrench: T_{inst} acc. to Table B1 and B2.
In case of using impact screw driver: T_{max} acc. to Table B1 and B2
WS= Wrench Size



Control of complete setting, full contact of screw head with fixture part.

ICCONS ThunderBolt® Pro - XTM

Intended Use
Installation Instruction

Annex B4

Table C1:
Characteristic resistance under tension loading (Steel 10B21)

Fastener size			IC 8			IC 10			IC 12
Head type			H HF	CS	PH	H HF	CS	PH	H HF
Material			Steel 10B21						
Steel failure									
Characteristic resistance	$N_{Rk,s}$	[kN]	35,9			57,0			83,0
Partial factor	$\gamma_{Ms}^{2)}$	[-]	1,4			1,4			1,4
Pull-out failure									
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p}$	[kN]	4,5			10,0			12,0
Characteristic resistance in uncracked concrete C20/25	$N_{Rk,p}$	[kN]	9,0	9,0	6,5	16,0	16,0	11	25,0
Increasing factors for $N_{Rk,p}$ in cracked or uncracked concrete	ψ_c	C30/37	1,22						
		C40/50	1,41						
		C50/60	1,58						
Installation factor	γ_{inst}	[-]	1,4			1,0			1,2
Concrete cone failure									
Effective anchorage depth	h_{ef}	[mm]	50,6			58,1			75,4
Characteristic edge distance	$c_{cr,N}$	[mm]	1,5 h_{ef}						
Characteristic spacing	$s_{cr,N}$	[mm]	3 h_{ef}						
Factor for cracked concrete	k_{cr}	[-]	7,7 ¹⁾						
Factor for uncracked concrete	k_{ucr}	[-]	11,0 ¹⁾						
Splitting failure									
Characteristic edge distance for splitting	$c_{cr,sp}$	[mm]	1,5 h_{ef}						
Characteristic anchor spacing for splitting	$s_{cr,sp}$	[mm]	3 h_{ef}						

1) Based on concrete strength measured on cylinders.

2) In absence of other national regulations.

ICCONS ThunderBolt® Pro - XTM

Performance
Characteristic values under tension loading

Annex C1

**Table C2: Characteristic resistance under tension loading
(Stainless Steel A4)**

Fastener size			IC 8			IC 10				IC 12
Head type			H HF	CS	PH	H HF	HB	CS	PH	H HF
Material			Stainless steel A4							
Steel failure										
Characteristic resistance	$N_{Rk,s}$	[kN]	33,0	22,3	22,3	53,7	53,7	36,2	36,2	78,1
Partial factor	$\gamma_{Ms}^{2)}$	[-]	1,5				1,5			1,5
Pull-out failure										
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p}$	[kN]	4,5	4,5	4,0	7,0	7,0	7,0	7,0	12,0
Characteristic resistance in uncracked concrete C20/25	$N_{Rk,p}$	[kN]	9,0	5,5	4,0	16,0	16,0	10	7,0	25,0
Increasing factors for $N_{Rk,p}$ in cracked or uncracked concrete	ψ_c	C30/37	1,22							
		C40/50	1,41							
		C50/60	1,58							
Installation factor	γ_{Inst}	[-]	1,4			1,0			1,2	
Concrete cone failure										
Effective anchorage depth	h_{ef}	[mm]	51,9			58,7			75,6	
Characteristic edge distance	$c_{cr,N}$	[mm]	$1,5h_{ef}$							
Characteristic spacing	$s_{cr,N}$	[mm]	$3h_{ef}$							
Factor for cracked concrete	k_{cr}	[-]	$7,7^{1)}$							
Factor for uncracked concrete	k_{ucr}	[-]	$11,0^{1)}$							
Splitting failure										
Characteristic edge distance for splitting	$c_{cr,sp}$	[mm]	$1,5h_{ef}$							
Characteristic anchor spacing for splitting	$s_{cr,sp}$	[mm]	$3h_{ef}$							

1) Based on concrete strength measured on cylinders.

2) In absence of other national regulations.

ICCONS ThunderBolt® Pro - XTM

Performance
Characteristic values under tension loading

Annex C2

Table C3: Displacements under tension loads for non-cracked and cracked concrete

Fastener size	Material	Head type	Concrete	Tension load N	Displacement			
					δ_{N0}	$\delta_{N\infty}$		
[-]	[-]	[-]	[-]	[kN]	[mm]	[mm]		
IC 8	Steel 10B21	H/HF	cracked C20/25	1,5	0,1	0,8		
		CS						
		PH						
IC 10		H/HF		4,8	0,2	1,0		
		CS						
		PH						
IC 12		H/HF		4,8	0,3	1,2		
IC 8		Stainless steel A4		H/HF	cracked C20/25	1,5	0,1	0,8
				CS		1,5		
	PH		1,4					
IC 10	H/HF/HB		3,3	0,2		1,0		
	CS							
	PH							
IC 12	H/HF		4,8	0,3		1,2		
IC 8	Steel 10B21		H/HF	uncracked C20/25		3,1	0,1	0,8
			CS			2,2		
		PH	7,6					
IC 10		H/HF	7,6		0,1	1,0		
		CS						
		PH						
IC 12		H/HF	9,9		0,3	1,2		
IC 8		Stainless steel A4	H/HF		uncracked C20/25	3,1	0,1	0,8
			CS			1,8		
	PH		1,4					
IC 10	H/HF/HB		7,6	0,1		1,0		
	CS						4,8	
	PH						3,3	
IC 12	H/HF		9,9	0,3		1,2		

ICCONS ThunderBolt® Pro - XTM

Performance
Displacements under tension loading

Annex C3

Table C4: Characteristic resistance under shear loading

Fastener size			IC 8			IC 10			IC 12	
Head type			H HF CS PH	H HF	CS PH	H HF CS PH	H HF, HB	CS PH	H HF CS PH	H HF
Material			10B21	A4		10B21	A4		10B21	A4
Setting depth	h_{nom}	[mm]	65	85		75	100		95	120
Effective embedment depth	h_{ef}	[mm]	50,6	51,9		58,1	58,7		75,4	75,6
Steel failure without lever arm										
Characteristic resistance	$V_{Rk,s}^0$	[kN]	16,9	16,5	11,2	26,8	26,8	18,1	39,0	39,0
Ductility factor	k_7	[-]	0,8							
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,5	1,25		1,5	1,25		1,5	1,25
Steel failure with lever arm										
Characteristic resistance	$M_{Rk,s}^0$	[Nm]	39,1	35,9	24,2	79,0	74,4	50,2	138,8	130,6
Partial factor	$\gamma_{Ms}^{1)}$	[-]	1,5	1,25		1,5	1,25		1,5	1,25
Concrete pryout failure										
k-factor	k_8	[-]	1,0						2,0	
Partial factor	$\gamma_{Mcp}^{1)}$	[-]	1,5							
Concrete edge failure										
Effective length of anchor	ℓ_f	[mm]	50,6	51,9		58,1	58,7		75,4	75,6
Outside diameter of fastener	d_{nom}	[mm]	7,25			9,24			11,15	
Partial factor	$\gamma_{Mc}^{1)}$	[-]	1,5							

1) In absence of other national regulations.

ICCONS ThunderBolt® Pro - XTM

Performance
Characteristic values under shear loading

Annex C4

Table C5: Displacements under shear loads for non-cracked and cracked concrete

Fastener size	Material	Head type	Concrete	Shear load V	Displacement	
					δ_{V0}	$\delta_{V\infty}$
[-]	[-]	[-]	[-]	[kN]	[mm]	[mm]
IC 8	Steel 10B21	H/HF	Cracked and uncracked C20/25	1,5	1,8	2,7
		CS				
		PH				
IC 10		H/HF		12,8		
		CS				
IC 12		PH		18,6		
	H/HF					
IC 8	Stainless steel A4	H/HF	Cracked and uncracked C20/25	9,4	1,8	2,7
		CS				
		PH				
IC 10		H/HF/HB		15,3		
		CS				
IC 12		PH		10,3		
	H/HF	22,3				

ICCONS ThunderBolt® Pro - XTM

Performance
Displacements under shear loading

Annex C5

Table C6: Characteristic tension resistance values for resistance to fire

Fastener size				IC 8			IC 10		IC 12	
Head type				H HF CS PH	H HF CS	PH	H HF CS PH	H HF HB CS PH	PH	H HF CS PH
Material				10B21	A4		10B21	A4	10B21	A4
Steel failure										
Characteristic resistance	R30	$N_{Rk,s,fi}$	[kN]	0,41	0,8		1,0	1,7	2,0	2,9
	R60	$N_{Rk,s,fi}$	[kN]	0,37	0,7		0,9	1,3	1,5	2,4
	R90	$N_{Rk,s,fi}$	[kN]	0,29	0,5		0,7	1,0	1,3	2,0
	R120	$N_{Rk,s,fi}$	[kN]	0,21	0,4		0,5	0,9	1,0	1,6
Pull-out failure										
Characteristic resistance in concrete \geq C20/25	R30	$N_{Rk,p,fi}$	[kN]	1,1	1,1	1,0	2,5	1,8	3,0	3,0
	R60									
	R90									
	R120	$N_{Rk,p,fi}$	[kN]	0,9	0,9	0,8	2,0	1,4	2,4	2,4
Concrete cone failure										
Characteristic resistance in concrete \geq C20/25	R30	$N^0_{Rk,c,fi}$	[kN]	3,1	3,3	4,4	4,5	8,5	8,6	
	R60									
	R90									
	R120	$N^0_{Rk,c,fi}$	[kN]	2,5	2,7	3,5	3,6	6,8	6,8	
Effective embedment depth	h_{ef}	[mm]	50,6	51,9	58,1	58,7	75,4	75,6		
Minimum member thickness	h_{min}	[mm]	110	125	130	140	160	170		
Spacing	$s_{cr,N,fi}$	[mm]	$4h_{ef}$							
	s_{min}	[mm]	50		60		70			
Edge distance	$c_{cr,N,fi}$	[mm]	$2h_{ef}$							
Fire exposure from one side only	c_{min}	[mm]	50		60		70			
Fire exposure from more than one side			≥ 300 mm							

1) In absence of other national regulations.

ICCONS ThunderBolt® Pro - XTM

Performance
Characteristic values for resistance to fire (tension)

Annex C6

Table C7: Characteristic shear resistance values for resistance to fire

Fastener size				IC 8		IC 10		IC 12	
Head type				all	all	all	all	all	all
Material				10B21	A4	10B21	A4	10B21	A4
Steel failure without level arm									
Characteristic resistance	R30	$V_{Rk,s,fi}$	[kN]	0,41	0,8	1,0	1,7	2,0	2,9
	R60	$V_{Rk,s,fi}$	[kN]	0,37	0,7	0,9	1,3	1,5	2,4
	R90	$V_{Rk,s,fi}$	[kN]	0,29	0,5	0,7	1,0	1,3	2,0
	R120	$V_{Rk,s,fi}$	[kN]	0,21	0,4	0,5	0,9	1,0	1,6
Steel failure with level arm									
Characteristic resistance	R30	$M_{Rk,p,fi}^0$	[Nm]	0,45	0,9	1,4	2,3	3,4	4,9
	R60	$M_{Rk,p,fi}^0$	[Nm]	0,40	0,7	1,2	1,9	2,5	4,0
	R90	$M_{Rk,p,fi}^0$	[Nm]	0,31	0,5	0,9	1,5	2,1	3,3
	R120	$M_{Rk,p,fi}^0$	[Nm]	0,22	0,45	0,7	1,3	1,6	2,6
Pry-out failure									
k_8			[-]	1		1		2	
Characteristic resistance	R30	$V_{Rk,cp,fi}$	[kN]	3,1	3,3	4,4	4,5	17,0	17,1
	R60								
	R90								
	R120	$V_{Rk,cp,fi}$	[kN]	2,5	2,7	3,5	3,6	13,6	13,7
Concrete edge failure									
Characteristic resistance	≤ R90	$V_{Rk,c,fi}$	[kN]	$V_{Rk,c,fi}^0 = 0.25 * V_{Rk,c}^0$ ²⁾					
	R120	$V_{Rk,c,fi}$	[kN]	$V_{Rk,c,fi}^0 = 0.20 * V_{Rk,c}^0$ ²⁾					

1) In absence of other national regulations.

2) $V_{Rk,c}^0$ = characteristic resistance for concrete edge failure in cracked concrete C20/C25 under normal temperature calculated acc. to EN 1992-4.

ICCONS ThunderBolt® Pro - XTM

Performance
Characteristic values for resistance to fire (shear)

Annex C7