

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments

★ ★ ★ ★ ★
★ Designated
according to
Article 29 of Regula-
tion (EU) No 305/2011
and member of EOTA
(European Organi-
sation for Technical
Assessment)
★ ★ ★ ★ ★

European Technical Assessment

ETA-19/0118
of 25 July 2019

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Trade name of the construction product

Product family
to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment
contains

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

Deutsches Institut für Bautechnik

URSA XPS D N-III
URSA XPS D N-V
URSA XPS D N-VII

Extruded polystyrene foam boards as load bearing layer
and/or thermal insulation outside the waterproofing

URSA Deutschland GmbH
Carl-Friedrich-Benz-Straße 46-48
04509 Delitzsch
DEUTSCHLAND

Werk Queis
Uralitastraße 1
D-06188 Queis
Werk St. Avold
Zone industrielle de l'europort
F-57500 Saint-Avold

11 pages including 1 annex which form an integral part of
this assessment

EAD 040650-00-1201

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

European Technical Assessment

ETA-19/0118

English translation prepared by DIBt

Page 3 of 11 | 25 July 2019

Specific Part

1 Technical description of the product

The extruded polystyrene foam boards are made of rigid cellular plastics material extruded from polystyrene or one of its copolymers and which has a closed cell structure. The blowing agent mixture is carbon dioxide (CO₂) and additives. The extruded polystyrene foam boards have a skin on both surfaces and a special edge treatment (shiplap).

The extruded polystyrene foam boards do not contain Hexabromocyclododecane (HBCD).

The extruded polystyrene foam boards have the following designations:

"URSA XPS D N-III ",

"URSA XPS D N-V" and

"URSA XPS D N-VII".

The extruded polystyrene foam boards are manufactured with the following dimensions:

Nominal thicknesses: 50 mm to 160 mm for URSA XPS D N-III,

50 mm to 140 mm for URSA XPS D N-V,

60 mm to 120 mm for URSA XPS D N-VII

Nominal length: 1250 mm

Nominal widths: 600 mm

The European Technical Assessment has been issued for the products on the basis of agreed data/information, deposited with Deutsches Institut für Bautechnik, which identifies the product that has been assessed. The European Technical Assessment applies only to products corresponding to this agreed data/information.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The extruded polystyrene foam boards are intended to be used as load bearing layer and /or thermal insulation outside the waterproofing. The boards are laid uniformly on the substrate to which they are applied. In particular the following applications are intended:

- Load bearing and thermal insulation underneath foundation slabs for "URSA XPS D N-III " boards up to 160 mm thickness, for boards "URSA XPS D N-V" and "URSA XPS D N-VII" up to 120 mm
- External horizontal and vertical thermal insulation of in-ground constructions in non-structural applications (also in case of groundwater)
- Inverted roof insulation (including park deck and green roof applications)

The performance according to section 3 only applies if the thermal insulation boards are installed according to the manufacturer's installation instructions and if they are protected from precipitation, wetting or weathering during transport and storage before installation.

Concerning the application of the thermal insulation boards, also the respective national regulations shall be observed.

Where the thermal insulation boards are fixed by using adhesives, only such adhesions shall be used, which are suitable for this purpose. The assessment of these fixings is not subject of this European Technical Assessment.

European Technical Assessment**ETA-19/0118**

English translation prepared by DIBt

Page 4 of 11 | 25 July 2019

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the extruded polystyrene foam boards of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

For sampling, conditioning and testing the provisions of the EAD No 040650-00-1201 "Extruded polystyrene foam boards as load bearing layer and/or thermal insulation outside the waterproofing" apply.

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Compressive stress at 10 % deformation or compressive strength test acc. to EN 826:2013 "URSA XPS D N-III" "URSA XPS D N-V" "URSA XPS D N-VII" Slip deformation Compressive stress or compressive strength in the transverse and longitudinal directions	Level (individual values may fall below this level up to 10 %): $\geq 300 \text{ kPa}$ $\geq 500 \text{ kPa}$ $\geq 700 \text{ kPa}$ See Annex A No performance assessed
Characteristic value of compressive stress or compressive strength 5 %-fractile value for a one-sided confidence level of 75 % under unknown or known variance using ISO 12491:1997 "URSA XPS D N-III" thickness $50 \text{ mm} \leq d \leq 120 \text{ mm}$ thickness $120 \text{ mm} < d \leq 160 \text{ mm}$ "URSA XPS D N-V" thickness $50 \text{ mm} \leq d \leq 120 \text{ mm}$ "URSA XPS D N-VII" thickness $60 \text{ mm} \leq d \leq 120 \text{ mm}$	$\sigma_{0,05} = 311 \text{ kPa}$ ($n= 50$; $\sigma_{\text{mean}}= 351 \text{ kPa}$; $s_0=25 \text{ kPa}$) $\sigma_{0,05} = 352 \text{ kPa}$ ($n= 50$; $\sigma_{\text{mean}}= 413 \text{ kPa}$; $s_0=35 \text{ kPa}$) $\sigma_{0,05} = 508 \text{ kPa}$ ($n= 33$; $\sigma_{\text{mean}}= 562 \text{ kPa}$; $s_0= 33 \text{ kPa}$) $\sigma_{0,05} = 705 \text{ kPa}$ ($n= 50$; $\sigma_{\text{mean}}= 734 \text{ kPa}$; $s_0= 17 \text{ kPa}$)
Compressive creep	See Annex A
Behaviour under shear load (large-sized specimen)	See Annex A
Creep under shear load	See Annex A
Creep under combined compressive and shear load	See Annex A

European Technical Assessment

ETA-19/0118

English translation prepared by DIBt

Page 5 of 11 | 25 July 2019

Essential characteristic	Performance
Compressive modulus of elasticity	No performance assessed
Adhesion behaviour under compressive and shear load on large-sized samples	No performance assessed
Shear strength	No performance assessed
Density test acc. to EN 1602:2013 "URSA XPS D N-III" "URSA XPS D N-V" "URSA XPS D N-VII"	density range: 33 kg/m ³ - 40 kg/m ³ 36 kg/m ³ - 42 kg/m ³ 40 kg/m ³ - 49 kg/m ³

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire test acc. to EN ISO 11925-2:2010	Class E acc. to EN 13501-1:2007 + A1:2009

3.3 Energy economy and heat retention (BWR 6)

Essential characteristic	Performance
Thermal conductivity at mean reference temperature of 10 °C test acc. to EN 12667:2001 or EN 12939:2001 and aging procedure acc. EN 13164:2012+A1:2015, Annex C with deviating storage time period (sliced specimen) of (90 +2/-2) days prior to testing "URSA XPS D N-III" thickness 50 mm ≤ d ≤ 60 mm thickness 60 mm < d ≤ 80 mm thickness 80 mm < d ≤ 120 mm thickness 120 mm < d ≤ 160 mm "URSA XPS D N-V" thickness 50 mm ≤ d ≤ 60 mm thickness 60 mm < d ≤ 80 mm thickness 80 mm < d ≤ 120 mm thickness 120 mm < d ≤ 140 mm "URSA XPS D N-VII" thickness d = 60 mm thickness 60 mm < d ≤ 120 mm Moisture conversion coefficient	$\lambda_{D(90d)} = 0,033 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,035 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,036 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,037 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,034 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,036 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,037 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,039 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,036 \text{ W}/(\text{m} \cdot \text{K})$ $\lambda_{D(90d)} = 0,037 \text{ W}/(\text{m} \cdot \text{K})$ No performance assessed

European Technical Assessment

ETA-19/0118

English translation prepared by DIBt

Page 6 of 11 | 25 July 2019

Essential characteristic	Performance
Water absorption Long term water absorption by total immersion test acc. to EN 12087:2013 (method 2A)	WL(T)0,7 (W _{lt} ≤ 0,7 Vol.%)
Long term water absorption by diffusion test acc. to EN 12088:2013	WD(V)3 (W _{dv} ≤ 3,0 Vol.%)
Freeze-thaw resistance test acc. to EN 12091:2013 using the wet test specimens from having done the water diffusion test in accordance with EN 12088: 2013 Reduction in compressive stress at 10 % deformation or in compressive strength of the re-dried specimens, when tested in accordance with EN 826:2013	FTCD1 (W _v ≤ 1,0 Vol.%) ≤ 10 %
Water vapour diffusion resistance factor	No performance assessed
Geometrical properties Thickness test acc. EN 823:2013 (clause 7.2, figure 2, measuring set-up 3) Length, width test acc. EN 822:2013 Squareness in direction of length and width; in direction of thickness test acc. EN 824:2013 Flatness in direction of length and width test acc. EN 825:2013	tolerance ± 2 mm (thickness ≤120 mm) +4/-2 mm (thickness >120 mm) ± 10 mm 5 mm/m 2 mm (thickness ≤120 mm) 3 mm (thickness >120 mm)
Deformation under specified compressive load and temperature conditions test acc. to EN 1605:2013	load: 40 kPa; temperature: (70 ± 1) °C; time: (168 ± 1) h ≤ 5 %
Dimensional stability under specified conditions test acc. to EN 1604:2013	temperature: 70 °C and 90 % R.H. DS (70,90) (Δε _l ≤ 5 %, Δε _b ≤ 5 %, Δε _d ≤ 5 %)

European Technical Assessment

ETA-19/0118

English translation prepared by DIBt

Page 7 of 11 | 25 July 2019

Essential characteristic	Performance
Tensile strength perpendicular to faces test acc. to EN 1607:2013	TR100 ($\sigma_{mt} \geq 100$ kPa)
Volume percentage of closed cells test acc. to EN ISO 4590:2016 (method 1 with correction)	≥ 95 %

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with EAD No. 040650-00-1201, the applicable European legal acts are: 1995/467/EC and 1999/91/EC¹.

The systems to be applied are:

System 1 for Essential characteristics concerning Mechanical resistance and stability (BWR 1)

System 3 all other Essential characteristics

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 19 July 2019 by Deutsches Institut für Bautechnik

Maja Tiemann
Head of Department

beglaubigt:
Wendler

¹ as amended

URSA XPS D N-III
URSA XPS D N-V
URSA XPS D N-VII

Annex A

1. Compressive stress

Slip deformation

Deformation until the conventional elastic zone (distinct straight portion of the force-displacement curve) is reached

URSA XPS D N-III ($\varphi = 34 \text{ kg/m}^3$)			
thickness (mm)	1x100	2x100	3x100
compressive stress, σ_a	130	102	90
initial displacement X_a (mm)	0,7	0,8	0,9
URSA XPS D N-VII ($\varphi = 41 \text{ kg/m}^3$)			
thickness (mm)	1x100	2x100	3x100
compressive stress, σ_a	135	114	113
initial displacement X_a (mm)	0,47	0,92	1,05

2. Compressive creep

2.1 Compressive creep (single-layer board)

URSA XPS D N-III	thickness 50 mm			thickness 50mm
density (kg/m^3)	34			33
compressive stress/ deformation acc. EN 826 (kPa / %)	380/2			350/3
load stage (kPa)	105	125	150	143
X_0 (mm)	0,26	0,25	0,32	0,38
X_{ct} (mm)	0,10	0,15	0,13	0,33
X_{ct50} (mm)	0,36	0,34	0,80	0,75
X_{t50}(mm)	0,62	0,59	1,12	1,13
URSA XPS D N-III	thickness 120 mm			
density (kg/m^3)	39			
compressive stress/ deformation acc. EN 826 (kPa / %)	492/2			
load stage (kPa)	100	130	150	
X_0 (mm)	0,51	0,66	0,77	
X_{ct} (mm)	0,39	0,42	0,56	
X_{ct50} (mm)	1,67	1,68	1,71	
X_{t50}(mm)	2,18	2,34	2,48	

URSA XPS D N-III
URSA XPS D N-V
URSA XPS D N-VII

Annex A

URSA XPS D N-III		thickness 160 mm			
density (kg/m ³)		41	39	38,5	
compressive stress/ deformation acc. EN 826 (kPa / %)		492/-	478/3	359/2	
load stage (kPa)	100	130	150	130	143
X ₀ (mm)	0,71	0,68	0,79	0,81	0,90
X _{ct} (mm)	0,66	0,68	0,77	0,60	0,77
X _{ct50} (mm)	2,97	2,99	3,23	2,19	2,45
X_{t50}(mm)	3,68	3,67	4,00	3,00	3,35
URSA XPS D N-V		thickness 50 mm		thickness 60 mm	
density (kg/m ³)		40	37		
compressive stress/ deformation acc. EN 826 (kPa / %)		550/2	517/3		
load stage (kPa)	125	175	200	198	
X ₀ (mm)	0,24	0,34	0,39	0,37	
X _{ct} (mm)	0,60	0,80	0,74	0,34	
X _{ct50} (mm)	1,02	1,42	1,44	0,98	
X_{t50}(mm)	1,26	1,76	1,83	1,35	
URSA XPS D N-V		thickness 120 mm		thickness 100 mm	
density (kg/m ³)		40	35		
compressive stress/ deformation acc. EN 826 (kPa / %)		596/3	557/3		
load stage (kPa)	140	180	220	198	
X ₀ (mm)	0,53	0,67	0,91	0,67	
X _{ct} (mm)	0,48	0,59	0,71	0,57	
X _{ct50} (mm)	1,71	1,98	2,28	1,54	
X_{t50}(mm)	2,24	2,65	3,19	2,21	
URSA XPS D N-VII		thickness 50 mm		thickness 60 mm	
density (kg/m ³)		42	46		
compressive stress/ deformation acc. EN 826 (kPa / %)		767	719/3		
load stage (kPa)	200	245	280	275	
X ₀ (mm)	0,19	0,23	0,23	0,41	
X _{ct} (mm)	0,20	0,22	0,21	0,37	
X _{ct50} (mm)	0,52	0,59	0,67	0,87	
X_{t50}(mm)	0,71	0,82	0,90	1,28	

URSA XPS D N-III
URSA XPS D N-V
URSA XPS D N-VII

Annex A

URSA XPS D N-VII	thickness 120 mm			thickness 100 mm
density (kg/m ³)	41			42
compressive stress/ deformation acc. EN 826 (kPa / %)	832/10			744/2
load stage (kPa)	200	250	300	275
X ₀ (mm)	0,61	0,91	1,38	0,56
X _{ct} (mm)	0,48	0,72	1,08	0,64
X _{ct50} (mm)	1,35	1,80	2,75	1,87
X_{t50}(mm)	1,96	2,71	4,13	2,43

2.2 Compressive creep (multi-layer installation)

URSA XPS D N-III	thickness 3x 100 mm		
density (kg/m ³)	37	36	37
compressive stress/ deformation acc. EN 826 (kPa / %)	502/2	522/2	506/3
load stage (kPa)	90	135	170
X ₀ (mm)	1,44	1,58	2,16
X _{ct} (mm)	0,84	0,86	1,26
X _{ct50} (mm)	2,65	4,20	4,84
X_{t50}(mm)	4,09	5,78	7,00
URSA XPS D N-V	thickness 3x 100 mm		
density (kg/m ³)	39	40	40
compressive stress/ deformation acc. EN 826 (kPa / %)	661/5	660/5	674/5
load stage (kPa)	140	180	220
X ₀ (mm)	1,08	2,06	2,80
X _{ct} (mm)	1,02	1,14	1,48
X _{ct50} (mm)	3,91	4,84	6,18
X_{t50}(mm)	4,99	6,91	8,98
URSA XPS D N-VII	thickness 3x 100 mm		
density (kg/m ³)	42	42	42
compressive stress/ deformation acc. EN 826 (kPa / %)	843/10	841/10	844/10
load stage (kPa)	200	250	300
X ₀ (mm)	1,94	2,19	2,50
X _{ct} (mm)	1,10	1,42	2,11
X _{ct50} (mm)	3,57	4,60	7,58
X_{t50}(mm)	5,51	6,79	10,09

Annex A

URSA XPS D N-III
URSA XPS D N-V
URSA XPS D N-VII

3. Behaviour under shear load (large-sized specimen)

URSA XPS D N-III	thickness 160 mm	
density (kg/m ³)	40	38
shear strength τ_{large} acc. EAD chapter 2.2.4 and the guidelines in EN 12090 (kPa)	250	165

4. Creep under shear load

URSA XPS D N-III	thickness 160 mm
density (kg/m ³)	40
shear strength τ_{large} (kPa)	250
load stage (kPa)	87,5
$X_{\text{t}0}$ (mm)	1,59
X_{ct} (mm)	1,96
$X_{\text{ct}50}$ (mm)	3,48
$X_{\text{ct}50}$ (mm)	5,07

5. Creep under combined compressive and shear load

URSA XPS D N-III		
thickness	160 mm	
density (kg/m ³)	40	
shear strength τ_{large} (kPa)	250	
load stage (kPa)	87,5	118
deformation under	shear load	compressive load
$X_{\text{t}0} / X_0$ (mm)	2,01	1,36
$X_{\text{ct}} / X_{\text{ct}}$ (mm)	2,28	0,68
$X_{\text{ct}50} / X_{\text{ct}50}$ (mm)	3,39	1,44
$X_{\text{ct}50} / X_{\text{t}50}$ (mm)	5,40	2,80