



Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and Laender Governments



European Technical Assessment

ETA-08/0266 of 15 June 2020

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:

Trade name of the construction product

Product family to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment contains

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of

This version replaces

Deutsches Institut für Bautechnik

Rebar connection with fischer injection mortar FIS V

Systems for post-installed rebar connection with mortar

fischerwerke GmbH & Co. KG Otto-Hahn-Straße 15 79211 Denzlingen DEUTSCHLAND

fischerwerke

24 pages including 3 annexes which form an integral part of this assessment

EAD 330087-00-0601

ETA-08/0266 issued on 7 January 2020



European Technical Assessment ETA-08/0266

Page 2 of 24 | 15 June 2020

English translation prepared by DIBt

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.



European Technical Assessment ETA-08/0266

Page 3 of 24 | 15 June 2020

English translation prepared by DIBt

Specific Part

1 Technical description of the product

The subject of this European technical assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the injection mortar FIS V in accordance with the regulations for reinforced concrete construction.

Reinforcing bars with a diameter ϕ from 8 to 28 mm or the fischer rebar anchor FRA of sizes M12 to M24 according to Annex A and the fischer injection mortar FIS V are used for the post-installed rebar connection. The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between embedded reinforcing bar, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connections of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under static and quasi-static loading	See Annex C 1

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance				
Reaction to fire	Class A1				
Resistance to fire	See Annex C 2 and C 3				

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330087-00-0601, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1





European Technical Assessment ETA-08/0266

Page 4 of 24 | 15 June 2020

English translation prepared by DIBt

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 15 June 2020 by Deutsches Institut für Bautechnik

BD Dipl.-Ing. Andreas Kummerow Head of Department

beglaubigt:

Lange



Installation conditions and application examples reinforcing bars, part 1

Figure A1.1:

Overlap joint with existing reinforcement for rebar connections of slabs and beams




Figure A1.2:

Overlap joint with existing reinforcement at a foundation of a column or wall where the rebars are stressed





Figure A1.3:

End anchoring of slabs or beams (e.g. designed as simply supported)



Figures not to scale

Rebar connection with fischer injection mortar FIS V

Product description

Installation conditions and application examples reinforcing bars, part 1

Annex A 1

Z46359.20



Installation conditions and application examples reinforcing bars, part 2

Figure A2.1:

Rebar connection for stressed primarily in compression





Figure A2.2:

Anchoring of reinforcement to cover the enveloped line of acting tensile force in the bending member



Note to figure A1.1 to A1.3 and figure A2.1 to A2.2

In the figures no traverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1: 2004+AC:2010.

Preparing of joints according to Annex B 2


Figures not to scale

Rebar connection with fischer injection mortar FIS V

Product description
Installation conditions and application examples reinforcing bars, part 2

Annex A 2





The required transverse reinforcement acc. to EN 1992-1-1:2004+AC:2010 is not shown in the figures. **The fischer rebar anchor FRA may be only used for axial tensile force.** The tensile force must transferred by lap to the existing reinforcement of the building. The transfer of the shear force has to be ensured by suitable measure, e.g. by means of shear force or anchors with European Technical Assessment (ETA)

Figures not to scale

Rebar connection with fischer injection mortar FIS V


Product description
Installation conditions and application examples fischer rebar anchors FRA, part 3

Annex A 3

Electronic copy of the ETA by DIBt: ETA-08/0266

English translation prepared by DIBt







Properties of reinforcing bars (rebar)

Figure A5.1:



- The minimum value of related rip area f_{R,min} according to EN 1992-1-1:2004+AC:2010
- The maximum outer rebar diameter over the rips shall be:
 - The nominal diameter of the rip ϕ + 2 * h (h ≤ 0,07 * ϕ)
 - (φ: Nominal diameter of the bar; h: rip height of the bar)

Table A5.1: Installation conditions for rebars

Nominal diameter of the bar	ф	8	1)	10) ¹⁾	1:	2 ¹⁾	14	16	20	25	28	
Nominal drill hole diameter d ₀			10	12	12	14	14	16	18	20	25	30	35
Drill hole depth	h₀			$h_0 = I_v$									
Effective embedment depth	l _v	[mm]	acc. to static calculation										
Minimum thickness of concrete member	h _{min}		l _v + 30 (≥ 100)										

¹⁾ Both drill hole diameters can be used

Table A5.2: Materials of rebars

Designation	Reinforcing bar (rebar)					
FN 1992-1-1:2004+AC:2010 Annex C	Bars and de-coiled rods class B or C with f_{yk} and k according to NDP or NCL of EN 1992-1-1/NA:2013 $f_{uk} = f_{tk} = k \cdot f_{yk}$					

Figures not to scale

Rebar connection with fischer injection mortar FIS V

Product description
Properties and materials of reinforcing bars (rebar)

Annex A 5






Table A6.1: Installation conditions for fischer rebar anchors FRA

FRA C (for high corrosion-resistant steel)

Threaded diameter			M1	2	M16	M20	M24
Nominal diameter ϕ			12	12 16		20	25
Width across flat	SW	[mm]	19)	24	30	36
Nominal drill bit diameter do			14 ²⁾	16	20	25	30
Drill hole depth $(h_0 = l_{e,ges})$	l _{e,ges}	[mm]					
Effective embedment depth	l _v	[mm]	acc. to static calculation				
Distance concrete surface welded join	l _e	[mm]	100				
Diameter of clearance	Pre-positioned ≤ d _f	[mm]	14	ļ	18	22	26
hole in the fixture ¹⁾	Push through ≤ d _f	[mm]	18	}	22	26	32
Minimum thickness of concrete member	h _{min}	[mm]	h_0+30 (≥ 100) h_0+2d_0				
Maximum torque moment f attachment of the fixture	or max T _{fix}	[Nm]	50)	100	150	150

¹⁾ For bigger clearance holes in the fixture see EN 1992-4

Table A6.2: Materials of fischer rebar anchors FRA

Part	Description	Materials					
		FRA	FRA C				
1	Reinforcing bar	B500B acc. to	DIN 488-1:2009				
2	Round bar with partial or full thread	Stainless steel acc. to EN 10088-1:2014	High corrosion-resistant steel acc. to EN 10088-1:2014				
3	Washer	Stainless steel acc. to EN 10088-1:2014	High corrosion-resistant steel acc. to EN 10088-1:2014				
4	Hexagon nut	Stainless steel acc. to EN 10088-1:2014, strength class 80; acc. to EN ISO 3506:2009	High corrosion-resistant steel acc. to EN 10088-1:2014, strength class 80; acc. to EN ISO 3506:2009				

Figures not to scale

Rebar connection with fischer injection mortar FIS V

Product description
Properties and materials of fischer rebar anchors FRA

Annex A 6

²⁾ Both drill bit diameters can be used



Specifications of intended use (part 1) **Table B1.1:** Overview use and performance categories Anchorages subject to FIS V with ... Reinforcing bar fischer rebar anchor FRA Hammer drilling with standard drill all sizes bit Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Nominal drill bit diameter (do) Expert"; Bosch 12 mm to 35 mm "Speed Clean"; Hilti "TE-CD, TE-YD") uncracked Tables: Tables: concrete Static and quasi C1.1 C1.1 all sizes all sizes C1.2 C1.2 static load, in cracked C1.3 C1.3 concrete Installation temperature $T_{i,min} = 0$ °C to $T_{i,max} = +40$ °C Fire exposure all sizes Annex C2 no performance assessed Rebar connection with fischer injection mortar FIS V Annex B 1 Intended use Specifications (part 1)



Specifications of intended use

Anchorages subject to:

- Static and quasi-static loads: reinforcing bar (rebar) size 8 mm to 28 mm
- Fire exposure

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013+A1:2016
- Strength classes C12/15 to C50/60 according to EN 206:2013+A1:2016
- Maximum chloride content of 0,40 % (CL 0.40) related to the cement content according to EN 206:2013+A1:2016
- · Non-carbonated concrete

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of ϕ + 60 mm prior to the installation of the new rebar. The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1 :2004+AC:2010. The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Temperature Range:

- 40°C to +80°C (max. short term temperature +80°C and max long term temperature +50°C).

Installation temperature:

0 °C to +40 °C

Use conditions (Environmental conditions) for fischer rebar anchors FRA

- Structures subject to dry internal conditions (fischer rebar anchors FRA and FRA C)
- Structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition, if no particular aggressive conditions exist (fischer rebar anchors FRA and FRA C)
- Structures subject to external atmospheric exposure and to permanently damp internal condition, if other
 particular aggressive conditions exist (fischer rebar anchors FRA C)
 Note: Particular aggressive conditions are e.g. permanent, alternating immersion in seawater or the splash zone of
 seawater, chloride atmosphere of indoor swimming pools or atmosphere with extreme chemical pollution (e.g. in
 desulphurization plants or road tunnels where de-icing materials are used).

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2004+AC:2010 and Annex B 3 and B 4.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

Installation:

- Dry or wet concrete
- Water filled holes, only with 380 ml, 400 ml or 410 ml cartridges
- · Hole drilling by hammer drill, hollow drill or compressed air drill mode
- · Overhead installation allowed
- The installation of post-installed rebar respectively fischer rebar anchor FRA shall be done only by suitable trained installer and under Supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for Supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

Rebar connection with fischer injection mortar FIS V

Intended use
Specifications (part 2)


Annex B 2



General construction rules for post-installed rebars

Figure B3.1:

- Only tension forces in the axis of the rebar may be transmitted.
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2004+AC:2010.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



- $^{1)}$ If the clear distance between lapped bars exceeds 4 ϕ then the lap length shall be increased by the difference between the clear bar distance and 4 ϕ
 - c concrete cover of post-installed rebar
 - c₁ concrete cover at end-face of existing rebar
 - c_{min} minimum concrete cover according to table B5.1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2
 - φ nominal diameter of reinforcing bar
 - lo lap length, according to EN 1992-1-1:2004+AC:2010
 - I_v effective embedment depth, $\geq I_0 + c_1$
 - d_0 nominal drill bit diameter, see Annex B 6

Figures not to scale

Rebar connection with fischer injection mortar FIS V

Intended use
General construction rules for post-installed rebars


Annex B 3



General construction rules for post-installed rebar anchors FRA

Figure B4.1:

- · Only tension forces in the axis of the FRA may be transmitted.
- · The tension force must be transferred via an overlap joint to the reinforcement in the building part.
- The transmission of the shear load shall be ensured by appropriate additional measures, e.g. by shear lugs or by anchors with a European Technical Assessment (ETA).
- In the anchor plate, the holes for the tension anchor shall be executed as slotted holes with the axis in the direction of the shear force.



 $^{1)}$ If the clear distance between lapped bars exceeds 4 ϕ then the lap length shall be increased by the difference between the clear bar distance and 4 ϕ .

c concrete cover of post-installed rebar anchor FRA

c₁ concrete cover at end-face of existing rebar

c_{min} minimum concrete cover according to table B5.1 and to EN 1992-1-1:2004+AC:2010,

Section 4.4.1.2

φ nominal diameter of reinforcing bar

lo lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3

 $l_{e,ges}$ overall embedment depth, $\geq l_0 + l_e$ d_0 nominal drill bit diameter, see Annex B 6 l_e length of the bonded in threaded part

 t_{fix} thickness of the fixture l_v effective embedment depth

Figures not to scale

Rebar connection with fischer injection mortar FIS V	
Intended use General construction rules for post-installed rebar anchors FRA	Annex B 4

Electronic copy of the ETA by DIBt: ETA-08/0266



Table B5.1:	Minimum concrete cover c _{min} 1) depending of the drilling method and the drilling tolerance							
Drilling method	nominal diameter of reinforcing bar φ [mm]	Without drilling aid [mm] Without drilling aid [mm]						
Hammer drilling with standard drill	< 25	30 mm + 0,06 l _v ≥ 2 ф	30 mm + 0,02 l _v ≥ 2 φ	······				
bit	≥ 25	40 mm + 0,06 l _ν ≥ 2 φ	40 mm + 0,02 l _v ≥ 2 φ					
Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE- YD")	< 25	30 mm + 0,06 l _ν ≥ 2 φ	30 mm + 0,02 l _ν ≥ 2 φ	Drilling aid				
	≥ 25	40 mm + 0,06 l _ν ≥ 2 φ	40 mm + 0,02 l _ν ≥ 2 φ					
Compressed air	< 25	50 mm + 0,08 l _v	50 mm + 0,02 l _v					
drilling	≥ 25	60 mm + 0,08 l _v ≥ 2 ф	60 mm + 0,02 l _v ≥ 2 ф					

¹⁾ See Annex B3, figure B3.1 and Annex B4, figure B4.1 Note: The minimum concrete cover as specified in EN 1992-1-1:2004+AC:2010 must be observed.

Dispensers and cartride sizes corresponding to maximum embedment depth **Table B5.2:** $I_{v,max}$

reinforcing bars (rebar)	rebar anchor	Manual dispenser	Accu and pneumatic dispenser (small)	Pneumatic dispenser (large)
	FRA			
		< 50	00 ml	> 500 ml
φ [mm]	thread [M]	l _{v,max} / l _{e,g}	l _{v,max} / l _{e,ges,max} [mm]	
8			1000	
10			1000	
12	FRA 12	1000	1200	1800
14			1200	1800
16	FRA 16		1500	1
20	FRA 20	700	1300	
25	FRA 24	700	1000	2000
28		500	700	2000

Rebar connection with fischer injection mortar FIS V	
Intended use	Annex B 5
Minimum concrete cover;	
dispenser and cartridge sizes corresponding to maximum embedment depth	



Table B6.1: Working times twork and curing times tcure							
Temperature in the anchorage base		orking time ¹⁾	Minimum curing time ²⁾ t _{cure}				
[°C]	FIS V	FIS VS Low Speed	FIS V	FIS VS Low Speed			
>±0 to +5	13 min ³⁾		3 h	6 h			
>+5 to +10	9 min ³⁾	20 min	90 min	3 h			
>+10 to +20	5 min	10 min	60 min	2 h			
>+20 to +30	4 min	6 min	45 min	60 min			
>+30 to +40	2 min ⁴⁾	4 min	35 min	30 min			

¹⁾ Maximum time from the beginning of the injection to rebar / FRA setting and positioning

Table B6.2: Installation tools for drilling and cleaning the bore hole and injection of the mortar

reinforcing	rebar		Drilling and		lnj	ection	
bars (rebar)	anchor FRA	Nominal drill bit diameter	Diameter of cutting edge	Steel brush diameter	Diameter of cleaning nozzle	Diameter of extension tube	Injection adapter
φ [mm]	thread [M]	d₀ [mm]	d _{cut} [mm]	d₀ [mm]	[mm]	[mm]	[colour]
81)		10	≤ 10,50	11,0			
0.7		12	≤ 12,50	12,5			nature
101)		12	≤ 12,50	12,5	11	9	Hature
10"		14	≤ 14,50	15] 9	blue
121)	FRA 12 ¹⁾	14	≤ 14,50	15			blue
12"	FDA 12"	16	≤ 16,50	17	15		red
14		18	≤ 18,50	19			yellow
16	FRA 16	20	≤ 20,55	21,5	19		green
20	FRA 20	25	≤ 25,55	26,5	19	9 or 15	black
25	FRA 24	30	≤ 30,55	32	28		grey
28		35	≤ 35,70	37	20		brown

¹⁾ Both drill bit diameters can be used

Rebar connection with fischer injection mortar FIS V

Intended use
Working times and curing times;
Installation tools for drilling and cleaning the bore hole and injection of the mortar

²⁾ For wet concrete the curing time must be doubled

³⁾ If the temperature in the concrete falls below 10 °C the cartridge has to be warmed up to +15 °C.

⁴⁾ If the temperature in the concrete exceeds 30 °C the cartridge has to be cooled down to +15 °C up to 20 °C



Safety regulations



Review the Safety Data Sheet (SDS) before use for proper and safe handling! Wear well-fitting protective goggles and protective gloves when working with mortar FIS V / FIS VS Low Speed.

Important: Observe the instructions for use provided with each cartridge.

Installation instruction part 1; Installation with FIS V / FIS VS Low Speed

Hole drilling

Note: Before drilling, remove carbonized concrete; clean contact areas (see Annex B 2) In case of aborted drill holes the drill hole shall be filled with mortar.

Hammer drilling or compressed air drilling Drill th


1a

Drill the hole to the required embedment depth using a hammer drill with carbide drill bit set in rotation hammer mode or a pneumatic drill.


Drill bit sizes see table B6.2.

Hammer drilling with hollow drill bit

1b



Drill the hole to the required embedment depth using a hammer drill with hollow drill bit in rotation hammer mode. Dust extraction conditions see drill hole cleaning annex B8. Drill bit sizes see table B6.2.




Measure and control concrete cover c

 $(C_{drill} = C + \emptyset / 2)$

Drill parallel to surface edge and to existing rebar. Where applicable use fischer drilling aid.

2



For holes $I_V > 20$ cm use drilling aid. Three different options can be considered:

- A) fischer drilling aid
- B) Slat or spirit level
- C) Visual check

Minimum concrete cover cmin see table B5.1

Rebar connection with fischer injection mortar FIS V

Intended use

Safety regulations; Installation instruction part 1, hole drilling

Annex B 7

Z46359.20



Installation instruction part 2; Installation with FIS V / FIS VS Low Speed Drill hole cleaning OHIMINI. Hammer or compressed air drilling Blowing three times from the back of the hole with the appropriate nozzle (oil-free compressed air ≥ 6 bar) until return air stream is free of noticeable dust. Personal protective equipment must be used (see regulations Annex B7). Brushing (with power drill) three times with the suitable brush size (brush diameter > drill hole diameter). Switch on the power drill after inserting the 3a steel brush into the drill hole. The brush must produce a noticeable resistance when it is inserted into the drill hole. If this is not the case, use a new or larger brush. If necessary, check with brush inspection template. Suitable brushes see table B6.2. **Blowing** three times from the back of the hole with the appropriate nozzle (oil-free compressed air ≥ 6 bar) until return air stream is free of noticeable dust. Personal protective equipment must be used. (see regulations Annex B7). Hammer drilling with hollow drill bit Use a suitable dust extraction system, e.g. fischer FVC 35 M or a comparable dust extraction system with 3b equivalent performance data. Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. No further drill hole cleaning necessary

Rebar connection with fischer injection mortar FIS V
--

Intended use

Installation instruction part 2, drill hole cleaning

Annex B 8


6

7




Installation instruction part 3; Installation with FIS V / FIS VS Low Speed

reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation




Before use, make asure that the rebar or the rebar anchor FRA is dry and free of oil or other residue. Mark the embedment depth l_v (e.g. with tape) Insert rebar in borehole, to verify drill hole depth and setting depth l_v resp. l_{e,ges}



Twist off the sealing cap

Twist on the static mixer (the spiral in the static mixer must be clearly visible).



Place the cartridge into a suitable dispenser.



Press out approximately 10 cm of mortar until the resin is permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed.

Rebar connection with fischer injection mortar FIS V

Intended use

Installation instruction part 3,

reinforcing bars (rebar) / fischer rebar anchor FRA and cartridge preparation


Annex B 9

8.06.01-116/20

Z46359.20

Installation instruction part 4; Installation with FIS V / FIS VS Low Speed

Injection of the mortar; borehole depth ≤ 250 mm



Inject the mortar from the back of the hole towards the front and slowly withdraw the mixing nozzle step by step with each trigger pull. Avoid bubbles.


Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the entire embedment length.

8a




After injecting, release the dispenser. This will prevent further mortar discharge from the mixing nozzle.

Injection of the mortar; borehole depth > 250 mm



Assemble mixing nozzle FIS MR Plus or FIS UMR, extension tube and appropriate injection adapter (see table B6.2)

Mortar level mark



Mark the required mortar level l_m and embedment depth l_v resp. $l_{e,ges}$ with tape or marker on the injection extension tube.


a) Estimation:

$$l_m = \frac{1}{3} * l_v resp. l_m = \frac{1}{3} * l_{e,ges}$$

b) Precise equation for optimum mortar volume:

$$l_m = l_v \, resp. \, l_{e,ges} \, \left((1,2 * \frac{d_s^2}{d_0^2} - 0,2) \right)$$
 [mm]

8b



Insert injection adapter to back of the hole. Begin injection allowing the pressure of the injected adhesive mortar to push the injection adapter towards the front of the hole. Do not actively pull out!

Fill holes approximately 2/3 full, to ensure that the annular gap between the rebar and the concrete will be completely filled with adhesive over the embedment length.

When using an injection adapter continue injection until the mortar level mark l_m becomes visible.

Maximum embedment depth see table B5.2



After injecting, release the dispenser. This will prevent further mortar discharge from the mixing nozzle.

Rebar connection with fischer injection mortar FIS V

Intended use

Installation instruction part 4, mortar injection


Annex B 10



Installation instruction part 5; Installation with FIS V / FIS VS Low Speed


Insert rebar / rebar anchor FRA

9




Insert the rebar / rebar anchor FRA slowly twisted into the borehole until the embedment mark is reached.

10



For overhead installation, support the rebar / rebar anchor FRA and secure it from falling till mortar started to harden, e.g. using wedges.

11



After installing the rebar or FRA the annular gap must be completely filled with mortar.

Proper installation

- Desired embedment depth is reached l_v: embedment mark at concrete surface
- Excess mortar flows out of the borehole after the rebar has been fully inserted up to the embedment mark.

12




Observe the working time " t_{work} " (see table B 6.1), which varies according to temperature of base material. Minor adjustments to the rebar / rebar anchor FRA position may be performed during the working time

Full load may be applied only after the curing time " t_{cure} " has elapsed (see table B 6.1)

13

Electronic copy of the ETA by DIBt: ETA-08/0266



Mounting the fixture, max T_{fix} see table A 6.1

Rebar connection with fischer injection mortar FIS V

Intended use

Installation instruction part 5, insert rebar / rebar anchor FRA

Annex B 11

Z46359.20

8.06.01-116/20



Minimum anchorage length and minimum lap length

The minimum anchorage length $l_{b,min}$ and the minimum lap length $l_{o,min}$ according to EN 1992-1-1 shall be multiply by the relevant amplification factor α_{lb} according to table C1.1.

Table C1.1: Amplification factor α_{lb} related to concrete strength class and drilling method

Concrete strength class	Drilling method	Amplification factor α_{lb}
	Hammer drilling with standard drill bit	1,0
C12/15 to C50/60	Hammer drilling with hollow drill bit (fischer "FHD", Heller "Duster Expert"; Bosch "Speed Clean"; Hilti "TE-CD, TE-YD")	1,0
	Compressed air drilling	1,0

Table C1.2: Bond efficiency factor k_b for hammer drilling, hollow drilling and compressed air drilling

ı	Hammer	drilling.	hollow	drilling	and	com	pressed	air	drilling	
ı	I I I I I I I I I I I I I I I I I I I	ai iiiiiig,	11011011	ar ming	alla	00111	P1 C 3 3 C 4	u	aiiiiiig	

Rebar / rebar	Bond efficiency factor k _b									
anchor FRA	Concrete strength class									
φ [mm]	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60	
8 to 28					1,00					

Table C1.3: Design values of the bond strength f_{bd,PIR} in N/mm² for hammer drilling, hollow drilling, compressed air drilling and for good bond conditions

 $f_{bd,PIR} = k_b \cdot f_{bd}$

fbd: Design value of the bond strength in N/mm² considering the concrete strength classes and the rebar diameter according to EN 1992-1-1: 2004+AC:2010 (for all other bond conditions multiply the values by 0,7)

k_b: Bond efficiency factor according to table C1.2

11	In a III acces	-L-2112			- 1111	11:
Hammer drilling	nollow	ariiiina	ลทต	COMPLESSED	air arii	แทก

	ming, none warming and compressed an arming								
bond strength f _{bd,PIR} [N/mm²]									
Rebar / rebar				Concr	ete strength	n class			
anchor FRA	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
φ [mm]									
8 to 28	1,6	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3

Rebar connection with fischer injection mortar FIS V	
Performance	Annex C 1
Amplification factor α_{lb} , bond efficiency factor k_b , design values of the bond strength $f_{bd,PlR}$	



Table C2.1: Essential characteristics of **tensile resistance** for **fischer rebar anchors FRA** under fire exposure

concrete strength classes C12/C15 to C50/60, according to EN 1992-4

fischer rebar anch	or FRA			M12	M16	M20	M24	
Stainless steel (FR	A or FRA	C)						
	R30			30				
Characteristic	R60	_	[N]/ma ma 21		2	25		
tensile resistance	R90	σ _{Rk,s,fi}	[N/mm²]		2	20		
	R120				1	6		

Design value of the steel bearing capacity $\sigma_{\text{Rd},s,\text{fi}}$ under fire exposure for fischer rebar anchor FRA

The design value of the steel bearing capacity $\sigma_{Rd,s,fi}$ under fire exposure has to be calculated by the following equation:

 $\sigma_{Rd,s,fi} = \sigma_{Rk,s,fi} / \gamma_{M,fi}$

with:

σ_{Rk,s,fi} Characteristic tensile resistance according to table C2.1 γ_{M,fi} Partial factor according to EN 1992-1-2:2004+AC:2008

Rebar connection with fischer injection mortar FIS V	
Performance	Annex C 2
Design value of the steel bearing capacity $\sigma_{\text{Rd,s,fi}}$ under fire exposure for fischer rebar	
anchor FRA	



Design values of the bond strength $f_{bk,fi}$ under fire exposure for concrete strength classes C12/15 to C50/60 (all drilling methods)

The design value of the bond strength f_{bk,fi} under fire exposure has to be calculated by the following equation:

$$f_{bk,fi} = k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \frac{\gamma_c}{\gamma_{M,fi}}$$

If:
$$\theta > 74$$
 °C
$$k_{fi}(\theta) = \frac{24,308 \cdot e^{-0,012 \cdot \theta}}{f_{bd,PIR} \cdot 4.3} \leq 1.0$$

If:
$$\theta > \theta_{max}$$
 (317 °C) k_{fi} (θ) = 0

 $f_{bk,fi}$ = Design value of the bond strength in case of fire (in N/mm²)

(θ) = Temperature in °C in the mortar layer $k_{fi}(θ)$ = Reduction factor under fire exposure

f_{bd,PIR} = Design value of the bond strength in N/mm² in cold condition according to table C1.3


considering the concrete classes, the rebar diameter, the drilling method and the bond conditions according to EN 1992-1-1:2004+AC:2010

 $\gamma_{\rm C}$ = Partial factor according to EN 1992-1-1:2004+AC:2010 Partial factor according to EN 1992-1-2:2004+AC:2008

 $\gamma_{M,fi}$ = Partial factor according to EN 1992-1-2:2004+AC:2008

For evidence under fire exposure the anchorage length shall be calculated according to EN 1992-1-1:2004+AC:2010 Equation 8.3 using the temperature-dependent ultimate bond strength f_{bk,fi}.

Figure C3.1: Example graph of reduction factor k_{fi} (θ) for concrete class C20/25 for good bond conditions



Rebar connection with fischer injection mortar FIS V

Performance

Design values of bond strength fbk,fi under fire exposure

Annex C 3