

Approval body for construction products  
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and  
Laender Governments



## European Technical Assessment

**ETA-17/0471**  
**of 20 October 2022**

English translation prepared by DIBt - Original version in German language

### General Part

Technical Assessment Body issuing the  
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

BOSSONG concrete screw CLS-CE, CLS-CE X4 and  
CLS-CE HCR

Product family  
to which the construction product belongs

Mechanical fasteners for use in concrete

Manufacturer

BOSSONG S.p.A.  
via Enrico Fermi 49/51  
24050 GRASSOBBIO (BG)  
ITALIEN

Manufacturing plant

Bossong S.p.A. Manufacturing plant 1

This European Technical Assessment  
contains

22 pages including 3 annexes which form an integral part  
of this assessment

This European Technical Assessment is  
issued in accordance with Regulation (EU)  
No 305/2011, on the basis of

EAD 330232-01-0601, Edition 05/2021

This version replaces

ETA-17/0471 issued on 19 June 2017

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

## Specific Part

### 1 Technical description of the product

The BOSSONG concrete screw CLS-CE is an anchor in size 6, 8, 10, 12 and 14 mm made of galvanised steel respectively steel with zinc flake coating, made of stainless or high corrosion resistant steel. The anchor is screwed into a predrilled cylindrical drill hole. The special thread of the anchor cuts an internal thread into the member while setting. The anchorage is characterised by mechanical interlock in the special thread.

Product and product description are given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex B4, C1 and C2
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C1 and C2
Displacements (static and quasi-static loading)	See Annex C7
Characteristic resistance and displacements for seismic performance category C1 and C2	See Annex C3 to C5, C8

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C6

#### 3.3 Aspects of durability linked with the Basic Works Requirements

Essential characteristic	Performance
Durability	See Annex B1

**4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base**

In accordance with European Assessment Document EAD No. 330232-01-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

**5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document**

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 20 October 2022 by Deutsches Institut für Bautechnik


Dipl.-Ing. Beatrix Wittstock  
Head of Section

*beglaubigt:*  
Tempel


## Product in installed condition

### BOSSONG concrete screw CLS-CE


- Galvanized carbon steel
- Zinc flakes coated carbon steel



- Stainless steel A4
- Stainless steel HCR



e.g. Bossong concrete screw, zinc flakes coated, with hexagon head and fixture





$d_0$  = nominal drill hole diameter  
 $t_{fix}$  = thickness of fixture  
 $d_f$  = clearance hole diameter

$h_{min}$  = minimum thickness of member  
 $h_{nom}$  = nominal embedment depth  
 $h_0$  = drill hole depth  
 $h_{ef}$  = effective embedment depth

Top








Filling washer (optional)  
to fill annular gap



**BOSSONG concrete screw CLS-CE**

**Product description**  
Product in installed condition

**Annex A1**

		Configuration with metric connection thread and hexagon socket e.g. CLS-CE 8x105 M10 SW5;
		Configuration with metric connection thread and hexagon drive e.g. CLS-CE 8x105 M10 SW7;
		Configuration with washer and hexagon head e.g. CLS-H CE 8x80 SW13
		Configuration with washer, hexagon head and TORX drive e.g. CLS-H CE 8x80 SW13;
		Configuration with washer and bund e.g. CLS-CE BC ST 14x130 SW24
		Configuration with hexagon head e.g. CLS-H CE 8x80 SW13 OS;
		Configuration with countersunk head and TORX drive e.g. CLS-S CE 8x80 C
		Configuration with pan head and TORX drive e.g. CLS-B CE 8x80
		Configuration with large pan head and TORX drive e.g. CLS-B CE 8x80
		Configuration with countersunk head and connection thread e.g. CLS-CE 6x55
		Configuration with hexagon drive and connection thread e.g. CLS-CE 6x55 M8 SW10;
		Configuration with internal thread and hexagon drive e.g. CLS-CE 6x55 IM M8/10

**BOSSONG concrete screw CLS-CE**

**Product description**  
Screw types

**Annex A2**

Table 1: Material

Part	Product name	Material		
all types	CLS-CE	- Steel EN 10263-4:2017 galvanized acc. to EN ISO 4042:2018 - Zinc flake coating according to EN ISO 10683:2018 ( $\geq 5\mu\text{m}$ ) - Zinc flake coating according to EN ISO 10683:2018 special coating TOGE KORR ( $\geq 20\mu\text{m}$ )		
	CLS-CE X4	1.4401; 1.4404; 1.4571; 1.4578		
	CLS-CE HCR	1.4529		
Part	Product name	Nominal characteristic steel		Rupture elongation
		Yield strength	Ultimate strength	$A_5$ [%]
		$f_{yk}$ [N/mm <sup>2</sup> ]	$f_{uk}$ [N/mm <sup>2</sup> ]	
all types	CLS-CE	560	700	$\leq 8$
	CLS-CE X4			
	CLS-CE HCR			


Table 2: Dimensions

Anchor size			6		8			10			12			14		
Nominal embedment depth	$h_{nom}$	[mm]	1	2	1	2	3	1	2	3	1	2	3	1	2	3
			40	55	45	55	65	55	75	85	65	85	100	75	100	115
Screw length	$\leq L$	[mm]	500													
Core diameter	$d_k$	[mm]	5,1		7,1			9,1			11,1			13,1		
Thread outer diameter	$d_s$	[mm]	7,5		10,6			12,6			14,6			16,6		
Thickness of filling washer	$t_v$	[mm]	-		5			5			5			5		

**Marking:**

**CLS-CE**

Screw type: TSM  
Screw size: 10  
Screw length: 100




**CLS-CE**

Screw type: TSM  
Screw size: 10  
Screw length: 100





**CLS-CE X4**

Screw type: TSM  
Screw size: 10  
Screw length: 100  
Material: A4



**CLS-CE HCR**

Screw type: TSM  
Screw size: 10  
Screw length: 100  
Material: HCR



**BOSSONG concrete screw CLS-CE**

**Product description**  
Material, Dimensions and markings

**Annex A3**

## Specification of Intended use

Table 3: Anchorages subject to

CLS-CE concrete screw size		6		8			10			12			14		
Nominal embedment depth		$h_{nom1}$	$h_{nom2}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$									
	[mm]	40	55	45	55	65	55	75	85	65	85	100	75	100	115
Static and quasi-static loads		All sizes and all embedment depths													
Fire exposure															
C1 category - seismic		ok	ok				ok						ok		
C2 category – seismic (A4 and HCR: no performance assessed)		1)		1)	ok	1)	1)	ok	1)	ok	1)	ok	1)	ok	

<sup>1)</sup> no performance assessed

### Base materials:

- Compacted reinforced and unreinforced concrete without fibers according to EN 206:2013.
- Strength classes C20/25 to C50/60 according to EN 206:2013.
- Cracked and uncracked concrete.

### Use conditions (Environmental conditions):

- Concrete screws subject to dry internal conditions: all screw types.
- For all other conditions corresponding to corrosion resistance classes CRC according to EN 1993-1-4:2006 + A1:2015
  - Stainless steel according to Annex A3, screw with marking A4: CRC III
  - High corrosion resistant steel according to Annex A3, screw with marking HCR: CRC V

**BOSSONG concrete screw CLS-CE**

**Intended use  
Specification**

**Annex B1**

## Specification of Intended use - continuation

### Design:

- Anchorages are to be designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed according to EN 1992-4:2018 and EOTA Technical Report TR 055. The design for shear load according to EN 1992-4:2018, Section 6.2.2 applies for all specified diameters  $d_f$  of clearance hole in the fixture in Annex B3, Table 4.

### Installation:

- Hammer drilling or hollow drilling.
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters on site.
- In case of aborted hole: new drilling must be drilled at a minimum distance of twice the depth of aborted hole or closer, if the aborted hole is filled with high strength mortar and only if the hole is not in the direction of the oblique tensile or shear load.
- After installation further turning of the anchor must not be possible. The head of the anchor is supported in the fixture and is not damaged.
- The borehole may be filled with injection mortar.
- Adjustability according to Annex B6 for sizes 6-14, all embedment depths except for seismic application.
- Cleaning of borehole is not necessary, if using a hollow drill.

**BOSSONG concrete screw CLS-CE**


**Intended use**  
Specification continuation

**Annex B2**

Table 4: Installation parameters

CLS-CE concrete screw size		6		8			10		
Nominal embedment depth	$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$
	[mm]	40	55	45	55	65	55	75	85
Nominal drill hole diameter	$d_0$	6		8			10		
Cutting diameter of drill bit	$d_{cut} \leq$	6,40		8,45			10,45		
Drill hole depth	$h_0 \geq$	45	60	55	65	75	65	85	95
Clearance hole diameter	$d_f \leq$	8		12			14		
Installation torque (version with connection thread)	$T_{inst}$	10		20			40		
Torque impact screw driver	[Nm]	Max. torque according to manufacturer's instructions							
		160		300			400		

CLS-CE concrete screw size		12			14		
Nominal embedment depth	$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$
	[mm]	65	85	100	75	100	115
Nominal drill hole diameter	$d_0$	12			14		
Cutting diameter of drill bit	$d_{cut} \leq$	12,50			14,50		
Drill hole depth	$h_0 \geq$	75	95	110	85	110	125
Clearance hole diameter	$d_f \leq$	16			18		
Installation torque (version with connection thread)	$T_{inst}$	60			80		
Torque impact screw driver	[Nm]	Max. torque according to manufacturer's instructions					
		650			650		



BOSSONG concrete screw CLS-CE

Intended use  
Installation parameters


Annex B3

Table 5: Minimum thickness of member, minimum edge distance and minimum spacing

CLS-CE concrete screw size		6			8			10		
Nominal embedment depth	$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	
	[mm]	40	55	45	55	65	55	75	85	
Minimum thickness of member	$h_{min}$	[mm]	100	100	100	120	100	130		
Minimum edge distance	$c_{min}$	[mm]	40	40	50	50	50	50		
Minimum spacing	$s_{min}$	[mm]	40	40	50	50	50	50		

CLS-CE concrete screw size		12			14			
Nominal embedment depth	$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	
	[mm]	65	85	100	75	100	115	
Minimum thickness of member	$h_{min}$	[mm]	120	130	150	130	150	170
Minimum edge distance	$c_{min}$	[mm]	50	70	50	70	70	
Minimum spacing	$s_{min}$	[mm]	50	70	50	70	70	







**BOSSONG concrete screw CLS-CE**

**Intended use**

Minimum thickness of member, minimum edge distance and minimum spacing

**Annex B4**

## Installation Instructions



**Note:**

Cleaning of borehole is not necessary when using a hollow drill


**BOSSONG concrete screw CLS-CE**

**Intended use**  
Installation instructions


**Annex B5**

## Installation Instructions – Adjustment


### 1. Adjustment



Screw may be untightened maximum 10mm




After adjustment, tighten the screw again




The head must be undamaged and in contact with the fixture


### 2. Adjustment



Screw may be untightened maximum 10mm



After adjustment, tighten the screw again



The head must be undamaged and in contact with the fixture

#### Note:

The fastener can be adjusted maximum two times. The total allowed thickness of shims added during the adjustment process is 10mm. The final embedment depth after adjustment process must be larger or equal than  $h_{nom}$ .





**BOSSONG concrete screw CLS-CE**

**Intended use**  
Installation instructions - Adjustment


**Annex B6**

## Installation Instructions – Filling annular gap

### Positioning of fixture and filling washer



### Filling the annular gap



Note:

For seismic loading the installation with filled and without filled annular gap is approved. Differences in performance can be found in Annex C5 - C7.

**BOSSONG concrete screw CLS-CE**

**Intended use**  
Installation instructions - Filling annular gap

**Annex B7**

Table 6: Characteristic values for static and quasi-static loading, sizes 6-10

CLS-CE concrete screw size			6			8			10		
Nominal embedment depth	$h_{nom}$		$h_{nom1}$	$h_{nom2}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	
	[mm]		40	55	45	55	65	55	75	85	
<b>Steel failure for tension and shear loading</b>											
Characteristic tension load	$N_{Rk,s}$	[kN]	14,0			27,0			45,0		
Partial factor	$\gamma_{Ms,N}$	[-]	1,5								
Characteristic shear load	$V_{Rk,s}^0$	[kN]	7,0		13,5		17,0	22,5	34,0		
Partial factor	$\gamma_{Ms,V}$	[-]	1,25								
Ductility factor	$k_7$	[-]	0,8								
Characteristic bending load	$M_{Rk,s}^0$	[Nm]	10,9			26,0			56,0		
<b>Pull-out failure</b>											
Characteristic tension load C20/25	cracked	$N_{Rk,p}$	[kN]	2,0	4,0	5,0	9,0	12,0	9,0	$\geq N_{Rk,c}^0$ <sup>1)</sup>	
	uncracked	$N_{Rk,p}$	[kN]	4,0	9,0	7,5	12,0	16,0	12,0	20,0	26,0
Increasing factor for $N_{Rk,p} = N_{Rk,p}(C20/25) * \psi_c$	C25/30	$\psi_c$	[-]	1,12							
	C30/37			1,22							
	C40/50			1,41							
	C50/60			1,58							
<b>Concrete failure: Splitting failure, concrete cone failure and pry-out failure</b>											
Effective embedment depth	$h_{ef}$	[mm]	31	44	35	43	52	43	60	68	
k-factor	cracked	$k_{cr}$	7,7								
	uncracked	$k_{ucr}$	11,0								
Concrete cone failure	spacing	$s_{cr,N}$	$3 \times h_{ef}$								
	edge distance	$c_{cr,N}$	$1,5 \times h_{ef}$								
Splitting failure	resistance	$N_{Rk,sp}^0$	[kN]	4,0	9,0	7,5	12,0	16,0	12,0	20,0	26,0
	spacing	$s_{cr,sp}$	[mm]	120	160	120	140	150	140	180	210
	edge distance	$c_{cr,sp}$	[mm]	60	80	60	70	75	70	90	105
Factor for pry-out failure	$k_8$	[-]	1,0						2,0		
Installation factor	$\gamma_{inst}$	[-]	1,0								
<b>Concrete edge failure</b>											
Effective length in concrete	$l_f = h_{ef}$	[mm]	31	44	35	43	52	43	60	68	
Nominal outer diameter of screw	$d_{nom}$	[mm]	6			8			10		
<sup>1)</sup> $N_{Rk,c}^0$ according to EN 1992-4:2018											
<b>BOSSONG concrete screw CLS-CE</b>									<b>Annex C1</b>		
<b>Performances</b> Characteristic values for static and quasi-static loading for sizes 6-8-10											

Table 7: Characteristic values for static and quasi-static loading, sizes 12-14

CLS-CE concrete screw size			12			14			
Nominal embedment depth	$h_{nom}$		$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	
	[mm]		65	85	100	75	100	115	
<b>Steel failure for tension and shear loading</b>									
Characteristic tension load	$N_{Rk,s}$	[kN]	67,0			94,0			
Partial factor	$\gamma_{Ms,N}$	[-]	1,5						
Characteristic shear load	$V_{Rk,s}^0$	[kN]	33,5	42,0		56,0			
Partial factor	$\gamma_{Ms,V}$	[-]	1,25						
Ductility factor	$k_7$	[-]	0,8						
Characteristic bending load	$M_{Rk,s}^0$	[Nm]	113,0			185,0			
<b>Pull-out failure</b>									
Characteristic tension load C20/25	cracked	$N_{Rk,p}$	[kN]	12,0	$\geq N_{Rk,c}^{0,1}$				
	uncracked	$N_{Rk,p}$	[kN]	16,0					
Increasing factor for $N_{Rk,p} = N_{Rk,p(C20/25)} * \psi_c$	C25/30	$\psi_c$	[-]	1,12					
	C30/37			1,22					
	C40/50			1,41					
	C50/60			1,58					
<b>Concrete failure: Splitting failure, concrete cone failure and pry-out failure</b>									
Effective embedment depth	$h_{ef}$	[mm]	50	67	80	58	79	92	
k-factor	cracked	$k_1 = k_{cr}$	[-]	7,7					
	uncracked	$k_1 = k_{ucr}$	[-]	11,0					
Concrete cone failure	spacing	$s_{cr,N}$	[mm]	$3 \times h_{ef}$					
	edge distance	$c_{cr,N}$	[mm]	$1,5 \times h_{ef}$					
Splitting failure	resistance	$N_{Rk,sp}^0$	[kN]	16,0	27,0	35,0	21,5	34,5	43,5
	spacing	$s_{cr,sp}$	[mm]	150	210	240	180	240	280
	edge distance	$c_{cr,sp}$	[mm]	75	105	120	90	120	140
Factor for pry-out failure	$k_8$	[-]	1,0	2,0		1,0	2,0		
Installation factor	$\gamma_{inst}$	[-]	1,0						
<b>Concrete edge failure</b>									
Effective length in concrete	$l_f = h_{ef}$	[mm]	50	67	80	58	79	92	
Nominal outer diameter of screw	$d_{nom}$	[mm]	12			14			
1) $N_{Rk,c}^0$ according to EN 1992-4:2018									
<b>BOSSONG concrete screw CLS-CE</b>							<b>Annex C2</b>		
<b>Performances</b> Characteristic values for static and quasi-static loading, sizes 12-14									

Table 8: Seismic category C1 – Characteristic load values (type H, type S, type B and type I<sup>1)</sup>)

CLS-CE concrete screw size		6	8	10	12	14			
Nominal embedment depth	$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom3}$	$h_{nom3}$	$h_{nom3}$	
	[mm]	40	55	65	55	85	100	115	
Steel failure for tension and shear load (version <b>type H, type S, type B, type I<sup>1)</sup></b> )									
Characteristic load	$N_{Rk,s,eq}$ [kN]	14,0	27,0	45,0	67,0	94,0			
Partial factor	$\gamma_{Ms,eq}$ [-]	1,5							
Characteristic load	$V_{Rk,s,eq}$ [kN]	4,7	5,5	8,5	13,5	15,3	21,0	22,4	
Partial factor	$\gamma_{Ms,eq}$ [-]	1,25							
With filling of the annular gap <sup>2)</sup>	$\alpha_{gap}$ [-]	1,0							
Without filling of the annular gap <sup>3)</sup>	$\alpha_{gap}$ [-]	0,5							
Pull-out failure (version <b>type H, type S, type B, type I<sup>1)</sup></b> )									
Characteristic tension load in cracked concrete C20/25	$N_{Rk,p,eq}$ [kN]	2,0	4,0	12,0	9,0	$\geq N_{Rk,c}^0$ <sup>4)</sup>			
Concrete cone failure (version <b>type H, type S, type B, type I<sup>1)</sup></b> )									
Effective embedment depth	$h_{ef}$ [mm]	31	44	52	43	68	80	92	
Edge distance	$c_{cr,N}$ [mm]	$1,5 \times h_{ef}$							
Spacing	$s_{cr,N}$ [mm]	$3 \times h_{ef}$							
Installation safety factor	$\gamma_{inst}$ [-]	1,0							
Concrete pry-out failure (version <b>type H, type S, type B</b> )									
Factor for pry-out failure	$k_8$ [-]	1,0				2,0			
Concrete edge failure (version <b>type H, type S, type B</b> )									
Effective length in concrete	$l_f = h_{ef}$ [mm]	31	44	52	43	68	80	92	
Nominal outer diameter of screw	$d_{nom}$ [mm]	6	6	8	10	10	12	14	
<sup>1)</sup> only tension load <sup>2)</sup> With filling of the annular gap according to annex B7, figure 5 <sup>3)</sup> Without filling of the annular gap according to annex B5 <sup>4)</sup> $N_{Rk,c}^0$ according to EN 1992-4:2018									
<b>BOSSONG concrete screw CLS-CE</b>							<b>Annex C3</b>		
<b>Performances</b> Seismic category C1 – Characteristic load values									

Table 9: Seismic category C2 <sup>1)</sup> – Characteristic load values with filled annular gap according to annex B7, figure 5 (type H, type S, type B)

CLS-CE concrete screw size			8	10	12	14
Nominal embedment depth	$h_{nom}$	$h_{nom3}$				
	[mm]	65	85	100	115	
<b>Steel failure for tension and shear load (version type H, type S, type B)</b>						
Characteristic load	$N_{Rk,s,eq}$	[kN]	27,0	45,0	67,0	94,0
Partial factor	$\gamma_{Ms,eq}$	[-]	1,5			
Characteristic load	$V_{Rk,s,eq}$	[kN]	9,9	18,5	31,6	40,7
Partial factor	$\gamma_{Ms,eq}$	[-]	1,25			
With filling of the annular gap	$\alpha_{gap}$	[-]	1,0			
<b>Pull-out failure (version type H, type S, type B)</b>						
Characteristic load in cracked concrete	$N_{Rk,p,eq}$	[kN]	2,4	5,4	7,1	10,5
<b>Concrete cone failure (version type H, type S, type B)</b>						
Effective embedment depth	$h_{ef}$	[mm]	52	68	80	92
Edge distance	$c_{cr,N}$	[mm]	$1,5 \times h_{ef}$			
Spacing	$s_{cr,N}$	[mm]	$3 \times h_{ef}$			
Installation safety factor	$\gamma_{inst}$	[-]	1,0			
<b>Concrete pry-out failure (version type H, type S, type B)</b>						
Factor for pry-out failure	$k_g$	[-]	1,0	2,0		
<b>Concrete edge failure (version type H, type S, type B)</b>						
Effective length in concrete	$l_f = h_{ef}$	[mm]	52	68	80	92
Nominal outer diameter of screw	$d_{nom}$	[mm]	8	10	12	14

1) A4 and HCR not suitable

**BOSSONG concrete screw CLS-CE**

**Performances**

Seismic category C2 – Characteristic load values with filled annular gap

**Annex C4**

Table 10: Seismic category C2 <sup>1)</sup> – Characteristic load values **without filled annular gap according to annex B5 (type H, type S, type B)**

CLS-CE concrete screw size			8	10	12	14
Nominal embedment depth	$h_{nom}$	$h_{nom3}$				
	[mm]	65	85	100	115	
<b>Steel failure for tension and shear load (version type H, type B)</b>						
Characteristic load	$N_{Rk,s,eq}$	[kN]	27,0	45,0	67,0	94,0
Partial factor	$\gamma_{Ms,eq}$	[-]	1,5			
Characteristic load	$V_{Rk,s,eq}$	[kN]	10,3	21,9	24,4	23,3
Partial factor	$\gamma_{Ms,eq}$	[-]	1,25			
Without filling of the annular gap	$\alpha_{gap}$	[-]	0,5			
<b>Pull-out failure (version type H, type B)</b>						
Characteristic load in cracked concrete	$N_{Rk,p,eq}$	[kN]	2,4	5,4	7,1	10,5
<b>Steel failure for tension and shear load (version type S)</b>						
Characteristic load	$N_{Rk,s,eq}$	[kN]	27,0	45,0	no performance assessed	
Partial factor	$\gamma_{Ms,eq}$	[-]	1,5			
Characteristic load	$V_{Rk,s,eq}$	[kN]	3,6	13,7		
Partial factor	$\gamma_{Ms,eq}$	[-]	1,25			
Without filling of the annular gap	$\alpha_{gap}$	[-]	0,5			
<b>Pull-out failure (version type S)</b>						
Characteristic load in cracked concrete	$N_{Rk,p,eq}$	[kN]	2,4	5,4	no performance assessed	
<b>Concrete cone failure (version type H, type S, type B)</b>						
Effective embedment depth	$h_{ef}$	[mm]	52	68	80	92
Edge distance	$c_{cr,N}$	[mm]	$1,5 \times h_{ef}$			
Spacing	$s_{cr,N}$	[mm]	$3 \times h_{ef}$			
Installation safety factor	$\gamma_{inst}$	[-]	1,0			
<b>Concrete pry-out failure (version type H, type S, type B)</b>						
Factor for pry-out failure	$k_g$	[-]	1,0	2,0		
<b>Concrete edge failure (version type H, type S, type B)</b>						
Effective length in concrete	$l_f = h_{ef}$	[mm]	52	68	80	92
Nominal outer diameter of screw	$d_{nom}$	[mm]	8	10	12	14

<sup>1)</sup> A4 and HCR not suitable

**BOSSONG concrete screw CLS-CE**

**Performances**

Seismic category C2 – Characteristic load values without filled annular gap

**Annex C5**

Table 11: Fire exposure – characteristic values of resistance

CLS-CE concrete screw size				6		8			10			12			14			
Nominal embedment depth				$h_{nom}$	1	2	1	2	3	1	2	3	1	2	3	1	2	3
				[mm]	40	55	45	55	65	55	75	85	65	85	100	75	100	115
<b>Steel failure for tension and shear load</b>																		
characteristic Resistance	R30	$N_{Rk,s,fi30}$	[kN]	0,9		2,4			4,4			7,3			10,3			
	R60	$N_{Rk,s,fi60}$	[kN]	0,8		1,7			3,3			5,8			8,2			
	R90	$N_{Rk,s,fi90}$	[kN]	0,6		1,1			2,3			4,2			5,9			
	R120	$N_{Rk,s,fi120}$	[kN]	0,4		0,7			1,7			3,4			4,8			
	R30	$V_{Rk,s,fi30}$	[kN]	0,9		2,4			4,4			7,3			10,3			
	R60	$V_{Rk,s,fi60}$	[kN]	0,8		1,7			3,3			5,8			8,2			
	R90	$V_{Rk,s,fi90}$	[kN]	0,6		1,1			2,3			4,2			5,9			
	R120	$V_{Rk,s,fi120}$	[kN]	0,4		0,7			1,7			3,4			4,8			
	R30	$M^0_{Rk,s,fi30}$	[Nm]	0,7		2,4			5,9			12,3			20,4			
	R60	$M^0_{Rk,s,fi60}$	[Nm]	0,6		1,8			4,5			9,7			15,9			
	R90	$M^0_{Rk,s,fi90}$	[Nm]	0,5		1,2			3,0			7,0			11,6			
	R120	$M^0_{Rk,s,fi120}$	[Nm]	0,3		0,9			2,3			5,7			9,4			
<b>Pull-out failure</b>																		
Characteristic Resistance	R30- R90	$N_{Rk,p,fi}$	[kN]	0,5	1,0	1,3	2,3	3,0	2,3	4,0	4,8	3,0	4,7	6,2	3,8	6,0	7,6	
	R120	$N_{Rk,p,fi}$	[kN]	0,4	0,8	1,0	1,8	2,4	1,8	3,2	3,9	2,4	3,8	4,9	3,0	4,8	6,1	
<b>Concrete cone failure</b>																		
Characteristic Resistance	R30- R90	$N^0_{Rk,c,fi}$	[kN]	0,9	2,2	1,2	2,1	3,4	2,1	4,8	6,6	3,0	6,3	9,9	4,4	9,6	14,0	
	R120	$N^0_{Rk,c,fi}$	[kN]	0,7	1,8	1,0	1,7	2,7	1,7	3,8	5,3	2,4	5,1	7,9	3,5	7,6	11,2	
<b>Edge distance</b>																		
R30 bis R120	$c_{cr,fi}$	[mm]	$2 \times h_{ef}$															
In case of fire attack from more than one side, the minimum edge distance shall be $\geq 300$ mm.																		
<b>Spacing</b>																		
R30 bis R120	$s_{cr,fi}$	[mm]	$4 \times h_{ef}$															
<b>Pry-out failure</b>																		
R30 bis R120	$k_g$	[-]	1,0			2,0			1,0	2,0			1,0	2,0				
The anchorage depth has to be increased for wet concrete by at least 30 mm compared to the given value.																		
<b>BOSSONG concrete screw CLS-CE</b>															<b>Annex C6</b>			
<b>Performances</b> Fire exposure – characteristic values of resistance																		

Table 12: Displacements under static and quasi-static tension load

CLS-CE concrete screw size				6			8			10		
Nominal embedment depth				$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$
				[mm]	40	55	45	55	65	55	75	85
Cracked concrete	tension load	N	[kN]	0,95	1,9	2,4	4,3	5,7	4,3	7,9	9,6	
	displacement	$\delta_{N0}$	[mm]	0,3	0,6	0,6	0,7	0,8	0,6	0,5	0,9	
		$\delta_{N\infty}$	[mm]	0,4	0,4	0,6	1,0	0,9	0,4	1,2	1,2	
Uncracked concrete	tension load	N	[kN]	1,9	4,3	3,6	5,7	7,6	5,7	9,5	11,9	
	displacement	$\delta_{N0}$	[mm]	0,4	0,6	0,7	0,9	0,5	0,7	1,1	1,0	
		$\delta_{N\infty}$	[mm]	0,4	0,4	0,6	1,0	0,9	0,4	1,2	1,2	

CLS-CE concrete screw size				12			14			
Nominal embedment depth				$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$
				[mm]	65	85	100	75	100	115
Cracked concrete	tension load	N	[kN]	5,7	9,4	12,3	7,6	12,0	15,1	
	displacement	$\delta_{N0}$	[mm]	0,9	0,5	1,0	0,5	0,8	0,7	
		$\delta_{N\infty}$	[mm]	1,0	1,2	1,2	0,9	1,2	1,0	
Uncracked concrete	tension load	N	[kN]	7,6	13,2	17,2	10,6	16,9	21,2	
	displacement	$\delta_{N0}$	[mm]	1,0	1,1	1,2	0,9	1,2	0,8	
		$\delta_{N\infty}$	[mm]	1,0	1,2	1,2	0,9	1,2	1,0	

Table 13: Displacements under static and quasi-static shear load

CLS-CE concrete screw size				6			8			10		
Nominal embedment depth				$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$
				[mm]	40	55	45	55	65	55	75	85
Cracked and uncracked concrete	shear load	V	[kN]	3,3			8,6			16,2		
	displacement	$\delta_{V0}$	[mm]	1,55			2,7			2,7		
		$\delta_{V\infty}$	[mm]	3,1			4,1			4,3		

CLS-CE concrete screw size				12			14			
Nominal embedment depth				$h_{nom}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$	$h_{nom1}$	$h_{nom2}$	$h_{nom3}$
				[mm]	65	85	100	75	100	115
Cracked and uncracked concrete	shear load	V	[kN]	20,0			30,5			
	displacement	$\delta_{V0}$	[mm]	4,0			3,1			
		$\delta_{V\infty}$	[mm]	6,0			4,7			

**BOSSONG concrete screw CLS-CE**

**Performances**  
Displacements under static and quasi-static loads

**Annex C7**

**Table 14: Seismic category C2 <sup>1)</sup> – Displacements with filled annular gap according to annex B7, figure 5 (type H, type S, type B)**

CLS-CE concrete screw size			8	10	12	14
Nominal embedment depth	$h_{nom}$	$h_{nom3}$				
	[mm]	65	85	100	115	
Displacements under tension loads (version <b>type H, type S, type B</b> )						
Displacement DLS	$\delta_{N,eq(DLS)}$	[mm]	0,66	0,32	0,57	1,16
Displacement ULS	$\delta_{N,eq(ULS)}$	[mm]	1,74	1,36	2,36	4,39
Displacements under shear loads (version <b>type H, type S, type B</b> with hole clearance)						
Displacement DLS	$\delta_{V,eq(DLS)}$	[mm]	1,68	2,91	1,88	2,42
Displacement ULS	$\delta_{V,eq(ULS)}$	[mm]	5,19	6,72	5,37	9,27

**Table 15: Seismic category C2 <sup>1)</sup> – Displacements without filled annular gap according to annex B5 (only version type H, type S, type B)**

CLS-CE concrete screw size			8	10	12	14
Nominal embedment depth	$h_{nom}$	$h_{nom3}$				
	[mm]	65	85	100	115	
Displacements under tension loads (version <b>type H, type B</b> )						
Displacement DLS	$\delta_{N,eq(DLS)}$	[mm]	0,66	0,32	0,57	1,16
Displacement ULS	$\delta_{N,eq(ULS)}$	[mm]	1,74	1,36	2,36	4,39
Displacements under tension loads (version <b>type S</b> )						
Displacement DLS	$\delta_{N,eq(DLS)}$	[mm]	0,66	0,32	no performance assessed	
Displacement ULS	$\delta_{N,eq(ULS)}$	[mm]	1,74	1,36		
Displacements under shear loads (version <b>type H, type B</b> with hole clearance)						
Displacement DLS	$\delta_{V,eq(DLS)}$	[mm]	4,21	4,71	4,42	5,60
Displacement ULS	$\delta_{V,eq(ULS)}$	[mm]	7,13	8,83	6,95	12,63
Displacements under shear loads (version <b>type S</b> with hole clearance)						
Displacement DLS	$\delta_{V,eq(DLS)}$	[mm]	2,51	2,98	no performance assessed	
Displacement ULS	$\delta_{V,eq(ULS)}$	[mm]	7,76	6,25		

<sup>1)</sup> A4 and HCR not suitable

**BOSSONG concrete screw CLS-CE**

**Performances**  
Displacements under seismic loads

**Annex C8**