



Approval body for construction products and types of construction

### **Bautechnisches Prüfamt**

An institution established by the Federal and Laender Governments



## European Technical Assessment

## ETA-22/0034 of 28 February 2022

English translation prepared by DIBt - Original version in German language

## **General Part**

Technical Assessment Body issuing the European Technical Assessment:

Trade name of the construction product

Product family to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment contains

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of Deutsches Institut für Bautechnik

Aminotop++

In-situ formed thermal insulation made of mineral-based foam

Iso-Team Bocholt Ferdinand-Braun-Straße 13 46399 Bocholt DEUTSCHLAND

Iso-Team Bocholt Ferdinand-Braun-Straße 13 46399 Bocholt DEUTSCHLAND

6 pages including 1 annex which form an integral part of this assessment

EAD 041561-00-1201

Deutsches Institut für Bautechnik Kolonnenstraße 30 B | 10829 Berlin | GERMANY | Phone: +49 30 78730-0 | Fax: +49 30 78730-320 | Email: dibt@dibt.de | www.dibt.de



European Technical Assessment ETA-22/0034 English translation prepared by DIBt

Page 2 of 6 | 28 February 2022

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.



Page 3 of 6 | 28 February 2022

**European Technical Assessment** English translation prepared by DIBt

## Specific part

ETA-22/0034

#### 1 Technical description of the product

This European Technical Assessment applies to thermal insulation product using the predominantly inorganic thermal insulation foam "Aminotop++" which is used to completely fill the cavity layer of double-wall masonry for external walls. The thermal insulation foam is subsequently injected as in-situ foam into the cavity layer of double-wall masonry.

The liquid components of the thermal insulation foam are delivered to the construction site e.g. in drums or containers. The first component (surfactant and additives) is foamed with the help of pressurized air and is then mixed with the second component (inorganic filler, polymer binders and additives). Finally a cross-linking agent is added as the third component.

The European Technical Assessment has been issued for the product on the basis of agreed data/ information, deposited with Deutsches Institut für Bautechnik, which identifies the product that has been assessed. The European Technical Assessment applies only to products corresponding to this agreed data/information.

#### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The thermal insulation foam "Aminotop++" can be used as a thermal insulation layer with a thickness  $d \le 150$  mm for thermally insulating double-wall masonry (cavity completely filled) in accordance with DIN EN 1996-1-1 (EC 6).

The performance according to section 3 only applies if the thermal insulation product is installed according to the manufacture's installation instructions by machine-processed injection and considering the conditions in accordance with annex A.

The thermal insulation foam is not intended for use between diffusion-resistant lavers.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the thermal insulation product of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the manufacturer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

#### 3 Performance of the product and references to the methods used for its assessment

For sampling, conditioning and testing the provisions of the EAD No 041561-00-1201 "In-situ formed thermal insulation made of mineral-based foam" apply.

#### 3.1 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A2-s1,d0
test acc. to EN 13823:2010+A1:2014 and EN ISO 1716:2010	acc. to EN 13501-1:2018 <sup>1, 2</sup>
<ul> <li>valid for applications on or between substrates made of building materials classified as A1 or A2-s1,d0 acc. to EN 13501-1 with a thickness d ≥ 12 mm and a density ρ ≥ 650 kg/m<sup>3</sup></li> <li>valid for a thickness range as stated in clause 2 and a density range as stated in table 3.2</li> </ul>	



Page 4 of 6 | 28 February 2022

## **European Technical Assessment**

ETA-22/0034

English translation prepared by DIBt

## 3.2 Energy economy and heat retention (BWR 6)

Essential characteristic	Performance
Thermal conductivity	Declared value of thermal
test acc. to EN 12667:2001	conductivity
	$\lambda_{D (23/50)} = 0.034 \text{ W/(m \cdot K)}^*$
Conversion of humidity acc. to EN ISO 10456:2010	
Moisture conversion factor (23 °C/ 50 % rel. humidity to 23 °C/ 80 % rel. humidity)	$F_{\rm m} = 1.015$
Density	Density range
test acc. to EN 1602:2013	29 kg/m <sup>3</sup> to 35 kg/m <sup>3</sup>
Water absorbtion at long term partial immersion	
test acc. to EN 12087:2013	$W_{\rm lp} \leq 1.0 \ \rm kg/m^2$
Dimensional stability at 23 °C and 50% relative humidity	Relative changes in length, width and thickness
test acc. to EN 1603:2013	
Conditioning: 28 d at 23 °C and 50 % relative humidity	≤ 2.0 % (length, width, thickness)
Dimensional stability at 70 °C and 90% relative humidity	Relative changes in length, width and thickness
test acc. to EN 1604:2013	
Conditioning: 28 d at 70°C and 90 % relative	$\leq$ 5.0 % (length, width)
humidity	≤ 12.0% (thickness)
Dimensional stability at - 30 °C	Relative changes in length, width
test acc. to EN 1604:2013	and thickness
Conditioning: 24 h at - 30 °C	
	≤ 2.0 % (length, width, thickness)
Reactivity	≤ 60 seconds
acc. to a.m. EAD (clause 2.2.8)	

humidity, representative of at least 90% of production with a 90% confidence level.

# Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD No 041561-00-1201 "In-situ formed thermal insulation made of mineral-based foam" the legal basis is:

Commission Decision 1999/91/EC (as amended).

The system to be applied is: system 3.

In addition, with regard to reaction to fire the applicable European legal act is: 1999/91/EC (as amended).

The system to be applied is: system 1.

4



## European Technical Assessment ETA-22/0034 English translation prepared by DIBt

Page 5 of 6 | 28 February 2022

# 5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 28 February 2022 by Deutsches Institut für Bautechnik

Frank Iffländer Head of Section *beglaubigt:* Getzlaff

Deutsches Institut für Bautechnik

Aminotop++

## Annex A

The performances of the thermal insulation foam given in Section 3 apply if the following is considered concerning installation and use:

- Before built-in the foam, the executing company ensures that the outer and inner masonry leaf are in a proper condition and free from moisture. Particular care must be taken to ensure that visible faces are properly jointed. Defects and cracks in the joints must be eliminated before inserting the core insulation.
- The foam is built-in at air temperatures of a least 5°C.
- Existing ventilation openings in the outer masonry leaf at the base of the wall are maintained.
- The thermal insulation foam is uniform in texture and colour. The density of the installed thermal insulation foam (dry) is 29 kg/m<sup>3</sup> to 35 kg/m<sup>3</sup>.
- The core insulation thickness used for the calculation of the thermal resistance is determined by the average clear distance between the masonry leaves. To determine this distance, the bed joint of the masonry is drilled through at at least five places per wall surface and floor to determine the depths of the free cavity at these places. The insulation thickness is given as the average of these five measurements (rounded to 5 mm).
- The executing company ensures the density and the thickness of the installed insulation layer.
- The thermal insulation product is only processed by companies stated in a list of the manufacturer which have adequate experience in installing the insulation foam. These companies have been trained for this purpose by the manufacturer.
- For each application site, the executing company issues a certificate which, by reference to this European Technical Assessment, contains the following information:
  - mineral-based thermal insulation foam built-in on site
  - name and address of the executing company
  - building project and building component
  - date of installation
  - installation thickness (average clear distance) of the core insulation