



Approval body for construction products and types of construction

**Bautechnisches Prüfamt** 

An institution established by the Federal and Laender Governments



# **European Technical Assessment**

ETA-19/0204 of 4 September 2023

English translation prepared by DIBt - Original version in German language

#### **General Part**

Technical Assessment Body issuing the European Technical Assessment:

Trade name of the construction product

Product family to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment contains

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of

This version replaces

Deutsches Institut für Bautechnik

Mungo Injection system MIT700RE for rebar connection

Systems for post-installed rebar connections with mortar

Mungo Befestigungstechnik AG Bornfeldstrasse 2 4603 OLTEN SCHWEIZ

Werk 13 / Plant 13

24 pages including 3 annexes which form an integral part of this assessment

330087-01-0601, Edition 06/2021

ETA-19/0204 issued on 2 December 2020



# European Technical Assessment ETA-19/0204

Page 2 of 24 | 4 September 2023

English translation prepared by DIBt

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.



**European Technical Assessment ETA-19/0204** 

Page 3 of 24 | 4 September 2023

English translation prepared by DIBt

#### **Specific Part**

#### 1 Technical description of the product

The subject of this European Technical Assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the "Mungo Injection system MIT700RE for rebar connection" in accordance with the regulations for reinforced concrete construction.

Reinforcing bars made of steel with a diameter  $\phi$  from 8 to 40 mm or the tension anchor ZA of sizes M12 to M24 according to Annex A and injection mortar MIT700RE are used for rebar connections. The rebar is placed into a drilled hole filled with injection mortar and is anchored via the bond between rebar, injection mortar and concrete.

The product description is given in Annex A.

# 2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the rebar connection is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connections of at least 50 and/or 100 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

#### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under static and quasi-static loading	See Annex C 1
Characteristic resistance under seismic loading	See Annex B 4 and C 2

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 3 to C 4

# 4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330087-01-0601, the applicable European legal act is: [96/582/EC].

The system to be applied is: 1





# **European Technical Assessment ETA-19/0204**

Page 4 of 24 | 4 September 2023

English translation prepared by DIBt

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 4 September 2023 by Deutsches Institut für Bautechnik

Dipl.-Ing. Beatrix Wittstock Head of Section


beglaubigt: Baderschneider

Electronic copy by DIBt: ETA-19/0204




### Installation post installed rebar


**Figure A1:** Overlapping joint for rebar connections of slabs and beams




**Figure A2:** Overlapping joint at a foundation of a wall or column where the rebars are stressed in tension




**Figure A3:** End anchoring of slabs or beams (e.g. designed as simply supported)



**Figure A5:** Anchoring of reinforcement to cover the line of acting tensile force



**Figure A4:** Rebar connection for components stressed primarily in compression. The rebars are stressed in compression



#### Note to Figure A1 to A5:

In the Figures no transverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1:2004+AC:2010.


Preparing of joints according to Annex B 2

# Mungo Injection system MIT700RE for rebar connection Product description Installed condition and examples of use for rebars Annex A 1




#### Installation tension anchor ZA

Figure A6: Anchorage of column to foundation with tension anchor ZA.



- 1 Tension anchor ZA (tension only)
- 2 Existing stirrup / reinforcement for overlap (lap splice)
- 3 Shear lug (or fastener loaded in shear)
- 4 Slotted hole with axial direction to the shear force

Figure A7: Anchorage of guardrail posts or cantilevered building components with tension anchor ZA and fastner.




- 1 Tension anchor ZA (tension only)
- 2 Existing stirrup / reinforcement for overlap (lap splice)
- 3 Fastener (or shear lug loaded in shear)
- 4 Slotted hole with axial direction to the shear force

**Note to Figure A6 and A7:** In the Figures no transverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1:2004+AC:2010. The tension anchor may be only used for axial tensile force. The tensile force must be transferred by lab to the existing reinforcement of the building. The transfer of the shear force has to be ensured by suitable measures, e.g. by means of shear lugs or anchors with European Technical Assessment (ETA). Generals construction rules see Annex B 3

Mungo Injection system MIT700RE for rebar connection	
Product description Installed condition and examples of use for tension anchors MIT-ZA	Annex A 2










### Reinforcing bar (rebar): ø8 up to ø40



- Minimum value of related rip area f<sub>R,min</sub> according to EN 1992-1-1:2004+AC:2010
- Rib height of the bar shall be in the range 0,05φ ≤ h<sub>rib</sub> ≤ 0,07φ
   (φ: Nominal diameter of the bar; h<sub>rib</sub>: Rib height of the bar)

#### **Table A1: Materials Rebar**

Designation	Material
Rebar EN 1992-1-1:2004+AC:2010, Annex C	Bars and de-coiled rods class B or C $f_{yk}$ and k according to NDP or NCI of EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$

Mungo Injection system MIT700RE for rebar connection

Product description
Specifications Rebar

Annex A 4






Table A2: Materials Tension Anchor ZA

							Mate	erial					
Part	Designation	Designation ZA vz			ZA A4			ZA HCR					
		M12	M16	M20	M24	M12	M16	M20	M24	M12	M16	M20	M24
1	Reinforcement bar		Class B according to NDP or $f_{uk} = f_{tk} = k \cdot f_{yk}$			NCI of EN 1992-1-1/NA			A				
	f <sub>yk</sub> [N/mm²]		50	00			50	00			50	00	
2	Threaded rod	to EN	Steel, zinc plated according to EN ISO 683-4:2018 or EN 10263:2017		Stainless steel, 1.4362, 1.4401, 1.4404, 1.4571, EN 10088-1:2014			High corrosion resistant steel, 1.4529, 1.4565, EN 10088-1:2014					
3	Washer		zinc pla			**************************************		, 1.4362				resista	
4	Nut	ACCESS OF THE PARTY OF THE PART	ISO 683 263:201		s or	and the same of th	, 1.4404 )88-1:20	4, 1.457 014	1,	50000000000000000000000000000000000000	1.4529, 088-1:2	1.4565, 014	

# Table A3: Dimensions and installation parameters

Size				ZA-M12 ZA-M16 ZA-M20 ZA-M24				
Diameter of threa	ded rod	d <sub>s</sub>	[mm]	12	16	20	24	
Diameter of reinfo	orcement bar	ф	[mm]	12	16	20	25	
Drill hole diamete	r	d <sub>o</sub>	[mm]	16	20	25	32	
Diameter of clear fixture	ance hole in	d <sub>f</sub>	[mm]	14	18	22	26	
With across nut fl	ats	SW	SW [mm] 19 24 30		30	36		
Stress area		As	[mm <sup>2</sup> ]	84 157 245 353		353		
Effective embedm	nent depth	I <sub>v</sub>	[mm]	according to static calculation				
Length of	plated		[mm]	≥ 20	≥ 20	≥ 20	≥ 20	
bonded thread	A4/HCR	] 'e	l <sub>e</sub> [mm]		≥ 100	≥ 100	≥ 100	
Minimum thicknes	ss of fixture	min t <sub>fix</sub>	[mm]	5	5	5	5	
Maximum thickne	ess of fixture	max t <sub>fix</sub>	[mm]	3000	3000	3000	3000	
Maximum installa	tion torque	max T <sub>inst</sub>	[Nm]	50	100	150	150	

Mungo Injection system MIT700RE for rebar connection	
Product description Specifications Tension Anchor ZA	Annex A 5



Specification of the intended use				
Anchorages subject to:		Working life 50 years	Working life 100 years	
HD: Hammer drilling HDB: Hammer drilling with	static and quasi-static loads	Ø8 to Ø40 ZA-M12 to ZA-M24	Ø8 to Ø40 ZA-M12 to ZA-M24	
hollow drill bit	seismic action	Ø10 to Ø40	Ø10 to Ø40	
CD: Compressed air drilling DD: Diamond drilling	fire exposure	Ø8 to Ø40 ZA-M12 to ZA-M24	Ø8 to Ø40 ZA-M12 to ZA-M24	
Temperature Range: - 40°C to +80°C (max long-term temperature +50 °C and max short-term temperature +80 °C)			term temperature +80 °C)	

#### Base materials:

- Reinforced or unreinforced normal weight concrete according to EN 206:2013 + A1:2016.
- Strength classes C12/15 to C50/60 according to EN 206:2013 + A1:2016.
- Maximum chloride content of 0,40% (CL 0.40) related to the cement content according to EN 206:2013 + A1:2016.
- Non-carbonated concrete.

Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of  $\phi + 60$  mm prior to the installation of the new rebar.

The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1:2004+AC:2010. The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

#### Use conditions (Environmental conditions) with tension anchor ZA:

- Structures subject to dry internal conditions (all materials).
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance class:
  - Stainless steel Stahl A4 according to Annex A 4, Table A1: CRC III
  - High corrosion resistance steel HCR according to Annex A 4, Table A1: CRC V

#### Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2004+AC:2010, EN 1992-1-2:2004+AC:2008 and Annex B 2 and B 3.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

#### Installation:


- Dry or wet concrete. It must not be installed in flooded holes.
- Overhead installation allowed.
- Hole drilling by hammer drill (HD), hollow drill (HDB), diamond drill (DD) or compressed air drill mode (CD).
- The installation of post-installed rebar resp. tension anchors shall be done only by suitable trained installer and under supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

Mungo Injection system MIT700RE for rebar connection	
Intended use Specifications	Annex B 1



### Figure B1: General construction rules for post-installed rebars

- Only tension forces in the axis of the rebar may be transmitted.
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2004+AC:2010.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



1) If the clear distance between lapped bars exceeds 4φ but at least 50 mm, then the lap length shall be increased by the difference between the clear bar distance and 4φ but at least 50 mm.

The following applies to Figure B1:

Electronic copy by DIBt: ETA-19/0204

c concrete cover of post-installed rebar

concrete cover at end-face of existing rebar

c<sub>min</sub> minimum concrete cover according to Table B1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2

φ diameter of post-installed rebar

 $I_0$  lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3

 $I_v$  effective embedment depth,  $\geq I_0 + c_1$ 


 ${\rm d}_0$  nominal drill bit diameter, see Annex B 5

Mungo Injection system MIT700RE for rebar connection	
Intended use General construction rules for post-installed rebars	Annex B 2



### Figure B2: General construction rules for tension anchors ZA

- The length of the bonded-in thread may be not be accounted as anchorage.
- Only tension forces in the direction of the bar axis may be transmitted by the tension anchor ZA.
- The tension force must be transferred via an overlap joint to the reinforcement in the building part.
- The transfer of shear forces shall be ensured by appropriate additional measures, e.g shear lugs or by anchors with an European technical assessment.
- In the anchor plate, the holes for the tension anchors shall be executed as elongated holes with axis in the direction of the shear force.



1) If the clear distance between lapped bars exceeds 4¢ but at least 50 mm, then the lap length shall be increased by the difference between the clear bar distance and 4¢ but at least 50 mm.

The following applies to Figure B2:

c concrete cover of tension anchor ZA

c<sub>1</sub> concrete cover at end-face of existing rebar

c<sub>min</sub> minimum concrete cover according to Table B1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2

φ diameter of tension anchor

l<sub>0</sub> lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3

 $egin{array}{ll} I_{v} & & \mbox{effective embedment depth} \\ I_{e} & & \mbox{length of bonded thread} \\ \end{array}$ 

 $I_{e,ges}$  overall embedment depth,  $\ge I_0 + c_2$ 

d<sub>0</sub> nominal drill bit diameter, see Annex B 5

Mungo Injection system MIT700RE for rebar connection	
Intended use General construction rules for tension anchors ZA	Annex B 3



Table B1:	Minimum concrete cover c <sub>min</sub> 1) of post-installed rebar and tie rod ZA
	depending of drilling method

•				
Drilling method	Rebar diameter	Without drilling aid	With dri	lling aid
HD: Hammer drilling HDB: Hammer drilling	< 25 mm	$30 \text{ mm} + 0.06 \cdot \text{l}_{\text{V}} \ge 2  \phi$	$30 \text{ mm} + 0.02 \cdot \text{I}_{\text{V}} \ge 2  \phi$	
with hollow drill bit	≥ 25 mm	40 mm + 0,06 · l <sub>v</sub> ≥ 2 φ	40 mm + 0,02 · I <sub>v</sub> ≥ 2 φ	Drilling aid
DD: Diamond drilling	< 25 mm	Drill rig used as drilling aid	30 mm + 0,02 · l <sub>v</sub> ≥ 2 ф	
DD. Diamond drilling	≥ 25 mm		$40 \text{ mm} + 0.02 \cdot \text{l}_{\text{v}} \ge 2  \phi$	
CD: Compressed air	< 25 mm	50 mm + 0,08 · l <sub>v</sub>	50 mm + 0,02 · I <sub>v</sub>	] д катататата
drilling	≥ 25 mm	60 mm + 0,08 · l <sub>v</sub> ≥ 2 ф	60 mm + 0,02 · l <sub>V</sub> ≥ 2 φ	

see Annex B 2, Figure B1 and Annex B 3, Figure B2
 Comments: The minimum concrete cover acc. EN 1992-1-1:2004+AC:2010 must be observed.

 For the minimum concrete cover cmin,seis in case of a seismic action, see Table B2.

Table B2: Minimum concrete cover min  $c_{\min,seis}$ 

Drilling method	Design conditions	Distance to 1st edge	Distance to 2nd edge
HD: Hammer drilling HDB: Hammer drilling with	Edge	≥ 2 ф	≥ 2 ф
hollow drill bit CD: Compressed air drilling	Corner	≥ 2 ф	≥ 2 ф
DD: Diamond drilling	Edge	≥ 4 ф	≥ 8 ф
Diamond drilling	Corner	≥ 6 ф	≥ 6 ф

# Table B3: Dispensing tools

Cartridge type/size	Ha	Pneumatic tool		
Side-by-side cartridges 440, 585 ml				
	e.g. SA 296C585	e.g. Type H 244 C	e.g. Type TS 444 KX	
Side-by-side cartridges 1400 ml		-	e.g. Type TS 471	

All cartridges could also be extruded by a battery tool.

Mungo Injection system MIT700RE for rebar connection	
Intended use Minimum concrete cover Dispensing tools	Annex B 4

40



					piston plugs, max anchorage depth and mixer extension, har nond (DD) and compressed air (CD) drilling						hammer			
de so			Drill				<b>d</b> <sub>b,min</sub>		Ca	rtridge: 440	ml or	585 ml	Cartri	dge: 1400 ml
Bar size	Tension anchor	ŀ	oit - Ø		d		min. Brush -	Piston plug	2007	land or ttery tool	Pneumatic tool		Pneumatic tool	
ф	ф	HD	DD	CD	Brush - Ø		Ø	I <sub>v,max</sub>		Mixer extension	I <sub>v,max</sub>	Mixer extension	I <sub>v,max</sub>	Mixer extension
[mm]	[mm]		[m	m]	MIT-	[mm]	[mm]	MIT-	[mm]		[mm]		[mm]	
8	-	1	0		BS10	11,5	10,5	Ψ.	250		250		250	
	-				BS12	13,5	12,5	_,	700		800		800	VL10/0,75
10	-	1	2	_	D012	10,0	12,0		250	6	250		250	or
10	-	-			BS14	15,5	14,5	VS14	700	s .	1000		1000	VL16/1,8
12	ZA-M12	14 - 16		:	<del>-</del> 77				250		250		250	
	Z/ \ \VI \Z			BS16	17,5	16,5	VS16			3 1000000000		1200		
14	-		18		BS18	20,0	18,5	VS18	700	VL10/0,75	1300		1400	
16	ZA-M16		20		BS20	22,0	20,5	VS20		or		VI 10/0 75	1600	
20	ZA-M20	2	5		BS25	27,0	25,5	VS25		VL16/1,8		VL10/0,75 or		
	27 ( 10120	- VIZU		26	BS26	28,0	26,5	VS25				VL16/1,8		
22	-		28		BS28	30,0	28,5	VS28				1210/1,0		
24/25	ZA-M24		30		BS30	32,0	30,5	VS30	500					VL16/1,8
24/23	ZA-IVIZ4		32		BS32	34,0	32,5	VS32			1000		2000	
28	-		35		BS35	37,0	35,5	VS35			1000		2000	
32/34	-		40		BS40	43,5	40,5	VS40						
36	-		45		BS45	47,0	45,5	VS45						
40	-	-11	52	52	BS52	54,0	52,5	VS52	-	-				
40								1 4 2	1					

Brushes, piston plugs, max anchorage depth and mixer extension, hammer drilling with hollow drill bit system (HDB) Table B5:

**VS55** 

55,5

55 BS55 58,0

_		Drill		<b>d</b> <sub>b,min</sub>		С	artridge: 440	Cartridge: 1400 ml				
Bar size	Tension anchor	bit - Ø	d <sub>b</sub>	a <sub>b</sub> min.		Hand or battery tool Pi		Pneu	Pneumatic tool		Pneumatic tool	
ф	ф	HDB	Brush - Ø	Brush -	plug	I <sub>v,max</sub>	Mixer extension	$I_{v,max}$	Mixer extension	$I_{v,max}$	Mixer extension	
[mm]	[mm]	[mm]			MIT-	[mm]		[mm]		[mm]		
8	-	10			-	250		250		250		
0	-	12			_	700		800	VL10/0,75 or VL16/1,8	800		
10	-	12				250		250		250		
10	-	14			VS14	700		1000		1000		
12	ZA-M12	14			V314	250		250		250		
12	ZA-IVI IZ	16	NI= =l==		VS16		VL10/0,75 or VL16/1,8				\/I 40/0 75	
14		18	No clea Requ		VS18						VL10/0,75 or VL16/1,8	
16	ZA-M16	20	nequ	iieu	VS20							
20	ZA-M20	25			VS25		VE10/1,0					
22		28			VS28			1000		1000		
04/05	74 MO4	30			VS30	500						
24/25 ZA-M2	ZA-IVIZ4	32			VS32	500						
28		35			VS35							
32/34		40			VS40							

Mungo Injection system MIT700RE for rebar connection	
Intended Use Parameter brushes, piston plugs, max anchorage depth and mixer extension	Annex B 5



### Cleaning and installation tools

#### HDB - Hollow drill bit system



The hollow drill system consists of MHP-Clean/ MHX-Clean and a class M vacuum cleaner with a minimum negative pressure of 253 hPa and a flow rate of minimum 150 m³/h (42 l/s).

#### Hand pump

(Volume 750 ml,  $h_0 \ge 10 d_s$ ,  $d_0 \le 20 mm$ )



## Manual slide valve

(min 6 bar)



#### **Brush MIT-BS**



#### **Piston Plug MIT-VS**



#### **Brush extension MIT-BSL**



# Table B6: Working time and curing time

Tempera	ature in bas	e material	Maximum working time	Initial curing time <sup>1)</sup>	Minimum curing time <sup>2)</sup>
	Т		t <sub>work</sub>	t <sub>cure,ini</sub>	t <sub>cure</sub>
0°C	up to	+ 4 °C	80 min	30 h	144 h
+ 5 °C	up to	+ 9 °C	80 min	20 h	48 h
+ 10°C	+ 10 °C up to + 14 °C		60 min	15 h	28 h
+ 15°C	up to	+ 19°C	40 min	9 h	18 h
+ 20 °C	up to	+ 24 °C	30 min	6 h	12 h
+ 25 °C	up to	+ 34 °C	12 min	4 h	9 h
+ 35 °C up to + 39 °C		8 min	3 h	6 h	
	+40°C		8 min	1,5 h	4 h
Car	tridge tempe	rature		+5°C up to +40°C	_

- 1) After Initial curing time has elapsed, the installation of the connecting reinforcement and the construction of the formwork can be continued
- 2) The minimum curing time is only valid for dry base material. In wet base material the curing time must be doubled.


Mungo Injection system MIT700RE for rebar connection	
Intended Use Cleaning and installation tools Working time and curing time	Annex B 6



#### Installation instructions


Attention: Before drilling, remove carbonated concrete and clean contact areas (see Annex B1) In case of aborted drill hole: the drill hole shall be filled with mortar.

#### Drilling of the bore hole



Hammer drilling (HD) / Compressed air drilling (CD)

Drill a hole to the required embedment depth.
Drill bit diameter according to Table B4.
Proceed with Step 2 (MAC or CAC).




Hollow drill bit system (HDB) (see Annex B 6)

Drill a hole to the required embedment depth.

Drill bit diameter according to Table B5.

The hollow drilling system removes the dust and cleans the bore hole.

Proceed with Step 3.



Electronic copy by DIBt: ETA-19/0204

Diamond drilling (DD)

Drill a hole to the required embedment depth required Drill bit diameter according to Table B4. Proceed with Step 2 (SPCAC).

Mungo Injection system MIT700RE for rebar connection


Intended use
Installation instruction

Annex B 7




#### Manual Air Cleaning (MAC)

for drill hole diameter  $d_0 \le 20$ mm and drill hole depth  $h_0 \le 10$  with drilling method HD/CD




Attention! Standing water in the bore hole must be removed before cleaning.

2a. Blow the bore hole clean minimum 4x from the bottom or back by hand pump (Annex B 6).



Brush the bore hole minimum 4x with brush MIT-BS according to Table B4 over the entire embedment depth in a twisting motion (if necessary, use a brush extension MIT-BSL).



Finally blow the bore hole clean minimum 4x from the bottom or back by hand pump (Annex B 6).


## Compressed Air Cleaning (CAC):

All diameter with drilling method HD/CD




Attention! Standing water in the bore hole must be removed before cleaning.

2a. Blow the bore hole clean minimum 2x with compressed air (min. 6 bar, oil-free) (Annex B 6) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)



Brush the bore hole minimum 2x with brush MIT-BS according to Table B4 over the entire embedment depth in a twisting motion. (If necessary, a brush extension MIT-BSL shall be used.)



Electronic copy by DIBt: ETA-19/0204

Finally blow the bore hole clean minimum 2x with compressed air (min. 6 bar, oil-free) (Annex B 6) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)


Protect cleaned bore hole against re-contamination in an appropriate way. If necessary, repeat cleaning process directly before dispensing the mortar. In-flowing water must not contaminate the bore hole again.

Mungo Injection system MIT700RE for rebar connection	
Intended use Installation instructions (continuation)	Annex B 8


772188.23 8.06.01-135/23

#### Flush & Compressed Air Cleaning (SPCAC):

All diameter with drilling method DD




2a. Flushing with water until clear water comes out.




2b. Brush the bore hole minimum 2x with brush MIT-BS according to Table B4 over the entire embedment depth in a twisting motion. (If necessary, a brush extension MIT-BSL shall be used.)



Flushing again with water until clear water comes out.



2d. Blow the bore hole clean minimum 2x with compressed air (min. 6 bar, oil-free) (Annex B 6) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)



Brush the bore hole minimum 2x with brush MIT-BS according to Table B4 over the entire embedment depth in a twisting motion. (If necessary, a brush extension MIT-BSL shall be used.)




Electronic copy by DIBt: ETA-19/0204

Finally blow the bore hole clean minimum 2x with compressed air (min. 6 bar, oil-free) (Annex B 6) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)


Protect cleaned bore hole against re-contamination in an appropriate way. If necessary, repeat cleaning process directly before dispensing the mortar. In-flowing water must not contaminate the bore hole again.

Mungo Injection system MIT700RE for rebar connection	
Intended use Installation instructions (continuation)	Annex B 9




Screw on static-mixing nozzle MIT-MI-4, and load the cartridge into an appropriate dispensing tool.

For every working interruption longer than the maximum working time t<sub>work</sub> (Annex B 6) as well as for new cartridges, a new static-mixer shall be used.



In case of using the mixer extension MIT-VL16/1,8, cut off the tip of the mixer nozzle at position  $_{\tt m}X^{\tt m}$ .




Mark embedment depth on the reinforcing bar .


The reinforcing bar shall be free of dirt, grease, oil or other foreign material.

Mark mixer nozzle and extension with mortar level mark Im and anchorage depth Iv resp. I<sub>e,ges</sub>


Quick estimation:  $I_m = 1/3 \cdot I_v$ Optimum mortar volume:

$$I_{m} = I_{v} \text{ resp. } I_{e,ges} \cdot \left(1,2 \cdot \frac{\phi^{2}}{d_{0}^{2}} - 0,2\right)$$





Not proper mixed mortar is not sufficient for fastening. Dispense and discard mortar until an uniform grey or red colour is shown (at least 3 full strokes).



Piston plugs MIT-VS and mixer nozzle extensions MIT-VL shall be used according to

Table B4 or B5.

Assemble mixing nozzle, mixer extension and piston plug before injecting mortar.

#### Mungo Injection system MIT700RE for rebar connection

#### **Intended Use**


Installation instructions (continuation)

Annex B 10

Z72188.23


Electronic copy by DIBt: ETA-19/0204

8.06.01-135/23



#### 8a. Injecting mortar without piston plug MIT-VS:


Starting at bottom of the hole and fill the hole with adhesive until the mortar level mark is visible. (If necessary, a mixer nozzle extension shall be used.) Slowly withdraw of the static mixing nozzle avoid creating air pockets Observe the temperature related working time  $t_{work}$  (Annex B 6).




#### Injecting mortar with piston plug MIT-VS:

Insert piston plug to bottom of the hole and fill the hole with mortar until mortar level mark  $l_{\rm m}$  is visible. (If necessary, a mixer nozzle extension shall be used.) During injection the piston plug is pushed out of the bore hole by the back pressure of the mortar.


Observe the temperature related working time  $t_{work}$  (Annex B 6).




Insert the reinforcing bar while turning slightly up to the embedment mark.



10. Annular gap between reinforcing bar and base material must be completely filled with mortar. Otherwise, the installation must be repeated starting from step 8 before the maximum working time t<sub>work</sub> has expired.



For application in vertical upwards direction the reinforcing bar shall be fixed (e.g. wedges).



Temperature related curing time  $t_{cure}$  (Annex B 6) must be observed. After initial curing time  $t_{cure,ini}$  has elapsed, the installation of the connecting reinforcement and the formwork can be continued. The full load to the reinforcing bar may be applied after the full curing time  $t_{cure}$  has elapsed.

## Mungo Injection system MIT700RE for rebar connection

#### **Intended Use**

Installation instructions (continuation)

Annex B 11

Z72188.23

Electronic copy by DIBt: ETA-19/0204



Table C1: Characteristic tension resistance for tension anchor MIT-ZA									
Tension Anchor M12 M16 M20 M24									
Steel, zinc plated (ZA vz)									
Characteristic tension resistance	$N_{Rk,s}$	[kN]	67	125	196	282			
Partial factor	γ <sub>Ms,N</sub>	[-]		1	,4				
Stainless Steel (ZA A4 or ZA HCR	Stainless Steel (ZA A4 or ZA HCR)								
Characteristic tension resistance	$N_{Rk,s}$	[kN]	67	125	171	247			
Partial factor	γ <sub>Ms,N</sub>	[-]	1,4 1,3 1,			1,4			

### Minimum anchorage length and minimum lap length under static or quasi-static loading

The minimum anchorage length  $l_{b,min}$  and the minimum lap length  $l_{0,min}$  according to EN 1992-1-1:2004+AC:2010 ( $l_{b,min}$  acc. to Eq. 8.6 and Eq. 8.7 and  $l_{0,min}$  acc. to Eq. 8.11) shall be multiply by the amplification factor  $\alpha_{lb} = \alpha_{lb}$ ,100y according to Table C2.

Table C2: Amplification factor  $\alpha_{lb} = \alpha_{lb,100y}$  related to concrete class and drilling method; working life 50 and 100 years

Concrete class	ete class Drilling method Bar size		Amplification factor $\alpha_{lb} = \alpha_{lb,100y}$
C12/15 to C50/60	all drilling methods	8 mm to 40 mm MIT-ZA-M12 to MIT-ZA-	1,0

# Table C3: Reduction factor $k_b = k_{b,100y}$ for all drilling methods; working life 50 and 100 years

Rebar		Concrete class							
ф	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 40 mm ZA-M12 to ZA-M24					1,0				

# Table C4: Design values of the ultimate bond stress $f_{bd,PIR}$ and $f_{bd,PIR,100y}$ in N/mm² for all drilling methods and for good conditions; working life 50 and 100 years

 $f_{bd.PIR} = k_b \cdot f_{bd}$ 

 $f_{bd,PIR,100y} = k_{b,100y} \cdot f_{bd}$ 

with

 $f_{bd}$ : Design value of the ultimate bond stress in N/mm² considering the concrete classes, the rebar diameter, the drilling method for good bond condition (for all other bond conditions multiply the values by  $\eta_1$  =0.7) and recommended partial factor  $\gamma_c$  = 1,5 according to EN 1992-1-1:2004+AC:2010.

k<sub>b</sub>, k<sub>b,100v</sub>: Reduction factor according to Table C3

Rebar		Concrete class							
ф	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 32 mm ZA-M12 to ZA-M24	1,6	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3
34 mm	1,6	2,0	2,3	2,6	2,9	3,3	3,6	3,9	4,2
36 mm	1,5	1,9	2,2	2,6	2,9	3,3	3,6	3,8	4,1
40 mm	1,5	1,8	2,1	2,5	2,8	3,1	3,4	3,7	4,0

#### Mungo Injection system MIT700RE for rebar connection

#### **Performances**

Characteristic tension resistance for tension anchor, Minimum anchorage length and minimum lap length, Amplification factor, Reduction factor and Design values of ultimate bond resistance

Annex C 1



#### Minimum anchorage length and minimum lap length under seismic action

The minimum anchorage length  $I_{b,min}$  and the minimum lap length  $I_{0,min}$  according to EN 1992-1-1:2004+AC:2010 ( $I_{b,min}$  acc. to Eq. 8.6 and Eq. 8.7 and  $I_{0,min}$  acc. to Eq. 8.11) shall be multiply by the amplification factor  $\alpha_{lb,seis} = \alpha_{lb,seis,100v}$  according to Table C5.

Table C5: Amplification factor  $\alpha_{lb,seis} = \alpha_{lb,seis,100y}$  related to concrete class and drilling method; working life 50 and 100 years

Concrete class	Drilling method	Bar size	Amplification factor
Concrete class	Drining method	<b>Dai 3126</b>	$\alpha_{\text{lb,seis}} = \alpha_{\text{lb,seis,100y}}$
C16/20 to C50/60	all drilling methods	10 mm to 40 mm	1,0

# Table C6: Reduction factor $k_{b,seis} = k_{b,seis,100y}$ for all drilling methods; working life 50 and 100 years

Rebar	Concrete classes								
ф	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
10 to 40 mm	No performance assessed				1	,0			

# Table C7: Design values of the ultimate bond stress $f_{bd,PIR,seis}$ and $f_{bd,PIR,seis,100y}$ in N/mm<sup>2</sup> for all drilling methods and for good conditions; working life 50 and 100 years

 $f_{bd,PIR,seis} = k_{b,seis \cdot fbd}$ 

 $f_{bd,PIR,seis,100y} = k_{b,seis,100y \cdot fbd}$ 

mit

fbd: Bemessungswert der Verbundspannung in N/mm², in Abhängigkeit von der

Betonfestigkeitsklasse und dem Stabdurchmesser für gute Verbundbedingungen (für alle anderen Verbundbedingungen sind die Werte mit  $\eta_1$  = 0,7 zu multiplizieren) und einem empfohlenen

Teilsicherheitsbeiwert  $\gamma_c$  = 1,5 gemäß EN 1992-1-1:2004+AC:2010.

 $k_{b,seis}, k_{b,seis,100y}$ : Reduktionsfaktor gem. Tabelle C6

Rebar	Concrete classes								
ф	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
10 to 32 mm	No performance assessed	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3
34 mm	1,6	2,0	2,3	2,6	2,9	3,3	3,6	3,9	4,2
36 mm	1,5	1,9	2,2	2,6	2,9	3,3	3,6	3,8	4,1
40 mm	1,5	1,8	2,1	2,5	2,8	3,1	3,4	3,7	4,0

Mungo Injection system MIT700RE for rebar connection	
Performances Minimum anchorage length and minimum lap length, Amplification factor, Reduction factor and Design values of ultimate bond stress under seismic action	Annex C 2



# Design value of the ultimate bond stress f<sub>bd,fi</sub>, f<sub>bd,fi,100v</sub> at increased temperature for concrete classes C12/15 to C50/60, (all drilling methods); working life 50 and 100 years:

The design value of the bond stress  $f_{bd,fi}$  at increased temperature has to be calculated by the following equation:

For working life 50 years:  $f_{bd.fi} = k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \gamma_{c} / \gamma_{M,fi}$ 

 $k_{fi}(\theta) = 4673.8 \cdot \theta^{-1.598} / (f_{bd,PIR} \cdot 4.3) \le 1.0$ θ ≤ 278°C: with:

 $k_{fi}(\theta) = 0$  $\theta > 278^{\circ}C$ :

For working life 100 years:

$$\begin{split} f_{bd,fi,100y} &= k_{fi,100y}(\theta) \cdot f_{bd,PIR,100y} \cdot \gamma_c \, / \, \gamma_{M,fi} \\ k_{fi,100y}(\theta) &= \, 4673,8 \, \cdot \, \theta^{\, -1,598} \, / \, (f_{bd,PIR,100y} \cdot \, 4,3) \leq 1,0 \end{split}$$
 $\theta \le 278^{\circ}\text{C}$ :

 $\theta > 278^{\circ}C$ :  $k_{fi,100v}(\theta) = 0$ 

Design value of the ultimate bond stress at increased temperature in N/mm<sup>2</sup> fbd,fi, fbd,fi,100y

Temperature in °C in the mortar layer.  $k_{fi}(\theta), k_{fi,100v}(\theta)$ Reduction factor at increased temperature.

Design value of the bond stress  $f_{bd,PIR} = f_{bd,PIR,100y}$  in N/mm<sup>2</sup> in cold condition according to f<sub>bd,PIR</sub>, f<sub>bd,PIR,100v</sub>

Table C4 considering the concrete classes, the rebar diameter, the drilling method and the bond


conditions according to EN 1992-1-1:2004+AC:2010.

= 1,5, recommended partial factor according to EN 1992-1-1:2004+AC:2010  $\gamma_{\text{C}}$ = 1,0, recommended partial factor according to EN 1992-1-2:2004+AC:2008

For evidence at increased temperature the anchorage length shall be calculated according to

EN 1992-1-1:2004+AC:2010 Equation 8.3 using the temperature-dependent design value of ultimate bond stress

# Example graph of Reduction factor $k_{fi}(\theta)$ , $k_{fi.100v}(\theta)$ for concrete classes C20/25 for good bond conditions:



Mungo Injection system MIT700RE for rebar connection	
Performances Design value of ultimate bond stress at increased temperature	Annex C 3

English translation prepared by DIBt



Tension Anchor				M12	M16	M20	M24
Steel, zinc plated	(MIT-ZA	/z)					
	R30			2,3	4,0	6,3	9,0
Characteristic	R60	N <sub>Rk,s,fi</sub> [kl	[kN]	1,7	3,0	4,7	6,8
tension resistance	R90			1,5	2,6	4,1	5,9
	R120			1,1	2,0	3,1	4,5
Stainless Steel (M	лТ-ZA A4	or MIT-ZA I	HCR)				
	R30			3,4	6,0	9,4	13,6
Characteristic tension resistance	R60	l N	FI N 17	2,8	5,0	7,9	11,3
	R90	$N_{Rk,s,fi}$	[kN]	2,3	4,0	6,3	9,0
	R120			1,8	3,2	5,0	7,2

Mungo Injection system MIT700RE for rebar connection	
Performances Characteristic tension resistance for tension anchor ZA under fire exposure	Annex C 4