Deutsches Institut für Bautechnik

Approval body for construction products and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and Laender Governments

Member of EOTA
www.eota.eu

Designated according to Article 29 of Regulation (EU) No 305/2011 and member of EOTA (European Organisation for Technical Assessment)

European Technical Assessment ETA-23/0765 of 9 November 2023

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:	Deutsches Institut für Bautechnik
Trade name of the construction product	B+BTec Injection System BIS-V for rebar connection
Product family to which the construction product belongs	Systems for post-installed rebar connections with mortar
Manufacturer	B+BTec Munterij 8 4762 AH ZEVENBERGEN NIEDERLANDE
Manufacturing plant	B+BTec, Plant1
This European Technical Assessment contains	22 pages including 3 annexes which form an integral part of this assessment
This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of	330087-01-0601, Edition 06/2021

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The subject of this European Technical Assessment is the post-installed connection, by anchoring or overlap connection joint, of reinforcing bars (rebars) in existing structures made of normal weight concrete, using the "B+BTect Injection system BIS-V for rebar connection" in accordance with the regulations for reinforced concrete construction.

Reinforcing bars made of steel with a diameter ϕ from 8 to 32 mm or the tension anchor ZA from sizes M12 to M24 according to Annex A and mortar BIS-V are used for rebar connections. The rebar is placed into a drilled hole filled with injection mortar and is anchored via the bond between rebar, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European assessment Document

The performances given in Section 3 are only valid if the rebar connection is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the rebar connection of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance under static and quasi-static loading	See Annex C 1
Characteristic resistance under seismic loading	No performance assessed

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 2 and C 3

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with European Assessment Document EAD No. 330087-01-0601, the applicable European legal act is: [96/582/EC].

The system(s) to be applied is (are): 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 9 November 2023 by Deutsches Institut für Bautechnik

LBD Dipl.-Ing. Andreas Kummerow
Head of Department

beglaubigt:
Baderschneider

Deutsches Institut für Bautechnik DIBt

Installation post installed rebar

Figure A1: Overlapping joint for rebar connections of slabs and beams



Figure A2: Overlapping joint at a foundation of a wall or column where the rebars are stressed in tension



Figure A3: End anchoring of slabs or beams (e.g. designed as simply supported)



Figure A4: Rebar connection for components stressed primarily in compression.



Figure A5: Anchoring of reinforcement to cover the line of acting tensile force



Note to Figure A1 to A5:

In the Figures no transverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1:2004+AC:2010.

Preparing of joints according to Annex B 2

B+BTec Injection System BIS-V for rebar connection	**Annex A 1**
Product description Installed condition and examples of use for rebars	

Installation tension anchor ZA

Figure A6: Anchorage of column to foundation with tension anchor ZA.



1 Tension anchor ZA (tension only)
2 Existing stirrup / reinforcement for overlap (lap splice)
3 Shear lug (or fastener loaded in shear)
4 Slotted hole with axial direction to the shear force

Figure A7: Anchorage of guardrail posts or cantilevered building components with tension anchor ZA and fastner.



1 Tension anchor ZA (tension only)
2 Existing stirrup / reinforcement for overlap (lap splice)
3 Fastener (or shear lug loaded in shear)
4 Slotted hole with axial direction to the shear force

Note to Figure A6 and A7: In the Figures no transverse reinforcement is plotted, the transverse reinforcement shall comply with EN 1992-1-1:2004+AC:2010. The tension anchor may be only used for axial tensile force. The tensile force must be transferred by lab to the existing reinforcement of the building. The transfer of the shear force has to be ensured by suitable measures, e.g. by means of shear lugs or anchors with European Technical Assessment (ETA). Generals construction rules see Annex B 3

B+BTec Injection System BIS-V for rebar connection	**Annex A 2**
Product description Installed condition and examples of use for tension anchors ZA	

Deutsches Institut für Bautechnik DIBt

Cartridge system

Coaxial Cartridge
150 ml, 280 ml, 300 ml up to 333 ml and 380 ml up to 420 ml



Imprint:
BIS-V
Processing and safety instructions, shelf life, charge number, manufacturer's information, quantity information

Side-by-Side Cartridge:
235 ml, 345 ml up to 360 ml and 825 ml



Imprint:
BIS-V
Processing and safety instructions, shelf life, charge number, manufacturer's information, quantity information

Foil tube Cartridge:
165 ml and 300 ml



Imprint:
BIS-V
Processing and safety instructions, shelf life, charge number, manufacturer's information, quantity information

Static mixer SM-14W



Static mixer PM-19E



Piston plug VS and mixer extension VL



B+BTec Injection System BIS-V for rebar connection	**Annex A 3**
Product description Injection system	

Deutsches Institut für Bautechnik DIBt

Reinforcing bar (rebar): ø8 up to ø32



- Minimum value of related rip area $f_{R,min}$ according to EN 1992-1-1:2004+AC:2010
- Rib height of the bar shall be in the range $0{,}05\phi \le h_{rib} \le 0{,}07\phi$
  (ϕ: Nominal diameter of the bar; h_{rib}: Rib height of the bar)

Table A1: Materials Rebar

Designation	Material
Rebar EN 1992-1-1:2004+AC:2010, Annex C	Bars and de-coiled rods class B or C f_{yk} and k according to NDP or NCI of EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$

B+BTec Injection System BIS-V for rebar connection

Product description
Specifications Rebar

Annex A 4

Deutsches Institut für Bautechnik DIBt

Tension Anchor: ZA-M12 up to ZA-M24

Marking: e.g. ◇ ZA 12 A4

◇	Mark of the producer
ZA	Trade name
12	Rod diameter/thread
A4	for stainless steel A4
HCR	for high corrosion resistance steel



Table A2: Materials Tension Anchor ZA

Part	Designation	Material											
		ZA vz				ZA A4				ZA HCR			
		M12	M16	M20	M24	M12	M16	M20	M24	M12	M16	M20	M24
1	Reinforcement bar	Class B according to NDP or NCI of EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$											
	f_{yk} [N/mm²]	500				500				500			
2	Threaded rod	Steel, zinc plated according to EN ISO 683-4:2018 or EN 10263:2017				Stainless steel, 1.4362, 1.4401, 1.4404, 1.4571, EN 10088-1:2014				High corrosion resistant steel, 1.4529, 1.4565, EN 10088-1:2014			
3	Washer	Steel, zinc plated according to EN ISO 683-4:2018 or EN 10263:2017				Stainless steel, 1.4362, 1.4401, 1.4404, 1.4571, EN 10088-1:2014				High corrosion resistant steel, 1.4529, 1.4565, EN 10088-1:2014			
4	Nut												

Table A3: Dimensions and installation parameters

Size				ZA-M12	ZA-M16	ZA-M20	ZA-M24
Diameter of threaded rod		d_s	[mm]	12	16	20	24
Diameter of reinforcement bar		ϕ	[mm]	12	16	20	25
Drill hole diameter		d_o	[mm]	16	20	25	32
Diameter of clearance hole in fixture		d_f	[mm]	14	18	22	26
With across nut flats		SW	[mm]	19	24	30	36
Stress area		A_s	[mm²]	84	157	245	353
Effective embedment depth		l_v	[mm]	according to static calculation			
Length of bonded thread	plated	l_e	[mm]	≥ 20	≥ 20	≥ 20	≥ 20
	A4/HCR			≥ 100	≥ 100	≥ 100	≥ 100
Minimum thickness of fixture		min t_{fix}	[mm]	5	5	5	5
Maximum thickness of fixture		max t_{fix}	[mm]	3000	3000	3000	3000
Maximum installation torque		max T_{inst}	[Nm]	50	100	150	150

B+BTec Injection System BIS-V for rebar connection

Product description
Specifications Tension Anchor ZA

Annex A 5

Deutsches Institut für Bautechnik DIBt

Specification of the intended use

Anchorages subject to:		Working life 50 years	Working life 100 years
HD: Hammer drilling HDB: Hammer drilling with hollow drill bit CD: Compressed air drilling	static and quasi-static loads	Ø8 to Ø32 ZA-M12 to ZA-M24	No performance assessed
	seismic action	No performance assessed	No performance assessed
	Fire exposure	Ø8 to Ø32 ZA-M12 to ZA-M24	No performance assessed
Temperature Range:	- 40°C to +80°C (max long-term temperature +50 °C and max short-term temperature +80 °C)		

Base materials:

- Reinforced or unreinforced normal weight concrete according to EN 206:2013 + A1:2016.
- Strength classes C12/15 to C50/60 according to EN 206:2013 + A1:2016.
- Maximum chloride content of 0,40% (CL 0.40) related to the cement content according to EN 206:2013 + A1:2016.
- Non-carbonated concrete.

  Note: In case of a carbonated surface of the existing concrete structure the carbonated layer shall be removed in the area of the post-installed rebar connection with a diameter of ϕ + 60 mm prior to the installation of the new rebar.

  The depth of concrete to be removed shall correspond to at least the minimum concrete cover in accordance with EN 1992-1-1:2004+AC:2010. The foregoing may be neglected if building components are new and not carbonated and if building components are in dry conditions.

Use conditions (Environmental conditions) with tension anchor ZA:

- Structures subject to dry internal conditions (all materials).
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance class:
  - Stainless steel Stahl A4 according to Annex A 4, Table A1: CRC III
  - High corrosion resistance steel HCR according to Annex A 4, Table A1: CRC V

Design:

- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the forces to be transmitted.
- Design according to EN 1992-1-1:2004+AC:2010, EN 1992-1-2:2004+AC:2008 and Annex B 2 and B 3.
- The actual position of the reinforcement in the existing structure shall be determined on the basis of the construction documentation and taken into account when designing.

Installation:

- Dry or wet concrete. It must not be installed in flooded holes.
- Overhead installation allowed.
- Hole drilling by hammer drill (HD), hollow drill (HDB) or compressed air drill mode (CD).
- The installation of post-installed rebar resp. tension anchors shall be done only by suitable trained installer and under supervision on site; the conditions under which an installer may be considered as suitable trained and the conditions for supervision on site are up to the Member States in which the installation is done.
- Check the position of the existing rebars (if the position of existing rebars is not known, it shall be determined using a rebar detector suitable for this purpose as well as on the basis of the construction documentation and then marked on the building component for the overlap joint).

B+BTec Injection System BIS-V for rebar connection	**Annex B 1**
Intended use Specifications	

Figure B1: General construction rules for post-installed rebars

- Only tension forces in the axis of the rebar may be transmitted.
- The transfer of shear forces between new concrete and existing structure shall be designed additionally according to EN 1992-1-1:2004+AC:2010.
- The joints for concreting must be roughened to at least such an extent that aggregate protrude.



1) If the clear distance between lapped bars exceeds 4ϕ but at least 50 mm, then the lap length shall be increased by the difference between the clear bar distance and 4ϕ but at least 50 mm.

The following applies to Figure B1:

c	concrete cover of post-installed rebar
c_1	concrete cover at end-face of existing rebar
c_{min}	minimum concrete cover according to Table B1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2
ϕ	diameter of post-installed rebar
l_0	lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3
l_v	effective embedment depth, $\geq l_0 + c_1$
d_0	nominal drill bit diameter, see Annex B 5

B+BTec Injection System BIS-V for rebar connection	**Annex B 2**
Intended use General construction rules for post-installed rebars	

Figure B2: General construction rules for tension anchors ZA

- The length of the bonded-in thread may be not be accounted as anchorage.
- Only tension forces in the direction of the bar axis may be transmitted by the tension anchor ZA.
- The tension force must be transferred via an overlap joint to the reinforcement in the building part.
- The transfer of shear forces shall be ensured by appropriate additional measures, e.g shear lugs or by anchors with an European technical assessment.
- In the anchor plate, the holes for the tension anchors shall be executed as elongated holes with axis in the direction of the shear force.



1) If the clear distance between lapped bars exceeds 4ϕ but at least 50 mm, then the lap length shall be increased by the difference between the clear bar distance and 4ϕ but at least 50 mm.

The following applies to Figure B2:

c	concrete cover of tension anchor ZA
c_1	concrete cover at end-face of existing rebar
c_{min}	minimum concrete cover according to Table B1 and to EN 1992-1-1:2004+AC:2010, Section 4.4.1.2
ϕ	diameter of tension anchor
l_0	lap length, according to EN 1992-1-1:2004+AC:2010, Section 8.7.3
l_v	effective embedment depth
l_e	Length of bonded thread
$l_{e,ges}$	overall embedment depth, ≥ l_0+c_2
d_0	nominal drill bit diameter, see Annex B 5

B+BTec Injection System BIS-V for rebar connection	**Annex B 3**
Intended use General construction rules for tension anchors ZA	

Deutsches Institut für Bautechnik DIBt

Table B1: Minimum concrete cover c_{min} [1)] of post-installed rebar and tie rod ZA depending of drilling method

Drilling method	Rebar diameter	Without drilling aid	With drilling aid	
Hammer drilling (HD) Hammer drilling with hollow drill (HDB)	< 25 mm	30 mm + 0,06 · l_v ≥ 2 ϕ	30 mm + 0,02 · l_v ≥ 2 ϕ	
	≥ 25 mm	40 mm + 0,06 · l_v ≥ 2 ϕ	40 mm + 0,02 · l_v ≥ 2 ϕ	
Compressed air drilling (CD)	< 25 mm	50 mm + 0,08 · l_v	50 mm + 0,02 · l_v	
	≥ 25 mm	60 mm + 0,08 · l_v ≥ 2 ϕ	60 mm + 0,02 · l_v ≥ 2 ϕ	

1) see Annex B 2, Figure B1 and Annex B 3, Figure B2
Comments: The minimum concrete cover acc. EN 1992-1-1:2004+AC:2010 must be observed.

Table B2: Dispensing tools

Cartridge type/size	Hand tool		Pneumatic tool
Coaxial cartridges and foil tube cartridges 150, 165, 280, 300 up to 333 ml	 e.g. Type H297 / H244C		 e.g. Type TS 492 X
Coaxial cartridges 380 up to 420 ml	 e.g. Type CCM 380/10	 e.g. Type H 285 or H244C	 e.g. Type TS 485 LX
Side-by-side cartridges 235, 345 ml	 e.g. Type CBM 330A	 e.g. Type H 260	 e.g. Type TS 477 LX
Side-by-side cartridge 825 ml	-	-	 e.g. Type TS 498X

All cartridges could also be extruded by a battery tool.

B+BTec Injection System BIS-V for rebar connection	Annex B 4
Intended use Minimum concrete cover Dispensing tools	

Deutsches Institut für Bautechnik DIBt

Table B3: Brushes, piston plugs, max anchorage depth and mixer extension, hollow drill bit system (HDB), hammer (HD) and compressed air (CD) drilling

Bar size - ϕ	Tension Anchor - ϕ	Drill bit - Ø		d_b Brush - Ø	$d_{b,min}$ min. Brush - Ø	Piston plug	Cartridge: All sizes				Cartridge: 825 ml	
							Hand or battery tool		Pneumatic tool		Pneumatic tool	
		HD HDB	CD				$l_{v,max}$	Mixer extension	$l_{v,max}$	Mixer extension	$l_{v,max}$	Mixer extension
[mm]	[mm]	[mm]		[mm]	[mm]		[mm]		[mm]		[mm]	
8	-	10	-	12	10,5	-	250	VL10/0,75 or VL16/1,8	250	VL10/0,75 or VL16/1,8	250	VL10/0,75 or VL16/1,8
	-			14	12,5	-	700		800		800	
10	-	12	-				250		250		250	
	-			16	14,5	VS14	700		1000		1000	
12	ZA-M12	14	-				250		250		250	
		16		18	16,5	VS16	700		1000		1200	VL16/1,8
14	-	18		20	18,5	VS18					1400	
16	ZA-M16	20		22	20,5	VS20					1600	
20	ZA-M20	25	-	27	25,5	VS25	500		700		2000	
		-	26	28	26,5	VS25						
22	-	28		30	28,5	VS28			500		1000	
24/25	ZA-M24	32		34	32,5	VS32						
28	-	35		37	35,5	VS35						
32	-	40		41,5	40,5	VS40						

Cleaning and installation tools

Hand pump
(Volume 750 ml, $h_0 \leq 10\ d_s$, $d_0 \leq 20$mm)

Manual slide valve
(min 6 bar)

Brush

Piston Plug VS

Brush extension RBL

B+BTec Injection System BIS-V for rebar connection	Annex B 5
Intended Use Parameter brushes, piston plugs, max anchorage depth and mixer extension Cleaning and installation tools	

Deutsches Institut für Bautechnik DIBt

Table B4: Working time and curing time

Temperature in base material			Maximum working time	Minimum curing time[1)]
T			t_{work}	t_{cure}
- 10 °C	up to	- 6 °C	90 min[2)]	24 h
- 5 °C	up to	- 1 °C	90 min[3)]	14 h
0 °C	up to	+ 4 °C	45 min[3)]	7 h
+ 5 °C	up to	+ 9 °C	25 min[3)]	2 h
+ 10 °C	up to	+ 19 °C	15 min[3)]	80 min
+ 20 °C	up to	+ 24 °C	6 min[3)]	45 min
+ 25 °C	up to	+ 29 °C	4 min[3)]	25 min
+ 30 °C	up to	+ 40 °C	2,5 min[4)]	15 min
Cartridge temperature			+5°C up to +40°C	

1) The minimum curing time is only valid for dry base material.
In wet base material the curing time must be doubled.
2) Cartridge temperature must be at least +15°C
3) Cartridge temperature must be between +5°C and +25°C
4) Cartridge temperature must be below +20°C

B+BTec Injection System BIS-V for rebar connection

Intended Use
Working and curing time

Annex B 6

Deutsches Institut für Bautechnik DIBt

Installation instructions

Attention: Before drilling, remove carbonated concrete and clean contact areas (see Annex B1)
In case of aborted drill hole: the drill hole shall be filled with mortar.

Drilling of the bore hole



1a. **Hammer drilling (HD) / Compressed air drilling (CD)**
Drill a hole to the required embedment depth.
Drill bit diameter according to Table B3.
Proceed with Step 2 (MAC or CAC).



1b. **Hollow drill bit system (HDB)**
Drill a hole to the required embedment depth.
Drill bit diameter according to Table B3.
Proceed with Step 2 (MAC or CAC).

Manual Air Cleaning (MAC)

for drill hole diameter $d_0 \leq 20$mm and drill hole depth $h_0 \leq 10\phi$ with drilling method HD, HDB and CD



Attention! Standing water in the bore hole must be removed before cleaning.
2a. Blow the bore hole clean minimum 4x from the bottom or back by hand pump (Annex B 5).



2b. Brush the bore hole minimum 4x with brush according to Table B3 over the entire embedment depth in a twisting motion (if necessary, a brush extension RBL shall be used).



2c. Finally blow the bore hole clean minimum 4x from the bottom or back by hand pump (Annex B 5).

B+BTec Injection System BIS-V for rebar connection	**Annex B 7**
Intended Use Installation instruction	

Deutsches Institut für Bautechnik DIBt

Installation instructions (continuation)

Compressed Air Cleaning (CAC):
All diameter with drilling method HD, HDB and CD



Attention! Standing water in the bore hole must be removed before cleaning.

2a. Blow the bore hole clean minimum 4x with compressed air (min. 6 bar) (Annex B 5) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)



2b. Brush the bore hole minimum 4x with brush according to Table B3 over the entire embedment depth in a twisting motion (If necessary, a brush extension RBL shall be used.).



2c. Finally blow the bore hole clean minimum 4x with compressed air (min. 6 bar) (Annex B 5) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.).

Protect cleaned bore hole against re-contamination in an appropriate way. If necessary, repeat cleaning process directly before dispensing the mortar. In-flowing water must not contaminate the bore hole again.



3. Screw on static-mixing nozzle SM-14W or PM-19E, and load the cartridge into an appropriate dispensing tool. Cut off the foil tube clip before use.
For every working interruption longer than the maximum working time t_{work} (Annex B 6) as well as for new cartridges, a new static-mixer shall be used.



3a. In case of using the mixer extension VL16/1,8 cut off the tip of the mixer nozzle PM-19E at position „X“.



4. Mark embedment depth on the reinforcing bar.
The reinforcing bar shall be free of dirt, grease, oil or other foreign material.

B+BTec Injection System BIS-V for rebar connection	**Annex B 8**
Intended Use Installation instruction (continuation)	

Deutsches Institut für Bautechnik DIBt

Installation instructions (continuation)

5. Mark mixer nozzle and extension with mortar level mark l_m and anchorage depth l_v resp. $l_{e,ges}$
Quick estimation: $l_m = 1/3 \cdot l_v$
Optimum mortar volume:

$$l_m = l_v \text{ bzw. } l_{e,ges} \cdot \left(1{,}2 \cdot \frac{\phi^2}{d_0^2} - 0{,}2\right)$$





6. Not proper mixed mortar is not sufficient for fastening.
Dispense and discard mortar until an uniform grey colour is shown, at least 3 full strokes. For foil tube cartridges it must be discarded a minimum of 6 full strokes.



7. Piston plugs VS and mixer nozzle extensions VL shall be used according to Table B3.
Assemble mixing nozzle, mixer extension and piston plug before injecting mortar.



8a. **Injecting mortar without piston plug VS:**
Starting at bottom of the hole and fill the hole with adhesive until the mortar level mark l_m is visible. (If necessary, a mixer nozzle extension shall be used.)
Slowly withdraw of the static mixing nozzle avoid creating air pockets
Observe the temperature related working time t_{work} (Annex B 6).



8b. **Injecting mortar with piston plug VS:**
Insert piston plug to bottom of the hole and fill the hole with mortar until mortar level mark l_m is visible. (If necessary, a mixer nozzle extension shall be used.)
During injection the piston plug is pushed out of the bore hole by the back pressure of the mortar.
Observe the temperature related working time t_{work} (Annex B 6).



9. Insert the reinforcing bar while turning slightly up to the embedment mark.

B+BTec Injection System BIS-V for rebar connection	**Annex B 9**
Intended Use Installation instruction (continuation)	

Deutsches Institut für Bautechnik DIBt

Installation instructions (continuation)



10. Annular gap between reinforcing bar and base material must be completely filled with mortar. Otherwise, the installation must be repeated starting from step 8 before the maximum working time t_{work} has expired.



11. For application in vertical upwards direction the reinforcing bar shall be fixed (e.g. wedges).



12. Temperature related curing time t_{cure} (Annex B 6) must be observed.
The full load to the reinforcing bar may be applied after the full curing time t_{cure} has elapsed.

B+BTec Injection System BIS-V for rebar connection	**Annex B 10**
Intended Use Installation instruction (continuation)	

Deutsches Institut für Bautechnik DIBt

Table C1: Characteristic tension resistance for tension anchor ZA

Tension Anchor			M12	M16	M20	M24
Steel, zinc plated (ZA vz)						
Characteristic tension resistance	$N_{Rk,s}$	[kN]	67	125	196	282
Partial factor	$\gamma_{Ms,N}$	[-]	1,4			
Stainless Steel (ZA A4 or ZA HCR)						
Characteristic tension resistance	$N_{Rk,s}$	[kN]	67	125	171	247
Partial factor	$\gamma_{Ms,N}$	[-]	1,4		1,3	1,4

Minimum anchorage length and minimum lap length under static or quasi-static loading

The minimum anchorage length $l_{b,min}$ and the minimum lap length $l_{0,min}$ according to EN 1992-1-1:2004+AC:2010 ($l_{b,min}$ acc. to Eq. 8.6 and Eq. 8.7 and $l_{0,min}$ acc. to Eq. 8.11) shall be multiply by the amplification factor α_{lb} according to Table C2.

Table C2: Amplification factor α_{lb} related to concrete class and drilling method

Concrete class	Drilling method	Bar size	Amplification factor α_{lb}
C12/15 to C50/60	all drilling methods	8 mm to 32 mm ZA-M12 to ZA-M24	1,0

Table C3: Reduction factor k_b for all drilling methods

Rebar	Concrete class								
ϕ	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 25 mm ZA-M12 to ZA-M24	1,0								
28 to 32 mm	1,0							0,92	0,86

Table C4: Design values of the ultimate bond stress $f_{bd,PIR}$ in N/mm² for all drilling methods and for good conditions

$f_{bd,PIR} = k_b \cdot f_{bd}$

with

f_{bd}: Design value of the ultimate bond stress in N/mm² considering the concrete classes, the rebar diameter, the drilling method for good bond condition (for all other bond conditions multiply the values by η_1 =0.7) and recommended partial factor γ_c = 1,5 according to EN 1992-1-1:2004+AC:2010.

k_b: Reduction factor according to Table C3

Rebar	Concrete class								
ϕ	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
8 to 25 mm ZA-M12 to ZA-M24	1,6	2,0	2,3	2,7	3,0	3,4	3,7	4,0	4,3
28 to 32 mm	1,6	2,0	2,3	2,7	3,0	3,4	3,7	3,7	3,7

B+BTec Injection System BIS-V for rebar connection

Performances
Characteristic tension resistance for tension anchor, Minimum anchorage length and minimum lap length, Amplification factor, Reduction factor and Design values of ultimate bond resistance

Annex C 1

Design value of the ultimate bond stress $f_{bd,fi}$ at increased temperature for concrete classes C12/15 to C50/60, (all drilling methods):

The design value of the bond stress $f_{bd,fi}$ at increased temperature has to be calculated by the following equation:

For working life 50 years: $f_{bd,fi} = k_{fi}(\theta) \cdot f_{bd,PIR} \cdot \gamma_c / \gamma_{M,fi}$

mit: $\theta \leq 243°C$: $k_{fi}(\theta) = 18{,}88 \cdot e^{(\theta \cdot -0{,}016)} / (f_{bd,PIR} \cdot 4{,}3) \leq 1{,}0$

$\theta > 243°C$: $k_{fi}(\theta) = 0$

$f_{bd,fi}$ Design value of the ultimate bond stress at increased temperature in N/mm²

θ Temperature in °C in the mortar layer.

$k_{fi}(\theta)$ Reduction factor at increased temperature.

$f_{bd,PIR}$ Design value of the bond stress in N/mm² in cold condition according to Table C4 considering the concrete classes, the rebar diameter, the drilling method and the bond conditions according to EN 1992-1-1:2004+AC:2010.

γ_c = 1,5 recommended partial factor according to EN 1992-1-1:2004+AC:2010

$\gamma_{M,fi}$ = 1,0 recommended partial factor according to EN 1992-1-2:2004+AC:2008

For evidence at increased temperature the anchorage length shall be calculated according to EN 1992-1-1:2004+AC:2010 Equation 8.3 using the temperature-dependent design value of ultimate bond stress $f_{bd,fi}$.

Example graph of Reduction factor $k_{fi}(\theta)$ for concrete classes C20/25 for good bond conditions:



B+BTec Injection System BIS-V for rebar connection	**Annex C 2**
Performances Design value of ultimate bond stress at increased temperature	

Deutsches Institut für Bautechnik DIBt

Table C5: Characteristic tension resistance for tension anchor ZA under fire exposure

Tension Anchor				**M12**	**M16**	**M20**	**M24**
Steel, zinc plated (ZA vz)							
Characteristic tension resistance	R30	$N_{Rk,s,fi}$	[kN]	2,3	4,0	6,3	9,0
	R60			1,7	3,0	4,7	6,8
	R90			1,5	2,6	4,1	5,9
	R120			1,1	2,0	3,1	4,5
Stainless Steel (ZA A4 or ZA HCR)							
Characteristic tension resistance	R30	$N_{Rk,s,fi}$	[kN]	3,4	6,0	9,4	13,6
	R60			2,8	5,0	7,9	11,3
	R90			2,3	4,0	6,3	9,0
	R120			1,8	3,2	5,0	7,2

B+BTec Injection System BIS-V for rebar connection

Performances
Characteristic tension resistance for tension anchor ZA under fire exposure

Annex C 3