Deutsches Institut für Bautechnik DIBt

Member of EOTA
www.eota.eu

Public-law institution jointly founded by the federal states and the Federation

European Technical Assessment Body for construction products

Designated according to Article 29 of Regulation (EU) No 305/2011 and member of EOTA (European Organisation for Technical Assessment)

European Technical Assessment

ETA-11/0449 of 8 August 2025

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:	Deutsches Institut für Bautechnik
Trade name of the construction product	Mapei Injection System Mapefix VE SF or VE SF CC for concrete
Product family to which the construction product belongs	Bonded fasteners and bonded expansion fasteners for use in concrete
Manufacturer	Mapei S.p.A. via Cafiero, 22 20158 MILANO (MI) ITALIEN
Manufacturing plant	Mapei S.p.A., Plant1 Germany
This European Technical Assessment contains	34 pages including 3 annexes which form an integral part of this assessment
This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of	EAD 330499-02-0601, Edition 12/2023
This version replaces	ETA-11/0449 issued on 4 December 2017

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The "Mapei Injection system Mapefix VE SF or VE SF CC for concrete" is a bonded anchor consisting of a cartridge with injection mortar Mapefix VE SF or Mapefix VE SF CC and a steel element. The steel element consists of a commercial threaded rod with washer and hexagon nut in the range of M8 to M30 or reinforcing bar in the range of ∅ 8 to ∅ 32 mm or an internal threaded anchor rod IG-M6 to IG-M20.
The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the fastener is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the fastener of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex B 3, C 1, C 2, C 3, C 5 and C 7
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1, C 4, C 6 and C 8
Displacements (static and quasi-static loading)	See Annex C 9 to C 11
Characteristic resistance for seismic performance categories C1	See Annex C 12 and C 13
Characteristic resistance and displacements for seismic performance categories C2	No performance assessed

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	See Annex C 14 to C 16

3.3 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD 330499-02-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 8 August 2025 by Deutsches Institut für Bautechnik

Dipl.-Ing. Beatrix Wittstock
Head of Section

beglaubigt:
Baderschneider

Installation threaded rod M8 up to M30

prepositioned installation or
push through installation (annular gap filled with mortar)



Installation reinforcing bar Ø8 up to Ø32



Installation internal threaded anchor rod IG-M6 up to IG-M20



t_{fix}	=	thickness of fixture	h_0	=	nominal drill hole diameter
h_{ef}	=	effective embedment depth	l_{IG}	=	thread engagement length
h_{min}	=	minum thickness of member			

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Product description
Installed condition

Annex A 1

Cartridge system

Coaxial Cartridge:
150 ml, 280 ml, 300 ml up to 333 ml and 380 ml up to 420 ml



Side-by-Side Cartridge:
235 ml, 345 ml up to 360 ml and 825 ml



Foil tube Cartridge:
165 ml and 300 ml



Static mixer SM-14W



Static mixer



Piston plug VS and mixer extension VL

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex A 2**
Product description Injection system	

Threaded rod M8 up to M30 with washer and hexagon nut



Commercial standard rod with:
- Materials, dimensions and mechanical properties acc. to Table A1
- Inspection certificate 3.1 acc. to EN 10204:2004. The document shall be stored.
- Marking of embedment depth

For hot dip galvanized elements, the requirements with regards to the combination of nuts and rods according to EN ISO 10684:2004+AC:2009 Annex F shall be considered.

Internal threaded rod IG-M6 to IG-M20





Producer marking: e.g. ◇I M8

I	Marking Internal thread (optional)
◇	Mark
M8	Thread size (Internal thread)
A4	additional mark for stainless steel
HCR	additional mark for high-corrosion resistance steel
-8	additional mark for property class 8.8

Filling washer VFS



Mixer reduction nozzle MR

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Product description
Threaded rod; Internal threaded rod
Filling washer; Mixer reduction nozzle

Annex A 3

Table A1: Materials

Part	Designation	Material				
Steel, zinc plated (Steel acc. to EN ISO 683-4:2018 or EN 10263:2017) - zinc plated ≥ 5 µm acc. to EN ISO 4042:2022 or - hot-dip galvanised ≥ 40 µm acc. to EN ISO 1461:2022 and EN ISO 10684:2004+AC:2009 or - sherardized ≥ 45 µm acc. to EN ISO 17668:2016						
1	Threaded rod	Property class		Characteristic steel ultimate tensile strength	Characteristic steel yield strength	Elongation at fracture
		acc. to EN ISO 898-1:2013	4.6	f_{uk} = 400 N/mm²	f_{yk} = 240 N/mm²	A_5 > 8%
			4.8	f_{uk} = 400 N/mm²	f_{yk} = 320 N/mm²	A_5 > 8%
			5.6	f_{uk} = 500 N/mm²	f_{yk} = 300 N/mm²	A_5 > 8%
			5.8	f_{uk} = 500 N/mm²	f_{yk} = 400 N/mm²	A_5 > 8%
			8.8	f_{uk} = 800 N/mm²	f_{yk} = 640 N/mm²	A_5 ≥ 8%
2	Hexagon nut	acc. to EN ISO 898-2:2022	4	for anchor rod class 4.6 or 4.8		
			5	for anchor rod class 5.6 or 5.8		
			8	for anchor rod class 8.8		
3a	Washer	Steel, zinc plated, hot-dip galvanised or sherardized (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 or EN ISO 7094:2000)				
3b	Filling washer	Steel, zinc plated, hot-dip galvanised or sherardized				
4	Internal threaded anchor rod	Property class		Characteristic steel ultimate tensile strength	Characteristic steel yield strength	Elongation at fracture
		acc. to EN ISO 898-1:2013	5.8	f_{uk} = 500 N/mm²	f_{yk} = 400 N/mm²	A_5 > 8%
			8.8	f_{uk} = 800 N/mm²	f_{yk} = 640 N/mm²	A_5 > 8%
Stainless steel A2 (Material 1.4301 / 1.4307 / 1.4311 / 1.4567 or 1.4541, acc. to EN 10088-1:2023) **Stainless steel A4** (Material 1.4401 / 1.4404 / 1.4571 / 1.4362 or 1.4578, acc. to EN 10088-1:2023) **High corrosion resistance steel** (Material 1.4529 or 1.4565, acc. to EN 10088-1:2023)						
1	Threaded rod[1)3)]	Property class		Characteristic steel ultimate tensile strength	Characteristic steel yield strength	Elongation at fracture
		acc. to EN ISO 3506-1:2020	50	f_{uk} = 500 N/mm²	f_{yk} = 210 N/mm²	A_5 ≥ 8%
			70	f_{uk} = 700 N/mm²	f_{yk} = 450 N/mm²	A_5 ≥ 8%
			80	f_{uk} = 800 N/mm²	f_{yk} = 600 N/mm²	A_5 ≥ 8%
2	Hexagon nut[1)3)]	acc. to EN ISO 3506-1:2020	50	for anchor rod class 50		
			70	for anchor rod class 70		
			80	for anchor rod class 80		
3a	Washer	A2: Material 1.4301 / 1.4307 / 1.4311 / 1.4567 or 1.4541, acc. to EN 10088-1:2023 A4: Material 1.4401 / 1.4404 / 1.4571 / 1.4362 or 1.4578, acc. to EN 10088-1:2023 HCR: Material 1.4529 or 1.4565, acc. to EN 10088-1:2023 (e.g.: EN ISO 887:2006, EN ISO 7089:2000, EN ISO 7093:2000 or EN ISO 7094:2000)				
3b	Filling washer	Stainless steel A4, High corrosion resistance steel				
4	Internal threaded anchor rod[1)2)]	Property class		Characteristic steel ultimate tensile strength	Characteristic steel yield strength	Elongation at fracture
		acc. to EN ISO 3506-1:2020	50	f_{uk} = 500 N/mm²	f_{yk} = 210 N/mm²	A_5 > 8%
			70	f_{uk} = 700 N/mm²	f_{yk} = 450 N/mm²	A_5 > 8%

1) Property class 70 or 80 for anchor rods and hexagon nuts up to M24 and Internal threaded anchor rods up to IG-M16
2) for IG-M20 only property class 50
3) Property class 80 only for stainless steel A4 and HCR

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Product description
Materials threaded rod and internal threaded rod

Annex A 4

Reinforcing bar: ø8 up to ø32



Minimum value of related rip area $f_{R,min}$ according to EN 1992-1-1:2004+AC:2010
Rib height of the bar shall be in the range $0{,}05d \leq h_{rib} \leq 0{,}07d$
(d: Nominal diameter of the bar; h_{rib}: Rib height of the bar)

Table A2: Materials Reinforcing bar

Part	Designation	Material
Rebar		
1	Reinforcing steel according to EN 1992 1 1:2004+AC:2010, Annex C	Bars and rebars from ring class B or C f_{yk} and k according to NDP or NCI according to EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Product description
Materials reinforcing bar

Annex A 5

Specification of the intended use

Fasteners subject to (Static and quasi-static loads):

	Working life 50 years		Working life 100 years	
Base material	uncracked concrete	cracked concrete	uncracked concrete	cracked concrete
HD: Hammer drilling HDB: Hammer drilling with hollow drill bit CD: Compressed air drilling	M8 to M30, ∅8 to ∅32, IG-M6 to IG-M20		No performance assessed	
Temperature Range	I: - 40°C to +40°C[1)] II: - 40°C to +80°C[2)] III: - 40°C to +120°C[3)]		No performance assessed	

Fasteners subject to (seismic action):

	Performance Category C1	Performance Category C2
Base material	Cracked and uncracked concrete	
HD: Hammer drilling HDB: Hammer drilling with hollow drill bit CD: Compressed air drilling	M8 to M30, Ø8 to Ø32	No performance assessed
Temperature Range	I: - 40°C to +40°C[1)] II: - 40°C to +80°C[2)] III: - 40°C to +120°C[3)]	No performance assessed

Fasteners subject to (fire exposure):

Base material	Cracked and uncracked concrete
HD: Hammer drilling HDB: Hammer drilling with hollow drill bit CD: Compressed air drilling	M8 to M30, ∅8 to ∅32, IG-M6 to IG-M20
Temperature Range:	I: - 40°C to +40°C[1)] II: - 40°C to +80°C[2)] III: - 40°C to +120°C[3)]

1) (max. long-term temperature +24°C and max. short-term temperature +40°C)
2) (max. long-term temperature +50°C and max. short-term temperature +80°C)
3) (max. long-term temperature +72°C and max. short-term temperature +120°C)

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex B 1**
Intended Use Specifications	

Base material:

- Compacted, reinforced or unreinforced normal weight concrete without fibres according to EN 206:2013 + A2:2021.
- Strength classes C20/25 to C50/60 according to EN 206:2013 + A2:2021.

Use conditions (Enviromental conditions):

- Structures subject to dry internal conditions (all materials).
- For all other conditions according to EN 1993-1-4:2006 + A1:2015 corresponding to corrosion resistance class:
  - Stainless steel Stahl A2 according to Annex A 4, Table A1: CRC II
  - Stainless steel Stahl A4 according to Annex A 4, Table A1: CRC III
  - High corrosion resistance steel HCR according to Annex A 4, Table A1: CRC V

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the fastener is indicated on the design drawings (e.g. position of the fastener relative to reinforcement or to supports, etc.).
- Fasteners are designed under the responsibility of an engineer experienced in fasteners and concrete work.
- The fasteners are designed in accordance to EN 1992-4:2018 and Technical Report TR 055, Edition February 2018

Installation:

- Dry, wet concrete or flooded bore holes (not sea-water).
- Hole drilling by hammer (HD), hollow (HDB) or compressed air (CD).
- Overhead installation allowed.
- Fastener installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- Installation temperature in concrete:
  Mapefix VE SF: -10°C up to +40°C for the standard variation of temperature after installation.
  Mapefix VE SF CC: -20°C up to +10°C for the standard variation of temperature after installation.

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex B 2**
Intended Use Specifications (Continued)	

Table B1: Installation parameters for threaded rod

Threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Diameter of element	$d = d_{nom}$	[mm]	8	10	12	16	20	24	27	30
Nominal drill hole diameter	d_0	[mm]	10	12	14	18	24	28	32	35
Effective embedment depth	$h_{ef,min}$	[mm]	60	60	70	80	90	96	108	120
	$h_{ef,max}$	[mm]	160	200	240	320	400	480	540	600
Diameter of clearance hole in the fixture	Prepositioned installation $d_f \leq$	[mm]	9	12	14	18	22	26	30	33
	Push through installation d_f	[mm]	12	14	16	20	24	30	33	40
Maximum installation torque	max T_{inst}	[Nm]	10	20	40	60	100	170	250	300
Minimum thickness of member	h_{min}	[mm]	h_{ef} + 30 mm ≥ 100 mm			$h_{ef} + 2d_0$				
Minimum spacing	s_{min}	[mm]	40	50	60	80	100	120	135	150
Minimum edge distance	c_{min}	[mm]	40	50	60	80	100	120	135	150

Table B2: Installation parameters for reinforcing bar

Reinforcing bar			Ø 8[1)]	Ø 10[1)]	Ø 12[1)]	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
Diameter of element	$d = d_{nom}$	[mm]	8	10	12	14	16	20	25	28	32
Nominal drill hole diameter	d_0	[mm]	10 | 12	12 | 14	14 | 16	18	20	25	32	35	40
Effective embedment depth	$h_{ef,min}$	[mm]	60	60	70	75	80	90	100	112	128
	$h_{ef,max}$	[mm]	160	200	240	280	320	400	500	560	640
Minimum thickness of member	h_{min}	[mm]	h_{ef} + 30 mm ≥ 100 mm			$h_{ef} + 2d_0$					
Minimum spacing	s_{min}	[mm]	40	50	60	70	80	100	125	140	160
Minimum edge distance	c_{min}	[mm]	40	50	60	70	80	100	125	140	160

1) both nominal drill hole diameter can be used

Table B3: Installation parameters for Internal threaded anchor rod

Internal threaded anchor rod			IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Internal diameter of anchor rod	d_2	[mm]	6	8	10	12	16	20
Outer diameter of anchor rod[1)]	$d = d_{nom}$	[mm]	10	12	16	20	24	30
Nominal drill hole diameter	d_0	[mm]	12	14	18	24	28	35
Effective embedment depth	$h_{ef,min}$	[mm]	60	70	80	90	96	120
	$h_{ef,max}$	[mm]	200	240	320	400	480	600
Diameter of clearance hole in the fixture	$d_f \leq$	[mm]	7	9	12	14	18	22
Maximum installation torque	max T_{inst}	[Nm]	10	10	20	40	60	100
Thread engagement length min/max	l_{IG}	[mm]	8/20	8/20	10/25	12/30	16/32	20/40
Minimum thickness of member	h_{min}	[mm]	h_{ef} + 30 mm ≥ 100 mm		$h_{ef} + 2d_0$			
Minimum spacing	s_{min}	[mm]	50	60	80	100	120	150
Minimum edge distance	c_{min}	[mm]	50	60	80	100	120	150

1) With metric threads according to EN 1993-1-8:2005+AC:2009

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Intended Use
Installation parameters

Annex B 3

Table B4: Parameter cleaning and installation tools





Threaded Rod	Re-inforcing bar	Internal threaded anchor rod	d_0 Drill bit - ∅ HD, HDB, CD	d_b Brush - ∅		$d_{b,min}$ min. Brush - ∅	Piston plug	Installation direction and use of piston plug		
[mm]	[mm]	[mm]	[mm]		[mm]	[mm]		⬇	➡	⬆
M8	8		10	RBT10	12	10,5	No plug required			
M10	8 / 10	IG-M6	12	RBT12	14	12,5				
M12	10 / 12	IG-M8	14	RBT14	16	14,5				
	12		16	RBT16	18	16,5				
M16	14	IG-M10	18	RBT18	20	18,5	VS18	h_{ef} > 250 mm	h_{ef} > 250 mm	all
	16		20	RBT20	22	20,5	VS20			
M20		IG-M12	24	RBT24	26	24,5	VS24			
	20		25	RBT25	27	25,5	VS25			
M24		IG-M16	28	RBT28	30	28,5	VS28			
M27	25		32	RBT32	34	32,5	VS32			
M30	28	IG-M20	35	RBT35	37	35,5	VS35			
	32		40	RBT40	41,5	40,5	VS40			

Cleaning and installation tools

Hand pump
(Volume 750 ml, $h_0 \leq 10\ d_s$, $d_0 \leq 20$mm)

Compressed air tool
(min 6 bar)

Brush RBT

Piston Plug VS

Brush extension RBL

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Intended Use
Cleaning and installation tools

Annex B 4

Table B5: Working time and curing time Mapefix VE SF

Temperature in base material			Maximum working time	Minimum curing time[1)]
T			t_{gel}	t_{cure}
- 10 °C	to	- 6 °C	90 min[2)]	24 h
- 5 °C	to	- 1 °C	90 min	14 h
0 °C	to	+ 4 °C	45 min	7 h
+ 5 °C	to	+ 9 °C	25 min	2 h
+ 10 °C	to	+ 19 °C	15 min	80 min
+ 20 °C	to	+ 29 °C	6 min	45 min
+ 30 °C	to	+ 34 °C	4 min	25 min
+ 35 °C	to	+ 39 °C	2 min	20 min
+40°C			1,5 min	15 min
Cartridge temperature			+5°C to +40°C	

1) The minimum curing time is only valid for dry base material.
In wet base material the curing time must be doubled.
2) Cartridge temperature must be at least +15°C

Table B6: Working time and curing time Mapefix VE SF CC

Temperature in base material			Maximum working time	Minimum curing time [1)]
T			t_{gel}	t_{cure}
- 20 °C	to	- 16 °C	75 min	24 h
- 15 °C	to	- 11 °C	55 min	16 h
- 10 °C	to	- 6 °C	35 min	10 h
- 5 °C	to	- 1 °C	20 min	5 h
0 °C	to	+ 4 °C	10 min	2,5 h
+ 5 °C	to	+ 9 °C	6 min	80 min
+ 10 °C			6 min	60 min
Cartridge temperature			-20°C to +10°C	

1) The minimum curing time is only valid for dry base material.
In wet base material the curing time must be doubled.

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Intended Use
Working time and curing time

Annex B 5

Installation instructions

Drilling of the bore hole



1a. **Hammer drilling (HD) / Compressed air drilling (CD)**
Drill a hole to the required embedment depth.
Drill bit diameter according to Table B1, B2 or B3.
Aborted drill holes shall be filled with mortar.
Proceed with Step 2 (CAC and MAC).



1b. **Hollow drill bit system (HDB)**
Drill a hole to the required embedment depth.
Drill bit diameter according to Table B1, B2 or B3.
Aborted drill holes shall be filled with mortar.
Proceed with Step 2 (CAC and MAC).

Attention! Standing water in the bore hole must be removed before cleaning

Manual Air Cleaning (MAC)
for bore hole diameter $d_0 \leq 20$mm and bore hole depth $h_0 \leq 10d_{nom}$ ($d_0 < 14$mm uncracked concrete only)
with drilling method HD, HDB and CD



2a. Blow the bore hole clean minimum 4x from the bottom or back by hand pump (Annex B 4).



2b. Brush the bore hole minimum 4x with brush RBT according to Table B4 over the entire embedment depth in a twisting motion. (If necessary, a brush extension RBL shall be used.)



2c. Finally blow the bore hole clean minimum 4x from the bottom or back by hand pump (Annex B 4).

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex B 6**
Intended Use Installation instructions	

Installation instructions (continuation)

Compressed Air Cleaning (CAC):
All diameter with drilling method HD, HDB and CD



2a. Blow the bore hole clean minimum 4x with compressed air (min. 6 bar) (Annex B 4) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)



2b. Brush the bore hole minimum 4x with brush RBT according to Table B4 over the entire embedment depth in a twisting motion. (If necessary, a brush extension RBL shall be used.)



2c. Finally blow the bore hole clean minimum 4x with compressed air (min. 6 bar) (Annex B 4) over the entire embedment depth until return air stream is free of noticeable dust. (If necessary, an extension shall be used.)

Cleaned bore hole has to be protected against re-contamination in an appropriate way,
If necessary, repeat cleaning process directly before dispensing the mortar. In-flowing water must not contaminate the bore hole again.



3. Screw on static-mixing nozzle SM-14W/ and load the cartridge into an appropriate dispensing tool. With foil tube cartridges cut off the foil tube clip before use.
For every working interruption longer than the maximum working time t_{work} (Annex B 5) as well as for new cartridges, a new static-mixer shall be used.



4. Mark embedment depth on the anchor rod.
The anchor rod shall be free of dirt, grease, oil or other foreign material.

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex B 7**
Intended Use Installation instructions (continuation)	

Installation instructions (continuation)



5. Not proper mixed mortar is not sufficient for fastening.
Dispense and discard mortar until an uniform grey or red colour is shown (at least 3 full strokes, for foil tube cartridges at least 6 full storkes).



6. Piston plugs VS and mixer nozzle extensions VL shall be used according to Table B4 for the following applications:
- Horizontal and vertical downwards direction: Drill bit-Ø d_0 ≥ 18 mm and embedment depth h_{ef} > 250mm
- Vertical upwards direction: Drill bit-Ø d_0 ≥ 18 mm

Assemble mixing nozzle, mixer extension and piston plug before injecting mortar.



7a. **Injecting mortar without piston plug VS:**
Starting at bottom of the hole and fill the hole up to approximately two-thirds with adhesive. (If necessary, a mixer nozzle extension shall be used.)
Slowly withdraw of the static mixing nozzle avoid creating air pockets.
Observe the temperature related working time t_{work} (Annex B 5).



7b. **Injecting mortar with piston plug VS:**
Starting at bottom of the hole and fill the hole up to approximately two-thirds with adhesive. (If necessary, a mixer nozzle extension shall be used.)
During injection the piston plug is pushed out of the bore hole by the back pressure of the mortar.
Observe the temperature related working time t_{work} (Annex B 5). .



8. Insert the anchor rod while turning slightly up to the embedment mark.

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex B 8**
Intended Use Installation instructions (continuation)	

Installation instructions (continuation)



9. Annular gap between anchor rod and base material must be completely filled with mortar. In case of push through installation the annular gap in the fixture must be filled with mortar also.
Otherwise, the installation must be repeated starting from step 7 before the maximum working time t_{work} has expired.



10. For application in vertical upwards direction the anchor rod shall be fixed (e.g. wedges).



11. Temperature related curing time t_{cure} (Annex B 5) must be observed.
Do not move or load the fastener during curing time.



12. Install the fixture by using a calibrated torque wrench. Observe maximum installation torque (Table B1, B2 or B3).
In case of static requirements (e.g. seismic), fill the annular gab in the fixture with mortar (Annex A 3). Therefore replace the washer by the filling washer VFS and use the mixer reduction nozzle MR.

Mapei Injection System Mapefix VE SF or VE SF CC for concrete	**Annex B 9**
Intended Use Installation instructions (continuation)	

Table C1: Characteristic values for steel tension resistance and steel shear resistance of threaded rods

Threaded rod				M8	M10	M12	M16	M20	M24	M27	M30
	Cross section area	A_s	[mm²]	36,6	58	84,3	157	245	353	459	561
	Characteristic tension resistance, Steel failure [1]										
	Steel, Property class 4.6 and 4.8	$N_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63	98	141	184	224
	Steel, Property class 5.6 and 5.8	$N_{Rk,s}$	[kN]	18 (17)	29 (27)	42	78	122	176	230	280
	Steel, Property class 8.8	$N_{Rk,s}$	[kN]	29 (27)	46 (43)	67	125	196	282	368	449
	Stainless steel A2, A4 and HCR, class 50	$N_{Rk,s}$	[kN]	18	29	42	79	123	177	230	281
	Stainless steel A2, A4 and HCR, class 70	$N_{Rk,s}$	[kN]	26	41	59	110	171	247	-[3]	-[3]
	Stainless steel A4 and HCR, class 80	$N_{Rk,s}$	[kN]	29	46	67	126	196	282	-[3]	-[3]
	Characteristic tension resistance, Partial factor [2]										
	Steel, Property class 4.6 and 5.6	$\gamma_{Ms,N}$	[-]	2,0							
	Steel, Property class 4.8, 5.8 and 8.8	$\gamma_{Ms,N}$	[-]	1,5							
	Stainless steel A2, A4 and HCR, class 50	$\gamma_{Ms,N}$	[-]	2,86							
	Stainless steel A2, A4 and HCR, class 70	$\gamma_{Ms,N}$	[-]	1,87							
	Stainless steel A4 and HCR, class 80	$\gamma_{Ms,N}$	[-]	1,6							
	Characteristic shear resistance, Steel failure [1]										
Without lever arm	Steel, Property class 4.6 and 4.8	$V^0_{Rk,s}$	[kN]	9 (8)	14 (13)	20	38	59	85	110	135
Without lever arm	Steel, Property class 5.6 and 5.8	$V^0_{Rk,s}$	[kN]	11 (10)	17 (16)	25	47	74	106	138	168
Without lever arm	Steel, Property class 8.8	$V^0_{Rk,s}$	[kN]	15 (13)	23 (21)	34	63	98	141	184	224
Without lever arm	Stainless steel A2, A4 and HCR, class 50	$V^0_{Rk,s}$	[kN]	9	15	21	39	61	88	115	140
Without lever arm	Stainless steel A2, A4 and HCR, class 70	$V^0_{Rk,s}$	[kN]	13	20	30	55	86	124	-[3]	-[3]
Without lever arm	Stainless steel A4 and HCR, class 80	$V^0_{Rk,s}$	[kN]	15	23	34	63	98	141	-[3]	-[3]
With lever arm	Steel, Property class 4.6 and 4.8	$M^0_{Rk,s}$	[Nm]	15 (13)	30 (27)	52	133	260	449	666	900
With lever arm	Steel, Property class 5.6 and 5.8	$M^0_{Rk,s}$	[Nm]	19 (16)	37 (33)	65	166	324	560	833	1123
With lever arm	Steel, Property class 8.8	$M^0_{Rk,s}$	[Nm]	30 (26)	60 (53)	105	266	519	896	1333	1797
With lever arm	Stainless steel A2, A4 and HCR, class 50	$M^0_{Rk,s}$	[Nm]	19	37	66	167	325	561	832	1125
With lever arm	Stainless steel A2, A4 and HCR, class 70	$M^0_{Rk,s}$	[Nm]	26	52	92	232	454	784	-[3]	-[3]
With lever arm	Stainless steel A4 and HCR, class 80	$M^0_{Rk,s}$	[Nm]	30	59	105	266	519	896	-[3]	-[3]
	Characteristic shear resistance, Partial factor [2]										
	Steel, Property class 4.6 and 5.6	$\gamma_{Ms,V}$	[-]	1,67							
	Steel, Property class 4.8, 5.8 and 8.8	$\gamma_{Ms,V}$	[-]	1,25							
	Stainless steel A2, A4 and HCR, class 50	$\gamma_{Ms,V}$	[-]	2,38							
	Stainless steel A2, A4 and HCR, class 70	$\gamma_{Ms,V}$	[-]	1,56							
	Stainless steel A4 and HCR, class 80	$\gamma_{Ms,V}$	[-]	1,33							

[1] Values are only valid for the given stress area A_s. Values in brackets are valid for undersized threaded rods with smaller stress area A_s for hot-dip galvanised threaded rods according to EN ISO 10684:2004+AC:2009.
[2] in absence of national regulation
[3] Fastener type not part of the ETA

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values for steel tension resistance and steel shear resistance of threaded rods

Annex C 1

Table C2: Characteristic values of tension loads under static and quasi-static action

Fastener				All Anchor types and sizes
Concrete cone failure				
Uncracked concrete		$k_{ucr,N}$	[-]	11,0
Cracked concrete		$k_{cr,N}$	[-]	7,7
Edge distance		$c_{cr,N}$	[mm]	1,5 h_{ef}
Axial distance		$s_{cr,N}$	[mm]	2 $c_{cr,N}$
Splitting				
Edge distance	$h/h_{ef} \geq 2,0$	$c_{cr,sp}$	[mm]	1,0 h_{ef}
	$2,0 > h/h_{ef} > 1,3$			$2 \cdot h_{ef} \left(2,5 - \frac{h}{h_{ef}} \right)$
	$h/h_{ef} \leq 1,3$			2,4 h_{ef}
Axial distance		$s_{cr,sp}$	[mm]	2 $c_{cr,sp}$

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values for Concrete cone failure and Splitting with all kind of action

Annex C 2

Table C3: Characteristic values of tension loads under static and quasi-static action

Threaded rod					**M8**	**M10**	**M12**	**M16**	**M20**	**M24**	**M27**	**M30**
Steel failure												
Characteristic tension resistance			$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$ (or see Table C1)							
Partial factor			$\gamma_{Ms,N}$	[-]	see Table C1							
Combined pull-out and concrete failure												
Characteristic bond resistance in uncracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	10	12	12	12	12	11	10	9,0
	II: 80°C/50°C				7,5	9,0	9,0	9,0	9,0	8,5	7,5	6,5
	III: 120°C/72°C				5,5	6,5	6,5	6,5	6,5	6,5	5,5	5,0
	I: 40°C/24°C	flooded bore hole			7,5	8,5	8,5	8,5	No Performance Assessed			
	II: 80°C/50°C				5,5	6,5	6,5	6,5				
	III: 120°C/72°C				4,0	5,0	5,0	5,0				
Characteristic bond resistance in cracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	4,0	5,0	5,5	5,5	5,5	5,5	6,5	6,5
	II: 80°C/50°C				2,5	3,5	4,0	4,0	4,0	4,0	4,5	4,5
	III: 120°C/72°C				2,0	2,5	3,0	3,0	3,0	3,0	3,5	3,5
	I: 40°C/24°C	flooded bore hole			4,0	4,0	5,5	5,5	No Performance Assessed			
	II: 80°C/50°C				2,5	3,0	4,0	4,0				
	III: 120°C/72°C				2,0	2,5	3,0	3,0				
Reduktion factor ψ^0_{sus} in cracked and uncracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,73							
	II: 80°C/50°C				0,65							
	III: 120°C/72°C				0,57							
Increasing factors for concrete			ψ_c	[-]	$(f_{ck} / 20)^{0,11}$							
Characteristic bond resistance depending on the concrete strength class			$\tau_{Rk,ucr}$ =		$\psi_c \cdot \tau_{Rk,ucr}(C20/25)$							
			$\tau_{Rk,cr}$ =		$\psi_c \cdot \tau_{Rk,cr}(C20/25)$							
Concrete cone failure												
Relevant parameter					see Table C2							
Splitting												
Relevant parameter					see Table C2							
Installation factor												
for dry and wet concrete			γ_{inst}	[-]	1,0	1,2						
for flooded bore hole					1,4				No Performance Assessed			

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension loads under static and quasi-static action (Threaded rod)

Annex C 3

Table C4: Characteristic values of shear loads under static and quasi-static action

Threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Steel failure without lever arm										
Characteristic shear resistance Steel, strength class 4.6, 4.8, 5.6 and 5.8	$V^0_{Rk,s}$	[kN]	$0{,}6 \cdot A_s \cdot f_{uk}$ (or see Table C1)							
Characteristic shear resistance Steel, strength class 8.8 Stainless Steel A2, A4 and HCR, all classes	$V^0_{Rk,s}$	[kN]	$0{,}5 \cdot A_s \cdot f_{uk}$ (or see Table C1)							
Partial factor	$\gamma_{Ms,V}$	[-]	see Table C1							
Ductility factor	k_7	[-]	1,0							
Steel failure with lever arm										
Characteristic bending moment	$M^0_{Rk,s}$	[Nm]	$1{,}2 \cdot W_{el} \cdot f_{uk}$ (or see Table C1)							
Elastic section modulus	W_{el}	[mm³]	31	62	109	277	541	935	1387	1874
Partial factor	$\gamma_{Ms,V}$	[-]	see Table C1							
Concrete pry-out failure										
Factor	k_8	[-]	2,0							
Installation factor	γ_{inst}	[-]	1,0							
Concrete edge failure										
Effective length of fastener	l_f	[mm]	$\min(h_{ef}; 12 \cdot d_{nom})$						$\min(h_{ef}; 300mm)$	
Outside diameter of fastener	d_{nom}	[mm]	8	10	12	16	20	24	27	30
Installation factor	γ_{inst}	[-]	1,0							

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of shear loads under static and quasi-static action (Threaded rod)

Annex C 4

Table C5: Characteristic values of tension loads under static and quasi-static action

Internal threaded anchor rods					IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Steel failure[1]										
Characteristic tension resistance, Steel, strength class		5.8	$N_{Rk,s}$	[kN]	10	17	29	42	76	123
		8.8	$N_{Rk,s}$	[kN]	16	27	46	67	121	196
Partial factor, strength class 5.8 and 8.8			$\gamma_{Ms,N}$	[-]	1,5					
Characteristic tension resistance, Stainless Steel A4 and HCR, Strength class 70 [2]			$N_{Rk,s}$	[kN]	14	26	41	59	110	124
Partial factor			$\gamma_{Ms,N}$	[-]	1,87					2,86
Combined pull-out and concrete cone failure										
Characteristic bond resistance in uncracked concrete C20/25										
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	12	12	12	12	11	9,0
	II: 80°C/50°C				9,0	9,0	9,0	9,0	8,5	6,5
	III: 120°C/72°C				6,5	6,5	6,5	6,5	6,5	5,0
	I: 40°C/24°C	flooded bore hole			8,5	8,5	8,5	No Performance Assessed		
	II: 80°C/50°C				6,5	6,5	6,5			
	III: 120°C/72°C				5,0	5,0	5,0			
Characteristic bond resistance in cracked concrete C20/25										
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	5,0	5,5	5,5	5,5	5,5	6,5
	II: 80°C/50°C				3,5	4,0	4,0	4,0	4,0	4,5
	III: 120°C/72°C				2,5	3,0	3,0	3,0	3,0	3,5
	I: 40°C/24°C	flooded bore hole			4,0	5,5	5,5	No Performance Assessed		
	II: 80°C/50°C				3,0	4,0	4,0			
	III: 120°C/72°C				2,5	3,0	3,0			
Reduktion factor ψ^0_{sus} in cracked and uncracked concrete C20/25										
Temperature range	I: 40°C/24°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,73					
	II: 80°C/50°C				0,65					
	III: 120°C/72°C				0,57					
Increasing factors for concrete			ψ_c	[-]	$(f_{ck} / 20)^{0,11}$					
Characteristic bond resistance depending on the concrete strength class			$\tau_{Rk,ucr} =$		$\psi_c \cdot \tau_{Rk,ucr}(C20/25)$					
			$\tau_{Rk,cr} =$		$\psi_c \cdot \tau_{Rk,cr}(C20/25)$					
Concrete cone failure										
Relevant parameter					see Table C2					
Splitting failure										
Relevant parameter					see Table C2					
Installation factor										
for dry and wet concrete			γ_{inst}	[-]	1,2					
for flooded bore hole					1,4			No Performance Assessed		

[1] Fastenings (incl. nut and washer) must comply with the appropriate material and property class of the internal threaded rod. The characteristic tension resistance for steel failure is valid for the internal threaded rod and the fastening element.
[2] For IG-M20 strength class 50 is valid

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension loads under static and quasi-static action
(Internal threaded anchor rod)

Annex C 5

Table C6: Characteristic values of shear loads under static and quasi-static action

Internal threaded anchor rods				IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Steel failure without lever arm[1)]									
Characteristic shear resistance, Steel, strength class	5.8	$V^0_{Rk,s}$	[kN]	5	9	15	21	38	61
	8.8	$V^0_{Rk,s}$	[kN]	8	14	23	34	60	98
Partial factor, strength class 5.8 and 8.8		$\gamma_{Ms,V}$	[-]	1,25					
Characteristic shear resistance, Stainless Steel A4 and HCR, Strength class 70[2)]		$V^0_{Rk,s}$	[kN]	7	13	20	30	55	40
Partial factor		$\gamma_{Ms,V}$	[-]	1,56					2,38
Ductility factor		k_7	[-]	1,0					
Steel failure with lever arm[1)]									
Characteristic bending moment, Steel, strength class	5.8	$M^0_{Rk,s}$	[Nm]	8	19	37	66	167	325
	8.8	$M^0_{Rk,s}$	[Nm]	12	30	60	105	267	519
Partial factor, strength class 5.8 and 8.8		$\gamma_{Ms,V}$	[-]	1,25					
Characteristic bending moment, Stainless Steel A4 and HCR, Strength class 70[2)]		$M^0_{Rk,s}$	[Nm]	11	26	52	92	233	456
Partial factor		$\gamma_{Ms,V}$	[-]	1,56					2,38
Concrete pry-out failure									
Factor		k_8	[-]	2,0					
Installation factor		γ_{inst}	[-]	1,0					
Concrete edge failure									
Effective length of fastener		l_f	[mm]	min(h_{ef}; 12 · d_{nom})					min (h_{ef}; 300mm)
Outside diameter of fastener		d_{nom}	[mm]	10	12	16	20	24	30
Installation factor		γ_{inst}	[-]	1,0					

1) Fastenings (incl. nut and washer) must comply with the appropriate material and property class of the internal threaded rod. The characteristic tension resistance for steel failure is valid for the internal threaded rod and the fastening element.
2) For IG-M20 strength class 50 is valid

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of shear loads under static and quasi-static action
(Internal threaded anchor rod)

Annex C 6

Table C7: Characteristic values of tension loads under static and quasi-static action

Reinforcing bar					Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
Steel failure													
Characteristic tension resistance			$N_{Rk,s}$	[kN]	$A_s \cdot f_{uk}$ [1)]								
Cross section area			A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor			$\gamma_{Ms,N}$	[-]	1,4 [2)]								
Combined pull-out and concrete failure													
Characteristic bond resistance in uncracked concrete C20/25													
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,ucr}$	[N/mm²]	10	12	12	12	12	12	11	10	8,5
	II: 80°C/50°C				7,5	9,0	9,0	9,0	9,0	9,0	8,0	7,0	6,0
	III: 120°C/72°C				5,5	6,5	6,5	6,5	6,5	6,5	6,0	5,0	4,5
	I: 40°C/24°C	flooded bore hole			7,5	8,5	8,5	8,5	8,5	No Performance Assessed			
	II: 80°C/50°C				5,5	6,5	6,5	6,5	6,5				
	III: 120°C/72°C				4,0	5,0	5,0	5,0	5,0				
Characteristic bond resistance in cracked concrete C20/25													
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,cr}$	[N/mm²]	4,0	5,0	5,5	5,5	5,5	5,5	5,5	6,5	6,5
	II: 80°C/50°C				2,5	3,5	4,0	4,0	4,0	4,0	4,0	4,5	4,5
	III: 120°C/72°C				2,0	2,5	3,0	3,0	3,0	3,0	3,0	3,5	3,5
	I: 40°C/24°C	flooded bore hole			4,0	4,0	5,5	5,5	5,5	No Performance Assessed			
	II: 80°C/50°C				2,5	3,0	4,0	4,0	4,0				
	III: 120°C/72°C				2,0	2,5	3,0	3,0	3,0				
Reduktion factor ψ^0_{sus} in cracked and uncracked concrete C20/25													
Temperature range	I: 40°C/24°C	Dry, wet concrete and flooded bore hole	ψ^0_{sus}	[-]	0,73								
	II: 80°C/50°C				0,65								
	III: 120°C/72°C				0,57								
Increasing factors for concrete			ψ_c	[-]	$(f_{ck} / 20)^{0,11}$								
Characteristic bond resistance depending on the concrete strength class			$\tau_{Rk,ucr} =$		$\psi_c \cdot \tau_{Rk,ucr}(C20/25)$								
			$\tau_{Rk,cr} =$		$\psi_c \cdot \tau_{Rk,cr}(C20/25)$								
Concrete cone failure													
Relevant parameter					see Table C2								
Splitting													
Relevant parameter					see Table C2								
Installation factor													
for dry and wet concrete			γ_{inst}	[-]	1,0	1,2							
for flooded bore hole					1,4					No Performance Assessed			

1) f_{uk} shall be taken from the specifications of reinforcing bars
2) in absence of national regulation

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension loads under static and quasi-static action
(Reinforcing bar)

Annex C 7

Table C8: Characteristic values of shear loads under static and quasi-static action

Reinforcing bar			**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure without lever arm											
Characteristic shear resistance	$V^0_{Rk,s}$	[kN]	$0{,}50 \cdot A_s \cdot f_{uk}$ [1)]								
Cross section area	A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 [2)]								
Ductility factor	k_7	[-]	1,0								
Steel failure with lever arm											
Characteristic bending moment	$M^0_{Rk,s}$	[Nm]	$1.2 \cdot W_{el} \cdot f_{uk}$ [1)]								
Elastic section modulus	W_{el}	[mm³]	50	98	170	269	402	785	1534	2155	3217
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 [2)]								
Concrete pry-out failure											
Factor	k_8	[-]	2,0								
Installation factor	γ_{inst}	[-]	1,0								
Concrete edge failure											
Effective length of fastener	l_f	[mm]	$\min(h_{ef}; 12 \cdot d_{nom})$						$\min(h_{ef}; 300mm)$		
Outside diameter of fastener	d_{nom}	[mm]	8	10	12	14	16	20	25	28	32
Installation factor	γ_{inst}	[-]	1,0								

1) f_{uk} shall be taken from the specifications of reinforcing bars
2) in absence of national regulation

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of shear loads under static and quasi-static action
(Reinforcing bar)

Annex C 8

Table C9: Displacements under tension load[1)]

Threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Uncracked concrete C20/25 under static and quasi-static action										
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,021	0,023	0,026	0,031	0,036	0,041	0,045	0,049
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,030	0,033	0,037	0,045	0,052	0,060	0,065	0,071
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,075	0,088	0,100	0,110	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,108	0,127	0,145	0,159	0,172
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,075	0,088	0,100	0,110	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,108	0,127	0,145	0,159	0,172
Cracked concrete C20/25 under static and quasi-static action										
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,090		0,070					
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,105		0,105					
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219		0,170					
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255		0,245					
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219		0,170					
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255		0,245					

1) Calculation of the displacement
$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau$; τ: action bond stress for tension
$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$;

Table C10: Displacements under shear load[1)]

Threaded rod			M8	M10	M12	M16	M20	M24	M27	M30
Uncracked concrete C20/25 under static and quasi-static action										
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,06	0,06	0,05	0,04	0,04	0,03	0,03	0,03
	$\delta_{V\infty}$-factor	[mm/kN]	0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,05
Cracked concrete C20/25 under static and quasi-static action										
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,12	0,12	0,11	0,10	0,09	0,08	0,08	0,07
	$\delta_{V\infty}$-factor	[mm/kN]	0,18	0,18	0,17	0,15	0,14	0,13	0,12	0,10

1) Calculation of the displacement
$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V$; V: action shear load
$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$;

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Displacements under static and quasi-static action
(threaded rods)

Annex C 9

Table C11: Displacements under tension load[1)]

Internal threaded anchor rod			IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Uncracked concrete C20/25 under static and quasi-static action								
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,023	0,026	0,031	0,036	0,041	0,049
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,033	0,037	0,045	0,052	0,060	0,071
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,056	0,063	0,075	0,088	0,100	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,081	0,090	0,108	0,127	0,145	0,172
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,056	0,063	0,075	0,088	0,100	0,119
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,081	0,090	0,108	0,127	0,145	0,172
Cracked concrete C20/25 under static and quasi-static action								
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,090	0,070				
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,105	0,105				
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219	0,170				
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255	0,245				
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219	0,170				
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255	0,245				

1) Calculation of the displacement

$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau$; τ: action bond stress for tension

$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$;

Table C12: Displacements under shear load[1]

Internal threaded anchor rod			IG-M6	IG-M8	IG-M10	IG-M12	IG-M16	IG-M20
Uncracked and cracked concrete C20/25 under static and quasi-static action								
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,07	0,06	0,06	0,05	0,04	0,04
	$\delta_{V\infty}$-factor	[mm/kN]	0,10	0,09	0,08	0,08	0,06	0,06

1) Calculation of the displacement

$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V$; V: action shear load

$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$;

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Displacements under static and quasi-static action
(Internal threaded anchor rod)

Annex C 10

Table C13: Displacements under tension load[1] (rebar)

Anchor size reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
Uncracked concrete C20/25 under static and quasi-static action											
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,021	0,023	0,026	0,028	0,031	0,036	0,043	0,047	0,052
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,030	0,033	0,037	0,041	0,045	0,052	0,061	0,071	0,075
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,069	0,075	0,088	0,104	0,113	0,126
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,099	0,108	0,127	0,149	0,163	0,181
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,050	0,056	0,063	0,069	0,075	0,088	0,104	0,113	0,126
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,072	0,081	0,090	0,099	0,108	0,127	0,149	0,163	0,181
Cracked concrete C20/25 under static and quasi-static action											
Temperature range I: 40°C/24°C	δ_{N0}-factor	[mm/(N/mm²)]	0,090	0,070							
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,105	0,105							
Temperature range II: 80°C/50°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219	0,170							
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255	0,245							
Temperature range III: 120°C/72°C	δ_{N0}-factor	[mm/(N/mm²)]	0,219	0,170							
	$\delta_{N\infty}$-factor	[mm/(N/mm²)]	0,255	0,245							

[1] Calculation of the displacement

$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau$; τ: action bond stress for tension

$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau$;

Table C14: Displacement under shear load[1] (rebar)

Anchor size reinforcing bar			Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 25	Ø 28	Ø 32
Uncracked concrete C20/25 under static and quasi-static action											
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,06	0,05	0,05	0,04	0,04	0,04	0,03	0,03	0,03
	$\delta_{V\infty}$-factor	[mm/kN]	0,09	0,08	0,08	0,06	0,06	0,05	0,05	0,04	0,04
Cracked concrete C20/25 under static and quasi-static action											
All temperature ranges	δ_{V0}-factor	[mm/kN]	0,12	0,12	0,11	0,11	0,10	0,09	0,08	0,07	0,06
	$\delta_{V\infty}$-factor	[mm/kN]	0,18	0,18	0,17	0,16	0,15	0,14	0,12	0,11	0,10

[1] Calculation of the displacement

$\delta_{V0} = \delta_{V0}\text{-factor} \cdot V$; V: action shear load

$\delta_{V\infty} = \delta_{V\infty}\text{-factor} \cdot V$;

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Displacements under static and quasi-static action
(Reinforcing bar)

Annex C 11

Table C15: Characteristic values of tension loads under seismic action (performance category C1)

Threaded rod					**M8**	**M10**	**M12**	**M16**	**M20**	**M24**	**M27**	**M30**
Steel failure												
Characteristic tension resistance			$N_{Rk,s,eq,C1}$	[kN]	$1{,}0 \cdot N_{Rk,s}$							
Partial factor			$\gamma_{Ms,N}$	[-]	see Table C1							
Combined pull-out and concrete failure												
Characteristic bond resistance in uncracked and cracked concrete C20/25												
Temperature range	I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	2,5	3,1	3,7	3,7	3,7	3,8	4,5	4,5
	II: 80°C/50°C				1,6	2,2	2,7	2,7	2,7	2,8	3,1	3,1
	III: 120°C/72°C				1,3	1,6	2,0	2,0	2,0	2,1	2,4	2,4
	I: 40°C/24°C	flooded bore hole			2,5	2,5	3,7	3,7	No Performance Assessed			
	II: 80°C/50°C				1,6	1,9	2,7	2,7				
	III: 120°C/72°C				1,3	1,6	2,0	2,0				
Increasing factors for concrete			ψ_c	[-]	1,0							
Characteristic bond resistance depending on the concrete strength class			$\tau_{Rk,eq,C1} =$		$\psi_c \cdot \tau_{Rk,eq,C1}(C20/25)$							
Installation factor												
for dry and wet concrete			γ_{inst}	[-]	1,0	1,2						
for flooded bore hole					1,4				No Performance Assessed			

Table C16: Characteristic values of shear loads under seismic action (performance category C1)

Threaded rod			**M8**	**M10**	**M12**	**M16**	**M20**	**M24**	**M27**	**M30**
Steel failure without lever arm										
Characteristic shear resistance (Seismic C1)	$V_{Rk,s,eq,C1}$	[kN]	$0{,}70 \cdot V^0_{Rk,s}$							
Partial factor	$\gamma_{Ms,V}$	[-]	see Table C1							
Factor for annular gap	α_{gap}	[-]	0,5 (1,0)[1)]							

1) Value in brackets valid for filled annular gab between fastener and clearance hole in the fixture. Use of special filling washer Annex A 3 is recommended

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension loads and shear loads under seismic action (performance category C1) (Threaded rod)

Annex C 12

Table C17: Characteristic values of tension loads under seismic action (performance category C1)

Reinforcing bar				**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure												
Characteristic tension resistance		$N_{Rk,s,eq,C1}$	[kN]	$1{,}0 \cdot A_s \cdot f_{uk}$ [1]								
Cross section area		A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor		$\gamma_{Ms,N}$	[-]	1,4 [2]								
Combined pull-out and concrete failure												
Characteristic bond resistance in uncracked and cracked concrete C20/25												
Temperature range I: 40°C/24°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	2,5	3,1	3,7	3,7	3,7	3,7	3,8	4,5	4,5
Temperature range II: 80°C/50°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	1,6	2,2	2,7	2,7	2,7	2,7	2,8	3,1	3,1
Temperature range III: 120°C/72°C	Dry, wet concrete	$\tau_{Rk,eq,C1}$	[N/mm²]	1,3	1,6	2,0	2,0	2,0	2,0	2,1	2,4	2,4
Temperature range I: 40°C/24°C	flooded bore hole	$\tau_{Rk,eq,C1}$	[N/mm²]	2,5	2,5	3,7	3,7	3,7	No Performance Assessed			
Temperature range II: 80°C/50°C	flooded bore hole	$\tau_{Rk,eq,C1}$	[N/mm²]	1,6	1,9	2,7	2,7	2,7				
Temperature range III: 120°C/72°C	flooded bore hole	$\tau_{Rk,eq,C1}$	[N/mm²]	1,3	1,6	2,0	2,0	2,0				
Increasing factors for concrete		ψ_c	[-]	1,0								
Characteristic bond resistance depending on the concrete strength class		$\tau_{Rk,eq,C1} =$		$\psi_c \cdot \tau_{Rk,eq,C1}(C20/25)$								
Installation factor												
for dry and wet concrete		γ_{inst}	[-]	1,2	1,2							
for flooded bore hole		γ_{inst}	[-]	1,4					No Performance Assessed			

1) f_{uk} shall be taken from the specifications of reinforcing bars
2) in absence of national regulation

Table C18: Characteristic values of shear loads under seismic action (performance category C1)

Reinforcing bar			**Ø 8**	**Ø 10**	**Ø 12**	**Ø 14**	**Ø 16**	**Ø 20**	**Ø 25**	**Ø 28**	**Ø 32**
Steel failure without lever arm											
Characteristic shear resistance	$V_{Rk,s,eq,C1}$	[kN]	$0{,}35 \cdot A_s \cdot f_{uk}$ [2]								
Cross section area	A_s	[mm²]	50	79	113	154	201	314	491	616	804
Partial factor	$\gamma_{Ms,V}$	[-]	1,5 [2]								
Factor for annular gap	α_{gap}	[-]	0,5 (1,0) [3]								

1) f_{uk} shall be taken from the specifications of reinforcing bars
2) in absence of national regulation
3) Value in brackets valid for filled annular gab between fastener and clearance hole in the fixture. Use of special filling washer Annex A 3 is recommended

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension loads and shear loads under seismic action (performance category C1) (Reinforcing bar)

Annex C 13

Table C19: Characteristic values of tension and shear loads under fire exposure in hammer drilled holes (HD), compressed air drilled holes (CD) and in hammer drilled holes with hollow drill bit (HDB)

Threaded rod					**M8**	**M10**	**M12**	**M16**	**M20**	**M24**	**M27**	**M30**
Steel failure												
Characteristic tension resistance; Steel, Stainless Steel A2, A4 and HCR, strength class 5.8 resp. 50 and higher	$N_{Rk,s,fi}$	[kN]	Fire exposure time [min]	30	1,1	1,7	3,0	5,7	8,8	12,7	16,5	20,2
				60	0,9	1,4	2,3	4,2	6,6	9,5	12,4	15,1
				90	0,7	1,0	1,6	3,0	4,7	6,7	8,7	10,7
				120	0,5	0,8	1,2	2,2	3,4	4,9	6,4	7,9
Characteristic bond resistance in cracked and uncracked concrete C20/25 up to C50/60 under fire conditions for a given temperature θ												
Temperature reduction factor	$k_{fi,p}(\theta)$	[-]	$\theta < 21°C$		1,0							
			$21°C \leq \theta \leq 331°C$		$589{,}7 \cdot \theta^{-1{,}726} \leq 1{,}0$							
			$\theta > 331°C$		0,0							



Characteristic bond resistance for a given temperature (θ)	$\tau_{Rk,fi}(\theta)$	[N/mm²]			$k_{fi,p}(\theta) \cdot \tau_{Rk,cr,(C20/25)}$ [1)]							
Steel failure without lever arm												
Characteristic shear resistance; Steel, Stainless Steel A2, A4 and HCR, strength class 5.8 resp. 50 and higher	$V_{Rk,s,fi}$	[kN]	Fire exposure time [min]	30	1,1	1,7	3,0	5,7	8,8	12,7	16,5	20,2
				60	0,9	1,4	2,3	4,2	6,6	9,5	12,4	15,1
				90	0,7	1,0	1,6	3,0	4,7	6,7	8,7	10,7
				120	0,5	0,8	1,2	2,2	3,4	4,9	6,4	7,9
Steel failure with lever arm												
Characteristic bending moment; Steel, Stainless Steel A2, A4 and HCR, strength class 5.8 resp. 50 and higher	$M^0_{Rk,s,fi}$	[Nm]	Fire exposure time [min]	30	1,1	2,2	4,7	12,0	23,4	40,4	59,9	81,0
				60	0,9	1,8	3,5	9,0	17,5	30,3	44,9	60,7
				90	0,7	1,3	2,5	6,3	12,3	21,3	31,6	42,7
				120	0,5	1,0	1,8	4,7	9,1	15,7	23,3	31,5

1) $\tau_{Rk,cr,(C20/25)}$ characteristic bond resistance for cracked concrete for concrete strength class C20/25 for the relevant temperature range

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension and shear loads under fire exposure (internal threaded anchor rod)

Annex C 14

Table C20: Characteristic values of tension and shear loads under fire exposure in hammer drilled holes (HD), compressed air drilled holes (CD) and in hammer drilled holes with hollow drill bit (HDB)

Internal threaded anchor rods					**IG-M6**	**IG-M8**	**IG-M10**	**IG-M12**	**IG-M16**	**IG-M20**
Steel failure										
Characteristic tension resistance; Steel, Stainless Steel A4 and HCR, strength class 5.8 and 8.8 resp. 70	$N_{Rk,s,fi}$	[kN]	Fire exposure time [min]	30	0,3	1,1	1,7	3,0	5,7	8,8
				60	0,2	0,9	1,4	2,3	4,2	6,6
				90	0,2	0,7	1,0	1,6	3,0	4,7
				120	0,1	0,5	0,8	1,2	2,2	3,4
Characteristic bond resistance in cracked and uncracked concrete C20/25 up to C50/60 under fire conditions for a given temperature θ										
Temperature reduction factor	$k_{fi,p}(\theta)$	[-]	$\theta < 21°C$		1,0					
			$21°C \leq \theta \leq 331°C$		$589{,}7 \cdot \theta^{-1{,}726} \leq 1{,}0$					
			$\theta > 331°C$		0,0					



Characteristic bond resistance for a given temperature (θ)	$\tau_{Rk,fi}(\theta)$	[N/mm²]			$k_{fi,p}(\theta) \cdot \tau_{Rk,cr,(C20/25)}$ [1)]					
Steel failure without lever arm										
Characteristic shear resistance; Steel, Stainless Steel A4 and HCR, strength class 5.8 and 8.8 resp. 70	$V_{Rk,s,fi}$	[kN]	Fire exposure time [min]	30	0,3	1,1	1,7	3,0	5,7	8,8
				60	0,2	0,9	1,4	2,3	4,2	6,6
				90	0,2	0,7	1,0	1,6	3,0	4,7
				120	0,1	0,5	0,8	1,2	2,2	3,4
Steel failure with lever arm										
Characteristic bending moment; Steel, Stainless Steel A4 and HCR, strength class 5.8 and 8.8 resp. 70	$M^0_{Rk,s,fi}$	[Nm]	Fire exposure time [min]	30	0,2	1,1	2,2	4,7	12,0	23,4
				60	0,2	0,9	1,8	3,5	9,0	17,5
				90	0,1	0,7	1,3	2,5	6,3	12,3
				120	0,1	0,5	1,0	1,8	4,7	9,1

1) $\tau_{Rk,cr,(C20/25)}$ characteristic bond resistance for cracked concrete for concrete strength class C20/25 for the relevant temperature range

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension and shear loads under fire exposure (internal threaded anchor rod)

Annex C 15

Table C21: Characteristic values of tension and shear loads under fire exposure in hammer drilled holes (HD), compressed air drilled holes (CD) and in hammer drilled holes with hollow drill bit (HDB)

Reinforcing bar					Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 20	Ø 24	Ø 25	Ø 28	Ø 32
Steel failure														
Characteristic tension resistance; BSt 500	$N_{Rk,s,fi}$	[kN]	Fire exposure time [min]	30	0,5	1,2	2,3	3,1	4,0	6,3	9,0	9,8	12,3	16,1
				60	0,5	1,0	1,7	2,3	3,0	4,7	6,8	7,4	9,2	12,1
				90	0,4	0,8	1,5	2,0	2,6	4,1	5,9	6,4	8,0	10,5
				120	0,3	0,6	1,1	1,5	2,0	3,1	4,5	4,9	6,2	8,0
Characteristic bond resistance in cracked and uncracked concrete C20/25 up to C50/60 under fire conditions for a given temperature θ														
Temperature reduction factor	$k_{fi,p}(\theta)$	[-]	$\theta < 21°C$		1,0									
			$21°C \leq \theta \leq 243°C$		$0{,}81 \cdot e^{-0{,}016 \cdot \theta} \leq 1{,}0$									
			$\theta > 243°C$		0,0									



Characteristic bond resistance for a given temperature (θ)	$\tau_{Rk,fi}(\theta)$	[N/mm²]			$k_{fi,p}(\theta) \cdot \tau_{Rk,cr,(C20/25)}$ [1)]									
Steel failure without lever arm														
Characteristic shear resistance; BSt 500	$V_{Rk,s,fi}$	[kN]	Fire exposure time [min]	30	0,5	1,2	2,3	3,1	4,0	6,3	9,0	9,8	12,3	16,1
				60	0,5	1,0	1,7	2,3	3,0	4,7	6,8	7,4	9,2	12,1
				90	0,4	0,8	1,5	2,0	2,6	4,1	5,9	6,4	8,0	10,5
				120	0,3	0,6	1,1	1,5	2,0	3,1	4,5	4,9	6,2	8,0
Steel failure with lever arm														
Characteristic bending moment; BSt 500	$M^0_{Rk,s,fi}$	[Nm]	Fire exposure time [min]	30	0,6	1,8	4,1	6,5	9,7	18,8	32,6	36,8	51,7	77,2
				60	0,5	1,5	3,1	4,8	7,2	14,1	24,4	27,6	38,8	57,9
				90	0,4	1,2	2,6	4,2	6,3	12,3	21,2	23,9	33,6	50,2
				120	0,3	0,9	2,0	3,2	4,8	9,4	16,3	18,4	25,9	38,6

1) $\tau_{Rk,cr,(C20/25)}$ characteristic bond resistance for cracked concrete for concrete strength class C20/25 for the relevant temperature range

Mapei Injection System Mapefix VE SF or VE SF CC for concrete

Performances
Characteristic values of tension and shear loads under fire exposure (reinforcing bar)

Annex C 16