

Public-law institution jointly founded by the federal states and the Federation

European Technical Assessment Body  
for construction products



## European Technical Assessment

ETA-17/0417  
of 18 November 2025

English translation prepared by DIBt - Original version in German language

### General Part

Technical Assessment Body issuing the European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

Injection system PFT bonded mortar for masonry

Product family to which the construction product belongs

Metal Injection anchors for use in masonry

Manufacturer

Handelskontor Seevetal GmbH  
Partner für Technik  
Hittfelder Kirchweg 10  
21220 Seevetal-Maschen  
DEUTSCHLAND

Manufacturing plant

Handelskontor Seevetal

This European Technical Assessment contains

51 pages including 3 annexes which form an integral part of this assessment

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of

EAD 330076-01-0604, Edition 10/2022

This version replaces

ETA-17/0417 issued on 14 December 2017

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

## Specific Part

### 1 Technical description of the product

The injection system PFT bonded mortar for masonry is a bonded anchor (injection type) consisting of a mortar cartridge with injection mortar PFT bonded mortar, PFT bonded mortar Low Speed or PFT bonded mortar High Speed, a perforated sieve sleeve and an anchor rod with hexagon nut and washer or an internal threaded rod. The steel elements are made of zinc coated steel, stainless steel or high corrosion resistant steel.

The anchor rod is placed into a drilled hole filled with injection mortar and is anchored via the bond between steel element, injection mortar and masonry and mechanical interlock.

The product description is given in Annex A.

### 2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the fastener is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the fastener of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance for static and quasi-static loading	See Annexes B4 to B6, B13, B14, C1 to C28
Characteristic resistance and displacements for seismic loading	No performance assessed

#### 3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire under tension and shear loading with and without lever arm. Minimum edge distances and spacing	No performance assessed

#### 3.3 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

### 4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD 330076-01-0604 the applicable European legal act is: [97/177/EC].

The system to be applied is: 1

**5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document**

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 18 November 2025 by Deutsches Institut für Bautechnik


Dipl.-Ing. Beatrix Wittstock  
Head of Section

*beglaubigt:*  
Baderschneider


### Installation conditions part 1

#### Anchor rods with perforated sleeve UPM-SH K; Installation in perforated and solid brick masonry

##### Pre-positioned installation:




##### Installation with render bridge



**Size of the perforated sleeve:** UPM-SH 12x50 K UPM-SH 16x85 K UPM-SH 20x85 K UPM-SH 20x200 K  
UPM-SH 12x85 K UPM-SH 16x130 K UPM-SH 20x130 K

#### Internal threaded anchor UPM-I with perforated sleeve UPM-SH K; Installation in perforated and solid brick masonry

##### Pre-positioned installation:



Figures not to scale

$h_{ef}$  = effective anchorage depth

$t_{tol}$  = thickness of unbearing layer (e.g. plaster)

$t_{fix}$  = thickness of fixture

Injection system PFT bonded mortar for masonry

#### Product description


Installation conditions part 1,  
Anchor rods and internal threaded anchor with perforated sleeve

**Annex A1**


## Installation conditions part 2

**Anchor rods without perforated sleeve UPM-SH K;  
installation in solid brick masonry and autoclaved aerated concrete**

**Pre-positioned installation:**




**Push through installation: Annular gap filled with mortar**




Installation with  
render bridge

**Internal threaded anchors UPM-I without perforated sleeve UPM-SH K;  
installation in solid brick masonry and autoclaved aerated concrete**

**Pre-positioned installation:**



**Installation with render bridge**



Figures not to scale

$h_0$  = depth of drill hole

$t_{tol}$  = thickness of unbearing layer (e.g. plaster)

$h_{ef}$  = effective anchorage depth

$t_{fix}$  = thickness of fixture

Injection system PFT bonded mortar for masonry

**Product description**

Installation conditions part 2, Anchor rods and internal threaded anchor without perforated sleeve

**Annex A2**



## Overview system components part 1

### Mortar cartridge (shuttle cartridge) with sealing cap

①

Size: 360 ml, 825 ml

**Imprint:** PFT bonded mortar, PFT bonded mortar Low Speed, PFT bonded mortar High Speed, processing notes, shelf-life, hazard code, piston travel scale (optional), curing time and processing time (depending on temperature), size, volume





### Mortar cartridge (coaxial cartridge) with sealing cap


①

Size: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml


**Imprint:** PFT bonded mortar, PFT bonded mortar Low Speed, PFT bonded mortar High Speed, processing notes, shelf-life, hazard code, piston travel scale (optional), curing time and processing time (depending on temperature), size, volume



### Upat static mixer MR Plus for injection cartridges $\leq 410$ ml



### Upat static mixer JMR for injection cartridges 825 ml



### Extension tube $\varnothing 9$ for static mixer MR Plus; Extension tube $\varnothing 9$ or $\varnothing 15$ for static mixer JMR



### Cleaning brush BS



### Blow-out pump ABG



### compressed-air cleaning tool






Figures not to scale

Injection system PFT bonded mortar for masonry

#### Product description

Overview system components part 1: cartridge / static mixer / cleaning tools

**Annex A3**

Overview system components part 2	
<p><b>Upat Anchor rod</b></p> <p>②  Size: M6, M8, M10, M12, M16</p>	
<p><b>Internal threaded anchor UPM-I</b></p> <p>⑤  Size: 11x85 M6 / M8 15x85 M10 / M12</p>	
<p><b>Perforated sleeve UPM-SH K</b></p> <p>⑦  Size: UPM-SH 12x50 K UPM-SH 12x85 K UPM-SH 16x85 K UPM-SH 20x85 K</p> <p>⑦  Size: UPM-SH 16x130 K UPM-SH 20x130 K UPM-SH 20x200 K</p>	
<p><b>Washer</b></p> <p>③  </p>	
<p><b>Hexagon nut</b></p> <p>④  </p>	
Figures not to scale	
<p>Injection system PfT bonded mortar for masonry</p>	<b>Annex A4</b>
<p><b>Product description</b> Overview system components part 2: steel parts / perforated sleeve</p>	

<b>Table A5.1: Materials</b>				
<b>Part</b>	<b>Designation</b>	<b>Material</b>		
1	Mortar cartridge	Mortar, hardener; filler		
		Steel	Stainless steel R	High corrosion resistant steel HCR
		zinc plated	acc. to EN 10088-1:2023 Corrosion resistance class CRC III acc. to EN 1993-1-4:2006+A1:2015	acc. to EN 10088-1:2023 Corrosion resistance class CRC V acc. to EN 1993-1-4:2006+A1:2015
2	Anchor rod	Property class 4.6; 4.8; 5.8 or 8.8; EN ISO 898-1: 2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 or hot-dip galvanised EN ISO 10684:2004+AC:2009 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062; 1.4662; 1.4462; EN 10088-1:2023 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2020 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529 EN 10088-1:2023 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 or hot-dip galvanised EN ISO 10684:2004+AC:2009	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	1.4565; 1.4529 EN 10088-1:2023
4	Hexagon nut	Property class 5 or 8; EN ISO 898-2:2022 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022 or hot-dip galvanised EN ISO 10684:2004+AC:2009	Property class 50, 70 or 80 EN ISO 3506-2:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 50, 70 or 80 EN ISO 3506-2:2020 1.4565; 1.4529 EN 10088-1:2023
5	Internal threaded anchor UPM-I	Property class 5.8; EN ISO 898-1:2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2023
6	Commercial standard screw or threaded rod for internal threaded anchor UPM-I	Property class 4.6, 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5\mu\text{m}$ , ISO 4042:2022	Property class 70 EN ISO 3506-1:2020 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2023	Property class 70 EN ISO 3506-1:2020 1.4565; 1.4529 EN 10088-1:2023
7	Perforated sleeve	PP		
Injection system PFT bonded mortar for masonry				<b>Annex A5</b>
Product description Materials				

<b>Specifications of intended use part 1</b>			
<b>Table B1.1: Overview use and performance categories</b>			
Anchorages subject to		<b>Injection system PFT bonded mortar for masonry</b>	
Hole drilling with hammer drill mode 		all bricks	
Hole drilling with rotary drill mode 		all bricks	
Static and quasi static load, in masonry		all bricks	
Installation	Pre-positioned installation	Anchor rod or internal threaded anchor (in solid brick masonry and autoclaved aerated concrete)	Perforated sleeve with anchor rod or internal threaded anchor (in perforated and solid brick masonry)  Size: UPM-SH 12x50 K UPM-SH 12x85 K UPM-SH 16x85 K UPM-SH 16x130 K UPM-SH 20x85 K UPM-SH 20x130 K UPM-SH 20x200 K
	Push through installation	Anchor rod; use in cylindrical drill hole (in solid brick masonry and autoclaved aerated concrete)	
Installation and use conditions	conditions d/d (dry/dry)	all bricks	
	conditions w/d (wet/dry)		
	conditions w/w (wet/wet)		
Installation direction		D3 (downward and horizontal installation)	
Installation temperature		$T_{i,min} = -5\text{ °C}$ to $T_{i,max} = +40\text{ °C}$	
In-service temperature	Temperature range Tb	-40 °C to +80 °C	(max. short term temperature +80 °C max. long term temperature +50 °C)
	Temperature range Tc	-40 °C to +120 °C	(max. short term temperature +120 °C; max. long term temperature +72 °C)
Injection system PFT bonded mortar for masonry		<b>Annex B1</b>	
<b>Intended Use</b> Specifications part 1			

## Specifications of intended use part 2

### Anchorage subject to:

- Static and quasi-static loads

### Base materials:

- Solid brick masonry (base material group b) and autoclaved aerated concrete (base material group d), acc. to Annex B10.
- Hollow brick masonry (base material group c), according to Annex B10.
- For minimum thickness of masonry member is  $h_{ef}+30\text{mm}$ .
- Mortar strength class of the masonry M2,5 at minimum according to EN 998-2:2016.
- For other bricks in solid masonry, hollow or perforated masonry and autoclaved aerated concrete, the characteristic resistance of the anchor may be determined by job site tests according to EOTA Technical Report TR 053:2022-07 under consideration of the  $\beta$ -factor according to Annex C28, Table C28.1.

Note (only applies to solid bricks and autoclaved aerated concrete):

The characteristic resistance is also valid for larger brick sizes, higher compressive strength and higher raw density of the masonry unit.

### Temperature Range:

- **Tb:** From -40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)
- **Tc:** From -40°C to +120°C (max. short term temperature +120°C and max. long term temperature +72°C)

### Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc plated steel, stainless steel or high corrosion resistant steel)
- For all other conditions according to EN 1993-1-4:2006+A1:2015 corresponding to corrosion resistance classes to Annex A5, Table A5.1.

Injection system PfT bonded mortar for masonry

**Intended Use**  
Specifications part 2

**Annex B2**

## Specifications of intended use part 3 continued

### Design:

- The anchorages have to be designed in accordance with EOTA Technical Report TR 054:2023-12, Design method A under the responsibility of a designer experienced in anchorages and masonry work.

Applies to all bricks, if no other values are specified:

$$N_{Rk} = N_{Rk,b} = N_{Rk,p} = N_{Rk,b,c} = N_{Rk,p,c}$$

$$V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}$$

For the calculation of pulling out a brick under tension loading  $N_{Rk,pb}$  or

pushing out a brick under shear loading  $V_{Rk,pb}$  see EOTA Technical Report TR 054:2023-12.

$N_{Rk,s}$ ,  $V_{Rk,s}$  and  $M^0_{Rk,s}$  see annexes C1-C3.

Factors for job site tests and displacements see annex C28.

- Verifiable calculation notes and drawings have to be prepared taking into account the relevant masonry in the region of the anchorage, the loads to be transmitted and their transmission to the supports of the structure. The position of the anchor is to be indicated on the design drawings.

### Installation:

- Conditions d/d: - Installation and use in dry structures.
- Conditions w/w: - Installation and use in dry and wet structures.
- Conditions w/d: - Installation in wet structures and use in dry structures.
- Hole drilling see Annex C (drilling method).
- In case of aborted hole: The hole shall be filled with injection mortar.
- Bridging of unbearing layer (e.g., plaster) is permitted for masonry with solid bricks and cylindrical drill hole. At perforated brick masonry see Annex B6, Table B6.1.
- Anchor installation carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site.
- Fastening screws or anchor rods (including nut and washer) must comply with the appropriate material and property class of the internal threaded anchor UPM-I mentioned in Annex A5, Table A5.1.
- Minimum curing time see Annex B7, Table B7.3.
- Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled:

Material dimensions and mechanical properties of the metal parts according to the specifications are given in Annex A5, Table A5.1

Conformation of material and mechanical properties of the metal parts by inspection certificate 3.1 according to EN 10204:2004, the documents shall be stored.

Marking of the anchor rod with the envisage embedment depth. This may be done by the manufacturer of the rod or by a person on job site.

Injection system PfT bonded mortar for masonry

**Intended Use**  
Specifications part 3 continued

**Annex B3**

**Table B4.1:** Installation parameters for anchor rods in solid bricks and autoclaved aerated concrete without perforated sleeves

Anchor rod	Thread	M6	M8	M10	M12	M16
Nominal drill hole diameter	$d_0$ [mm]	8	10	12	14	18
Effective anchorage depth $h_{ef}^{1)}$ in AAC cylindrical drill hole	$h_{0,min} \geq h_{ef,min}$ [mm]	100				
	$h_{0,max} \geq h_{ef,max}$ [mm]	$h-30, \leq 200$				
Effective anchorage depth $h_{ef}^{1)}$ in solid brick (depth of drill hole $h_0 \geq h_{ef}$ )	$h_{ef,min}$ [mm]	50				
	$h_{ef,max}$ [mm]	$h-30, \leq 200$				
Diameter of clearance hole in the fixture	pre-positioning $d_f \leq$ [mm]	7	9	12	14	18
	push through $d_f \leq$ [mm]	9	11	14	16	20
Diameter of cleaning brush	$d_b \geq$ [mm]	see Table B7.1				
Maximum installation torque	$T_{inst}$ [Nm]	see parameters of brick				

<sup>1)</sup>  $h_{ef,min} \leq h_{ef} \leq h_{ef,max}$  is possible.

**Upat anchor rods M6, M8, M10, M12, M16**




**Marking (on random place) Upat anchor rod:**

Steel zinc plated PC <sup>1)</sup> 8.8	• or +	Steel hot-dip galvanised PC <sup>1)</sup> 8.8	•
High corrosion resistant steel HCR PC <sup>1)</sup> 50	•	High corrosion resistant steel HCR PC <sup>1)</sup> 70	–
High corrosion resistant steel HCR PC <sup>1)</sup> 80	(	Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1: 2016;  
property class 4.6 marking according to EN ISO 898-1:2013

<sup>1)</sup> PC = property class

**Installation conditions:**



Figures not to scale

Injection system PFT bonded mortar for masonry


**Intended Use**  
Installation parameters for anchor rods without perforated sleeve

**Annex B4**

**Table B5.1:** Installation parameters for internal threaded anchors UPM-I in solid bricks and autoclaved aerated concrete without perforated sleeves

Internal threaded anchor UPM-I		11x85 M6	11x85 M8	15x85 M10	15x85 M12
Diameter of anchor	$d_H$ [mm]	11		15	
Nominal drill hole diameter	$d_0$ [mm]	14		18	
Length of anchor	$L_H$ [mm]	85			
Effective anchorage depth	$h_0 \geq h_{ef}$ [mm]	85			
Diameter of cleaning brush	$d_b \geq$ [mm]	see Table B7.1			
Maximum installation torque	$T_{inst}$ [Nm]	see parameters of brick			
Diameter of clearance hole in the fixture	$d_f$ [mm]	7	9	12	14
Screw-in depth	$l_{E,min}$ [mm]	6	8	10	12
	$l_{E,max}$ [mm]	60			

**Internal threaded anchor UPM-I**




**Marking:**

Size, e.g. **M8**, Stainless steel: R, e.g. **M8 R**, High corrosion resistant steel: HCR, e.g. **M8 HCR**

**Installation conditions:**

Internal threaded anchor in cylindrical drill hole



Figures not to scale

Injection system PFT bonded mortar for masonry

**Intended Use**

Installation parameters for internal threaded rods UPM-I without perforated sleeve

**Annex B5**

**Table B6.1:** Installation parameters for anchor rods and internal threaded anchors UPM-I with perforated sleeves (pre-positioned installation)

perforated sleeve UPM-SH K	12x50	12x85 <sup>2)</sup>	16x85	16x130 <sup>2)</sup>	20x85	20x130 <sup>2)</sup>	20x200 <sup>2)</sup>
Nominal drill hole diameter $d_0 = D_{\text{sleeve, nom}}$	12		16		20		
Depth of drill hole $h_0$ [mm]	55	90	90	135	90	135	205
Effective anchorage depth	$h_{\text{ef, min}}$ [mm]	50	65	85	110	85	110
	$h_{\text{ef, max}}$ [mm]	50	85	85	130	85	200
Size of threaded rod [-]	M6 and M8		M8 and M10		M12 and M16		
Size of internal threaded anchor UPM-I	-	-	11x85	-	15x85	-	-
Diameter of cleaning brush <sup>1)</sup> $d_b \geq$ [mm]	see Table B7.1						
Maximum installation torque $T_{\text{inst}}$ [Nm]	see parameters of brick						

<sup>1)</sup> Only for solid areas in hollow bricks and solid bricks.


<sup>2)</sup> Bridging of unbearing layer (e.g. plaster) is possible. When reducing the effective anchorage depth  $h_{\text{ef, min}}$ , the values of the next shorter perforated sleeve of the same diameter must be used. The smaller value of characteristic resistance must be taken.

**Perforated sleeve**

UPM-SH 12x50 K; UPM-SH 12x85 K; UPM-SH 16x85 K; UPM-SH 16x130 K;  
UPM-SH 20x85 K; UPM-SH 20x130 K; UPM-SH 20x200 K

**Marking:**



Size  $D_{\text{sleeve, nom}} \times L_{\text{sleeve}}$   
(e.g.: 16x85)



**Internal threaded anchor UPM-I**

UPM-I 11x85 M6, UPM-I 11x85 M8



UPM-I 15x85 M10, UPM-I 15x85 M12



**Installation conditions:**

Anchor rod with perforated sleeve

Internal threaded anchor with perforated sleeve



Figures not to scale

Injection system Pft bonded mortar for masonry

**Intended Use**


Installation parameters for anchor rods and internal threaded anchors UPM-I with perforated sleeve (pre-positioned installation)

**Annex B6**

**Table B7.1:** Parameters of the cleaning brush BS (steel brush with steel bristles)

The size of the cleaning brush refers to the drill hole diameter

Drill hole diameter	$d_0$ [mm]	8	10	12	14	16	18	20
Brush diameter	$d_b$ [mm]	9	11	14	16	20	20	25



Only for solid bricks and autoclaved aerated concrete or solid areas of perforated bricks and hollow blocks

**Table B7.2:** Conditions for use static mixer without an extension tube

Nominal drill hole diameter	$d_0$	[mm]	10	12	14	16	18	20
Drill hole depth $h_0$ by using	R Plus	[mm]	≤90		≤120	≤140	≤150	≤160
	JMR	[mm]	-		≤90			≤260

**Table B7.3:** Maximum processing times and minimum curing times

(During the curing time of the mortar the masonry temperature may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time <sup>2)</sup> $t_{work}$			Minimum curing time <sup>1), 2)</sup> $t_{cure}$		
	PfT bonded mortar High Speed	PfT bonded mortar	PfT bonded mortar Low Speed	PfT bonded mortar High Speed	PfT bonded mortar	PfT bonded mortar Low Speed
-10 to -5	-	-	-	12 h	-	-
> -5 to 0	5 min	-	-	3 h	24 h	-
> 0 to 5	5 min	13 min	-	3 h	3 h	6 h
> 5 to 10	3 min	9 min	20 min	50 min	90 min	3 h
> 10 to 20	1 min	5 min	10 min	30 min	60 min	2 h
> 20 to 30	-	4 min	6 min	-	45 min	60 min
> 30 to 40	-	2 min	4 min	-	35 min	30 min

<sup>1)</sup> For wet bricks the curing time must be doubled.

<sup>2)</sup> Minimum cartridge temperature +5°C.

Figures not to scale

Injection system PfT bonded mortar for masonry












**Intended Use**

Cleaning brush (steel brush)  
Maximum processing times and minimum curing times

**Annex B7**

### Installation instruction part 1

#### Installation in solid brick and autoclaved aerated concrete (without perforated sleeve)

1		<p>Drill the hole (drilling method see Annex C of the respective brick) depth of drill hole <math>h_0</math> and drill hole diameter <math>d_0</math> see <b>Table B4.1; B5.1</b>.</p>	
2			 <p>Blow out the drill hole twice. Brush twice and blow out twice again.</p>
3		<p>Remove the sealing cap. Screw on the static mixer. (the spiral in the static mixer must be clearly visible).</p>	
4		<p>Place the cartridge into a suitable dispenser.</p>	 <p>Press out approximately 10 cm of mortar until the resin is permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed of.</p>
5		<p>Fill approximately 2/3 of the drill hole with mortar beginning from the bottom of the hole<sup>1)</sup>. Avoid bubbles!</p>	 <p>For push through installation fill the annular clearance with mortar.</p>
6		<p>Only use clean and oil-free metal parts. Mark the anchor rod for setting depth. Insert the anchor rod or internal threaded anchor UPM-I by hand using light turning motions. When reaching the setting depth marking, excess mortar must emerge from the mouth of the drill hole.</p>	
7		<p>Do not touch. Minimum curing time see <b>Table B7.3</b>.</p>	 <p>Mounting the fixture. max <math>T_{inst}</math> see parameter of brick in <b>Annex C</b>.</p>

<sup>1)</sup> Exact volume of mortar see manufacturer's specification.









Injection system PFT bonded mortar for masonry

**Intended Use**  
Installation instruction (without perforated sleeve) part 1

**Annex B8**

## Installation instruction part 2

### Installation in perforated or solid brick with perforated sleeve (pre-positioned installation)

1		Drill the hole (drilling method see Annex C of the respective brick). depth of drill hole $h_0$ and drill hole diameter $d_0$ see <b>Table B6.1</b>	When install perforated sleeves in solid bricks or solid areas of hollow bricks, also clean the hole by blowing out and brushing.	
2		Remove the sealing cap. Screw on the static mixer. (the spiral in the static mixer must be clearly visible).		
3		Place the cartridge into a suitable dispenser.		Press out approximately 10 cm of mortar until the resin is permanently grey in colour. Mortar which is not grey in colour will not cure and must be disposed of.
4		Insert the perforated sleeve flush with the surface of the masonry or plaster.		Fill the perforated sleeve completely with mortar beginning from the bottom of the hole <sup>1)</sup> .
5		Only use clean and oil-free metal parts. Mark the anchor rod for setting depth. Insert the anchor rod or the internal threaded anchor UPM-I by hand using light turning motions until reaching the setting depth marking (anchor rod) or flush with the surface (internal threaded anchor).		
6		Do not touch. Minimum curing time see <b>Table B7.3</b>		Mounting the fixture. max $T_{inst}$ see parameter of brick in <b>Annex C</b> .

<sup>1)</sup> Exact volume of mortar see manufacturer's specification.

Injection system PfT bonded mortar for masonry


**Intended Use**  
Installation instruction (with perforated sleeve) part 2

**Annex B9**


<b>Table B10.1: Overview of assessed bricks</b>					
Kind of masonry	Brick format [mm]	Mean compressive strength [N/mm <sup>2</sup> ]	Main country of origin	Mean gross density $\rho$ [kg/dm <sup>3</sup> ]	Annex
<b>Solid brick Mz</b>					
<b>Solid brick Mz</b>	<b>NF</b> $\geq 240 \times 115 \times 71$	15 / 25 / 35	Germany	$\geq 1,8$	C4 – C7
<b>Solid calcium silicate (sand- lime) brick KS / perforated calcium silicate (sand- lime) brick KSL</b>					
<b>Solid calcium silicate brick KS</b>	<b>NF</b> $\geq 240 \times 115 \times 71$	15 / 25 / 35	Germany	$\geq 2,0$	C8 / C9
	$\geq 240 \times 115 \times 113$	12,5 / 25	Germany	$\geq 1,8$	C10 / C11
<b>Perforated calcium silicate brick KSL</b>	<b>3DF</b> 240x175x113	10 / 12,5 / 15 / 20 / 25	Germany	$\geq 1,4$	C12 – C14
<b>Vertical perforated brick HLz</b>					
<b>Vertical perforated brick HLz</b>	370x240x237	5 / 7,5 / 10 / 12,5 / 15	Germany	$\geq 1,0$	C15 / C16
	500x175x237	5 / 7,5 / 10 / 12,5 / 15	Germany	$\geq 1,0$	C15 / C16
	<b>2DF</b> 240x115x113	7,5 / 12,5 / 20 / 25 / 35	Germany	$\geq 1,4$	C17 / C18
	365x248x245	10	Austria	$\geq 0,6$	C19 – C20
	240x175x113	12,5	Germany	$\geq 0,9$	C21 / C22
<b>Light-weight concrete hollow block Hbl</b>					
<b>Light-weight concrete hollow block Hbl</b>	362x240x240	2,5 / 5	Germany	$\geq 1,0$	C23 / C24
<b>Autoclaved aerated concrete (AAC)</b>					
<b>PP2 / AAC</b>	-	2,5	Germany	0,35	C25 – C27
<b>PP4 / AAC</b>	-	5	Germany	0,5	C25 – C27
<b>PP6 / AAC</b>	-	8	Germany	0,65	C25 – C27
Injection system Pft bonded mortar for masonry					<b>Annex B10</b>
Intended Use Overview of assessed bricks					

**Table B11.1:** Overview dimensions of perforated and hollow bricks part 1


Perforated calcium silicate brick KSL, 3DF,  
EN 771-2:2011+A1:2015; e.g. KS Wending according to Annex C12



Vertical perforated brick HLz,  
EN 771-1:2011+A1:2015; e.g. Wienerberger, Poroton according to Annex C15



Vertical perforated brick HLz, 2DF,  
EN 771-1:2011+A1:2015; e.g. Wienerberger according to Annex C17



Measures in [mm]  
Figures not to scale


Injection system PFT bonded mortar for masonry

**Intended Use**  
Overview dimensions of perforated and hollow bricks part 1


**Annex B11**

**Table B12.1:** Overview dimensions of perforated and hollow bricks part 2


Vertical perforated brick filled with mineral wool,  
EN 771-1:2011+A1:2015; according to Annex C19



Vertical perforated brick HLz,  
EN 771-1:2011+A1:2015; e.g. Wienerberger according to Annex C21



Light-weight concrete hollow block Hbl,  
EN 771-3:2011+A1:2015; according to Annex C23




Measures in [mm]  
Figures not to scale

Injection system Pft bonded mortar for masonry

**Intended Use**  
Overview dimensions of perforated and hollow bricks part 2

**Annex B12**

## Spacing and edge distance part 1



\* Only, if vertical joints are not completely filled with mortar

$s_{min II}$	=	Minimum spacing parallel to horizontal joint
$s_{min \perp}$	=	Minimum spacing perpendicular to horizontal joint
$s_{cr II}$	=	Characteristic spacing parallel to horizontal joint
$s_{cr \perp}$	=	Characteristic spacing perpendicular to horizontal joint
$c_{cr} = c_{min}$	=	Edge distance
$\alpha_{g,N}(s_{min II})$	=	Group factor for tension load, anchor group parallel to horizontal joint
$\alpha_{g,V}(s_{min II})$	=	Group factor for shear load, anchor group parallel to horizontal joint
$\alpha_{g,N}(s_{min \perp})$	=	Group factor for tension load, anchor group perpendicular to horizontal joint
$\alpha_{g,V}(s_{min \perp})$	=	Group factor for shear load, anchor group perpendicular to horizontal joint

Figures not to scale

Injection system PFT bonded mortar for masonry

**Intended Use**  
Spacing and edge distance part 1

**Annex B13**

## Spacing and edge distance part 2

For  $s \geq s_{cr}$ :  $\alpha_g = 2$

For  $s_{min} \leq s < s_{cr}$ :  $\alpha_g$  according to installation parameters of brick Annex C

Group of 2 anchors

$$N_{Rk}^g = \alpha_{g,N} \cdot N_{Rk}; V_{Rk,b}^g = V_{Rk,c,II}^g = V_{Rk,c,\perp}^g = \alpha_{g,V} \cdot V_{Rk}$$

Group of 4 anchors

$$N_{Rk}^g = \alpha_{g,N}(s_{minII}) \cdot \alpha_{g,N}(s_{min\perp}) \cdot N_{Rk};$$

$$V_{Rk,b}^g = V_{Rk,c,II}^g = V_{Rk,c,\perp}^g = \alpha_{g,V}(s_{minII}) \cdot \alpha_{g,V}(s_{min\perp}) \cdot V_{Rk}$$

with  $N_{Rk}$  and  $\alpha_{g,N}$  depending on  $s_{minII}$  or  $s_{min\perp}$  acc. to Annex C

with  $V_{Rk}$  and  $\alpha_{g,V}$  depending on  $s_{minII}$  or  $s_{min\perp}$  acc. to Annex C

Injection system PfT bonded mortar for masonry

**Intended Use**  
Spacing and edge distance part 2


**Annex B14**

<b>Table C1.1: Characteristic resistance to steel failure under tension loading of anchor rods and standard threaded rods</b>									
<b>Anchor rod / standard threaded rod</b>		<b>M6</b>	<b>M8<sup>3)</sup></b>	<b>M10<sup>3)</sup></b>	<b>M12</b>	<b>M16</b>			
<b>Characteristic resistance to steel failure under tension loading</b>									
Characteristic resistance $N_{Rk,s}$	Steel zinc plated	4.6	[kN]	8,0	14,6(13,2)	23,2(21,4)	33,7	62,8	
		4.8		8,0	14,6(13,2)	23,2(21,4)	33,7	62,8	
	Stainless steel R and High corrosion resistant steel HCR	5.8		10,0	18,3(16,6)	29,0(26,8)	42,1	78,5	
		8.8		16,0	29,2(26,5)	46,4(42,8)	67,4	125,6	
		Property class		50	10,0	18,3	29,0	42,1	78,5
				70	14,0	25,6	40,6	59,0	109,9
				80	16,0	29,2	46,4	67,4	125,6
<b>Partial factors <sup>1)</sup></b>									
Partial factors $\gamma_{Ms,N}$	Steel zinc plated	4.6	[-]	2,00					
		4.8		1,50					
		5.8		1,50					
	Stainless steel R and High corrosion resistant steel HCR	8.8		1,50					
		Property class		50	2,86				
				70	1,50 <sup>2)</sup> / 1,87				
				80	1,60				
<p>1) In absence of other national regulations.</p> <p>2) Only for Upat UPM A made of high corrosion resistant steel HCR.</p> <p>3) Values in brackets are valid for undersized threaded rods with smaller stress area <math>A_s</math> for hot-dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009.</p>									
Injection system PfT bonded mortar for masonry						<b>Annex C1</b>			
<b>Performance</b> Characteristic resistance to steel failure under tension loading of Upat anchor rods and standard threaded rods									

Table C2.1: Characteristic resistance to steel failure under shear loading of anchor rods and standard threaded rods								
Anchor rod / standard threaded rod		M6	M8 <sup>3)</sup>	M10 <sup>3)</sup>	M12	M16		
<b>Characteristic resistance to steel failure under shear loading</b>								
<b>without lever arm</b>								
Characteristic resistance $V_{Rk,s}$	Steel zinc plated	4.6	[kN]	4,8	8,7(7,9)	13,9(12,8)	20,2	37,6
		4.8		4,8	8,7(7,9)	13,9(12,8)	20,2	37,6
	Property class	5.8		6,0	10,9(9,9)	17,4(16,0)	25,2	47,1
		8.8		8,0	14,6(13,2)	23,2(21,4)	33,7	62,8
		Stainless steel R and High corrosion resistant steel HCR		50	5,0	9,1	14,5	21,0
	70			7,0	12,8	20,3	29,5	54,9
	80	8,0		14,6	23,2	33,7	62,8	
<b>with lever arm</b>								
Characteristic resistance $M^0_{Rk,s}$	Steel zinc plated	4.6	[Nm]	6,1	14,9(12,9)	29,9(26,5)	52,3	132,9
		4.8		6,1	14,9(12,9)	29,9(26,5)	52,3	132,9
	Property class	5.8		7,6	18,7(16,1)	37,3(33,2)	65,4	166,2
		8.8		12,2	29,9(25,9)	59,8(53,1)	104,6	265,9
		Stainless steel R and High corrosion resistant steel HCR		50	7,6	18,7	37,3	65,4
	70			10,6	26,2	52,3	91,5	232,6
	80	12,2		29,9	59,8	104,6	265,9	
<b>Partial factors<sup>1)</sup></b>								
Partial factors $\gamma_{Ms,V}$	Steel zinc plated	4.6	[-]	1,67				
		4.8		1,25				
	Property class	5.8		1,25				
		8.8		1,25				
		Stainless steel R and High corrosion resistant steel HCR		50	2,38			
	70			1,25 <sup>2)</sup> / 1,56				
	80	1,33						
<p>1) In absence of other national regulations</p> <p>2) Only for Upat UPM A made of high corrosion resistant steel HCR</p> <p>3) Values in brackets are valid for undersized threaded rods with smaller stress area <math>A_s</math> for hot-dip galvanised standard threaded rods (M8 resp. M10) according to EN ISO 10684:2004+AC:2009.</p>								
Injection system PfT bonded mortar for masonry						<b>Annex C2</b>		
<b>Performance</b> Characteristic resistance to steel failure under shear loading of Upat anchor rods and standard threaded rods								

<b>Table C3.1: Characteristic resistance to steel failure under tension / shear loading of internal threaded anchors UPM-I</b>								
<b>Internal threaded anchor UPM-I</b>				<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>	
<b>Characteristic resistance to steel failure under tension loading, decisive values of internal threaded anchor UPM-I with screw/threaded rod</b>								
Characteristic resistance	$N_{Rk,s}$	Property class 4.6	[kN]	8,0	14,6	23,2	33,7	
		Property class 5.8		10,0	18,3	29,0	42,1	
		Property class 70		R	14,0	25,6	40,6	59,0
		HCR		14,0	25,6	40,6	59,0	
<b>Partial factors<sup>1)</sup></b>								
Partial factors	$\gamma_{Ms,N}$	Property class 4.6	[-]	2,00				
		Property class 5.8		1,50				
		Property class 70		R	1,87			
		HCR		1,87				
<b>Characteristic resistance to steel failure under shear loading; decisive values of internal threaded anchor UPM-I with screw/threaded rod</b>								
<b>without lever arm</b>								
Characteristic resistance	$V_{Rk,s}$	Property class 4.6	[kN]	4,8	8,7	13,9	20,2	
		Property class 5.8		6,0	10,9	15,0	21,0	
		Property class 70		R	7,0	12,8	20,3	29,5
		HCR		7,0	12,8	20,3	29,5	
<b>with lever arm</b>								
Characteristic resistance	$M^0_{Rk,s}$	Property class 4.6	[Nm]	6,1	14,9	29,9	52,3	
		Property class 5.8		7,6	18,7	37,3	65,4	
		Property class 70		R	10,6	26,2	52,3	91,5
		HCR		10,6	26,2	52,3	91,5	
<b>Partial factors<sup>1)</sup></b>								
Partial factors	$\gamma_{Ms,V}$	Property class 4.6	[-]	1,67				
		Property class 5.8		1,25				
		Property class 70		R	1,56			
		HCR		1,56				
1) In absence of other national regulations								
Injection system PfT bonded mortar for masonry						<b>Annex C3</b>		
<b>Performance</b> Characteristic resistance to steel failure under tension / shear loading of internal threaded anchors UPM-I								

**Solid brick Mz, NF, EN 771-1:2011+A1:2015**



Producer	e.g. Wienerberger			
Nominal dimensions	[mm]	length L	width W	height H
		≥ 240	≥ 115	≥ 71
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	≥ 1,8		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	15 / 12 or 25 / 20 or 35 / 28		
Standard or annex	EN 771-1:2011+A1:2015			

**Table C4.1:** Installation parameters for edge distance  $c=100\text{mm}$

Anchor rod	M6	M8	M10	M12	-	-	
Internal threaded anchor UPM-I	-	-	-	-	M6 11x85	M8 M10 M12 15x85	
<b>Anchor rod and internal threaded anchor UPM-I without perforated sleeve</b>							
Effective anchorage depth $h_{ef}$	[mm]	50	50	50	50	85	
		80	80	80	80		
		200	200	200	200		
Max. installation torque $\max T_{inst}$	[Nm]	4	10		4	10	
<b>General installation parameters</b>							
Edge distance $c_{min} = c_{cr}$	[mm]	100			100		
Edge distance $h_{ef}=200$ $c_{min} = c_{cr}$		150			- <sup>2)</sup>		
Spacing		$s_{min II,N}$	60			60	
		$h_{ef}=200$ $s_{min II,N}$	240			- <sup>2)</sup>	
		$s_{min II,V}$	240			240	
		$s_{cr II}$	240			240	
		$s_{cr \perp} = s_{min \perp}$	75			75	

**Drilling method**

Hammer drilling with hard metal hammer drill

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> No performance assessed

**Table C4.2:** Group factors

Anchor rods	M6	M8	M10	M12	-	-	
Internal threaded anchor UPM-I	-	-	-	-	M6 11x85	M8 M10 M12 15x85	
Edge distance $c_{min}$	[mm] 100						
Group factor	[-]	$\alpha_{a,N} (s_{min II})$	1,5				
		$\alpha_{g,V} (s_{min II})$	2,0				
		$h_{ef}=200$ $\alpha_{g,N} (s_{min II})$	1,5				
		$h_{ef}=200$ $\alpha_{g,V} (s_{min II})$	2,0				
		$\alpha_{a,N} (s_{min \perp})$	2,0				
		$\alpha_{g,V} (s_{min \perp})$	2,0				
		$h_{ef}=200$ $\alpha_{a,N} (s_{min \perp})$	2,0				
		$h_{ef}=200$ $\alpha_{g,V} (s_{min \perp})$	2,0				

Injection system PFT bonded mortar for masonry

**Performance**

Solid brick Mz, NF, dimensions, installation parameters for edge distance  $c=100\text{mm}$ , Group factors

**Annex C4**

**Solid brick Mz, NF, EN 771-1:2011+A1:2015**

**Table C5.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading for edge distance  $c=100\text{mm}$

Anchor rod		M6	M8	M10			M12			-	-		
Internal threaded anchor UPM-I		-	-	-			-			M6	M8	M10	M12
										11x85		15x85	
<b><math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN]; temperature range 50/80°C <sup>2)</sup></b>													
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions	Effective anchorage depth $h_{ef}$ [mm]											
		≥50	≥50	50	80	200	50	80	200	85			
15 / 12 N/mm <sup>2</sup>	w/w	w/d	2,5	2,5	2,0	3,0	7,5	2,0	3,5	5,0	3,5		
	d/d		4,0	4,0	3,5	5,0	12,0	3,0	5,5	8,0	5,5		
25 / 20 N/mm <sup>2</sup>	w/w	w/d	3,5	3,5	3,0	4,5	11,0	3,0	5,0	7,0	5,0		
	d/d		5,5	5,5	5,0	7,0	12,0	4,5	8,0	11,5	8,0		

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
<sup>2)</sup> For temperature range 72/120°C:  $N_{Rk(72/120^\circ\text{C})} = 0,83 \cdot N_{Rk(50/80^\circ\text{C})}$ .

**Table C5.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading for edge distance  $c=100\text{mm}$

Anchor rod		M6	M8	M10			M12			-	-		
Internal threaded anchor UPM-I		-	-	-			-			M6	M8	M10	M12
										11x85		15x85	
<b><math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,\perp}</math> [kN]; temperature range 50/80°C and 72/120°C</b>													
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions	Effective anchorage depth $h_{ef}$ [mm]											
		≥50	≥50	≥50	200	≥50	200	85					
15 / 12 N/mm <sup>2</sup>	w/w	w/d	2,5	2,5	4,0	8,5	4,0	11,5	2,5				
	d/d												
25 / 20 N/mm <sup>2</sup>	w/w	w/d	4,0	4,0	6,0	12,0	5,5	12,0	4,0				
	d/d												

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
Factor for job site tests and displacements see annex C28.

Injection system PfT bonded mortar for masonry

**Performance**

Solid brick Mz, NF, Characteristic resistance under tension and shear loading, edge distance  $c=100\text{mm}$

**Annex C5**

**Solid brick Mz, NF, EN 771-1:2011+A1:2015**

**Table C6.1:** Installation parameters for edge distance  $c=60\text{mm}$

Anchor rod		M6	M8	M10	M12	M16	-	-
Internal threaded anchor UPM-I		-	-	-	-	-	M6	M8
							11x85	15x85
<b>Anchor rod and internal threaded anchor UPM-I without perforated sleeve</b>								
Effective anchorage depth $h_{ef}$	[mm]	50	50	50	50	50	85	
		100	100	100	100	100		
		200	200	200	200	200		
Max. installation torque $\max T_{inst}$	[Nm]	4	10				4	10

**General installation parameters**

Edge distance $c_{min} = c_{cr}$		60
Edge distance $h_{ef}=200$	$c_{min}$	60
Spacing	$s_{min \parallel, N}$	80
	$h_{ef}=200$ $s_{min \parallel, N}$	80
	$s_{min \parallel, V}$	80
	$s_{cr \parallel}$	$3x h_{ef}$
	$s_{min \perp}$	80
	$s_{cr \perp}$	$3x h_{ef}$

**Drilling method**

Hammer drilling with hard metal hammer drill

**Table C6.2:** Group factors

Anchor rods		M6	M8	M10	M12	M16	-	-		
Internal threaded anchor UPM-I		-	-	-	-	-	M6	M8		
							11x85	15x85		
Edge distance $c_{min}$	[mm]	60								
Group factor	$\alpha_{g, N} (s_{min \parallel})$	[-]	0,6							
	$\alpha_{g, V} (s_{min \parallel})$		1,3							
	$h_{ef}=200$ $\alpha_{g, N} (s_{min \parallel})$		1,4							
	$h_{ef}=200$ $\alpha_{g, V} (s_{min \parallel})$		1,5							
	$\alpha_{g, N} (s_{min \perp})$		0,3							
	$\alpha_{g, V} (s_{min \perp})$		1,3							
	$h_{ef}=200$ $\alpha_{g, N} (s_{min \perp})$		2,0							
	$h_{ef}=200$ $\alpha_{g, V} (s_{min \perp})$		1,1							

Injection system Pft bonded mortar for masonry

**Performance**

Solid brick Mz, NF, dimensions, installation parameters, edge distance  $c=60\text{mm}$ , Group factors

**Annex C6**

**Solid brick Mz, NF, EN 771-1:2011+A1:2015**

**Table C7.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading for edge distance  $c=60\text{mm}$

Anchor rod	M6		M8		M10			M12			M16			-	-		
Internal threaded anchor UPM-I	-		-		-			-			-			M6	M8	M10	M12
														11x85		15x85	
<b><math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN]; temperature range 50/80°C<sup>3)</sup></b>																	
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions	Effective anchorage depth $h_{ef}$ [mm]														85	
		50	100	50	100	50	100	200	50	100	200	50	100	200			
15 / 12 N/mm <sup>2</sup>	w/w	w/d	1,5	2,0	2,0	2,0	2,5	- <sup>2)</sup>	2,0	2,5	- <sup>2)</sup>	2,0	5,5	- <sup>2)</sup>	-		
	d/d		2,5	3,0	4,0	3,0	4,0	9,5	3,0	4,0	9,5	3,0	8,5	9,5	-		
25 / 20 N/mm <sup>2</sup>	w/w	w/d	2,0	2,5	3,0	2,5	3,5	- <sup>2)</sup>	3,0	3,5	- <sup>2)</sup>	3,0	7,5	- <sup>2)</sup>	-		
	d/d		3,5	4,5	5,5	4,5	5,5	12	4,5	5,5	12	4,5	12	12	-		
35 / 28 N/mm <sup>2</sup>	w/w	w/d	2,5	3,0	4,0	3,0	4,0	- <sup>2)</sup>	3,5	4,0	- <sup>2)</sup>	3,5	9,0	- <sup>2)</sup>	-		
	d/d		4,0	5,5	6,5	5,5	6,5	12	5,5	6,5	12	5,5	12	12	-		

- 1) The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
 2) No performance assessed.  
 3) For temperature range 72/120°C:  $N_{Rk(72/120^\circ\text{C})} = 0,83 \cdot N_{Rk(50/80^\circ\text{C})}$ .

**Table C7.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading for edge distance  $c=60\text{mm}$


Anchor rod	M6		M8		M10			M12			M16			-	-		
Internal threaded anchor UPM-I	-		-		-			-			-			M6	M8	M10	M12
														11x85		15x85	
<b><math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,L}</math> [kN]; temperature range 50/80°C and 72/120°C</b>																	
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions	Effective anchorage depth $h_{ef}$ [mm]														85	
		50	100	50	100	50	100	200	50	100	200	50	100	200			
15 / 12 N/mm <sup>2</sup>	w/w w/d d/d	1,2	2,5	1,2	3,0	2,0	3,0	1,5	1,5	3,0	3,0	0,6	3,0	4,5	-		
25 / 20 N/mm <sup>2</sup>		1,5	3,5	1,5	4,5	3,0	4,5	2,5	2,0	4,5	4,5	0,9	4,5	6,0	-		
35 / 28 N/mm <sup>2</sup>		2,0	4,0	2,0	5,0	3,5	5,0	3,0	2,5	5,0	5,0	1,2	5,0	7,5	-		

- 1) The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
 2) No performance assessed.

Factor for job site tests and displacements see Annex C28.

Injection system Pft bonded mortar for masonry	<b>Annex C7</b>
<b>Performance</b> Solid brick Mz, NF, Characteristic resistance under tension and shear loading, edge distance $c=60\text{mm}$	

### Solid calcium silicate brick KS, NF, EN 771-2:2011+A1:2015



Producer	-			
Nominal dimensions	[mm]	length L	width W	height H
		≥ 240	≥ 115	≥ 71
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	≥ 1,8		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	15 / 12 or 25 / 20 or 35 / 28		
Standard or annex	EN 771-2:2011+A1:2015			

**Table C8.1:** Installation parameters

<b>Anchor rod</b>	<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>	<b>M16</b>	-	-							
<b>Internal threaded anchor UPM-I</b>	-	-	-	-	-	<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>					
						<b>11x85</b>	<b>15x85</b>							
<b>Anchor rod and internal threaded anchor UPM-I without perforated sleeve</b>														
Effective anchorage depth $h_{ef}$	[mm]	50	100	50	100	50	100	50	100	85	85			
						200		200				200		
Max. installation torque $\max T_{inst}$	[Nm]	3		5		15		15		25		3	5	15
<b>General installation parameters</b>														
Edge distance $c_{min} = c_{cr}$								60						
Spacing	$s_{min \parallel}$							80						
	$s_{cr \parallel}$							80						
	$s_{min \perp}$							3x $h_{ef}$						
	$s_{cr \perp}$							3x $h_{ef}$						
<b>Drilling method</b>														
Hammer drilling with hard metal hammer drill														

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength..

**Table C8.2:** Group factors

<b>Anchor rod</b>	<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>	<b>M16</b>	-	-						
<b>Internal threaded anchor UPM-I</b>	-	-	-	-	-	<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>				
						<b>11x85</b>	<b>15x85</b>						
Group factor	$\alpha_{g,N} (s_{min \parallel})$							0,7					
	$\alpha_{g,V} (s_{min \parallel})$							1,3					
	$\alpha_{g,N} (s_{min \perp})$							2,0					
	$\alpha_{g,V} (s_{min \perp})$							2,0					

Injection system PFT bonded mortar for masonry

**Performance**

Solid calcium silicate brick KS, NF, dimensions, installation parameters, Group factors

**Annex C8**

**Solid calcium silicate brick KS, NF, EN 771-2:2011+A1:2015**

**Table C9.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod		M6		M8		M10			M12			M16			-		-	
Internal threaded anchor UPM-I		-		-		-			-			-			M6	M8	M10	M12
															11x85		15x85	
<b><math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN]; temperature range 50/80°C <sup>2)</sup></b>																		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions		Effective anchorage depth $h_{ef}$ [mm]															
			50	100	50	100	50	100	200	50	100	200	50	100	200	85	85	
15 / 12 N/mm <sup>2</sup>	w/w	w/d	2,0	3,0	2,5	4,5	2,5	3,5	7,0	2,5	3,0	6,5	2,5	3,5	8,0	2,5	2,5	
	d/d		4,0	5,5	4,0	8,0	4,0	5,5	12	4,0	4,5	12	4,5	5,5	12	4,0	4,0	
25 / 20 N/mm <sup>2</sup>	w/w	w/d	3,0	4,5	3,5	6,5	3,5	4,5	10	3,5	4,0	9,5	4,0	5,0	11	3,5	3,5	
	d/d		5,5	7,5	6,0	11	6,0	8,0	12	6,0	6,5	12	6,5	8,0	12	6,0	6,0	
35 / 28 N/mm <sup>2</sup>	w/w	w/d	3,5	5,0	4,0	8,0	4,5	5,5	12	4,5	5,0	11	4,5	5,5	12	4,5	4,5	
	d/d		6,5	9,0	7,0	12	7,0	9,0	12	7,0	7,5	12	7,5	9,5	12	7,0	7,0	

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
<sup>2)</sup> For temperature range 72/120°C:  $N_{Rk(72/120°C)} = 0,83 \cdot N_{Rk(50/80°C)}$ .


**Table C9.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod		M6		M8		M10			M12			M16			-		-	
Internal threaded anchor UPM-I		-		-		-			-			-			M6	M8	M10	M12
															11x85		15x85	
<b><math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}</math> [kN]; temperature range 50/80°C and 72/120°C</b>																		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions		Effective anchorage depth $h_{ef}$ [mm]															
			50	100	50	100	50	≥100	50	≥100	50	≥100	85	85				
15 / 12 N/mm <sup>2</sup>	w/w	w/d	1,5	3,0	1,5	3,0	1,2	2,0	1,2	2,0	1,2	2,0	1,2	1,2				
	d/d																	
25 / 20 N/mm <sup>2</sup>	w/w	w/d	2,5	4,0	2,5	4,0	1,5	3,0	1,5	3,0	1,5	3,0	1,5	1,5				
	d/d																	
35 / 28 N/mm <sup>2</sup>	w/w	w/d	3,0	4,5	3,0	4,5	1,5	3,5	1,5	3,5	1,5	3,5	1,5	1,5				
	d/d																	

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
Factor for job site tests and displacements see annex C28.

Injection system Pft bonded mortar for masonry	<b>Annex C9</b>
<b>Performance</b> Solid calcium silicate brick KS, NF, Characteristic resistance under tension and shear loading	

### Solid calcium silicate brick KS, EN 771-2:2011+A1:2015



Producer	-			
Nominal dimensions	[mm]	length L	width W	height H
		≥ 240	≥ 115	≥ 113
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	1,8		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	12,5 / 10 or 25 / 20		
Standard or annex	EN 771-2:2011+A1:2015			

**Table C10.1:** Installation parameters  
(Pre-positioned installation with perforated sleeve UPM-SH K)

Anchor rod	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-		M6 M8	-		-		M10 M12	-		-	
			11x85					15x85				
Perforated sleeve UPM-SH K	12x85		16x85		16x130		20x85		20x130			
<b>Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K</b>												
Max. installation torque	max T <sub>inst</sub> [Nm]	2		4								
<b>General installation parameters</b>												
Edge distance	c <sub>min</sub> = c <sub>cr</sub>	100										
Spacing	s <sub>min</sub>	[mm]	255	255	390	255	390					
	s <sub>cr</sub>											
	s <sub>min</sub> ⊥											
	s <sub>cr</sub> ⊥											
<b>Drilling method</b>												
Hammer drilling with hard metal hammer drill												
<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.												
<b>Table C10.2: Group factors</b>												
Anchor rod	M6	M8	M8	M10	M8	M10	M12	M16	M12	M16		
Perforated sleeve UPM-SH K	12x85		16x85		16x130		20x85		20x130			
Group factors	$\frac{\alpha_{g,N}(s_{min   })}{\alpha_{g,V}(s_{min   })}$ $\frac{\alpha_{g,N}(s_{min \perp})}{\alpha_{g,V}(s_{min \perp})}$		[-]		2,0							
Injection system PFT bonded mortar for masonry											<b>Annex C10</b>	
<b>Performance</b> Solid calcium silicate brick KS, dimensions, installation parameters, Group factors												

**Solid calcium silicate brick KS, EN 771-2:2011+A1:2015**

**Table C11.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-	M6	M8	-	-	-	-	M10	M12	-	-	-
		11x85						15x85				
Perforated sleeve UPM-SH K	12x85		16x85			16x130		20x85			20x130	

$N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN]; temperature range 50/80°C <sup>2)</sup>

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions										
12,5 / 10 N/mm <sup>2</sup>	w/w	3,5	2,0	2,0	2,0	6,5				4,5	
	d/d	6,0	4,0	3,5	3,5	10,5				7,0	
25 / 20 N/mm <sup>2</sup>	w/w	5,0	3,0	3,0	3,0	9,5				6,0	
	d/d	8,5	5,5	5,5	5,5	12,0				10,0	

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C no performance assessed.

**Table C11.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-	M6	M8	-	-	-	-	M10	M12	-	-	-
		11x85						15x85				
Perforated sleeve UPM-SH K	12x85		16x85			16x130		20x85			20x130	

$V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}$  [kN]; temperature range 50/80°C <sup>2)</sup>

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions										
12,5 / 10 N/mm <sup>2</sup>	w/w	3,0	3,5								
	d/d										
25 / 20 N/mm <sup>2</sup>	w/w	4,0	5,5								
	d/d										

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C no performance assessed.

Factor for job site tests and displacements see annex C28.


Injection system Pft bonded mortar for masonry

**Performance**


Solid calcium silicate brick KS, Characteristic resistance under tension loading and shear loading

**Annex C11**

**Perforated calcium silicate brick KSL, 3DF, EN 771-2:2011+A1:2015**



Producer	-			
Nominal dimensions	[mm]	length L	width W	height H
		240	175	113
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	$\geq 1,4$		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	10 / 8 or 12,5 / 10 or 15 / 12 or 20 / 16 or 25 / 20		
Standard or annex	EN 771-2:2011+A1:2015			



Dimension see also Annex B11

**Table C12.1:** Installation parameters  
(Pre-positioned installation with perforated sleeve UPM-SH K)

<b>Anchor rod</b>	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	
<b>Internal threaded anchor UPM-I</b>	-		-		M6	M8	-		-		M10	M12	-		
					11x85						15x85				
<b>Perforated sleeve UPM-SH K</b>	12x50		12x85		16x85			16x130		20x85			20x130		
<b>Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K</b>															
Max. installation torque	max T <sub>inst</sub>	[Nm]	2												
<b>General installation parameters</b>															
Edge distance	C <sub>min</sub> = C <sub>cr</sub>		60				80								
Spacing	s <sub>min</sub>	[mm]	100												
	s <sub>cr</sub>		240												
	s <sub>min</sub> ⊥		115												
	s <sub>cr</sub> ⊥		115												
<b>Drilling method</b>															
Hammer drilling with hard metal hammer drill															
<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.															
<b>Table C12.2:</b> Group factors															
<b>Anchor rod</b>	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	
<b>Internal threaded anchor UPM-I</b>	-		-		M6	M8	-		-		M10	M12	-		
					11x85						15x85				
<b>Perforated sleeve UPM-SH K</b>	12x50		12x85		16x85			16x130		20x85			20x130		
Group factors	$\frac{\alpha_{g,N}(s_{min}   )}{\alpha_{g,V}(s_{min}   )}$	[-]	1,5												
	$\frac{\alpha_{g,N}(s_{min} \perp)}{\alpha_{g,V}(s_{min} \perp)}$		2,0												
<b>Injection system PFT bonded mortar for masonry</b>											<b>Annex C12</b>				
<b>Performance</b> Perforated calcium silicate brick KSL, 3DF, dimensions, installation parameters, Group factors															

**Perforated calcium silicate brick KSL, 3DF, EN 771-2:2011+A1:2015**

**Table C13.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-	-	M6	M8	11x85	-	-	-	-	M10	M12	15x85	-	-
Perforated sleeve UPM-SH K	12x50	12x85	16x85			16x130			20x85			20x130		

$N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN]; temperature range 50/80°C<sup>2)</sup>

Mean compressive strength/ Min. comp. strength single brick <sup>1)</sup>	Use conditions													
	w/w	w/d	1,5		2,0		2,0		2,0		2,0		2,0	
<b>10 / 8 N/mm<sup>2</sup></b>	w/w	w/d	1,5		2,0		2,0		2,0		2,0		2,0	
	d/d		1,5		2,0		2,5		2,5		2,5		2,5	
<b>12,5 / 10 N/mm<sup>2</sup></b>	w/w	w/d	2,0		2,0		2,5		2,5		2,5		2,5	
	d/d		2,0		2,5		3,0		3,0		3,0		3,0	
<b>15 / 12 N/mm<sup>2</sup></b>	w/w	w/d	2,5		2,5		3,0		3,0		3,0		3,0	
	d/d		2,5		3,0		3,5		3,5		3,5		3,5	
<b>20 / 16 N/mm<sup>2</sup></b>	w/w	w/d	3,0		3,5		4,5		4,5		4,5		4,5	
	d/d		3,5		4,0		4,5		4,5		4,5		4,5	
<b>25 / 20 N/mm<sup>2</sup></b>	w/w	w/d	4,0		4,5		5,5		5,5		5,5		5,5	
	d/d		4,5		5,0		6,0		6,0		6,0		6,0	

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C:  $N_{Rk(72/120°C)} = 0,83 \cdot N_{Rk(50/80°C)}$ .

Factor for job site tests and displacements see annex C28.

Injection system Pft bonded mortar for masonry

**Performance**

Perforated calcium silicate brick KSL, 3DF, Characteristic resistance under tension loading

**Annex C13**

**Perforated calcium silicate brick KSL, 3DF, EN 771-2:2011+A1:2015**

**Table C14.1:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-		-		M6	M8	-		-		M10	M12	-	
					11x85						15x85			
Perforated sleeve UPM-SH K	12x50		12x85		16x85			16x130		20x85			20x130	

$V_{RK} = V_{RK,b} = V_{RK,c,II} = V_{RK,c,\perp}$  [kN]; temperature range 50/80°C and 72/120°C

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions																
10 / 8 N/mm <sup>2</sup>	w/w	w/d	1,5						3,0						2,5	3,0	2,5
	d/d																
12,5 / 10 N/mm <sup>2</sup>	w/w	w/d	2,0						3,5								
	d/d																
15 / 12 N/mm <sup>2</sup>	w/w	w/d	2,5						4,5						4,0	4,5	4,0
	d/d																
20 / 16 N/mm <sup>2</sup>	w/w	w/d	3,0	3,5	3,0	3,5	3,0	6,0						5,5	6,0	5,5	
	d/d																
25 / 20 N/mm <sup>2</sup>	w/w	w/d	4,0	4,5	4,0	4,5	4,0	7,5						6,5	7,5	6,5	
	d/d																

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Factor for job site tests and displacements see annex C28.


Injection system PfT bonded mortar for masonry

**Performance**


Perforated calcium silicate brick KSL, 3DF, Characteristic resistance under shear loading

**Annex C14**

### Vertical perforated brick HLz, EN 771-1:2011+A1:2015



Producer	e.g. Wienerberger, Poroton			
Nominal dimensions	[mm]	length L	width W	height H
		500	175	237
		370	240	237
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	≥ 1,0		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	5 / 4 or 7,5 / 6 or 10 / 8 or 12,5 / 10 or 15 / 12		
Standard or annex	EN 771-1:2011+A1:2015			



Dimension see also Annex B11

Table C15.1: Installation parameters

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-	-	-	-	M6	M8	-	-	-	M10	M12	-	-	-
					11x85					15x85				
Perforated sleeve UPM-SH K	12x50		12x85		16x85			16x130		20x85			20x130	
Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K														
Max. installation torque	max T <sub>inst</sub>	[Nm]	2											
General installation parameters														
Edge distance	C <sub>min</sub> = C <sub>cr</sub>	[mm]	100											
Spacing	S <sub>min</sub>	[mm]	100											
	S <sub>cr</sub>	[mm]	500 (370)											
	S <sub>min</sub> ⊥	[mm]	100											
	S <sub>cr</sub> ⊥	[mm]	240											
Drilling method														
Hammer drilling with hard metal hammer drill														

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Table C15.2: Group factors

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-	-	-	-	M6	M8	-	-	-	M10	M12	-	-	-
					11x85					15x85				
Perforated sleeve UPM-SH K	12x50		12x85		16x85			16x130		20x85			20x130	
Group factors	$\alpha_{g,N} (S_{min}   ) =$ $\alpha_{g,V} (S_{min}   ) =$ $\alpha_{g,N} (S_{min} \perp) =$ $\alpha_{g,V} (S_{min} \perp) =$	[-]	1,0											

Injection system PfT bonded mortar for masonry

**Performance**

Vertical perforated brick HLz, dimensions, installation parameters, Group factors

**Annex C15**

### Vertical perforated brick HLz, EN 771-1:2011+A1:2015

**Table C16.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-	-	M6	M8	M6	M8	-	-	M10	M12	-	-	-	-
			11x85						15x85					
Perforated sleeve UPM-SH K	12x50	12x85	16x85		16x130		20x85		20x130					
<b><math>N_{RK} = N_{RK,p} = N_{RK,b} = N_{RK,p,c} = N_{RK,b,c}</math> [kN]; temperature range 50/80°C<sup>2)</sup></b>														
Mean compressive strength / Min. comp. strength single brick <sup>1)</sup>	Use conditions													
<b>5 / 4 N/mm<sup>2</sup></b>	w/w	w/d	0,30		0,90		1,20							
	d/d		0,40		0,90		1,20							
<b>7,5 / 6 N/mm<sup>2</sup></b>	w/w	w/d	0,50		1,50		2,00							
	d/d		0,60		1,50		2,00							
<b>10 / 8 N/mm<sup>2</sup></b>	w/w	w/d	0,75		2,00		2,50							
	d/d		0,75		2,00		2,50							
<b>12,5 / 10 N/mm<sup>2</sup></b>	w/w	w/d	0,90		2,50		3,00							
	d/d		0,90		2,50		3,00							
<b>15 / 12 N/mm<sup>2</sup></b>	w/w	w/d	0,90		3,00		3,50							
	d/d		1,20		3,00		4,00							

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C:  $N_{RK(72/120°C)} = 0,83 \cdot N_{RK(50/80°C)}$ .

**Table C16.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	
Internal threaded anchor UPM-I	-	-	M6	M8	M6	M8	-	-	M10	M12	-	-	-	-	
			11x85						15x85						
Perforated sleeve UPM-SH K	12x50	12x85	16x85		16x130		20x85		20x130						
<b><math>V_{RK} = V_{RK,b} = V_{RK,c,II} = V_{RK,c,I}</math> [kN]; temperature range 50/80°C and 72/120°C</b>															
Mean compressive strength / Min. comp. strength single brick <sup>1)</sup>	Use conditions														
<b>5 / 4 N/mm<sup>2</sup></b>	w/w w/d d/d	0,50		0,60		0,50		0,60							
		0,75		0,90		0,75		0,90							
0,90		1,20		0,90		1,20									
1,20		1,50		1,20		1,50									
1,50		2,00		1,50		2,00									

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Factor for job site tests and displacements see annex C28.


Injection system Pft bonded mortar for masonry

**Performance**


Vertical perforated brick HLz, Characteristic resistance under tension and shear loading

**Annex C16**

### Vertical perforated brick HLz, 2DF, EN 771-1:2011+A1:2015



Producer	e.g. Wienerberger			
Nominal dimensions	[mm]	length L	width W	height H
		240	115	113
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	$\geq 1,4$		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	7,5 / 6 or 12,5 / 10 or 20 / 16 or 25 / 20 or 35 / 28		
Standard or annex	EN 771-1:2011+A1:2015			



Dimension see also Annex B11

Table C20.1: Installation parameters

Anchor rod	M6	M8	M6	M8	-	M8	M10	-	M12	M16	
Internal threaded anchor UPM-I	-		-		M6	M8	-		M10	M12	-
					11x85				15x85		
Perforated sleeve UPM-SH K	12x50		12x85		16x85			20x85			

#### Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K

Max. installation torque	$\max T_{inst}$ [Nm]	2
--------------------------	----------------------	---

#### General installation parameters

Edge distance	$C_{min} = C_{cr}$	80
Spacing	$S_{cr \parallel} = S_{min \parallel}$	240
	$S_{cr \perp} = S_{min \perp}$	115

#### Drilling method

Hammer drilling with hard metal hammer drill

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Table C20.2: Group factors

Anchor rod	M6	M8	M6	M8	-	M8	M10	-	M12	M16	
Internal threaded anchor UPM-I	-		-		M6	M8	-		M10	M12	-
					11x85				15x85		
Perforated sleeve UPM-SH K	12x50		12x85		16x85			20x85			

Group factors	$\alpha_{g,N} (S_{min \parallel})$	[-]	2
	$\alpha_{g,V} (S_{min \parallel})$		
	$\alpha_{g,N} (S_{min \perp})$		
	$\alpha_{g,V} (S_{min \perp})$		

Injection system PfT bonded mortar for masonry

#### Performance

Vertical perforated brick HLz, 2DF, dimensions, installation parameters, Group factors

**Annex C17**

### Vertical perforated brick HLz, 2DF, EN 771-1:2011+A1:2015

**Table C18.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M6	M8	M6	M8	-	M8	M10	-	M12	M16
Internal threaded anchor UPM-I	-	-	M6	M8				M10	M12	-
			11x85					15x85		
Perforated sleeve UPM-SH K	12x50		12x85		16x85			20x85		
<b><math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN]; temperature range 50/80°C<sup>2)</sup></b>										
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions									
7,5 / 6 N/mm <sup>2</sup>	w/w	w/d	0,75	0,90	0,75			0,90		
	d/d		0,75	1,20	0,75			0,90		
12,5 / 10 N/mm <sup>2</sup>	w/w	w/d	1,20	1,50	1,20			1,50		
	d/d		1,20	2,00	1,20			1,50		
20 / 16 N/mm <sup>2</sup>	w/w	w/d	2,00	2,50	2,00			2,00		
	d/d		2,00	3,00	2,00			2,50		
25 / 20 N/mm <sup>2</sup>	w/w	w/d	2,50	3,50	2,50			3,00		
	d/d		2,50	4,00	2,50			3,00		
35 / 28 N/mm <sup>2</sup>	w/w	w/d	3,00	5,00	3,50			4,00		
	d/d		3,50	5,50	3,50			4,50		

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C:  $N_{Rk(72/120^\circ C)} = 0,83 \cdot N_{Rk(50/80^\circ C)}$ .

**Table C18.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod	M6	M8	M6	M8	-	M8	M10	-	M12	M16
Internal threaded anchor UPM-I	-	-	M6	M8				M10	M12	-
			11x85					15x85		
Perforated sleeve UPM-SH K	12x50		12x85		16x85			20x85		
<b><math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}</math> [kN]; temperature range 50/80°C and 72/120°C</b>										
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions									
7,5 / 6 N/mm <sup>2</sup>	w/w	w/d	1,2	1,5	1,2	2,0	1,2	1,5		2,5
			2,0	2,5	2,0	4,0	2,0	2,5		4,5
			3,0	3,5	3,0	6,0	3,0	3,5		7,0
			4,0	4,5	4,0	7,5	4,0	4,5		8,5
			5,0	6,5	5,0	9,5	5,0	6,5		12,0

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Factor for job site tests and displacements see annex C28.


Injection system Pft bonded mortar for masonry

**Performance**

Vertical perforated brick HLz, 2DF,  
Characteristic resistance under tension and shear loading

**Annex C18**

**Vertical perforated brick HLz filled with mineral wool, EN 771-1:2011+A1:2015**



Producer	e.g. Wienerberger			
Nominal dimensions	[mm]	length L	width W	height H
		≥ 365	≥ 248	≥ 245
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	0,6		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	10 / 8		
Standard or annex	EN 771-1:2011+A1:2015			



Dimension see also Annex B12

**Table C19.1:** Installation parameters  
(Pre-positioned installation with perforated sleeve UPM-SH K)

<b>Anchor rod</b>	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
<b>Internal threaded anchor UPM-I</b>	-		M6	M8	-		-		M10	M12	-	
			11x85						15x85			
<b>Perforated sleeve UPM-SH K</b>	12x85		16x85			16x130		20x85			20x130	
<b>Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K</b>												
Max. installation torque	max T <sub>inst</sub> [Nm]	2		4								
<b>General installation parameters</b>												
Edge distance	C <sub>min</sub> = C <sub>cr</sub>	100										
Spacing	S <sub>min</sub>	250										
	S <sub>cr</sub>	245										
	S <sub>min</sub> ⊥	245										
	S <sub>cr</sub> ⊥	245										
<b>Drilling method</b>												
Hammer drilling with hard metal hammer drill												
<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.												
<b>Table C19.2: Group factors</b>												
<b>Anchor rod</b>	M6	M8	M8	M10	M8	M10	M12	M16	M12	M16		
<b>Perforated sleeve UPM-SH K</b>	12x85		16x85		16x130		20x85			20x130		
Group factors	$\alpha_{g,N} (S_{min}   ) =$ $\alpha_{g,V} (S_{min}   ) =$ $\alpha_{g,N} (S_{min} \perp) =$ $\alpha_{g,V} (S_{min} \perp) =$	[-]		2,0								
Injection system Pft bonded mortar for masonry										<b>Annex C19</b>		
<b>Performance</b> Vertical perforated brick HLz filled with mineral wool, dimensions, installation parameters, Group factors												

**Vertical perforated brick HLz filled with mineral wool, EN 771-1:2011+A1:2015**

**Table C20.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	M12	M16
Internal threaded anchor UPM-I	-		M6	M8	-		-	M10	M12	-		-	-	
	-		11x85		-		-	15x85		-		-	-	
Perforated sleeve UPM-SH K	12x85		16x85			16x130		20x85			20x130		20x200	
<b><math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN]; temperature range 50/80°C <sup>2)</sup></b>														
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions													
10 / 8 N/mm <sup>2</sup>	w/w	2,0	1,5	2,5		2,0		2,0	2,0	3,0				
	d/d	2,0	2,0	3,0		2,0		2,0	2,0	3,0				

- <sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
<sup>2)</sup> For temperature range 72/120°C no performance assessed.

**Table C20.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading (Pre-positioned installation)

Anchor rod	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	M12	M16
Internal threaded anchor UPM-I	-		M6	M8	-		-	M10	M12	-		-	-	
	-		11x85		-		-	15x85		-		-	-	
Perforated sleeve UPM-SH K	12x85		16x85			16x130		20x85			20x130		20x200	
<b><math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}</math> [kN]; temperature range 50/80°C <sup>2)</sup></b>														
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions													
10 / 8 N/mm <sup>2</sup>	w/w	2,5	3,0	3,0		3,0		1,5		1,5		1,5		1,5
	d/d	2,5	3,0	3,0		3,0		1,5		1,5		1,5		1,5

- <sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.  
<sup>2)</sup> For temperature range 72/120°C no performance assessed.

Factor for job site tests and displacements see annex C28.


Injection system PfT bonded mortar for masonry

**Performance**


Vertical perforated brick HLz filled with mineral wool, Characteristic resistance under tension loading and shear loading

**Annex C20**

### Vertical perforated brick HLz, EN 771-1:2011+A1:2015



Producer	e.g. Wienerberger			
Nominal dimensions	[mm]	length L	width W	height H
		≥ 240	≥ 175	≥ 113
Mean gross dry density $\rho$	[kg/dm <sup>3</sup> ]	0,9		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	[N/mm <sup>2</sup> ]	12,5 / 10		
Standard or annex	EN 771-1:2011+A1:2015			



Dimension see also Annex B12

**Table C21.1:** Installation parameters  
(Pre-positioned installation with perforated sleeve UPM-SH K)

Anchor rod	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16
Internal threaded anchor UPM-I	-		M6	M8	-		-		M10	M12	-	
			11x85						15x85			
Perforated sleeve UPM-SH K	12x85		16x85			16x130		20x85			20x130	

#### Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K

Max. installation torque	max $T_{inst}$ [Nm]	2	4									
--------------------------	---------------------	---	---	--	--	--	--	--	--	--	--	--

#### General installation parameters

Edge distance	$c_{min} = c_{cr}$	100										
Spacing	$s_{min \parallel}$	240										
	$s_{cr \parallel}$	240										
	$s_{min \perp}$	115										
	$s_{cr \perp}$	115										

#### Drilling method

Hammer drilling with hard metal hammer drill

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

**Table C21.2:** Group factors

Anchor rod	M6	M8	M8	M10	M8	M10	M12	M16	M12	M16
Perforated sleeve UPM-SH K	12x85		16x85		16x130		20x85		20x130	
Group factors	$\alpha_{g,N}(s_{min \parallel}) =$ $\alpha_{g,V}(s_{min \parallel}) =$ $\alpha_{g,N}(s_{min \perp}) =$ $\alpha_{g,V}(s_{min \perp}) =$		[-]		2,0					

Injection system PFT bonded mortar for masonry

#### Performance

Vertical perforated brick HLz, dimensions, installation parameters, Group factors

**Annex C21**

**Vertical perforated brick HLz, EN 771-1:2011+A1:2015**

**Table C22.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading (Pre-positioned installation)

Anchor rod	M6	M8	-		M8	M10	M8	M10	-		M12	M16	M12	M16
Internal threaded anchor UPM-I	-		M6	M8	-		-		M10	M12	-		-	
			11x85						15x85					
Perforated sleeve UPM-SH K	12x85		16x85			16x130			20x85			20x130		

$N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}$  [kN]; temperature range 50/80°C <sup>2)</sup>

Mean compressive strength/ Min. compressive strength single brick <sup>1)</sup>	Use con- ditions													
12,5 / 10 N/mm <sup>2</sup>	w/w	3,5	4,0			4,5			4,5			4,0		
	d/d	4	4,5			5,0			5,0			4,0		

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C no performance assessed.

**Table C22.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading (Pre-positioned installation)

Anchor rod	M6	M8	-		M8	M10	M8	M10	-		M12	M16	M12	M16
Internal threaded anchor UPM-I	-		M6	M8	-		-		M10	M12	-		-	
			11x85						15x85					
Perforated sleeve UPM-SH K	12x85		16x85			16x130			20x85			20x130		

$V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}$  [kN]; temperature range 50/80°C <sup>2)</sup>

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use con- ditions														
12,5 / 10 N/mm <sup>2</sup>	w/w	4,0	5,5	4,0	5,5	5,5	7,0	5,5	7,0	7,0	6,0	6,0	8,0	6,0	8,0
	d/d	4,0	5,5	4,0	5,5	5,5	7,0	5,5	7,0	7,0	6,0	6,0	8,0	6,0	8,0

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C no performance assessed.

Factor for job site tests and displacements see annex C28.


Injection system PfT bonded mortar for masonry

**Performance**


Vertical perforated brick HLz, Characteristic resistance under tension loading and shear loading

**Annex C22**

**Light-weight concrete hollow block Hbl, EN 771-3:2011+A1:2015**



Producer	-		
Nominal dimensions [mm]	length L	width W	height H
	362	240	240
Mean gross dry density $\rho$ [kg/dm <sup>3</sup> ]	≥ 1,0		
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup> [N/mm <sup>2</sup> ]	2,5 / 2 or 5 / 4		
Standard or annex	EN 771-3:2011+A1:2015		



Dimension see also Annex B12

**Table C23.1:** Installation parameters  
(Pre-positioned installation with perforated sleeve UPM-SH K)

<b>Anchor rod</b>	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	M12	M16
<b>Internal threaded anchor UPM-I</b>	-		-		M6	M8	-		-		M10	M12	-		-	
					11x85						15x85					
<b>Perforated sleeve UPM-SH K</b>	12x50		12x85		16x85			16x130		20x85			20x130		20x200	

**Anchor rod and internal threaded anchor UPM-I with perforated sleeve UPM-SH K**

Max. installation torque $\max T_{inst}$ [Nm]	2														
---	---	--	--	--	--	--	--	--	--	--	--	--	--	--	--

**General installation parameters**

Edge distance $C_{min} = C_{cr}$	60															
Spacing	[mm]	$S_{min \parallel}$	100													
		$S_{cr \parallel}$	362													
		$S_{min \perp} = S_{cr \perp}$	240													

**Drilling method**

Hammer drilling with hard metal hammer drill

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

**Table C23.2:** Group factors

<b>Anchor rod</b>	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	M12	M16
<b>Internal threaded anchor UPM-I</b>	-		-		M6	M8	-		-		M10	M12	-		-	
					11x85						15x85					
<b>Perforated sleeve UPM-SH K</b>	12x50		12x85		16x85			16x130		20x85			20x130		20x200	

Group factors	[-]	$\alpha_{g,N} (S_{min \parallel})$	1,2													
		$\alpha_{g,V} (S_{min \parallel})$	1,1													
		$\alpha_{g,N} (S_{min \perp})$	2,0													
		$\alpha_{g,V} (S_{min \perp})$														

Injection system Pft bonded mortar for masonry

**Performance**

Light-weight concrete hollow block Hbl, dimensions, installation parameters, Group factors

**Annex C23**

### Light-weight concrete hollow block Hbl, EN 771-3:2011+A1:2015

**Table C24.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading (Pre-positioned installation)

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	M12	M16	
Internal threaded anchor UPM-I	-		-		M6	M8	-		-		M10	M12	-		-		
	-		-		11x85		-		-		15x85		-		-		
Perforated sleeve UPM-SH K	12x50		12x85		16x85			16x130			20x85			20x130		20x200	

$N_{RK} = N_{RK,p} = N_{RK,b} = N_{RK,p,c} = N_{RK,b,c}$  [kN]; temperature range 50/80°C<sup>2)</sup>

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions															
	2,5 / 2 N/mm <sup>2</sup>	w/w	w/d	1,2				1,5				2,5				
d/d		d/d	1,2				1,5				2,5					
5 / 4 N/mm <sup>2</sup>	w/w	w/d	2,0				3,0				5,0					
	d/d	d/d	2,5				3,0				5,5					

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>2)</sup> For temperature range 72/120°C:  $N_{RK(72/120^\circ C)} = 0,83 \cdot N_{RK(50/80^\circ C)}$ .

**Table C24.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading (Pre-positioned installation)

Anchor rod	M6	M8	M6	M8	-	M8	M10	M8	M10	-	M12	M16	M12	M16	M12	M16	
Internal threaded anchor UPM-I	-		-		M6	M8	-		-		M10	M12	-		-		
	-		-		11x85		-		-		15x85		-		-		
Perforated sleeve UPM-SH K	12x50		12x85		16x85			16x130			20x85			20x130		20x200	

$V_{RK} = V_{RK,b} = V_{RK,c,II} = V_{RK,c,I}$  [kN]; temperature range 50/80°C and 72/120°C

Mean compressive strength / Min. compressive strength single brick <sup>1)</sup>	Use conditions															
	2,5 / 2 N/mm <sup>2</sup>	w/w	w/d	0,9												
d/d		d/d	0,9													
5 / 4 N/mm <sup>2</sup>	w/w	w/d	2,0													
	d/d	d/d	2,0													

<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

Factor for job site tests and displacements see annex C28.


Injection system Pft bonded mortar for masonry

**Performance**

Light-weight concrete hollow block Hbl, Characteristic resistance under tension loading and shear loading

**Annex C24**

### Autoclaved aerated concrete, EN 771-4:2011+A1:2015



Producer	e.g. Ytong		
Mean gross dry density $\rho$ [kg/dm <sup>3</sup> ]	0,35	0,5	0,65
Mean compressive strength / Min. compressive strength single brick <sup>1)</sup> [N/mm <sup>2</sup> ]	2,5 / 2	5 / 4	8 / 6
Standard or annex	EN 771-4:2011+A1:2015		

**Table C25.1: Installation parameters**

Anchor rod	M6	M8	M10	M12	M16	-		-				
<b>Internal threaded anchor UPM-I</b>	-	-	-	-	-	<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>			
						<b>11x85</b>		<b>15x85</b>				
<b>Anchor rod and internal threaded anchor UPM-I without perforated sleeve</b>												
Effective anchorage depth $h_{ef}$ [mm]	100	200	100	200	100	200	100	200	85			
Max. installation torque $\max T_{inst}$ [Nm]	1	4	1	8	2	12	2	16	2	20	1	2
<b>General installation parameters</b>												
Edge distance $c_{min} = c_{cr}$	100											
$s_{cr \parallel} = s_{min \parallel}$	250											
$h_{ef}=200mm$ $s_{min \parallel}$	80											
$h_{ef}=200mm$ $s_{cr \parallel}$ [mm]	3x $h_{ef}$											
Spacing $s_{cr \perp} = s_{min \perp}$	250											
$h_{ef}=200mm$ $s_{min \perp}$	80											
$h_{ef}=200mm$ $s_{cr \perp}$	3x $h_{ef}$											
<b>Drilling method</b>												
Hammer drilling with hard metal hammer drill												
<sup>1)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.												
Injection system PFT bonded mortar for masonry								<b>Annex C25</b>				
<b>Performance</b> Autoclaved aerated concrete, dimensions, installation parameters												

**Autoclaved aerated concrete, EN 771-4:2011+A1:2015**

**Table C26.1:** Group factors for autoclaved aerated concrete  
(Min. compressive strength single brick = 2 N/mm<sup>2</sup>)

Anchor rod	M6	M8	M10	M12	M16	-		-	
Internal threaded anchor UPM-I	-	-	-	-	-	M6	M8	M10	M12
						11x85		15x85	
Group factors	[-]	$h_{ef}=200 \alpha_{g,N} (S_{min} \parallel)$	1,6			- <sup>1)</sup>		- <sup>1)</sup>	
		$h_{ef}=200 \alpha_{g,V} (S_{min} \parallel)$	1,1			- <sup>1)</sup>		- <sup>1)</sup>	
		$\alpha_{g,N} \parallel, \alpha_{g,V} (S_{min} \parallel)$	2,0						
		$h_{ef}=200 \alpha_{g,N} (S_{min} \perp)$	1,6			- <sup>1)</sup>		- <sup>1)</sup>	
		$h_{ef}=200 \alpha_{g,V} (S_{min} \perp)$	0,8			- <sup>1)</sup>		- <sup>1)</sup>	
		$\alpha_{g,N} \perp, \alpha_{g,V} (S_{min} \perp)$	2,0						

<sup>1)</sup> No performance assessed.

**Table C26.2:** Group factors for autoclaved aerated concrete  
(Min. compressive strength single brick = 4 N/mm<sup>2</sup>)

Anchor rod	M6	M8	M10	M12	M16	-		-	
Internal threaded anchor UPM-I	-	-	-	-	-	M6	M8	M10	M12
						11x85		15x85	
Group factors	[-]	$h_{ef}=200 \alpha_{g,N} (S_{min} \parallel)$	0,7			- <sup>1)</sup>		- <sup>1)</sup>	
		$h_{ef}=200 \alpha_{g,V} (S_{min} \parallel)$	2,0			- <sup>1)</sup>		- <sup>1)</sup>	
		$\alpha_{g,N} \parallel, \alpha_{g,V} (S_{min} \parallel)$	2,0						
		$h_{ef}=200 \alpha_{g,N} (S_{min} \perp)$	0,7			- <sup>1)</sup>		- <sup>1)</sup>	
		$h_{ef}=200 \alpha_{g,V} (S_{min} \perp)$	1,2			- <sup>1)</sup>		- <sup>1)</sup>	
		$\alpha_{g,N} \perp, \alpha_{g,V} (S_{min} \perp)$	2,0						

<sup>1)</sup> No performance assessed.

**Table C26.3:** Group factors for autoclaved aerated concrete  
(Min. compressive strength single brick = 6 N/mm<sup>2</sup>)

Anchor rod	M6	M8	M10	M12	M16	-		-	
Internal threaded anchor UPM-I	-	-	-	-	-	M6	M8	M10	M12
						11x85		15x85	
Group factors	[-]	$h_{ef}=200 \alpha_{g,N} (S_{min} \parallel)$	0,7			- <sup>1)</sup>		- <sup>1)</sup>	
		$h_{ef}=200 \alpha_{g,V} (S_{min} \parallel)$	2,0			- <sup>1)</sup>		- <sup>1)</sup>	
		$\alpha_{g,N} \parallel, \alpha_{g,V} (S_{min} \parallel)$	2,0						
		$h_{ef}=200 \alpha_{g,N} (S_{min} \perp)$	0,7			- <sup>1)</sup>		- <sup>1)</sup>	
		$h_{ef}=200 \alpha_{g,V} (S_{min} \perp)$	1,2			- <sup>1)</sup>		- <sup>1)</sup>	
		$\alpha_{g,N} \perp, \alpha_{g,V} (S_{min} \perp)$	2,0						

<sup>1)</sup> No performance assessed.

Injection system Pft bonded mortar for masonry

**Performance**  
Autoclaved aerated concrete, Group factors

**Annex C26**

**Autoclaved aerated concrete, EN 771-4:2011+A1:2015**

**Table C27.1:** Characteristic resistance to pull-out failure or brick breakout failure of a single anchor under tension loading

Anchor rod		M6	M8	M10	M12	M16	-		-				
Internal threaded anchor UPM-I		-	-	-	-	-	M6	M8	M10	M12			
							11x85		15x85				
<b><math>N_{Rk} = N_{Rk,p} = N_{Rk,b} = N_{Rk,p,c} = N_{Rk,b,c}</math> [kN]; temperature range 50/80°C<sup>3)</sup></b>													
Mean compressive strength / Min. compressive strength single brick <sup>2)</sup>	Use conditions	Effective anchorage depth $h_{ef}$ [mm]											
		100	200	100	200	100	200	100	200	100	200	85	
2,5 / 2 N/mm <sup>2</sup>	w/w w/d	1,2	1,2	1,5	2,0	1,5	3,0	1,5	3,0	2,0	3,0	1,5	1,5
	d/d	1,5	3,0	1,5	3,0	1,5	3,5	2,0	4,0	2,0	4,0	1,5	1,5
5 / 4 N/mm <sup>2</sup>	w/w w/d	1,2	- <sup>1)</sup>	2,0	1,5	2,5	3,5	2,5	3,5	2,0	3,5	2,0	1,5
	d/d	1,5	- <sup>1)</sup>	2,0	3,0	3,0	5,0	2,5	5,0	2,0	5,0	2,0	1,5
8 / 6 N/mm <sup>2</sup>	w/w w/d	1,5	- <sup>1)</sup>	3,0	2,5	4,5	5,0	4,5	7,0	3,0	8,5	3,5	2,5
	d/d	1,5	- <sup>1)</sup>	3,5	4,0	5,0	7,0	5,0	9,0	3,0	11,5	3,5	2,5

<sup>1)</sup> No performance assessed.

<sup>2)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength.

<sup>3)</sup> For temperature range 72/120°C:  $N_{Rk(72/120°C)} = 0,83 \cdot N_{Rk(50/80°C)}$ .

**Table C27.2:** Characteristic resistance to local brick failure or brick edge failure of a single anchor under shear loading

Anchor rod		M6	M8	M10	M12	M16	-		-				
Internal threaded anchor UPM-I		-	-	-	-	-	M6	M8	M10	M12			
							11x85		15x85				
<b><math>V_{Rk} = V_{Rk,b} = V_{Rk,c,II} = V_{Rk,c,I}</math> [kN]; temperature range 50/80°C and 72/120°C</b>													
Mean compressive strength / Min. compressive strength single brick <sup>2)</sup>	Use conditions	Effective anchorage depth $h_{ef}$ [mm]											
		100	200	100	200	100	200	100	200	100	200	85	
2,5 / 2 N/mm <sup>2</sup>	w/w w/d	1,2	1,2	1,2	1,2	1,2	1,2	1,5	1,2	1,2	1,2	1,2	1,5
	d/d	1,2	1,2	1,2	1,2	1,2	1,2	1,5	1,2	1,2	1,2	1,2	1,5
5 / 4 N/mm <sup>2</sup>	w/w w/d	2,0	- <sup>1)</sup>	2,5	2,0	2,0	2,0	2,5	2,0	2,0	2,0	2,0	2,5
	d/d	2,0	- <sup>1)</sup>	2,5	2,0	2,0	2,0	2,5	2,0	2,0	2,0	2,0	2,5
8 / 6 N/mm <sup>2</sup>	w/w w/d	2,5	- <sup>1)</sup>	3,0	2,5	3,0	3,0	3,5	4,0	4,5	4,5	2,5	3,5
	d/d	2,5	- <sup>1)</sup>	3,0	2,5	3,0	3,0	3,5	4,0	4,5	4,5	2,5	3,5

<sup>1)</sup> No performance assessed.

<sup>2)</sup> The minimum compressive strength of the single brick must not be less than 80% of the mean compressive strength

Factor for job site tests and displacements see annex C28.

Injection system PFT bonded mortar for masonry

**Performance**

Autoclaved aerated concrete,  
Characteristic resistance under tension and shear loading

**Annex C27**

<b>β-factors for job site tests; displacements</b>					
<b>Table C28.1: β-factors for job site tests</b>					
use conditions		w/w and w/d		d/d	
temperature range [°C]		50/80	72/120	50/80	72/120
Material	Size	β-factors [-]			
solid units	M6	0,55	0,46	0,96	0,80
	M8	0,57	0,51		
	M10	0,59	0,52		
	M12 UPM-I 11x85	0,60	0,54		
	M16 UPM-I 15x85	0,62	0,52		
	UPM-SH 16x85 K	0,55	0,46		
hollow units	all sizes	0,86	0,72	0,96	0,80
Autoclaved aerated concrete cylindrical drill hole	all sizes	0,73	0,73	0,81	0,81

<b>Table C28.2: Displacements</b>						
Material	N /[kN]	δN <sub>0</sub> [mm]	δN <sub>∞</sub> [mm]	V [kN]	δV <sub>0</sub> [mm]	δV <sub>∞</sub> [mm]
solid units and autoclaved aerated concrete h <sub>ef</sub> =100mm	$\frac{N_{Rk}}{1,4 * \gamma_{Mm}}$	0,03	0,06	$\frac{V_{Rk}}{1,4 * \gamma_{Mm}}$	0,82	0,88
hollow units	$\frac{N_{Rk}}{1,4 * \gamma_{Mm}}$	0,48	0,06	$\frac{V_{Rk}}{1,4 * \gamma_{Mm}}$	1,71	2,56
solid brick Mz NF Annex C4 - C7	$\frac{N_{Rk}}{1,4 * \gamma_{Mm}}$	0,74	1,48	$\frac{V_{Rk}}{1,4 * \gamma_{Mm}}$	1,23	1,85
solid brick KS NF Annex C8 / C9	$\frac{N_{Rk}}{1,4 * \gamma_{Mm}}$	0,20	0,40	$\frac{V_{Rk}}{1,4 * \gamma_{Mm}}$	0,91	1,37
AAC h <sub>ef</sub> =200 mm Annex C25 – C27	$\frac{N_{Rk}}{1,4 * \gamma_{Mm}}$	1,03	2,06	$\frac{V_{Rk}}{1,4 * \gamma_{Mm}}$	1,25	1,88

For anchorage in autoclaved aerated concrete (AAC), the partial factor  $\gamma_{MAAC}$  shall be used instead of  $\gamma_{Mm}$ .

Injection system PFT bonded mortar for masonry	<b>Annex C28</b>
<b>Performance</b> β-factors for job site tests; displacements	