

Public-law institution jointly founded by the federal states and the Federation

European Technical Assessment Body
for construction products



European Technical Assessment

ETA-19/0483
of 16 December 2025

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

Injection system VME plus

Product family
to which the construction product belongs

Bonded fasteners and bonded expansion fasteners for use in concrete
(Alternative drilling methods, seismic and fire in steel fibre reinforced concrete, variable working life, time-to-failure assessment)

Manufacturer

MKT
Metall-Kunststoff-Technik GmbH & Co. KG
Auf dem Immel 2
67685 Weilerbach
DEUTSCHLAND

Manufacturing plant

Werk 1,D und Werk 2,D

This European Technical Assessment contains

48 pages including 3 annexes which form an integral part of this assessment

This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of

EAD 330499-02-0601-v01

This version replaces

ETA-19/0483 issued on 12 May 2021

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

The "Injection system VME plus" is a bonded anchor consisting of a cartridge with injection mortar Injection mortar VME plus and a steel element according to Annex A 3 to Annex A 7.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life according to Annex B2, use conditions. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

| Essential characteristic | Performance |
|--|---|
| Characteristic resistance to tension load (static and quasi-static loading) | See Annex B4, C1, C3 to C7, C11 to C14 and C16 to C18 |
| Characteristic resistance to shear load (static and quasi-static loading) | See Annex C2, C8, C15 and C19 |
| Displacements under short-term and long-term loading | See Annex C21 to C25 |
| Characteristic resistance and displacements for seismic performance categories C1 and C2 | See Annex C9, C10, C20, C21 and C22 |

3.2 Safety in case of fire (BWR 2)

| Essential characteristic | Performance |
|--------------------------|----------------------|
| Reaction to fire | Class A1 |
| Resistance to fire | See Annex C26 to C28 |

3.3 Hygiene, health and the environment (BWR 3)

| Essential characteristic | Performance |
|--|-------------------------|
| Content, emission and/or release of dangerous substances | No performance assessed |

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD 330499-02-0601-v01 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.


Issued in Berlin on 16 December 2025 by Deutsches Institut für Bautechnik

Dipl.-Ing. Beatrix Wittstock
Head of Section


beglaubigt:
Baderschneider

Installation threaded rod M8 to M30


Pre-setting installation or through-setting installation (optional annular gap filled with mortar)



Installation internally threaded anchor rod IG M6 to IG M20



Installation reinforcing bar $\varnothing 8$ to $\varnothing 40$



h_{ef} = effective anchorage depth
 h_0 = depth of drill hole
 h_{min} = minimum thickness of member
 t_{fix} = thickness of fixture


Injection System VME plus

Product description
Installation situation

Annex A1

Cartridge Injection Mortar VME plus

Side-by-side cartridge
440 ml
500 bis 540 ml
585 ml
1400 ml




Imprint:


VME plus

Processing and safety instructions, shelf life, charge number, manufacturer's information, quantity information

Static Mixer VM-XHP



Retaining washer and extension nozzle



Injection System VME plus

Product description

Cartridge, static mixer and retaining washer with extension nozzle


Annex A2

Threaded rod

Threaded rod VMU-A and V-A

M8, M10, M12, M16, M20, M24, M27, M30 (zinc plated, A4, HCR)
with washer and hexagon nut

VMU-A



Marking e.g.: \diamond M10

\diamond identifying mark of manufacturing plant

M10 size of thread


additional marking:

-8 strength class 8.8

A4 stainless steel

HC high corrosion resistant steel

V-A



Threaded rod VM-A

M8, M10, M12, M16, M20, M24, M27, M30 (zinc plated, A2, A4, HCR)

- Materials, dimensions and mechanical properties see Table A1

Commercial standard threaded rod

M8, M10, M12, M16, M20, M24, M27, M30 (zinc plated, A2, A4, HCR)


- Materials, dimensions and mechanical properties see Table A1

- Inspection certificate 3.1 acc. to EN 10204:2004 (documents must be retained)

For hot dip galvanized elements, the requirements with regards to the combination of nuts and rods according to EN ISO 10684:2004+AC:2009 Annex F shall be considered.

Filling Washer and reducing adapter

for filling the gap between threaded rod and fixture



Thickness of filling washer
for diameter
< M24: $t = 5$ mm
 \geq M24: $t = 6$ mm



Injection System VME plus

Product description


Threaded rods, Marking, Filling washer VS

Annex A3

Internally threaded anchor rod

Internally threaded anchor rod VMU-IG

VMU-IG M6, VMU-IG M8, VMU-IG M10, VMU-IG M12, VMU-IG M16, VMU-IG M20
(zinc plated, A4, HCR)



Marking e.g.: \diamond M8


\diamond Identifying mark of manufacturing plant

I internal thread (optional)

M8 size of internal thread

Internally threaded anchor rod VZ-IG

VZ-IG M6, VZ-IG M8, VZ-IG M10, VZ-IG M12, VZ-IG M16, VZ-IG M20
(zinc plated, A4, HCR)



Additional marking:

-8 strength class 8.8

A4 stainless steel

HCR high corrosion resistant steel

Requirements on the fastening screw or the threaded rod and nut according to the engineering documents:

- Minimum screw-in depth $L_{sd,min}$ see Table B2
- The length of screw or the threaded rod shall be determined depending on the thickness of fixture t_{fix} , available thread length and the minimum screw-in depth $L_{sd,min}$.
- Materials for screws and threaded rods (incl. nut and washer) must at least correspond to the material and strength class of the internally threaded anchor rod used.

Injection System VME plus

Product description
Internally threaded anchor rods, Marking

Annex A4

Table A1: Materials - Threaded rod and internally threaded anchor rods

| Part | Designation | Material and mechanical properties | | | | | | |
|---|--------------------------------|---|--|------------------------------------|---|----------------------|---|---|
| Steel, zinc plated | | | | | | | | |
| electroplated | | ≥ 5 µm acc. to EN ISO 4042:2022 or | | | | | | |
| hot-dip galvanized | | ≥ 50 µm in average acc. to EN ISO 1461:2022, EN ISO 10684:2004+AC:2009 or | | | | | | |
| sherardized | | ≥ 45 µm acc. to EN ISO 17668:2016 | | | | | | |
| 1 | Threaded rod | Property class | characteristic ultimate strength | | characteristic yield strength | | fracture elongation | EN ISO 683-4:2018, EN 10263:2017 Commercial standard threaded rod: EN ISO 898-1:2013 |
| | | 4.6 | f _{uk} [N/mm ²] | 400 | f _{yk} [N/mm ²] | 240 | A ₅ > 8 % | |
| | | 4.8 | | 400 | | 320 | A ₅ > 8 % | |
| | | 5.6 | | 500 | | 300 | A ₅ > 8 % | |
| | | 5.8 | | 500 | | 400 | A ₅ > 8 % | |
| 8.8 | 800 | 640 | | A ₅ ≥ 12% ¹⁾ | | | | |
| 2 | Hexagon nut | 4 | for class 4.6 or 4.8 rods | | | | Commercial standard nut: e.g. EN ISO 898-2:2022 | |
| | | 5 | for class 4.6, 4.8, 5.6 or 5.8 rods | | | | | |
| | | 8 | for class 4.6, 4.8, 5.6, 5.8 or 8.8 rods | | | | | |
| 3a | Washer | e.g.: EN ISO 7089:2000, EN ISO 7093:2000, EN ISO 7094:2000, EN ISO 887:2006 | | | | | | |
| 3b | Washer with bore | Steel, zinc plated | | | | | | |
| 4 | Internally threaded anchor rod | 5.8 | Steel, electroplated or sherardized | | | A ₅ > 8% | EN ISO 683-4:2018 | |
| | | 8.8 | | | | A ₅ > 8% | | |
| Stainless steel A2 ²⁾ | | CRC II (1.4301 / 1.4307 / 1.4311 / 1.4567 / 1.4541) | | | | | | |
| Stainless steel A4 | | CRC III (1.4401 / 1.4404 / 1.4571 / 1.4578) | | | | | | |
| High corrosion resistant steel HCR | | CRC V (1.4529 / 1.4565) | | | | | | |
| 1 | Threaded rod | Property class | characteristic ultimate strength | | characteristic yield strength | | fracture elongation | EN 10088-1:2023 Commercial standard threaded rod: EN ISO 3506-1:2020 |
| | | 50 | f _{uk} [N/mm ²] | 500 | f _{yk} [N/mm ²] | 210 | A ₅ > 8% | |
| | | 70 | | 700 | | (560) ⁴⁾ | A ₅ ≥ 12% ¹⁾ | |
| 80 ³⁾ | 800 | (640) ⁴⁾ | | A ₅ ≥ 12% ¹⁾ | | | | |
| 2 | Hexagon nut | 50 | for class 50 rods | | | | EN 10088-1:2023 Commercial standard nut: e.g.: EN ISO 3506-2:2020 | |
| | | 70 | for class 50 or 70 rods | | | | | |
| | | 80 ³⁾ | for class 50, 70 or 80 rods | | | | | |
| 3a | Washer | e.g.: EN ISO 7089:2000, EN ISO 7093:2000, EN ISO 7094:2000; EN ISO 887:2006 | | | | | | |
| 3b | Washer with bore | stainless steel A4; high corrosion resistant steel HCR | | | | | | |
| 4 | Internally threaded anchor rod | 50 | IG-M20 | | | A ₅ > 8 % | EN 10088-1:2023 | |
| | | 70 | IG-M6 to IG-M20 | | | A ₅ > 8 % | | |

¹⁾ Fracture elongation A₅ > 8 % for applications without requirements for seismic performance category C2

²⁾ Property classes 50 and 70

³⁾ Property classes 80: M8 up to M24

⁴⁾ Value in brackets for anchor rods VMU-A and V-A


Injection System VME plus

Product description
Materials

Annex A5

Reinforcing bar

Ø 8, Ø 10, Ø 12, Ø 14, Ø 16, Ø 20, Ø 24, Ø 25, Ø 28, Ø 32, Ø 36, Ø 40



- Minimum value of related rip area $f_{R,min}$ according to EN 1992-1-1:2004+AC:2010
- Rip height of the bar shall be in the range $0,05d \leq h \leq 0,07d$
(d: Nominal diameter of the bar; h: Rip height of the bar)

Table A2: Material reinforcing bar

| Part | Designation | Material |
|--------------|---|--|
| Rebar | | |
| 5 | Rebar EN 1992-1-1:2004+AC:2010, Annex C | Bars and de-coiled rods class B or C f_{yk} and k according to NDP or NCI acc. EN 1992-1-1/NA $f_{uk} = f_{tk} = k \cdot f_{yk}$ |

Injection System VME plus

Product description
Product description and material reinforcing bar

Annex A6

Specification of intended use

| Static and quasi-static action | | | | | |
|--------------------------------|--|--|--|---|-------------------------|
| Working life | | 50 years | | 100 years | |
| Base material | | uncracked concrete | cracked concrete | uncracked concrete | cracked concrete |
| | | strength classes C20/25 to C90/105 without fibers strength classes C20/25 to C50/60 with fibers ¹⁾ | | | |
| Drilling method | hammer drilling (HD) vacuum drilling (VD) compressed air drilling (CD) | M8 – M30 IG M6 – IG M20 Ø8 – Ø32 | | | |
| | hammer drilling (HD) compressed air drilling (CD) | Ø36 – Ø40 | no performance assessed | Ø36 – Ø40 | no performance assessed |
| | diamond drilling (DD) | M8 – M30 IG M6 – IG M20 Ø8 – Ø40 | M16 – M30 IG M10 – IG M20 (C20/25 - C50/60 without fibers) | M8 – M30 IG M6 – IG M20 Ø8 – Ø40 | no performance assessed |
| Seismic action | | | | | |
| Performance category | | C1 | | C2 | |
| Base material | | cracked or uncracked concrete | | | |
| | | strength classes C20/25 to C50/60 without fibers strength classes C20/25 to C50/60 with fibers ¹⁾ | | | |
| Drilling method | hammer drilling (HD) vacuum drilling (VD) compressed air drilling (CD) | M8 – M30 Ø8 – Ø32 | | M12 – M30 | |
| | diamond drilling (DD) | no performance assessed | | | |
| Fire exposure | | | | | |
| Base material | | cracked or uncracked concrete | | | |
| | | strength classes C20/25 to C90/105 without fibers strength classes C20/25 to C50/60 with fibers ¹⁾ | | | |
| Drilling method | hammer drilling (HD) vacuum drilling (VD) compressed air drilling (CD) | M8 – M30 IG M6 – IG M20 Ø8 – Ø32 | | | |
| | diamond drilling (DD) | no performance assessed | | | |
| Temperature range | | | | | |
| I: | -40°C to +40°C | max. long term temperature +24°C and max. short term temperature +40°C | | | |
| II: | -40°C to +72°C | max. long term temperature +50°C and max. short term temperature +72°C | | | |
| III: | -40°C to +80°C | max. long term temperature +60°C and max. short term temperature +80°C | | | |

¹⁾ With fibers only by hammer drilling (HD), vacuum drilling (VD) or compressed air drilling (CD)

Injection System VME plus

Intended Use
Specifications

Annex B1

Specification of intended use

Base material:

- compacted, reinforced or unreinforced normal weight concrete with strength classes C20/25 to C90/105 acc. to EN 206:2013+A2:2021
- Steel fiber reinforced concrete according to EN 206:2013 + A2:2021 with steel fibers according to EN 14889-1:2006, section 5, group 1, with a maximum fiber content of 80kg/m³.

Use conditions (Environmental conditions):

For working life for at least 50 and/ or 100 years:

- Structures subject to dry internal conditions: all materials
- For all other conditions:
Intended use of Materials according to Annex A5, Table A1 corresponding corrosion resistance classes CRC according to EN 1993-1-4:2006+A1:2015

For variable working life:

- Structures subject to internal and external conditions (carbon steel, hot dip galvanized according to EN ISO 10684:2004 + AC:2009 with mean thickness $\geq 50 \mu\text{m}$): Classification of atmospheric corrosivity, determination and estimation C1-CX according to EN ISO 9233:2012-02 Table C.1 for a variable working life according to Table B1.

Table B1: Variable working life

| Corrosivity category ¹⁾ | Corrosivity | Working life (years) |
|------------------------------------|-------------|----------------------|
| C1 | very low | 50 |
| C2 | low | 50 |
| C3 | medium | 25 |
| C4 | high | 12,5 |
| C5 | very High | 5 |
| CX | extreme | 2 |

¹⁾ Corrosivity categories according to EN ISO 9233:2012-02, Table C.

Design:

- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e.g. position of the anchor relative to reinforcement or to supports, etc.)
- Anchorages are designed under the responsibility of an engineer experienced in anchorages and concrete work
- Anchorages are designed in accordance with EN 1992-4:2018 or Technical Report TR 055, Edition February 2018
- Fasteners in steel fiber reinforced concrete may be designed in accordance with EN 1992-4:2018. All performance parameters are to be applied as for normal concrete of strength classes C20/25 to C50/60 without fibers
- Anchorages under fire exposure are designed in accordance with Technical Report TR 082, Edition June 2023

Injection System VME plus

Intended Use
Specifications of intended use

Annex B2

Installation:

- Dry or wet concrete or waterfilled drill holes (not seawater)
- Hole drilling
 - HD: hammer drilling,
 - VD: vacuum drilling
 - CD: compressed air drilling,
 - DD: diamond drilling
- Overhead installation allowed
- Fastener installation carried out by appropriately qualified personnel and under the responsibility of the person responsible for technical matters of the site.
- Drill hole must be cleaned directly before installation of the anchor or it must be protected against recontamination in a suitable manner until installation of the anchor. In the event of water inflow or renewed soiling, cleaning must be repeated before assembly.

| | |
|---|-----------------|
| Injection System VME plus | Annex B3 |
| Intended Use Specifications of intended use | |

Table B2: Installation parameters for threaded rods

| Threaded rod | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|---|----------------------------|-----|--------------------------|-----------------|-----|-----|-----|-----|
| Diameter of threaded rod | $d=d_{nom}$ [mm] | 8 | 10 | 12 | 16 | 20 | 24 | 27 | 30 |
| Nominal drill hole diameter | d_0 [mm] | 10 | 12 | 14 | 18 | 22 | 28 | 30 | 35 |
| Effective anchorage depth | $h_{ef,min}$ [mm] | 60 | 60 | 70 | 80 | 90 | 96 | 108 | 120 |
| | $h_{ef,max}$ [mm] | 160 | 200 | 240 | 320 | 400 | 480 | 540 | 600 |
| Diameter of clearance hole in the fixture | Pre-setting installation $d_f \leq$ [mm] | 9 | 12 | 14 | 18 | 22 | 26 | 30 | 33 |
| | Through setting installation d_f [mm] | 12 | 14 | 16 | 20 | 24 | 30 | 33 | 40 |
| Maximum installation torque | $max. T_{inst}$ [Nm] | 10 | 20 | 40 (35) ¹⁾ | 60 | 100 | 170 | 250 | 300 |
| Minimum thickness of member | h_{min} [mm] | $h_{ef} + 30mm \geq 100mm$ | | | $h_{ef} + 2d_0$ | | | | |
| Minimum spacing | s_{min} [mm] | 40 | 50 | 60 | 75 | 95 | 115 | 125 | 140 |
| Minimum edge distance | c_{min} [mm] | 35 | 40 | 45 | 50 | 60 | 65 | 75 | 80 |

¹⁾ Max. installation torque for property class 4.6

Table B3: Installation parameters for internally threaded anchor rods

| Internally threaded anchor rod | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 |
|---|---------------------------|----------------------------|--------|-----------------|---------|---------|---------|
| Inner diameter of threaded rod | d_2 [mm] | 6 | 8 | 10 | 12 | 16 | 20 |
| Outer diameter of threaded rod | $d=d_{nom}$ [mm] | 10 | 12 | 16 | 20 | 24 | 30 |
| Nominal drill hole diameter | d_0 [mm] | 12 | 14 | 18 | 22 | 28 | 35 |
| Effective anchorage depth | $h_{ef,min}$ [mm] | 60 | 70 | 80 | 90 | 96 | 120 |
| | $h_{ef,max}$ [mm] | 200 | 240 | 320 | 400 | 480 | 600 |
| Diameter of clearance hole in the fixture | $d_f \leq$ [mm] | 7 | 9 | 12 | 14 | 18 | 22 |
| Maximum installation torque | $max. T_{inst} \leq$ [Nm] | 10 | 10 | 20 | 40 | 60 | 100 |
| Minimum screw-in depth | $L_{sd,min}$ [mm] | 8 | 8 | 10 | 12 | 16 | 20 |
| Minimum thickness of member | h_{min} [mm] | $h_{ef} + 30mm \geq 100mm$ | | $h_{ef} + 2d_0$ | | | |
| Minimum spacing | s_{min} [mm] | 50 | 60 | 75 | 95 | 115 | 140 |
| Minimum edge distance | c_{min} [mm] | 40 | 45 | 50 | 60 | 65 | 80 |

Table B4: Installation parameters for rebar

| Rebar | | $\varnothing 8$ | $\varnothing 10$ | $\varnothing 12$ | $\varnothing 14$ | $\varnothing 16$ | $\varnothing 20$ | $\varnothing 24$ | $\varnothing 25$ | $\varnothing 28$ | $\varnothing 32$ | $\varnothing 36$ | $\varnothing 40$ |
|---|-------------------|------------------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|------------------|
| Diameter of rebar | $d=d_{nom}$ [mm] | 8 | 10 | 12 | 14 | 16 | 20 | 24 | 25 | 28 | 32 | 36 | 40 |
| Nominal drill hole diameter ¹⁾ | d_0 [mm] | 10 12 | 12 14 | 14 16 | 18 | 20 | 25 | 30 32 | 30 32 | 35 | 40 | 45 | 52 55 |
| Effective anchorage depth | $h_{ef,min}$ [mm] | 60 | 60 | 70 | 75 | 80 | 90 | 96 | 100 | 112 | 128 | 144 | 160 |
| | $h_{ef,max}$ [mm] | 160 | 200 | 240 | 280 | 320 | 400 | 480 | 500 | 560 | 640 | 720 | 800 |
| Minimum member thickness | h_{min} [mm] | $h_{ef} + 30 mm \geq 100 mm$ | | | $h_{ef} + 2d_0$ | | | | | | | | |
| Minimum spacing | s_{min} [mm] | 40 | 50 | 60 | 70 | 75 | 95 | 120 | 120 | 130 | 150 | 180 | 200 |
| Minimum edge distance | c_{min} [mm] | 35 | 40 | 45 | 50 | 50 | 60 | 70 | 70 | 75 | 85 | 180 | 200 |

¹⁾ For $\varnothing 8, \varnothing 10, \varnothing 12, \varnothing 24, \varnothing 25$ and $\varnothing 40$ both nominal drill hole diameter can be used

| | |
|---|-----------------|
| Injection System VME plus | Annex B4 |
| Intended Use Installation parameters | |

Table B5: Parameter for cleaning and setting tools

| Threaded rod | Internally threaded anchor rod | Rebar | Drill bit \varnothing | Brush \varnothing | min. Brush \varnothing | Retaining washer Installation direction and use | | | |
|--------------|--------------------------------|---------|-------------------------|---------------------|--------------------------|--|-------------------------|-----|---|
| | | | | | | [-] | ↓ | → | ↑ |
| M8 | | 8 | 10 | 11,5 | 10,5 | No retaining washer required | | | |
| M10 | IG M6 | 8 / 10 | 12 | 13,5 | 12,5 | | | | |
| M12 | IG M8 | 10 / 12 | 14 | 15,5 | 14,5 | | | | |
| | | 12 | 16 | 17,5 | 16,5 | | | | |
| M16 | IG M10 | 14 | 18 | 20,0 | 18,5 | h _{ef} > 250mm | h _{ef} > 250mm | all | |
| | | 16 | 20 | 22,0 | 20,5 | | | | |
| M20 | IG M12 | | 22 | 24,0 | 22,5 | | | | |
| | | 20 | 25 | 27,0 | 25,5 | | | | |
| M24 | IG M16 | | 28 | 30,0 | 28,5 | | | | |
| M27 | | 24 / 25 | 30 | 31,8 | 30,5 | | | | |
| | | 24 / 25 | 32 | 34,0 | 32,5 | all | all | all | |
| M30 | IG M20 | 28 | 35 | 37,0 | 35,5 | | | | |
| | | 32 | 40 | 43,5 | 40,5 | | | | |
| | | 36 | 45 | 47,0 | 45,5 | | | | |
| | | 40 | 52 | 54,0 | 52,5 | all | all | all | |
| | | | 55 | 58,5 | 55,5 | | | | |

| | | |
|--|--|--|
| <p>Vacuum drill bit Vacuum drill bit (MKT Hollow drill bit SB, Würth Hammer drill bit with suction or Heller Duster Expert hollow drill bit system) and a vacuum cleaner with minimum negative pressure of 253 hPa and flow rate of minimum 42 l/s (150 m³/h)</p> |  | |
| <p>Compressed air tool min 6 bar Drill bit diameter (d₀): all diameters</p> |  | |
| <p>Cleaning Brush RB</p> |  | |
| <p>Retaining washer VM-IA</p> |  | |
| <p>Centring Aid ZH</p> | <p>ZH-Cap </p> | <p>ZH-Ring </p> |

| | |
|---|------------------------|
| <p>Injection System VME plus</p> | <p>Annex B5</p> |
| <p>Intended Use Cleaning and setting tools</p> | |

Table B6: Installation parameters centring aid ZH

| Threaded rod | | | M10 | M12 | M16 | M20 | M24 |
|---|------------|------|---|--------|---------|------------------|---------|
| Internally threaded anchor rod | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 |
| Centring aid ZH-Ring / ZH-Cap | | | ZH-M10 | ZH-M12 | ZH-M16 | ZH-M20 | ZH-M24 |
| Centring aid ZH-Ring | h_{Ring} | [mm] | 6,5 | 8,0 | 9,0 | 9,0 | 12,0 |
| Centring aid ZH-Cap | h_{Cap} | [mm] | 8,0 | 10,0 | 12,0 | 14,0 | 16,0 |
| Drill hole depth | h_0 | [mm] | $h_0 \geq h_{nom} + 3 \text{ mm}$ | | | | |
| Minimum thickness of member | h_{min} | [mm] | $h_{nom} + 30\text{mm} \geq 100\text{mm}$ | | | $h_{nom} + 2d_0$ | |
| Effective anchorage depth ¹⁾ | h_{ef} | [mm] | $h_{ef} = h_{nom} - h_{cap} - n \cdot h_{Ring} \geq h_{ef,min}$ | | | | |

¹⁾ The effective anchorage depth h_{ef} is reduced by the height of all centring aids used.

n = number of used centring rings „ZH-Ring“




Table B7: Working time and curing time

| Concrete temperature | | | Maximum working time | Minimum curing time | |
|------------------------------|----|-------|----------------------|---------------------|--------------|
| | | | | dry concrete | wet concrete |
| 0°C | to | +4°C | 80 min | 144 h | 288 h |
| +5°C | to | +9°C | 80 min | 48 h | 96 h |
| +10°C | to | +14°C | 60 min | 28 h | 56 h |
| +15°C | to | +19°C | 40 min | 18 h | 36 h |
| +20°C | to | +24°C | 30 min | 12 h | 24 h |
| +25°C | to | +34°C | 12 min | 9 h | 18 h |
| +35°C | to | +39°C | 8 min | 6 h | 12 h |
| +40°C | | | 8 min | 4 h | 8 h |
| Cartridge temperature | | | +5°C to +40°C | | |


Injection System VME plus

Intended Use
Installation parameters centring aid
Working and curing time

Annex B6


Installation instructions

Hole drilling and cleaning: Vacuum drilling

| | | |
|----------|---|---|
| 1 |  | <p>Vacuum drilling: see Annex B5 Drill hole with prescribed nominal drill hole diameter (Table B2, B3 or B4) and selected drill hole depth. This drilling method removes dust and cleans the drill hole during drilling. <u>Continue with step 3.</u> In case of aborted drill hole, the drill hole shall be filled with mortar.</p> |
|----------|---|---|




No further cleaning steps required when using a vacuum drill!

Hole drilling and cleaning: Hammer drilling, compressed air drilling

| | | |
|----------|---|---|
| 1 |  | <p>Hammer drilling or compressed air drilling: Drill hole with hammer drill or compressed air drill into the base material with prescribed nominal drill hole diameter (Table B2, B3 or B4) and selected drill hole depth. <u>Continue with step 2.</u> In case of aborted drill hole, the drill hole shall be filled with mortar.</p> |
|----------|---|---|

Attention! Standing water in the drill hole must be removed before cleaning!

Cleaning: dry, wet and water-filled drill holes with all diameter in uncracked and cracked concrete

| | | |
|-----------|---|---|
| 2a |  | <p>Starting from the bottom or back of the drill hole, blow out the hole with compressed air (min. 6 bar) a minimum of two times until return air stream is free of noticeable dust. If the drill hole ground is not reached, an extension must be used.</p> |
| 2b |  | <p>Check brush diameter (Table B5). Brush the hole with an appropriate sized wire brush $\geq d_{b,min}$ a minimum of two times. If the drill hole ground is not reached with the brush, an appropriate brush extension must be used.</p> |
| 2c |  | <p>Starting from the bottom or back of the drill hole, blow out the hole with compressed air (min. 6 bar) again a minimum of two times until return air stream is free of noticeable dust. If the drill hole ground is not reached, an extension must be used.</p> |

Injection System VME plus









Intended Use

Installation instructions – Drilling and cleaning:
Hammer-, compressed air- or vacuum drilling

Annex B7

Installation instructions (continuation)

Hole drilling and cleaning: Diamond drilling






| | | |
|---|---|--|
| 1 |  | Drill a hole into the base material with prescribed nominal drill hole diameter (Table B2, B3 or B4) and selected drill hole depth. Continue with step 2. In case of aborted drill hole, the drill hole shall be filled with mortar. |
| Cleaning: dry, wet and water-filled drill holes | | |
| 2a |  | Remove drill core at least up to the nominal drill hole depth and check drill hole depth. |
| 2b |  | Flush drill hole with water, starting from the bottom until clear water gets out of the drill hole. |
| 2c |  | Check brush diameter (Table B5). Brush the hole with an appropriate sized wire brush $\geq d_{b,min}$ a minimum of two times. If the drill hole ground is not reached with the brush, an appropriate brush extension must be used. |
| 2d |  | Flush drill hole again with water, starting from the bottom until clear water gets out of the drill hole. |
| Attention! Standing water in the borehole must be removed before proceeding. | | |
| 2e |  | Starting from the bottom or back of the drill hole, blow out the hole with compressed air (min. 6 bar) again a minimum of two times until return air stream is free of noticeable dust. If the drill hole ground is not reached, an extension must be used. |
| 2f |  | Check brush diameter (Table B5). Brush the hole again with an appropriate sized wire brush $\geq d_{b,min}$ a minimum of two times. If the drill hole ground is not reached with the brush, an appropriate brush extension must be used. |
| 2g |  | Starting from the bottom or back of the drill hole, blow out the hole with compressed air (min. 6 bar) again a minimum of two times until return air stream is free of noticeable dust. If the drill hole ground is not reached, an extension must be used. |

Injection System VME plus

Intended Use
Installation instructions – Drilling and cleaning:
Diamond drilling

Annex B8

Installation instructions (continuation)

| Injection | | |
|-----------|---|---|
| 3 |  | Attach the supplied static-mixing nozzle to the cartridge and load the cartridge into the correct dispensing tool. For every working interruption longer than the recommended working time (Table B7) as well as for new cartridges, a new static-mixer shall be used. |
| 4 |  | Prior to inserting the rod into the filled drill hole, the position of the embedment depth shall be marked on the threaded rod or rebar. |
| 5 |  | Prior to dispensing into the drill hole, squeeze out separately a minimum of three full strokes and discard non-uniformly mixed adhesive components until the mortar shows a consistent grey or red colour. |
| 6 |  | Starting from the bottom or back of the cleaned drill hole fill the hole up to approximately two-thirds with adhesive. Slowly withdraw the static mixing nozzle as the hole fills to avoid air pockets. If the drill hole ground is not reached, an appropriate mixer extension shall be used. Observe temperature dependent working times given in Table B7. |
| 7 |  | Retaining washer and mixer extensions shall be used according to Table B5 for the following applications: <ul style="list-style-type: none"> • Horizontal installation (horizontal direction) and ground installation (vertical downwards direction): Drill bit-Ø $d_0 \geq 18$ mm and anchorage depth $h_{ef} > 250$mm • Overhead installation: Drill bit-Ø $d_0 \geq 18$ mm |

Injection System VME plus

Intended Use
Installation instructions - Injection

Annex B9

Installation instructions (continuation)

| Inserting the fastening element | | |
|---------------------------------|--|--|
| 8 | | Push the threaded rod or reinforcing bar into the hole while turning slightly to ensure proper distribution of the adhesive until the embedment depth is reached. The anchor shall be free of dirt, grease, oil or other foreign material. |
| 9 | | Make sure that excess mortar is visible at the top of the hole and in case of through-setting installation also in the fixture. If these requirements are not maintained, repeat application before end of working time! For overhead installation, the anchor should be fixed (e.g. by wedges). |
| 10 | | Allow the adhesive to cure to the specified time prior to applying any load or torque. Do not move or load the anchor until it is fully cured (attend Table B7). |
| 11 | | Remove excess mortar. |
| 12 | | The fixture can be mounted after curing time. Apply installation torque T_{inst} according to Table B2 or B3. |
| 13 | | In case of pre-setting installation the annular gap between anchor rod and fixture can optionally be filled with mortar. Therefore, replace regular washer by filling washer and plug on reducing adapter on static mixer. Annular gap is completely filled, when excess mortar seeps out. |

Injection System VME plus

Intended Use
Installation instructions – Inserting the fastening element

Annex B10

Table C1: Characteristic steel resistance for threaded rods under tension load

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|--------------------------------------|-----------------|------|-----------------------------|--------------------------|------|-----|-----|-----|-----------------|-----------------|
| Steel failure | | | | | | | | | | | |
| Cross sectional area A_s [mm ²] | | | | 36,6 | 58,0 | 84,3 | 157 | 245 | 353 | 459 | 561 |
| Characteristic resistance under tension load ¹⁾ | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 and 4.8 | $N_{Rk,s}$ | [kN] | 15 (13) ¹⁾ | 23 (21) ¹⁾ | 34 | 63 | 98 | 141 | 184 | 224 |
| | Property class 5.6 and 5.8 | $N_{Rk,s}$ | [kN] | 18 (17) ¹⁾ | 29 (27) ¹⁾ | 42 | 79 | 123 | 177 | 230 | 281 |
| | Property class 8.8 | $N_{Rk,s}$ | [kN] | 29 (27) ¹⁾ | 46 (43) ¹⁾ | 67 | 126 | 196 | 282 | 367 | 449 |
| Stainless steel | Property class 50 (A2 / A4 / HCR) | $N_{Rk,s}$ | [kN] | 18 | 29 | 42 | 79 | 123 | 177 | 230 | 281 |
| | Property class 70 (A2 / A4 / HCR) | $N_{Rk,s}$ | [kN] | 26 | 41 | 59 | 110 | 172 | 247 | 321 | 393 |
| | Property class 80 (A4 / HCR) | $N_{Rk,s}$ | [kN] | 29 | 46 | 67 | 126 | 196 | 282 | - ³⁾ | - ³⁾ |
| Partial factors ²⁾ | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 | $\gamma_{Ms,N}$ | [-] | 2,0 | | | | | | | |
| | Property class 4.8 | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| | Property class 5.6 | $\gamma_{Ms,N}$ | [-] | 2,0 | | | | | | | |
| | Property class 5.8 | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| | Property class 8.8 | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| Stainless steel | Property class 50 (A2 / A4 / HCR) | $\gamma_{Ms,N}$ | [-] | 2,86 | | | | | | | |
| | Property class 70 (A2 / A4 / HCR) | $\gamma_{Ms,N}$ | [-] | 1,87 (1,5) ⁴⁾ | | | | | | | |
| | Property class 80 (A4 / HCR) | $\gamma_{Ms,N}$ | [-] | 1,6 (1,5) ⁴⁾ | | | | | | - ³⁾ | - ³⁾ |

¹⁾ The characteristic resistances apply for all anchor rods with the cross sectional area A_s specified here: VMU-A, V-A, VM-A. For commercial standard threaded rods with a smaller cross sectional area (e.g. hot-dip galvanized threaded rods M8, M10 according to EN ISO 10684:2004 + AC:2009), the values in brackets are valid.

²⁾ In absence of national regulation

³⁾ Anchor type not part of the ETA

⁴⁾ Value in brackets for anchor rods VMU-A or V-A

Injection System VME plus

Performance

Characteristic **steel resistance** for threaded rods under tension load

Annex C1

Table C2: Characteristic steel resistance for threaded rods under shear load

| Threaded rod | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|-----------------------------------|---------------------|---------------------------|------------|------|------|-----|-----|-----------------|-----------------|-----------------|
| Steel failure | | | | | | | | | | | |
| Cross sectional area | | | A_s [mm ²] | 36,6 | 58,0 | 84,3 | 157 | 245 | 353 | 459 | 561 |
| Characteristic resistance under shear load ¹⁾ | | | | | | | | | | | |
| Steel failure <u>without</u> lever arm | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 and 4.8 | $V^{0}_{RK,S}$ [kN] | 9 (8) | 14 (13) | 20 | 38 | 59 | 85 | 110 | 135 | |
| | Property class 5.6 and 5.8 | $V^{0}_{RK,S}$ [kN] | 11 (10) | 17 (16) | 25 | 47 | 74 | 106 | 138 | 168 | |
| | Property class 8.8 | $V^{0}_{RK,S}$ [kN] | 15 (13) | 23 (21) | 34 | 63 | 98 | 141 | 184 | 224 | |
| Stainless steel | Property class 50 (A2 / A4 / HCR) | $V^{0}_{RK,S}$ [kN] | 9 | 15 | 21 | 39 | 61 | 88 | 115 | 140 | |
| | Property class 70 (A2 / A4 / HCR) | $V^{0}_{RK,S}$ [kN] | 13 | 20 | 30 | 55 | 86 | 124 | 161 | 196 | |
| | Property class 80 (A4 / HCR) | $V^{0}_{RK,S}$ [kN] | 15 | 23 | 34 | 63 | 98 | 141 | _ ³⁾ | _ ³⁾ | |
| Steel failure <u>with</u> lever arm | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 and 4.8 | $M^{0}_{RK,S}$ [Nm] | 15 (13) | 30 (27) | 52 | 133 | 260 | 449 | 666 | 900 | |
| | Property class 5.6 and 5.8 | $M^{0}_{RK,S}$ [Nm] | 19 (16) | 37 (33) | 65 | 166 | 325 | 561 | 832 | 1124 | |
| | Property class 8.8 | $M^{0}_{RK,S}$ [Nm] | 30 (26) | 60 (53) | 105 | 266 | 519 | 898 | 1332 | 1799 | |
| Stainless steel | Property class 50 (A2 / A4 / HCR) | $M^{0}_{RK,S}$ [Nm] | 19 | 37 | 65 | 166 | 325 | 561 | 832 | 1124 | |
| | Property class 70 (A2 / A4 / HCR) | $M^{0}_{RK,S}$ [Nm] | 26 | 52 | 92 | 233 | 454 | 785 | 1165 | 1574 | |
| | Property class 80 (A4 / HCR) | $M^{0}_{RK,S}$ [Nm] | 30 | 60 | 105 | 266 | 519 | 898 | _ ³⁾ | _ ³⁾ | |
| Partial factor ²⁾ | | | | | | | | | | | |
| Steel, zinc plated | Property class 4.6 | $\gamma_{Ms,V}$ [-] | 1,67 | | | | | | | | |
| | Property class 4.8 | $\gamma_{Ms,V}$ [-] | 1,25 | | | | | | | | |
| | Property class 5.6 | $\gamma_{Ms,V}$ [-] | 1,67 | | | | | | | | |
| | Property class 5.8 | $\gamma_{Ms,V}$ [-] | 1,25 | | | | | | | | |
| | Property class 8.8 | $\gamma_{Ms,V}$ [-] | 1,25 | | | | | | | | |
| Stainless steel | Property class 50 (A2 / A4 / HCR) | $\gamma_{Ms,V}$ [-] | 2,38 | | | | | | | | |
| | Property class 70 (A2 / A4 / HCR) | $\gamma_{Ms,V}$ [-] | 1,56 (1,25) ⁴⁾ | | | | | | | | |
| | Property class 80 (A4 / HCR) | $\gamma_{Ms,V}$ [-] | 1,33 (1,25) ⁴⁾ | | | | | | | _ ³⁾ | _ ³⁾ |

¹⁾ The characteristic resistances apply for all anchor rods with the cross sectional area A_s specified here: VMU-A, V-A, VM-A. For commercial standard threaded rods with a smaller cross sectional area (e.g. hot-dip galvanized threaded rods M8, M10 according to EN ISO 10684:2004 + AC:2009), the values in brackets are valid.

²⁾ In absence of national regulation

³⁾ Anchor type not part of the ETA

⁴⁾ Value in brackets for anchor rods VM-A or commercial standard threaded rods

Injection System VME plus

Performance
Characteristic **steel resistance for threaded rods under shear load**

Annex C2

Table C3: Characteristic values for concrete cone and splitting

| Threaded rods / Internally threaded anchor rods / Rebars | | | | all sizes |
|--|------------------------|---------------|------|-------------------------------------|
| Concrete cone failure | | | | |
| Factor k_1 | uncracked concrete | $k_{ucr,N}$ | [-] | 11,0 |
| | cracked concrete | $k_{cr,N}$ | [-] | 7,7 |
| Edge distance | | $C_{cr,N}$ | [mm] | $1,5 \cdot h_{ef}$ |
| Spacing | | $S_{cr,N}$ | [mm] | $2 \cdot C_{cr,N}$ |
| Splitting failure | | | | |
| Characteristic resistance | | $N^0_{RK,sp}$ | [kN] | $\min (N_{RK,p} ; N^0_{RK,c})$ |
| Edge distance | $h/h_{ef} \geq 2,0$ | $C_{cr,sp}$ | [mm] | $1,0 \cdot h_{ef}$ |
| | $2,0 > h/h_{ef} > 1,3$ | | | $2 \cdot h_{ef} (2,5 - h / h_{ef})$ |
| | $h/h_{ef} \leq 1,3$ | | | $2,4 \cdot h_{ef}$ |
| Spacing | | $S_{cr,sp}$ | [mm] | $2 \cdot C_{cr,sp}$ |

Injection System VME plus

Performance
Characteristic values for concrete cone and splitting

Annex C3

Table C4: Characteristic values of tension load for threaded rods, static and quasi-static action, working life 50 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | | |
|--|-----|-------------|----------------|------------------|----------------------|---|-----|-----|--------------------------|-----|-----|-----|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | | | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}$ (or see Table C1) | | | | | | | |
| Partial factor | | | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD | $\tau_{Rk,ucr}$ | [N/mm ²] | 20 | 20 | 19 | 19 | 18 | 17 | 16 | 16 |
| | II | 50°C / 72°C | | | | 15 | 15 | 15 | 14 | 13 | 13 | 12 | 12 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 | 5,5 |
| Temperature range | I | 24°C / 40°C | VD | $\tau_{Rk,ucr}$ | [N/mm ²] | 17 (16) ¹⁾ | 16 | 16 | 16 (15) ¹⁾ | 15 | 14 | 14 | 13 |
| | II | 50°C / 72°C | | | | 14 | 14 | 14 | 13 | 13 | 12 | 12 | 11 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 | 5,5 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | $\tau_{Rk,cr}$ | [N/mm ²] | 7,0 | 7,0 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 |
| | II | 50°C / 72°C | | | | 6,0 | 6,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 |
| | III | 60°C / 80°C | | | | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 |
| Reduction factor ψ^{0}_{sus} | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | ψ^{0}_{sus} | [-] | 0,99 | | | | | | | |
| | II | 50°C / 72°C | | | | 0,68 | | | | | | | |
| | III | 60°C / 80°C | | | | 0,70 | | | | | | | |
| Characteristic bond resistance in concrete \geq C25/30 | | | | | | | | | | | | | |
| Increasing factor ψ_c for | | | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,1} \leq 1,1$ | | | | | | | |
| $\tau_{Rk,ucr} = \psi_c \cdot \tau_{Rk,ucr} (C20/25)$ | | | | | | | | | | | | | |
| $\tau_{Rk,cr} = \psi_c \cdot \tau_{Rk,cr} (C20/25)$ | | | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | | | HD CD | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | | VD | γ_{inst} | [-] | 1,2 | | | | | | | |

¹⁾ Value in brackets: characteristic bond resistance for waterfilled drill holes

Injection System VME plus

Performance
Characteristic values of tension load for threaded rods, working life 50 years

Annex C4

Table C5: Characteristic values of tension load for threaded rods, static and quasi-static action, working life 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | | |
|--|-----|-------------|----------------|---------------------|----------------------|---|-----|-----|--------------------------|-----|-----|-----|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | | | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}$ (or see Table C1) | | | | | | | |
| Partial factor | | | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 20 | 20 | 19 | 19 | 18 | 17 | 16 | 16 |
| | II | 50°C / 72°C | | | | 15 | 15 | 15 | 14 | 13 | 13 | 12 | 12 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 | 5,5 |
| Temperature range | I | 24°C / 40°C | VD | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 17 (16) ¹⁾ | 16 | 16 | 16 (15) ¹⁾ | 15 | 14 | 14 | 13 |
| | II | 50°C / 72°C | | | | 14 | 14 | 14 | 13 | 13 | 12 | 12 | 11 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 | 5,5 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | $\tau_{Rk,cr,100}$ | [N/mm ²] | 6,5 | 6,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 |
| | II | 50°C / 72°C | | | | 5,5 | 5,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| | III | 60°C / 80°C | | | | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 |
| Reduction factor ψ^0_{sus} | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | $\psi^0_{sus,100}$ | [-] | 0,97 | | | | | | | |
| | II | 50°C / 72°C | | | | 0,68 | | | | | | | |
| | III | 60°C / 80°C | | | | 0,70 | | | | | | | |
| Characteristic bond resistance in concrete \geq C25/30 | | | | | | | | | | | | | |
| Increasing factor ψ_c for | | | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,1} \leq 1,1$ | | | | | | | |
| $\tau_{Rk,ucr,100} = \psi_c \cdot \tau_{Rk,ucr,100}$ (C20/25) | | | | | | | | | | | | | |
| $\tau_{Rk,cr,100} = \psi_c \cdot \tau_{Rk,cr,100}$ (C20/25) | | | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | | | HD CD | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | | VD | γ_{inst} | [-] | 1,2 | | | | | | | |

¹⁾ Value in brackets: characteristic bond resistance for waterfilled drill holes

Injection System VME plus

Performance
Characteristic values of tension load for threaded rods, working life 100 years

Annex C5

**Table C6: Characteristic values of tension load for threaded rods,
static and quasi-static action, working life 50 years, diamond drilling**

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | | |
|---|-----|-------------|----|-----------------|----------------------|--|-----|-----|-----|-----|-----|-----|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | | | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}$ (or see Table C1) | | | | | | | |
| Partial factor | | | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\tau_{Rk,ucr}$ | [N/mm ²] | 15 | 14 | 14 | 13 | 12 | 12 | 11 | 11 |
| | II | 50°C / 72°C | | | | 12 | 12 | 11 | 10 | 9,5 | 9,5 | 9,0 | 9,0 |
| | III | 60°C / 80°C | | | | 5,5 | 5,5 | 5,0 | 4,5 | 4,5 | 4,5 | 4,0 | 4,0 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\tau_{Rk,cr}$ | [N/mm ²] | 1) | | | 5,5 | 5,5 | 5,5 | 5,5 | 5,4 |
| | II | 50°C / 72°C | | | | | | | 4,6 | 4,6 | 4,6 | 4,6 | 4,5 |
| | III | 60°C / 80°C | | | | | | | 2,4 | 2,3 | 2,4 | 2,4 | 2,3 |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | ψ_{sus}^0 | [-] | 0,77 | | | | | | | |
| | II | 50°C / 72°C | | | | 0,72 | | | | | | | |
| | III | 60°C / 80°C | | | | 0,72 | | | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | | | |
| Increasing factor ψ_c for | | | | $\psi_{c,ucr}$ | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,2} \leq 1,2$ | | | | | | | |
| $\tau_{Rk,ucr} = \psi_{c,ucr} \cdot \tau_{Rk,ucr} (C20/25)$ | | | | | | | | | | | | | |
| | | | | $\psi_{c,cr}$ | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,4} \leq 1,44$ | | | | | | | |
| $\tau_{Rk,cr} = \psi_{c,cr} \cdot \tau_{Rk,cr} (C20/25)$ ²⁾ | | | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | | | | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | | | γ_{inst} | [-] | 1,2 | | | 1,4 | | | | |

¹⁾ No performance assessed

²⁾ only concrete strength classes C20/25 to C50/60

Injection System VME plus

Performance
Characteristic values of tension load for threaded rods, working life 50 years,
diamond drilling

Annex C6

**Table C7: Characteristic values of tension load for threaded rods,
static and quasi-static action, working life 100 years, diamond drilling**

| Threaded rod | | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|-----|-------------|----|---------------------|----------------------|---|-----|-----|-----|-----|-----|-----|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | | | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}$ (or see Table C1) | | | | | | | |
| Partial factor | | | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\tau_{RK,ucr,100}$ | [N/mm ²] | 15 | 14 | 14 | 13 | 12 | 12 | 11 | 11 |
| | II | 50°C / 72°C | | | | 11 | 11 | 10 | 10 | 9,5 | 9,0 | 8,5 | 8,5 |
| | III | 60°C / 80°C | | | | 5,5 | 5,5 | 5,0 | 4,5 | 4,5 | 4,5 | 4,0 | 4,0 |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\psi_{sus,100}^0$ | [-] | 0,73 | | | | | | | |
| | II | 50°C / 72°C | | | | 0,70 | | | | | | | |
| | III | 60°C / 80°C | | | | 0,72 | | | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | | | |
| Increasing factor ψ_c for <small>$\tau_{RK,ucr,100} = \psi_c \cdot \tau_{RK,ucr} \cdot \tau_{RK,ucr,100}$ (C20/25)</small> | | | | $\psi_{c,ucr}$ | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,2} \leq 1,2$ | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | |
| Relevant parameter | | | | | see Table C3 | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | |
| Relevant parameter | | | | | see Table C3 | | | | | | | | |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | | | | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | | | γ_{inst} | [-] | 1,2 | | | 1,4 | | | | |

Injection System VME plus

Performance
Characteristic values of **tension load for threaded rods, working life 100 years, diamond drilling**

Annex C7

Table C8: Characteristic values of shear load for threaded rods, static and quasi-static action, working life 50 and 100 years

| Threaded rod | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|--|-----------------|--------------------|--|-----|-----|-----|-----|-----|------|----------------------------|
| Steel failure <u>without</u> lever arm | | | | | | | | | | |
| Characteristic shear resistance Steel, property class 4.6, 4.8, 5.6 and 5.8 | $V_{RK,s}^0$ | [kN] | 0,6 · A_s · f_{uk} or see Table C2 | | | | | | | |
| Characteristic shear resistance Steel, property class 8.8 Stainless steel A2, A4 and HCR all property classes | $V_{RK,s}^0$ | [kN] | 0,5 · A_s · f_{uk} or see Table C2 | | | | | | | |
| Ductility factor | k_7 | [-] | 1,0 | | | | | | | |
| Partial factor | $\gamma_{Ms,V}$ | [-] | see Table C2 | | | | | | | |
| Steel failure <u>with</u> lever arm | | | | | | | | | | |
| Characteristic bending resistance | $M_{RK,s}^0$ | [Nm] | 1,2 · W_{el} · f_{uk} or see Table C2 | | | | | | | |
| Elastic section modulus | W_{el} | [mm ³] | 31 | 62 | 109 | 277 | 541 | 935 | 1387 | 1874 |
| Partial factor | $\gamma_{Ms,V}$ | [-] | see Table C2 | | | | | | | |
| Concrete pry-out failure | | | | | | | | | | |
| Pry-out factor | k_8 | [-] | 2,0 | | | | | | | |
| Concrete edge failure | | | | | | | | | | |
| Effective length of anchor | l_f | [mm] | min (h_{ef} ; 12 d_{nom}) | | | | | | | min (h_{ef} ; 300mm) |
| Outside diameter of anchor | d_{nom} | [mm] | 8 | 10 | 12 | 16 | 20 | 24 | 27 | 30 |
| Installation factor | γ_{inst} | [-] | 1,0 | | | | | | | |

Injection System VME plus

Performance
Characteristic values of **shear load for threaded rods**

Annex C8

Table C9: Characteristic values of tension load for threaded rods, seismic action performance category C1, working life 50 and 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | | |
|---|-----|-------------|----|--------------------|----------------------|----------------------|-----|-----|-----|-----|-----|-----|-----|
| Tension loads | | | | | | | | | | | | | |
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance C1 | | | | $N_{Rk,s,C1}$ | [kN] | $1,0 \cdot N_{Rk,s}$ | | | | | | | |
| Partial factor | | | | $\gamma_{Ms,N}$ | [-] | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in concrete C20/25 to C50/60 Working life 50 years | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD | $\tau_{Rk,C1}$ | [N/mm ²] | 7,0 | 7,0 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | |
| | II | 50°C / 72°C | CD | | | 6,0 | 6,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 |
| | III | 60°C / 80°C | VD | | | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 |
| Characteristic bond resistance in concrete C20/25 to C50/60 Working life 100 years | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD | $\tau_{Rk,C1,100}$ | [N/mm ²] | 6,5 | 6,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | |
| | II | 50°C / 72°C | CD | | | 5,5 | 5,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| | III | 60°C / 80°C | VD | | | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 |
| Installation factor | | | | | | | | | | | | | |
| Dry or wet concrete | | | | γ_{inst} | [-] | 1,0 | | | | | | | |
| Waterfilled drill hole | | | | γ_{inst} | [-] | 1,2 | | | | | | | |

Table C10: Characteristic values of shear load for threaded rods, seismic action performance category C1, working life 50 and 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|---|--|--|-----------------|------|------------------------|-----|-----|-----|-----|-----|
| Shear loads | | | | | | | | | | | |
| Steel failure <u>without</u> lever arm | | | | | | | | | | | |
| Characteristic resistance C1 | | | | $V_{Rk,s,C1}$ | [kN] | $0,7 \cdot V_{Rk,s}^0$ | | | | | |
| Partial factor | | | | $\gamma_{Ms,N}$ | [-] | see Table C2 | | | | | |
| Factor for anchorages | without annular gap | | | α_{gap} | [-] | 1,0 | | | | | |
| | with annular gap between threaded rod and fixture | | | | | 0,5 | | | | | |

Injection System VME plus

Performance
Characteristic values for **threaded rods**, seismic action C1

Annex C9

Table C11: Characteristic values of tension load for threaded rods, seismic action performance category C2, working life 50 and 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|-----|-----------------|------|-----------------|----------------------|-----------------|-----|-----|-----|-----|-----|-----|
| Tension loads | | | | | | | | | | | | |
| Steel failure | | | | | | | | | | | | |
| Characteristic resistance C2 steel, zinc plated, property class 8.8 stainless steel A4 and HCR, property class ≥ 70 | | $N_{Rk,s,C2}$ | [kN] | - ¹⁾ | $1,0 \cdot N_{Rk,s}$ | | | | | | | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | - ¹⁾ | see Table C1 | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | |
| Characteristic bond resistance in concrete C20/25 to C50/60 | | | | | | | | | | | | |
| Working life 50 and 100 years | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD | $\tau_{Rk,C2}$ | [N/mm ²] | - ¹⁾ | 5,8 | 4,8 | 5,0 | 5,1 | 4,8 | 5,0 |
| | II | 50°C / 72°C | CD | | | - ¹⁾ | 5,0 | 4,1 | 4,3 | 4,4 | 4,1 | 4,3 |
| | III | 60°C / 80°C | VD | | | - ¹⁾ | 1,9 | 1,6 | 1,6 | 1,7 | 1,5 | 1,6 |
| Installation factor | | | | | | | | | | | | |
| Dry or wet concrete | | γ_{inst} | [-] | - ¹⁾ | 1,0 | | | | | | | |
| Waterfilled drill hole | | γ_{inst} | [-] | - ¹⁾ | 1,2 | | | | | | | |

¹⁾ No performance assessed

Table C12: Characteristic values of shear load for threaded rods, seismic action performance category C2, working life 50 and 100 years

| Threaded rod | | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 |
|---|---|-----------------|------|-----------------|------------------------|-----|-----|-----|-----|-----|-----|
| Shear loads | | | | | | | | | | | |
| Steel failure <u>without</u> lever arm | | | | | | | | | | | |
| Characteristic resistance C2 steel, zinc plated, property class 8.8 stainless steel A4 and HCR, property class ≥ 70 | | $V_{Rk,s,C2}$ | [kN] | - ¹⁾ | $0,7 \cdot V^0_{Rk,s}$ | | | | | | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | - ¹⁾ | see Table C2 | | | | | | |
| Factor for anchorages | without annular gap | α_{gap} | [-] | - ¹⁾ | 1,0 | | | | | | |
| | with annular gap between threaded rod and fixture | | | - ¹⁾ | 0,5 | | | | | | |

¹⁾ No performance assessed

Injection System VME plus

Performance
Characteristic values for **threaded rods**, seismic action C2

Annex C10

Table C13: Characteristic values of tension load for internally threaded anchor rod, static and quasi-static action, working life 50 years

| Internally threaded anchor rod | | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | | |
|---|----------------|-----------------|-----------------|-----------------|----------------------|---|---------|-----------------------|-------------------------|-----|-----|
| Steel failure ¹⁾ | | | | | | | | | | | |
| Characteristic resistance, steel, zinc plated, property class | 5.8 | $N_{Rk,s}$ | [kN] | 10 | 17 | 29 | 42 | 76 | 123 | | |
| | 8.8 | $N_{Rk,s}$ | [kN] | 16 | 27 | 46 | 67 | 121 | 196 | | |
| Partial factor 5.8 and 8.8 | | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| Characteristic resistance, Stainless steel A4 / HCR, property class 70 | | $N_{Rk,s}$ | [kN] | 14 | 26 | 41 | 59 | 110 | 172 (123) ²⁾ | | |
| | Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,87 | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | |
| Characteristic bond resistance in uncracked concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD | $\tau_{Rk,ucr}$ | [N/mm ²] | 20 | 19 | 19 | 18 | 17 | 16 |
| | II | 50°C / 72°C | | | | 15 | 15 | 14 | 13 | 13 | 12 |
| | III | 60°C / 80°C | 6,5 | | | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 | |
| Temperature range | I | 24°C / 40°C | VD | $\tau_{Rk,ucr}$ | [N/mm ²] | 16 | 16 | 16 (15) ³⁾ | 15 | 14 | 13 |
| | II | 50°C / 72°C | | | | 14 | 14 | 13 | 13 | 12 | 11 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 |
| Characteristic bond resistance in cracked concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD | $\tau_{Rk,cr}$ | [N/mm ²] | 7,0 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 |
| | II | 50°C / 72°C | | | | 6,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 |
| | III | 60°C / 80°C | VD | | | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,5 |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | ψ_{sus}^0 | [-] | 0,99 | | | | | |
| | II | 50°C / 72°C | | | | 0,68 | | | | | |
| | III | 60°C / 80°C | | | | 0,70 | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | |
| Increasing factor ψ_c for | | | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,1} \leq 1,1$ | | | | | |
| $\tau_{Rk,ucr} = \psi_c \cdot \tau_{Rk,ucr}(C20/25)$ | | | | | | | | | | | |
| $\tau_{Rk,cr} = \psi_c \cdot \tau_{Rk,cr}(C20/25)$ | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Splitting failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Installation factor | | | | | | | | | | | |
| dry or wet concrete | | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,2 | | | | | | | |

- ¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.
- ²⁾ Value in bracket is valid for property class 50
- ³⁾ Value in bracket is valid for waterfilled drill hole

Injection System VME plus

Performance
Characteristic values of tension load for internally threaded anchor rods, working life 50 years

Annex C11

Table C14: Characteristic values of tension load for internally threaded anchor rod static and quasi-static action, working life 100 years

| Internally threaded anchor rod | | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | | |
|---|----------------|-----------------|-----------------|---------------------|---------------------------|---|---------|-----------------------|-------------------------|-----|-----|
| Steel failure ¹⁾ | | | | | | | | | | | |
| Characteristic resistance, steel, zinc plated, property class | 5.8 | $N_{Rk,s}$ | [kN] | 10 | 17 | 29 | 42 | 76 | 123 | | |
| | 8.8 | $N_{Rk,s}$ | [kN] | 16 | 27 | 46 | 67 | 121 | 196 | | |
| Partial factor 5.8 and 8.8 | | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| Characteristic resistance, Stainless steel A4 / HCR, property class 70 | | $N_{Rk,s}$ | [kN] | 14 | 26 | 41 | 59 | 110 | 172 (123) ²⁾ | | |
| | Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,87 (2,86) ²⁾ | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 20 | 19 | 19 | 18 | 17 | 16 |
| | II | 50°C / 72°C | | | | 15 | 15 | 14 | 13 | 13 | 12 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 |
| Temperature range | I | 24°C / 40°C | VD | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 16 | 16 | 16 (15) ³⁾ | 15 | 14 | 13 |
| | II | 50°C / 72°C | | | | 14 | 14 | 13 | 13 | 12 | 11 |
| | III | 60°C / 80°C | | | | 6,5 | 6,5 | 6,0 | 6,0 | 5,5 | 5,5 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | $\tau_{Rk,cr,100}$ | [N/mm ²] | 6,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 |
| | II | 50°C / 72°C | | | | 5,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| | III | 60°C / 80°C | | | | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,5 |
| Reduction factor ψ^0_{sus} | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | $\psi^0_{sus,100}$ | [-] | 0,97 | | | | | |
| | II | 50°C / 72°C | | | | 0,68 | | | | | |
| | III | 60°C / 80°C | | | | 0,70 | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | |
| Increasing factor ψ_c for | | | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,1} \leq 1,1$ | | | | | |
| $\tau_{Rk,ucr,100} = \psi_c \cdot \tau_{Rk,ucr,100} (C20/25)$ | | | | | | | | | | | |
| $\tau_{Rk,cr,100} = \psi_c \cdot \tau_{Rk,cr,100} (C20/25)$ | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Splitting failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Installation factor | | | | | | | | | | | |
| dry or wet concrete | | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,2 | | | | | | | |

¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.

²⁾ For property class 50

³⁾ Value in bracket is valid for waterfilled drill hole

Injection System VME plus

Performance
Characteristic values of tension load for internally threaded anchor rods, working life 100 years

Annex C12

Table C15: Characteristic values of tension loads for internally threaded anchor rod, static and quasi-static action, working life 50 years, diamond drilling

| Internally threaded anchor rod | | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | | |
|---|----------------|-----------------|-----------------|---|----------------------|--|---------|---------|----------------------------|-----|-----|
| Steel failure ¹⁾ | | | | | | | | | | | |
| Characteristic resistance, steel, zinc plated, property class | 5.8 | $N_{Rk,s}$ | [kN] | 10 | 17 | 29 | 42 | 76 | 123 | | |
| | 8.8 | $N_{Rk,s}$ | [kN] | 16 | 27 | 46 | 67 | 121 | 196 | | |
| Partial factor 5.8 and 8.8 | | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| Characteristic resistance, stainless steel A4 / HCR, property class 70 | | $N_{Rk,s}$ | [kN] | 14 | 26 | 41 | 59 | 110 | 172 (123) ²⁾ | | |
| | Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,87 | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\tau_{Rk,ucr}$ | [N/mm ²] | 14 | 14 | 13 | 12 | 12 | 11 |
| | II | 50°C / 72°C | | | | 12 | 11 | 10 | 9,5 | 9,5 | 9,0 |
| | III | 60°C / 80°C | | | | 5,5 | 5,0 | 4,5 | 4,5 | 4,5 | 4,0 |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\tau_{Rk,cr}$ | [N/mm ²] | 3) | 5,5 | 5,5 | 5,5 | 5,4 | |
| | II | 50°C / 72°C | | | | | 4,6 | 4,6 | 4,6 | 4,5 | |
| | III | 60°C / 80°C | | | | | 2,4 | 2,3 | 2,4 | 2,3 | |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | ψ_{sus}^0 | [-] | 0,77 | | | | | |
| | II | 50°C / 72°C | | | | 0,72 | | | | | |
| | III | 60°C / 80°C | | | | 0,72 | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | |
| Increasing factor ψ_c for | | $\psi_{c,ucr}$ | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,2} \leq 1,2$ | | | | | | | |
| $\tau_{Rk,ucr} = \psi_{c,ucr} \cdot \tau_{Rk,ucr} (C20/25)$ | | | | | | | | | | | |
| | | $\psi_{c,cr}$ | [-] | 3) | | $\left(\frac{f_{ck}}{20}\right)^{0,4} \leq 1,44$ | | | | | |
| | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Splitting failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Installation factor | | | | | | | | | | | |
| dry or wet concrete | | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,2 | | 1,4 | | | | | |

¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.

²⁾ For property class 50

³⁾ No performance assessed

⁴⁾ Only concrete strength classes C20/25 to C50/60

Injection System VME plus

Performance

Characteristic values of tension load for internally threaded anchor rods, working life 50 years, diamond drilling

Annex C13

Table C16: Characteristic values of tension loads for internally threaded anchor rod, static and quasi-static action, working life 100 years, diamond drilling

| Internally threaded anchor rod | | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | | |
|---|----------------|-----------------|-----------------|---|----------------------|---------|---------|---------|----------------------------|------------------------------|-----|
| Steel failure ¹⁾ | | | | | | | | | | | |
| Characteristic resistance, steel, zinc plated, property class | 5.8 | $N_{Rk,s}$ | [kN] | 10 | 17 | 29 | 42 | 76 | 123 | | |
| | 8.8 | $N_{Rk,s}$ | [kN] | 16 | 27 | 46 | 67 | 121 | 196 | | |
| Partial factor 5.8 and 8.8 | | $\gamma_{Ms,N}$ | [-] | 1,5 | | | | | | | |
| Characteristic resistance, stainless steel A4 / HCR, property class 70 | | $N_{Rk,s}$ | [kN] | 14 | 26 | 41 | 59 | 110 | 172 (123) ²⁾ | | |
| | Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,87 | | | | | 1,87 (2,86) ²⁾ | |
| Combined pull-out and concrete failure | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\tau_{Rk,ucr,100}$ | [N/mm ²] | 14 | 14 | 13 | 12 | 12 | 11 |
| | II | 50°C / 72°C | | | | 11 | 10 | 10 | 9,5 | 9,0 | 8,5 |
| | III | 60°C / 80°C | | | | 5,5 | 5,0 | 4,5 | 4,5 | 4,5 | 4,0 |
| Reduction factor ψ^0_{sus} | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | DD | $\psi^0_{sus,100}$ | [-] | 0,73 | | | | | |
| | II | 50°C / 72°C | | | | 0,70 | | | | | |
| | III | 60°C / 80°C | | | | 0,72 | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | |
| Increasing factor $\psi_{c,ucr}$ for $\tau_{Rk,ucr,100} = \psi_{c,ucr} \cdot \tau_{Rk,ucr,100}$ (C20/25) | | $\psi_{c,ucr}$ | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,2} \leq 1,2$ | | | | | | | |
| Concrete cone failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Splitting failure | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | |
| Installation factor | | | | | | | | | | | |
| dry or wet concrete | | γ_{inst} | [-] | 1,0 | | | | | | | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,2 | | | 1,4 | | | | |

¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod. The characteristic tension resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.

²⁾ For property class 50

Injection System VME plus

Performance
Characteristic values of **tension load** for **internally threaded anchor rods**, working life **100 years**, **diamond drilling**

Annex C14

Table C17: Characteristic values of shear load for internally threaded anchor rod, static and quasi-static action, working life 50 and 100 years

| Internally threaded anchor rod | | | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | |
|---|--|-----------------|-------------------|---------------------------------|--------|---------|---------|---------|----------------------------|--|
| Steel failure <u>without</u> lever arm ¹⁾ | | | | | | | | | | |
| Steel, zinc plated | Characteristic resistance, property class | 5.8 | $V_{Rk,s}^0$ [kN] | 6 | 10 | 17 | 25 | 45 | 74 | |
| | | 8.8 | $V_{Rk,s}^0$ [kN] | 8 | 14 | 23 | 34 | 60 | 98 | |
| | Partial factor 5.8 and 8.8 | | $\gamma_{Ms,V}$ | [-] | 1,25 | | | | | |
| Stainless steel | Characteristic resistance, A4 / HCR, property class 70 | | $V_{Rk,s}^0$ [kN] | 7 | 13 | 20 | 30 | 55 | 62 ²⁾ | |
| | Partial factor | $\gamma_{Ms,V}$ | [-] | 1,56 | | | | | 2,38 | |
| Ductility factor | | | k_7 | [-] | 1,0 | | | | | |
| Steel failure <u>with</u> lever arm ¹⁾ | | | | | | | | | | |
| Steel, zinc plated | Characteristic bending resistance, property class | 5.8 | $M_{Rk,s}^0$ [Nm] | 8 | 19 | 37 | 66 | 167 | 325 | |
| | | 8.8 | $M_{Rk,s}^0$ [Nm] | 12 | 30 | 60 | 105 | 267 | 519 | |
| | Partial factor 5.8 and 8.8 | | $\gamma_{Ms,V}$ | [-] | 1,25 | | | | | |
| Stainless steel | Characteristic bending resistance A4 / HCR, property class 70 | | $M_{Rk,s}^0$ [Nm] | 11 | 26 | 53 | 92 | 234 | 643 ²⁾ | |
| | Partial factor | $\gamma_{Ms,V}$ | [-] | 1,56 | | | | | 2,38 | |
| Concrete pry-out failure | | | | | | | | | | |
| Pry-out factor | | | k_8 | [-] | 2,0 | | | | | |
| Concrete edge failure | | | | | | | | | | |
| Effective length of anchor | | | l_f [mm] | min (h_{ef} ; 12 d_{nom}) | | | | | min (h_{ef} ; 300mm) | |
| Outside diameter of anchor | | | d_{nom} [mm] | 10 | 12 | 16 | 20 | 24 | 30 | |
| Installation factor | | | γ_{inst} | [-] | 1,0 | | | | | |

¹⁾ Fastening screws or threaded rods (incl. nut and washer) must comply with the appropriate material and property class of the internally threaded anchor rod (exception: IG M20). The characteristic shear resistance for steel failure of the given strength class are valid for the internally threaded anchor rod and the fastening element.

²⁾ For IG-M20: Internally threaded rod: property class 50;
Fastening screws or threaded rods (incl. nut and washer): property class 70

Injection System VME plus

Performance
Characteristic values of **shear load** for **internally threaded anchor rods**,
working life 50 and 100 years

Annex C15

**Table C18: Characteristic values of tension loads for rebar,
static and quasi-static action, working life 50 years**

| Reinforcing bar | | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | Ø 36 | Ø 40 | | | |
|---|-----|--|--------------------|-------------------------|----------------------|---|--------------------------|--------------------------|------|------|------|------|------|------|------|-----|-----|-----|
| Steel failure | | | | | | | | | | | | | | | | | | |
| Characteristic tension resistance | | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | | | | | |
| Cross sectional area | | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | 1018 | 1256 | | | |
| Partial factor | | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD | $\tau_{Rk,ucr}$ | [N/mm ²] | 16 | 16 | 16 | 16 | 16 | 16 | 15 | 15 | 15 | 15 | 15 | | |
| | II | 50°C / 72°C | | | | 12 | 12 | 12 | 12 | 12 | 12 | 12 | 12 | 11 | 11 | 11 | 11 | 11 |
| | III | 60°C / 80°C | | | | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,0 | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 |
| Temperature range | I | 24°C / 40°C | VD | $\tau_{Rk,ucr}$ | [N/mm ²] | 14 (13) ³⁾ | 14 (13) ³⁾ | 13 | 13 | 13 | 13 | 13 | 13 | 13 | 13 | 4) | | |
| | II | 50°C / 72°C | | | | 12 (11) ³⁾ | 12 (11) ³⁾ | 12 (11) ³⁾ | 11 | 11 | 11 | 11 | 11 | 11 | 11 | | | |
| | III | 60°C / 80°C | | | | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,0 | 5,0 | 5,0 | 5,0 | | | |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | $\tau_{Rk,cr}$ | [N/mm ²] | 7,0 | 7,0 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 4) | | |
| | II | 50°C / 72°C | | | | 6,0 | 6,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | | | |
| | III | 60°C / 80°C | | | | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | | | |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | | | | | | | | |
| Temperature range | I | 24°C / 40°C | HD CD VD | ψ_{sus}^0 | [-] | 0,99 | | | | | | | | | | | | |
| | II | 50°C / 72°C | | | | 0,68 | | | | | | | | | | | | |
| | III | 60°C / 80°C | | | | 0,70 | | | | | | | | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | | | | | | | | |
| Increasing factor ψ_c for | | $\tau_{Rk,ucr} = \psi_c \cdot \tau_{Rk,ucr} (C20/25)$ $\tau_{Rk,cr} = \psi_c \cdot \tau_{Rk,cr} (C20/25)$ | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,1} \leq 1,1$ | | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | | | | | | |
| Relevant parameter | | | | see Table C3 | | | | | | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | | | | | | |
| dry or wet concrete | | γ_{inst} | [-] | 1,0 | | | | | | | | | | | 1,2 | | | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,2 | | | | | | | | | | | 4) | | | |

- 1) f_{uk} shall be taken from the specifications of reinforcing bars
- 2) In absence of national regulation
- 3) Value in brackets: characteristic bond resistance for waterfilled drill holes
- 4) No performance assessed

Injection System VME plus

Performance
Characteristic values of tension load for rebar, working life 50 years

Annex C16

Table C19: Characteristic values of tension loads for rebar, static and quasi-static action, working life 100 years

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | Ø 36 | Ø 40 | | |
|---|-----------------|--------------------|---|----------------------|--------------------------|--------------------------|--------------------------|------|------|------|------|------|------|------|-----|-----|
| Steel failure | | | | | | | | | | | | | | | | |
| Characteristic tension resistance | $N_{RK,s}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | 1018 | 1256 | | |
| Partial factor | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | | | | |
| Characteristic bond resistance in <u>uncracked</u> concrete C20/25 | | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | HD CD | $\tau_{RK,ucr,100}$ | [N/mm ²] | 16 | 16 | 16 | 16 | 16 | 16 | 15 | 15 | 15 | 15 | 15 | |
| | II: 50°C/72°C | | | | 12 | 12 | 12 | 12 | 12 | 12 | 12 | 12 | 11 | 11 | 11 | 11 |
| | III: 60°C/80°C | | | | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,0 | 5,0 | 5,0 | 5,0 | 4,5 |
| Temperature range | I: 24°C/40°C | VD | $\tau_{RK,ucr,100}$ | [N/mm ²] | 14 (13) ³⁾ | 14 (13) ³⁾ | 13 | 13 | 13 | 13 | 13 | 13 | 13 | 13 | 4) | |
| | II: 50°C/72°C | | | | 12 (11) ³⁾ | 12 (11) ³⁾ | 12 (11) ³⁾ | 11 | 11 | 11 | 11 | 11 | 11 | 11 | | |
| | III: 60°C/80°C | | | | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,5 | 5,0 | 5,0 | 5,0 | 5,0 | | |
| Characteristic bond resistance in <u>cracked</u> concrete C20/25 | | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | HD CD VD | $\tau_{RK,cr,100}$ | [N/mm ²] | 7,0 | 7,0 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 4) | |
| | II: 50°C/72°C | | | | 6,0 | 6,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | | |
| | III: 60°C/80°C | | | | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | | |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | HD CD VD | $\psi_{sus,100}^0$ | [-] | 0,97 | | | | | | | | | | | |
| | II: 50°C/72°C | | | | 0,68 | | | | | | | | | | | |
| | III: 60°C/80°C | | | | 0,70 | | | | | | | | | | | |
| Characteristic bond resistance for concrete \geq C25/30 | | | | | | | | | | | | | | | | |
| Increasing factor ψ_c for $\tau_{RK,ucr,100} = \psi_c \cdot \tau_{RK,ucr,100}$ (C20/25) | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,1} \leq 1,1$ | | | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | | | | |
| Relevant parameter | see Table C3 | | | | | | | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | | | | |
| Relevant parameter | see Table C3 | | | | | | | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | | | | |
| dry or wet concrete | γ_{inst} | [-] | 1,0 | | | | | | | | | | | 1,2 | | |
| waterfilled drill hole | γ_{inst} | [-] | 1,2 | | | | | | | | | | | 4) | | |

- 1) f_{uk} shall be taken from the specifications of reinforcing bars
 2) In absence of national regulation
 3) Value in brackets: characteristic bond resistance for waterfilled drill holes
 4) No performance assessed

Injection System VME plus

Performance
 Characteristic values of **tension load for rebar**, working life **100 years**

Annex C17

Table C20: Characteristic values of tension loads for rebar, static and quasi-static action, working life 50 and 100 years, diamond drilling

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | Ø 36 | Ø 40 | |
|--|-----------------|--------------------|--|---|------|------|------|------|------|------|------|------|------|---------------|-----|
| Steel failure | | | | | | | | | | | | | | | |
| Characteristic tension resistance | $N_{Rk,s}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | 1018 | 1256 | |
| Partial factor | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | | | |
| Characteristic bond resistance in uncracked concrete C20/25 Working life 50 years | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | DD | $\tau_{Rk,ucr}$ [N/mm ²] | 14 | 13 | 13 | 13 | 12 | 12 | 11 | 11 | 11 | 11 | 11 | 10 |
| | II: 50°C/72°C | | $\tau_{Rk,ucr}$ [N/mm ²] | 11 | 11 | 10 | 10 | 10 | 9,5 | 9,5 | 9,5 | 9,0 | 9,0 | 8,5 | 8,5 |
| | III: 60°C/80°C | | $\tau_{Rk,ucr}$ [N/mm ²] | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,0 | 4,0 | 4,0 | 4,0 | 4,0 | 4,0 |
| Reduction factor ψ_{sus}^0 | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | DD | ψ_{sus}^0 [-] | 0,77 | | | | | | | | | | | |
| | II: 50°C/72°C | | ψ_{sus}^0 [-] | 0,72 | | | | | | | | | | | |
| | III: 60°C/80°C | | ψ_{sus}^0 [-] | 0,72 | | | | | | | | | | | |
| Characteristic bond resistance in uncracked concrete C20/25 Working life 100 years | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | DD | $\tau_{Rk,ucr,100}$ [N/mm ²] | 14 | 13 | 13 | 13 | 12 | 12 | 11 | 11 | 11 | 11 | 11 | 10 |
| | II: 50°C/72°C | | $\tau_{Rk,ucr,100}$ [N/mm ²] | 11 | 10 | 10 | 10 | 9,5 | 9,0 | 9,0 | 9,0 | 8,5 | 8,5 | 8,0 | 8,0 |
| | III: 60°C/80°C | | $\tau_{Rk,ucr,100}$ [N/mm ²] | 5,0 | 5,0 | 5,0 | 4,5 | 4,5 | 4,5 | 4,0 | 4,0 | 4,0 | 4,0 | 4,0 | 4,0 |
| Reduction factor $\psi_{sus,100}^0$ | | | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | DD | $\psi_{sus,100}^0$ [-] | 0,73 | | | | | | | | | | | |
| | II: 50°C/72°C | | $\psi_{sus,100}^0$ [-] | 0,70 | | | | | | | | | | | |
| | III: 60°C/80°C | | $\psi_{sus,100}^0$ [-] | 0,72 | | | | | | | | | | | |
| Characteristic bond resistance for concrete ≥ C25/30 | | | | | | | | | | | | | | | |
| Increasing factor ψ_c for | | ψ_c | [-] | $\left(\frac{f_{ck}}{20}\right)^{0,2} \leq 1,2$ | | | | | | | | | | | |
| $\tau_{Rk,ucr} = \psi_c \cdot \tau_{Rk,ucr} (C20/25)$ $\tau_{Rk,ucr,100} = \psi_c \cdot \tau_{Rk,ucr,100} (C20/25)$ | | | | | | | | | | | | | | | |
| Concrete cone failure | | | | | | | | | | | | | | | |
| Relevant parameter | | | see Table C3 | | | | | | | | | | | | |
| Splitting failure | | | | | | | | | | | | | | | |
| Relevant parameter | | | see Table C3 | | | | | | | | | | | | |
| Installation factor | | | | | | | | | | | | | | | |
| dry or wet concrete | | γ_{inst} | [-] | 1,0 | | | | | | | | | | 1,2 | |
| waterfilled drill hole | | γ_{inst} | [-] | 1,2 | | | | | 1,4 | | | | | ³⁾ | |

1) f_{uk} shall be taken from the specifications of reinforcing bars

2) In absence of national regulation

3) No performance assessed

Injection System VME plus

Performance
Characteristic values of tension load for rebar, working life 50 and 100 years,
Diamond drilling

Annex C18

Table C21: Characteristic values of shear loads for rebar, static and quasi-static action, working life 50 and 100 years

| Reinforcing bar | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | Ø 36 | Ø 40 | |
|---|-----------------|--------------------|--------------------------------------|------|------|------|------|------|-------------------------|------|------|------|------|------|
| Steel failure <u>without</u> lever arm | | | | | | | | | | | | | | |
| Characteristic shear resistance | $V_{RK,S}^0$ | [kN] | $0,50 \cdot A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | 1018 | 1256 |
| Partial factor | $\gamma_{Ms,V}$ | [-] | 1,5 ²⁾ | | | | | | | | | | | |
| Ductility factor | k_7 | [-] | 1,0 | | | | | | | | | | | |
| Steel failure <u>with</u> lever arm | | | | | | | | | | | | | | |
| Characteristic bending resistance | $M_{RK,S}^0$ | [Nm] | $1,2 \cdot W_{el} \cdot f_{uk}^{1)}$ | | | | | | | | | | | |
| Elastic section modulus | W_{el} | [mm ³] | 50 | 98 | 170 | 269 | 402 | 785 | 1357 | 1534 | 2155 | 3217 | 4580 | 6283 |
| Partial factor | $\gamma_{Ms,V}$ | [-] | 1,5 ²⁾ | | | | | | | | | | | |
| Concrete pry-out failure | | | | | | | | | | | | | | |
| Pry-out factor | k_8 | [-] | 2,0 | | | | | | | | | | | |
| Concrete edge failure | | | | | | | | | | | | | | |
| Effective length of rebar | l_f | [mm] | min (h_{ef} ; 12 d_{nom}) | | | | | | min (h_{ef} ; 300mm) | | | | | |
| Outside diameter of rebar | d_{nom} | [mm] | 8 | 10 | 12 | 14 | 16 | 20 | 24 | 25 | 28 | 32 | 36 | 40 |
| Installation factor | γ_{inst} | [-] | 1,0 | | | | | | | | | | | |

¹⁾ f_{uk} shall be taken from the specifications of reinforcing bars

²⁾ In absence of national regulation

Injection System VME plus

Performance
Characteristic values of **shear load** for rebar, working life 50 and 100 years

Annex C19

Table C22: Characteristic values of tension load for rebar, seismic action (performance category C1), working life 50 and 100 years

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | |
|---|-----------------|--------------------|-------------------------|----------------------|------|------|------|------|------|------|------|------|-----|
| Steel failure | | | | | | | | | | | | | |
| Characteristic resistance | $N_{Rk,s,C1}$ | [kN] | $A_s \cdot f_{uk}^{1)}$ | | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 | |
| Partial factor | $\gamma_{Ms,N}$ | [-] | 1,4 ²⁾ | | | | | | | | | | |
| Combined pull-out and concrete failure | | | | | | | | | | | | | |
| Characteristic bond resistance in concrete C20/25 to C50/60 Working life 50 years | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | HD CD VD | $\tau_{Rk,C1}$ | [N/mm ²] | 7,0 | 7,0 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 | 8,5 |
| | II: 50°C/72°C | | $\tau_{Rk,C1}$ | [N/mm ²] | 6,0 | 6,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 | 7,0 |
| | III: 60°C/80°C | | $\tau_{Rk,C1}$ | [N/mm ²] | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 |
| Characteristic bond resistance in concrete C20/25 to C50/60 Working life 100 years | | | | | | | | | | | | | |
| Temperature range | I: 24°C/40°C | HD CD VD | $\tau_{Rk,C1,100}$ | [N/mm ²] | 6,5 | 6,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 | 7,5 |
| | II: 50°C/72°C | | $\tau_{Rk,C1,100}$ | [N/mm ²] | 5,5 | 5,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 | 6,5 |
| | III: 60°C/80°C | | $\tau_{Rk,C1,100}$ | [N/mm ²] | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 | 4,5 |
| Installation factor | | | | | | | | | | | | | |
| dry or wet concrete | γ_{inst} | [-] | 1,0 | | | | | | | | | | |
| waterfilled drill hole | γ_{inst} | [-] | 1,2 | | | | | | | | | | |

1) f_{uk} shall be taken from the specifications of reinforcing bars

2) In absence of national regulation

Table C23: Characteristic values of shear loads for rebar, seismic action (performance category C1), working life 50 and 100 years

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 |
|---|-----------------|--------------------|------------------------------------|------|------|------|------|------|------|------|------|------|
| Steel failure <u>without</u> lever arm Working life 50 and 100 years | | | | | | | | | | | | |
| Characteristic resistance | $V_{Rk,s,C1}$ | [kN] | $0,35 \cdot A_s \cdot f_{uk}^{1)}$ | | | | | | | | | |
| Cross sectional area | A_s | [mm ²] | 50 | 79 | 113 | 154 | 201 | 314 | 452 | 491 | 616 | 804 |
| Partial factor | $\gamma_{Ms,V}$ | [-] | 1,5 ²⁾ | | | | | | | | | |
| Ductility factor | k_7 | [-] | 1,0 | | | | | | | | | |

1) f_{uk} shall be taken from the specifications of reinforcing bars

2) In absence of national regulation

Injection System VME plus

Performance
Characteristic values for rebar, seismic action C1

Annex C20

Table C24: Displacements under tension load, threaded rod

| Threaded rod | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|--|-----------------------------|------------------------------|-----------------|-------|-------|-------|-------|-------|-------|-------|
| Hammer-, compressed air or vacuum drilling (HD, CD, VD) | | | | | | | | | | |
| Displacement factor¹⁾ | | | | | | | | | | |
| Uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | $\frac{\text{mm}}{[N/mm^2]}$ | 0,028 | 0,029 | 0,030 | 0,033 | 0,035 | 0,038 | 0,039 | 0,041 |
| | $\delta_{N\infty}$ - factor | | 0,028 | 0,029 | 0,030 | 0,033 | 0,035 | 0,038 | 0,039 | 0,041 |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | | 0,038 | 0,039 | 0,040 | 0,044 | 0,047 | 0,051 | 0,052 | 0,055 |
| | $\delta_{N\infty}$ - factor | | 0,047 | 0,049 | 0,051 | 0,055 | 0,059 | 0,064 | 0,067 | 0,070 |
| Temperature range III: 60°C / 80°C | δ_{N0} - factor | | 0,069 | 0,071 | 0,072 | 0,074 | 0,076 | 0,079 | 0,081 | 0,082 |
| | $\delta_{N\infty}$ - factor | | 0,100 | 0,115 | 0,122 | 0,128 | 0,135 | 0,142 | 0,155 | 0,171 |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | 0,092 | 0,095 | 0,096 | 0,099 | 0,102 | 0,106 | 0,109 | 0,110 | |
| | $\delta_{N\infty}$ - factor | 0,134 | 0,154 | 0,163 | 0,172 | 0,181 | 0,189 | 0,207 | 0,229 | |
| Temperature range III: 60°C / 80°C | δ_{N0} - factor | 0,069 | 0,071 | 0,072 | 0,074 | 0,076 | 0,079 | 0,081 | 0,082 | |
| | $\delta_{N\infty}$ - factor | 0,100 | 0,115 | 0,122 | 0,128 | 0,135 | 0,142 | 0,155 | 0,171 | |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | 0,092 | 0,095 | 0,096 | 0,099 | 0,102 | 0,106 | 0,109 | 0,110 | |
| | $\delta_{N\infty}$ - factor | 0,134 | 0,154 | 0,163 | 0,172 | 0,181 | 0,189 | 0,207 | 0,229 | |
| Displacement factor¹⁾ | | | | | | | | | | |
| Cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | $\frac{\text{mm}}{[N/mm^2]}$ | 0,069 | 0,071 | 0,072 | 0,074 | 0,076 | 0,079 | 0,081 | 0,082 |
| | $\delta_{N\infty}$ - factor | | 0,100 | 0,115 | 0,122 | 0,128 | 0,135 | 0,142 | 0,155 | 0,171 |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | | 0,092 | 0,095 | 0,096 | 0,099 | 0,102 | 0,106 | 0,109 | 0,110 |
| | $\delta_{N\infty}$ - factor | | 0,134 | 0,154 | 0,163 | 0,172 | 0,181 | 0,189 | 0,207 | 0,229 |
| Temperature range III: 60°C / 80°C | δ_{N0} - factor | | 0,069 | 0,071 | 0,072 | 0,074 | 0,076 | 0,079 | 0,081 | 0,082 |
| | $\delta_{N\infty}$ - factor | | 0,100 | 0,115 | 0,122 | 0,128 | 0,135 | 0,142 | 0,155 | 0,171 |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | 0,092 | 0,095 | 0,096 | 0,099 | 0,102 | 0,106 | 0,109 | 0,110 | |
| | $\delta_{N\infty}$ - factor | 0,134 | 0,154 | 0,163 | 0,172 | 0,181 | 0,189 | 0,207 | 0,229 | |
| Displacement | | | | | | | | | | |
| Uncracked and cracked concrete, seismic action (C2) | | | | | | | | | | |
| All temperature ranges | $\delta_{N,C2}$ (DLS) | [mm] | - ²⁾ | | 0,21 | 0,24 | 0,27 | 0,36 | 0,92 | 0,70 |
| | $\delta_{N,C2}$ (ULS) | | 0,54 | 0,51 | 0,54 | 0,63 | 1,70 | 0,92 | | |
| Diamond drilling (DD) | | | | | | | | | | |
| Displacement factor¹⁾ | | | | | | | | | | |
| Uncracked concrete, static and quasi-static action, working life 50 years | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | $\frac{\text{mm}}{[N/mm^2]}$ | 0,011 | 0,012 | 0,012 | 0,013 | 0,014 | 0,014 | 0,015 | 0,015 |
| | $\delta_{N\infty}$ - factor | | 0,018 | 0,019 | 0,019 | 0,020 | 0,022 | 0,023 | 0,024 | 0,025 |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | | 0,013 | 0,014 | 0,014 | 0,015 | 0,016 | 0,016 | 0,018 | 0,018 |
| | $\delta_{N\infty}$ - factor | | 0,052 | 0,053 | 0,055 | 0,058 | 0,062 | 0,065 | 0,068 | 0,070 |
| Temperature range III: 60°C / 80°C | δ_{N0} - factor | | 0,011 | 0,012 | 0,012 | 0,013 | 0,014 | 0,014 | 0,015 | 0,015 |
| | $\delta_{N\infty}$ - factor | | 0,020 | 0,021 | 0,021 | 0,023 | 0,024 | 0,025 | 0,026 | 0,027 |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | 0,013 | 0,014 | 0,014 | 0,015 | 0,016 | 0,016 | 0,018 | 0,018 | |
| | $\delta_{N\infty}$ - factor | 0,038 | 0,039 | 0,040 | 0,043 | 0,045 | 0,047 | 0,049 | 0,051 | |
| Temperature range III: 60°C / 80°C | δ_{N0} - factor | 0,011 | 0,012 | 0,012 | 0,013 | 0,014 | 0,014 | 0,015 | 0,015 | |
| | $\delta_{N\infty}$ - factor | 0,020 | 0,021 | 0,021 | 0,023 | 0,024 | 0,025 | 0,026 | 0,027 | |
| Temperature range II: 50°C / 72°C | δ_{N0} - factor | 0,013 | 0,014 | 0,014 | 0,015 | 0,016 | 0,016 | 0,018 | 0,018 | |
| | $\delta_{N\infty}$ - factor | 0,038 | 0,039 | 0,040 | 0,043 | 0,045 | 0,047 | 0,049 | 0,051 | |

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{-factor} \cdot \tau; \quad \tau: \text{acting bond stress under tension load}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-factor} \cdot \tau;$$

²⁾ No Performance assessed

Injection System VME plus

Performance
Displacements (**threaded rod** under tension load)

Annex C21

Table C25: Displacements under shear load, threaded rod

| Threaded rod | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|--|-----------------------------|-----------|-----------------|------|------|------|------|------|------|------|
| All drilling methods | | | | | | | | | | |
| Displacement factor¹⁾ | | | | | | | | | | |
| Uncracked and cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | |
| All temperature ranges | δ_{v0} - factor | [mm/(kN)] | 0,06 | 0,06 | 0,05 | 0,04 | 0,04 | 0,03 | 0,03 | 0,03 |
| | $\delta_{v\infty}$ - factor | | 0,09 | 0,08 | 0,08 | 0,06 | 0,06 | 0,05 | 0,05 | 0,05 |
| Displacement | | | | | | | | | | |
| Uncracked and cracked concrete, seismic action (C2) | | | | | | | | | | |
| All temperature ranges | $\delta_{V,C2}$ (DLS) | [mm] | - ²⁾ | 3,1 | 3,4 | 3,5 | 4,2 | 4,0 | 3,8 | |
| | $\delta_{V,C2}$ (ULS) | | | 6,0 | 7,6 | 7,3 | 10,9 | 11,1 | 11,2 | |

¹⁾ Calculation of the displacement

$$\delta_{v0} = \delta_{v0}\text{-factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{v\infty} = \delta_{v\infty}\text{-factor} \cdot V;$$

³⁾ No Performance assessed

Injection System VME plus

Performance
Displacements (**threaded rod** under shear load)

Annex C22

Table C26: Displacement factors¹⁾ under tension load, internally threaded anchor rod

| Internally threaded anchor rod | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | |
|--|-----------------------------|----------------------------|--------|---------|---------|---------|---------|-------|
| Hammer-, compressed air or vacuum drilling (HD, CD, VD) | | | | | | | | |
| Uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,029 | 0,030 | 0,033 | 0,035 | 0,038 | 0,041 |
| | $\delta_{N\infty}$ - factor | | 0,029 | 0,030 | 0,033 | 0,035 | 0,038 | 0,041 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,039 | 0,040 | 0,044 | 0,047 | 0,051 | 0,055 |
| | $\delta_{N\infty}$ - factor | | 0,049 | 0,051 | 0,055 | 0,059 | 0,064 | 0,070 |
| Cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,071 | 0,072 | 0,074 | 0,076 | 0,079 | 0,082 |
| | $\delta_{N\infty}$ - factor | | 0,115 | 0,122 | 0,128 | 0,135 | 0,142 | 0,171 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,095 | 0,096 | 0,099 | 0,102 | 0,106 | 0,110 |
| | $\delta_{N\infty}$ - factor | | 0,154 | 0,163 | 0,172 | 0,181 | 0,189 | 0,229 |
| Diamond drilling (DD) | | | | | | | | |
| Cracked and uncracked concrete, static and quasi-static action, working life 50 years | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,012 | 0,012 | 0,013 | 0,014 | 0,014 | 0,015 |
| | $\delta_{N\infty}$ - factor | | 0,019 | 0,019 | 0,020 | 0,022 | 0,023 | 0,025 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,014 | 0,014 | 0,015 | 0,016 | 0,016 | 0,018 |
| | $\delta_{N\infty}$ - factor | | 0,053 | 0,055 | 0,058 | 0,062 | 0,065 | 0,070 |
| Uncracked concrete, static and quasi-static action, working life 100 years | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,012 | 0,012 | 0,013 | 0,014 | 0,014 | 0,015 |
| | $\delta_{N\infty}$ - factor | | 0,021 | 0,021 | 0,023 | 0,024 | 0,025 | 0,027 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,014 | 0,014 | 0,015 | 0,016 | 0,016 | 0,018 |
| | $\delta_{N\infty}$ - factor | | 0,039 | 0,040 | 0,043 | 0,045 | 0,047 | 0,051 |

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{- factor} \cdot \tau; \quad \tau: \text{acting bond stress under tension load}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{- factor} \cdot \tau;$$

Table C27: Displacement factors¹⁾ under shear load, internally threaded anchor rod

| Internally threaded anchor rod | | IG-M 6 | IG-M 8 | IG-M 10 | IG-M 12 | IG-M 16 | IG-M 20 | |
|--|-----------------------------|-----------|--------|---------|---------|---------|---------|------|
| Cracked and uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | |
| All temperature ranges | δ_{V0} - factor | [mm/(kN)] | 0,07 | 0,06 | 0,06 | 0,05 | 0,04 | 0,04 |
| | $\delta_{V\infty}$ - factor | | 0,10 | 0,09 | 0,08 | 0,08 | 0,06 | 0,06 |

¹⁾ Calculation of the displacement

$$\delta_{V0} = \delta_{V0}\text{- factor} \cdot V; \quad V: \text{acting shear load}$$

$$\delta_{V\infty} = \delta_{V\infty}\text{- factor} \cdot V;$$

| | |
|---|------------------|
| Injection System VME plus | Annex C23 |
| Performance Displacement (internally threaded anchor rod) | |

Table C28: Displacement factors¹⁾ under tension load, rebar

| Reinforcing bar | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | Ø 36 | Ø 40 | |
|--|-----------------------------|----------------------------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------------------------------|-------|
| Hammer-, compressed air or vacuum drilling (HD, CD, VD) | | | | | | | | | | | | | | |
| Uncracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,028 | 0,029 | 0,030 | 0,031 | 0,033 | 0,035 | 0,038 | 0,038 | 0,040 | 0,043 | 0,045 | 0,047 |
| | $\delta_{N\infty}$ - factor | | 0,015 | 0,015 | 0,016 | 0,017 | 0,017 | 0,019 | 0,020 | 0,020 | 0,021 | 0,023 | 0,045 | 0,047 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,038 | 0,039 | 0,040 | 0,042 | 0,044 | 0,047 | 0,051 | 0,051 | 0,054 | 0,058 | 0,060 | 0,063 |
| | $\delta_{N\infty}$ - factor | | 0,047 | 0,049 | 0,051 | 0,053 | 0,055 | 0,059 | 0,065 | 0,065 | 0,068 | 0,072 | 0,074 | 0,079 |
| Cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,069 | 0,071 | 0,072 | 0,073 | 0,074 | 0,076 | 0,079 | 0,079 | 0,081 | 0,084 | no performance assessed | |
| | $\delta_{N\infty}$ - factor | | 0,115 | 0,122 | 0,128 | 0,135 | 0,142 | 0,155 | 0,171 | 0,171 | 0,181 | 0,194 | | |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,092 | 0,095 | 0,096 | 0,098 | 0,099 | 0,102 | 0,106 | 0,106 | 0,109 | 0,113 | | |
| | $\delta_{N\infty}$ - factor | | 0,154 | 0,163 | 0,172 | 0,181 | 0,189 | 0,207 | 0,229 | 0,229 | 0,242 | 0,260 | | |
| Diamond drilling (DD) | | | | | | | | | | | | | | |
| Uncracked concrete, static and quasi-static action, working life 50 years | | | | | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,008 | 0,009 | 0,009 | 0,010 | 0,011 | 0,012 | 0,013 | 0,013 | 0,014 | 0,015 | 0,016 | 0,017 |
| | $\delta_{N\infty}$ - factor | | 0,018 | 0,018 | 0,019 | 0,020 | 0,021 | 0,024 | 0,027 | 0,027 | 0,028 | 0,031 | 0,032 | 0,034 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,009 | 0,011 | 0,011 | 0,012 | 0,013 | 0,014 | 0,015 | 0,015 | 0,016 | 0,018 | 0,019 | 0,020 |
| | $\delta_{N\infty}$ - factor | | 0,048 | 0,051 | 0,054 | 0,058 | 0,061 | 0,068 | 0,076 | 0,076 | 0,081 | 0,088 | 0,090 | 0,097 |
| Uncracked concrete, static and quasi-static action, working life 100 years | | | | | | | | | | | | | | |
| Temperature range I: 24°C / 40°C | δ_{N0} - factor | mm [N/mm ²] | 0,008 | 0,009 | 0,009 | 0,010 | 0,011 | 0,012 | 0,013 | 0,013 | 0,014 | 0,015 | 0,016 | 0,017 |
| | $\delta_{N\infty}$ - factor | | 0,018 | 0,020 | 0,021 | 0,022 | 0,024 | 0,026 | 0,029 | 0,029 | 0,031 | 0,034 | 0,035 | 0,037 |
| Temperature range II: 50°C / 72°C III: 60°C / 80°C | δ_{N0} - factor | | 0,009 | 0,011 | 0,011 | 0,012 | 0,013 | 0,014 | 0,015 | 0,015 | 0,016 | 0,018 | 0,019 | 0,020 |
| | $\delta_{N\infty}$ - factor | | 0,035 | 0,037 | 0,040 | 0,042 | 0,045 | 0,049 | 0,055 | 0,055 | 0,059 | 0,064 | 0,066 | 0,070 |

¹⁾ Calculation of the displacement

$$\delta_{N0} = \delta_{N0}\text{- factor} \cdot \tau; \quad \tau: \text{acting bond stress under tension load}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{- factor} \cdot \tau;$$

Injection System VME plus

Performance
Displacement (rebar under tension load)

Annex C24

Table C29: Displacement factors¹⁾ under shear load, rebar

| Reinforcing bar | | | Ø 8 | Ø 10 | Ø 12 | Ø 14 | Ø 16 | Ø 20 | Ø 24 | Ø 25 | Ø 28 | Ø 32 | Ø 36 | Ø 40 |
|--|-----------------------------|-------------------------------|------|------|------|------|------|------|------|------|------|------|------|------|
| Uncracked and cracked concrete, static and quasi-static action, working life 50 and 100 years | | | | | | | | | | | | | | |
| All temperature ranges | δ_{v0} - factor | $\frac{\text{mm}}{\text{kN}}$ | 0,06 | 0,05 | 0,05 | 0,04 | 0,04 | 0,04 | 0,03 | 0,03 | 0,03 | 0,03 | 0,03 | 0,03 |
| | $\delta_{v\infty}$ - factor | | 0,09 | 0,08 | 0,08 | 0,06 | 0,06 | 0,05 | 0,05 | 0,05 | 0,05 | 0,04 | 0,04 | 0,04 |

¹⁾ Calculation of the displacement

$$\delta_{v0} = \delta_{v0}\text{-factor} \cdot V;$$

V: acting shear load

$$\delta_{v\infty} = \delta_{v\infty}\text{-factor} \cdot V;$$

Injection System VME plus

Performance
Displacement (rebar under shear load)

Annex C25

Table C30: Characteristic values of tension and shear loads under fire exposure, threaded rod

| Threaded rod | | | M8 | M10 | M12 | M16 | M20 | M24 | M27 | M30 | |
|---|------------------------|----------------------|---|---|-----|-----|------|------|------|------|------|
| Steel failure | | | | | | | | | | | |
| Steel zinc plated (property class ≥ 5.8) and stainless steel A2, A4, HCR (property class ≥ 50) | | | | | | | | | | | |
| Characteristic tension resistance | $N_{Rk,s,fi}$ | [kN] | R30 | 1,1 | 1,7 | 3,0 | 5,7 | 8,8 | 12,7 | 16,5 | 20,2 |
| | | | R60 | 0,9 | 1,4 | 2,3 | 4,2 | 6,6 | 9,5 | 12,4 | 15,1 |
| | | | R90 | 0,7 | 1,0 | 1,6 | 3,0 | 4,7 | 6,7 | 8,7 | 10,7 |
| | | | R120 | 0,5 | 0,8 | 1,2 | 2,2 | 3,4 | 4,9 | 6,4 | 7,9 |
| Characteristic bond resistance in cracked and uncracked concrete C20/25 up to C50/60 under fire exposure for temperature θ | | | | | | | | | | | |
| Temperature-dependent reduction factor | $k_{fi,p}(\theta)$ | [-] | $\theta < 23^\circ\text{C}$ | 1,0 | | | | | | | |
| | | | $23^\circ\text{C} \leq \theta \leq 278^\circ\text{C}$ | $150,28 \cdot \theta^{-1,598} \leq 1,0$ | | | | | | | |
| | | | $\theta > 278^\circ\text{C}$ | 0,0 | | | | | | | |
| | | | | | | | | | | | |
| Characteristic bond resistance for a given temperature (θ) | $\tau_{Rk,fi}(\theta)$ | [N/mm ²] | $k_{fi,p}(\theta) \cdot \tau_{Rk,cr(20/25)}^{1)}$ | | | | | | | | |
| Steel failure without lever arm | | | | | | | | | | | |
| Steel zinc plated (property class ≥ 5.8) and stainless steel A2, A4, HCR (property class ≥ 50) | | | | | | | | | | | |
| Characteristic shear resistance | $V_{Rk,s,fi}$ | [kN] | R30 | 1,1 | 1,7 | 3,0 | 5,7 | 8,8 | 12,7 | 16,5 | 20,2 |
| | | | R60 | 0,9 | 1,4 | 2,3 | 4,2 | 6,6 | 9,5 | 12,4 | 15,1 |
| | | | R90 | 0,7 | 1,0 | 1,6 | 3,0 | 4,7 | 6,7 | 8,7 | 10,7 |
| | | | R120 | 0,5 | 0,8 | 1,2 | 2,2 | 3,4 | 4,9 | 6,4 | 7,9 |
| Steel failure with lever arm | | | | | | | | | | | |
| Steel zinc plated (property class ≥ 5.8) and stainless steel A2, A4, HCR (property class ≥ 50) | | | | | | | | | | | |
| Characteristic bending moment | $M^0_{Rk,s,fi}$ | [Nm] | R30 | 1,1 | 2,2 | 4,7 | 12,0 | 23,4 | 40,4 | 59,9 | 81,0 |
| | | | R60 | 0,9 | 1,8 | 3,5 | 9,0 | 17,5 | 30,3 | 44,9 | 60,7 |
| | | | R90 | 0,7 | 1,3 | 2,5 | 6,3 | 12,3 | 21,3 | 31,6 | 42,7 |
| | | | R120 | 0,5 | 1,0 | 1,8 | 4,7 | 9,1 | 15,7 | 23,3 | 31,5 |

¹⁾ $\tau_{Rk,cr(20/25)}$ characteristic bond resistance for cracked concrete for concrete strength class C20/25 for the relevant temperature range and working life

Injection System VME plus

Performance
Characteristic values of tension and shear loads under fire exposure (threaded rods)

Annex C26

Table C31: Characteristic values of tension and shear loads under fire exposure (internally threaded anchor rod)

| Internally threaded anchor rod VMU-IG and VZ-IG | | | IG-M6 | IG-M8 | IG-M10 | IG-M12 | IG-M16 | IG-M20 | |
|---|------------------------|----------------------|---|---|--------|--------|--------|--------|------|
| Steel failure | | | | | | | | | |
| Steel zinc plated (property class 5.8 and 8.8) and stainless steel A4 and HCR (property class 70) | | | | | | | | | |
| Characteristic tension resistance | $N_{Rk,s,fi}$ | [kN] | R30 | 0,3 | 1,1 | 1,7 | 3,0 | 5,7 | 8,8 |
| | | | R60 | 0,2 | 0,9 | 1,4 | 2,3 | 4,2 | 6,6 |
| | | | R90 | 0,2 | 0,7 | 1,0 | 1,6 | 3,0 | 4,7 |
| | | | R120 | 0,1 | 0,5 | 0,8 | 1,2 | 2,2 | 3,4 |
| Characteristic bond resistance in cracked and uncracked concrete C20/25 up to C50/60 under fire conditions for a given temperature θ | | | | | | | | | |
| Temperature reduction factor | $k_{fi,p}(\theta)$ | [-] | $\theta < 23^\circ\text{C}$ | 1,0 | | | | | |
| | | | $23^\circ\text{C} \leq \theta \leq 278^\circ\text{C}$ | $150,28 \cdot \theta^{-1,598} \leq 1,0$ | | | | | |
| | | | $\theta > 278^\circ\text{C}$ | 0,0 | | | | | |
| | | | | | | | | | |
| Characteristic bond resistance for a given temperature (θ) | $\tau_{Rk,fi}(\theta)$ | [N/mm ²] | $k_{fi,p}(\theta) \cdot \tau_{Rk,cr(20/25)}^1$ | | | | | | |
| Steel failure without lever arm | | | | | | | | | |
| Steel zinc plated (property class 5.8 and 8.8) and stainless steel A4 and HCR (property class 70) | | | | | | | | | |
| Characteristic shear resistance | $V_{Rk,s,fi}$ | [kN] | R30 | 0,3 | 1,1 | 1,7 | 3,0 | 5,7 | 8,8 |
| | | | R60 | 0,2 | 0,9 | 1,4 | 2,3 | 4,2 | 6,6 |
| | | | R90 | 0,2 | 0,7 | 1,0 | 1,6 | 3,0 | 4,7 |
| | | | R120 | 0,1 | 0,5 | 0,8 | 1,2 | 2,2 | 3,4 |
| Steel failure with lever arm | | | | | | | | | |
| Steel zinc plated (property class 5.8 and 8.8) and stainless steel A4 and HCR (property class 70) | | | | | | | | | |
| Characteristic bending moment | $M^0_{Rk,s,fi}$ | [Nm] | R30 | 0,2 | 1,1 | 2,2 | 4,7 | 12,0 | 23,4 |
| | | | R60 | 0,2 | 0,9 | 1,8 | 3,5 | 9,0 | 17,5 |
| | | | R90 | 0,1 | 0,7 | 1,3 | 2,5 | 6,3 | 12,3 |
| | | | R120 | 0,1 | 0,5 | 1,0 | 1,8 | 4,7 | 9,1 |

¹⁾ $\tau_{Rk,cr(20/25)}$ characteristic bond resistance for cracked concrete for concrete strength class C20/25 for the relevant temperature range and working life

Injection System VME plus

Performance

Characteristic values of tension and shear loads under fire exposure (internally threaded rods)

Annex C27

Table C32: Characteristic values of tension and shear loads under fire exposure (rebar)

| Rebar | | | | Ø8 | Ø10 | Ø12 | Ø14 | Ø16 | Ø20 | Ø24 | Ø25 | Ø28 | Ø32 |
|--|------------------------|----------------------|---|---|-----|-----|-----|-----|------|------|------|------|------|
| Steel failure | | | | | | | | | | | | | |
| BSt 500 | | | | | | | | | | | | | |
| Characteristic tension resistance | $N_{Rk,s,fi}$ | [kN] | R30 | 0,5 | 1,2 | 2,3 | 3,1 | 4,0 | 6,3 | 9,0 | 9,8 | 12,3 | 16,1 |
| | | | R60 | 0,5 | 1,0 | 1,7 | 2,3 | 3,0 | 4,7 | 6,8 | 7,4 | 9,2 | 12,1 |
| | | | R90 | 0,4 | 0,8 | 1,5 | 2,0 | 2,6 | 4,1 | 5,9 | 6,4 | 8,0 | 10,5 |
| | | | R120 | 0,3 | 0,6 | 1,1 | 1,5 | 2,0 | 3,1 | 4,5 | 4,9 | 6,0 | 8,0 |
| Characteristic bond resistance in cracked and uncracked concrete C20/25 up to C50/60 under fire conditions for a given temperature θ | | | | | | | | | | | | | |
| Temperature reduction factor | $k_{fi,p}(\theta)$ | [-] | $\theta < 25^\circ\text{C}$ | 1,0 | | | | | | | | | |
| | | | $25^\circ\text{C} \leq \theta \leq 278^\circ\text{C}$ | $176,37 \cdot \theta^{-1,598} \leq 1,0$ | | | | | | | | | |
| | | | $\theta > 278^\circ\text{C}$ | 0,0 | | | | | | | | | |
| <p>The graph shows the reduction factor $k_{fi}(\theta)$ as a function of temperature θ in degrees Celsius. The y-axis ranges from 0.0 to 1.0, and the x-axis ranges from 0 to 350. The curve is constant at 1.0 for temperatures up to 25°C, then decreases according to the formula $176,37 \cdot \theta^{-1,598} \leq 1,0$ until it reaches 0.0 at 278°C, where it remains for all higher temperatures.</p> | | | | | | | | | | | | | |
| Characteristic bond resistance for a given temperature (θ) | $\tau_{Rk,fi}(\theta)$ | [N/mm ²] | $k_{fi,p}(\theta) \cdot \tau_{Rk,cr(20/25)}^1$ | | | | | | | | | | |
| Steel failure without lever arm | | | | | | | | | | | | | |
| BSt 500 | | | | | | | | | | | | | |
| Characteristic shear resistance | $V_{Rk,s,fi}$ | [kN] | R30 | 0,5 | 1,2 | 2,3 | 3,1 | 4,0 | 6,3 | 9,0 | 9,8 | 12,3 | 16,1 |
| | | | R60 | 0,5 | 1,0 | 1,7 | 2,3 | 3,0 | 4,7 | 6,8 | 7,4 | 9,2 | 12,1 |
| | | | R90 | 0,4 | 0,8 | 1,5 | 2,0 | 2,6 | 4,1 | 5,9 | 6,4 | 8,0 | 10,5 |
| | | | R120 | 0,3 | 0,6 | 1,1 | 1,5 | 2,0 | 3,1 | 4,5 | 4,9 | 6,0 | 8,0 |
| Steel failure with lever arm | | | | | | | | | | | | | |
| BSt 500 | | | | | | | | | | | | | |
| Characteristic bending moment | $M^0_{Rk,s,fi}$ | [Nm] | R30 | 0,6 | 1,8 | 4,1 | 6,5 | 9,7 | 18,8 | 32,6 | 36,8 | 51,7 | 77,2 |
| | | | R60 | 0,5 | 1,5 | 3,1 | 4,8 | 7,2 | 14,1 | 24,4 | 27,6 | 38,8 | 57,9 |
| | | | R90 | 0,4 | 1,2 | 2,6 | 4,2 | 6,3 | 12,3 | 21,2 | 23,9 | 33,6 | 50,2 |
| | | | R120 | 0,3 | 0,8 | 2,0 | 3,2 | 4,8 | 9,4 | 16,3 | 18,4 | 25,9 | 38,6 |

¹⁾ $\tau_{Rk,cr(20/25)}$ characteristic bond resistance for cracked concrete for concrete strength class C20/25 for the relevant temperature range and working life

Injection System VME plus

Performance
Characteristic values of tension and shear loads under fire exposure (rebar)

Annex C28