

Public-law institution jointly founded by the federal states and the Federation

**European Technical Assessment Body
for construction products**



European Technical Assessment

**ETA-25/0073
of 21 July 2025**

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

StoTherm Mineral AimS

Product family
to which the construction product belongs

External Thermal Insulation Composite System with
rendering on mineral wool for the use as external
insulation of building walls

Manufacturer

Sto SE & Co. KGaA
Ehrenbachstraße 1
79780 Stühlingen
GERMANY

Manufacturing plant

This European Technical Assessment
contains

17 pages including 5 annexes which form an integral part
of this assessment

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

040083-00-0404

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

This product is an ETICS (External Thermal Insulation Composite System) with rendering - a kit comprising components which are factory-produced by the manufacturer or component suppliers. It's made up on site from these. The ETICS manufacturer is ultimately responsible for the ETICS.

The ETICS is comprised a prefabricated insulation product of mineral wool (MW) to be bonded and if necessary additional mechanically fixed onto a wall.

The walls are made of masonry (bricks, blocks, stones...) or concrete (cast on site or as prefabricated panels). The methods of fixing and the relevant components are specified in annex 1 below.

The insulation product is faced with a rendering system consisting of one base and finishing coat (site applied), the base coat contains reinforcement. The rendering system is applied directly to the insulating panels, without any air gap or disconnecting layer.

The ETICS may include special fittings (e.g. base profiles, corner profiles ...) for connection to adjacent building elements (apertures, corners, parapets...). Assessment and performance of these components is not addressed in this ETA, however the ETICS-manufacturer is responsible for adequate compatibility and performance within the ETICS when the components are delivered as a part of the kit.

2 Specification of the intended use in accordance with the applicable European assessment Document

The performances in Section 3 can only be assumed if the ETICS is used in accordance with the specifications and under the boundary conditions specified in Annexes 2 to 5.

The verifications and assessment methods on which this ETA is based lead to the assumption of a working life of the ETICS "StoTherm Mineral AimS" of at least 25 years. The indications given on the working life cannot be interpreted as a guarantee given by the manufacturer, but are to be regarded only as a means for choosing the right products in relation to the assumed economically reasonable working life of the works.

For use, maintenance and repair, the finishing coat shall normally be maintained in order to fully preserve the ETICS performance. Maintenance includes at least:

- visual inspection of the ETICS,
- the repairing of localized damaged areas due to accidents,
- the aspect maintenance with products compatible with the ETICS (possibly after washing or ad hoc preparation).

Necessary repairs are to be carried out as soon as the need has been identified.

The information on use, maintenance and repair is given in the manufacturer's technical documentation.

It is the responsibility of the manufacturer to ensure that this information is made known to the concerned people.

3 Performance of the product and references to the methods used for its assessment

3.1 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire of the ETICS	(see annex 2) Euroclass according to EN 13501-1
Reaction to fire of the MW-insulation product <ul style="list-style-type: none"> - Cross heat of combustion for the MW-insulation product EN ISO 1716 - Apparent density EN 1602 	(see annex 2) Euroclass A1 according EN 13501-1 Value [MJ/kg] Value [kg/m³]
Facade fire performance	no performance assessed
Propensity to undergo continuous smouldering of ETICS	no performance assessed

3.2 Hygiene, health and environment (BWR 3)

Essential characteristic	Performance
Release of dangerous substances	no performance assessed
Water absorption Base coat after 1 hour after 24 hours Rendering system after 1 hour after 24 hours MW insulation product after 24 hours	(see annex 3.1) Average [kg/m²] Average [kg/m²] Average [kg/m²] Average [kg/m²] Maximum value 3.0 kg/m²
Water-tightness of the ETICS Hygrothermal behaviour on the test wall	Pass without defects
Water-tightness of the ETICS: Freeze/thaw behaviour	The water absorption of the base coats as well as the rendering systems with all finishing coats except "StoSilco blue K/MP" is less than 0.5 kg/m² after 24 hours. The ETICS with the finishing coat "StoSilco blue K/MP" has been assessed as freeze/thaw resistant according to the simulated method.
Impact resistance	(see annex 3.2) Category
Water vapour permeability - Rendering system - MW insulation product	(see annex 3.3) s _d value [m] μ = 1 Thickness of the insulation product 340 mm

3.3 Safety and accessibility in use (BWR 4)

Essential characteristic	Performance
Bond strength between base coat and MW insulation product between adhesive and substrate between adhesive and MW insulation	(see annex 4.1) - Minimal value/average [kPa] - Minimal value/average [kPa] (see annex 4.2) - Thickness [mm] of the used adhesives - Minimal value [kPa], rupture type: Initial state (dry conditions) - Minimal value/average [kPa], rupture type: after 2 d immersion in water, 2 h drying - Minimal value/average [kPa], rupture type: after 2 d immersion in water, 7 d drying (see annex 4.3) - Thickness [mm] of the used adhesives - Minimal value [kPa], rupture type: Initial state (dry conditions) - Minimal value/average [kPa], rupture type: after 2 d immersion in water, 2 h drying - Minimal value/average [kPa], rupture type: after 2 d immersion in water, 7 d drying
Fixing strength (displacement test)	Test not required therefore no limitation of ETICS length required.
Wind load resistance of ETICS pull-through test of fixing static foam block test	(see annex 4.4) - R_{panel} [kN/fixing], - R_{joint} [kN/fixing], - Plate diameter of anchor ≥ 60 mm, ≥ 90 mm res. ≥ 140 mm - plate stiffness ≥ 0.3 kN/mm ² - load resistance of the anchor plate ≥ 1.0 kN
Tensile strength perpendicular to the faces in dry conditions MW panel, MW panel MW lamella in wet conditions - series 2 - series 3	$\sigma_{\text{mt}} \geq 14$ kPa, $\sigma_{\text{mt}} \geq 5$ kPa (mechanically fixed ETICS with anchors and supplementary adhesive) $\sigma_{\text{mt}} \geq 80$ kPa (bonded ETICS) ≥ 33 % of average value in dry conditions ≥ 50 % of average value in dry conditions

Essential characteristic	Performance
Shear strength of the ETICS MW panel $\sigma_{mt} \geq 14$ kPa MW lamella $\sigma_{mt} \geq 80$ kPa MW panel $\sigma_{mt} \geq 5$ kPa	≥ 20 kPa ≥ 20 kPa ≥ 6 kPa
Shear modulus of the ETICS MW panel $\sigma_{mt} \geq 14$ kPa MW lamella $\sigma_{mt} \geq 80$ kPa MW panel $\sigma_{mt} \geq 5$ kPa	≥ 1.0 MPa ≥ 1.0 MPa ≥ 0.3 MPa
Render strip tensile test	(see annex 4.5) Crack width w_{rk} [mm]
Bond strength after ageing finishing coat tested on the rig finishing coat not tested on the rig	(see annex 4.6) Minimal value/average [kPa] Minimal value/average [kPa]
Tensile strength of the glass fibre mesh in the as-delivered state	(see annex 4.7) Average [N/mm]
Residual tensile strength of the glass fibre mesh after aging	(see annex 4.7) Average [N/mm]
Relative residual tensile strength of the glass fibre mesh after aging	(see annex 4.7) Average [%]
Elongation of the glass fibre mesh in the as-delivered state	(see annex 4.7) Average [%]
Elongation of the glass fibre mesh after aging	(see annex 4.7) Average [%]

3.4 Protection against noise (BWR 5)

Essential characteristic	Performance
Airborne sound insulation of ETICS	no performance assessed
Dynamic stiffness of the MW insulation product	no performance assessed
Air flow resistance of the MW insulation product	no performance assessed

3.5 Energy economy and heat retention (BWR 6)

Essential characteristic	Performance
Thermal resistance of ETICS	(see annex 5) Calculated value or measurement value R [(m ² · K)/W]
Thermal transmittance of ETICS	(see annex 5) Calculated value or measurement value U [W/(m ² · K)]

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with EAD No. 040083-00-0404 the applicable European legal act is: 97/556/EC changed by 2001/596/EC.

The systems to be applied are:

Product	Intended use	Levels or classes (Reaction to fire)	Systems
"StoTherm Mineral AimS"	ETICS in external wall subject to fire regulations	A1 ⁽¹⁾ , A2 ⁽¹⁾ , B ⁽¹⁾ , C ⁽¹⁾	1
		A1 ⁽²⁾ , A2 ⁽²⁾ , B ⁽²⁾ , C ⁽²⁾ , D, E, (A1 to E) ⁽³⁾ , F	2+
	ETICS in external wall not subject to fire regulations	any	2+
<p>⁽¹⁾ Products/materials for which a clearly identifiable stage in the production process results in an improvement of the reaction to fire classification (e. g. an addition of fire retardants or a limiting of organic material)</p> <p>⁽²⁾ Products/materials not covered by footnote (1)</p> <p>⁽³⁾ Products/materials that do not require to be tested for reaction to fire (e.g. products/materials of Classes A1 according to Commission Decision 96/603/EC)</p>			

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable European Assessment Document

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at Deutsches Institut für Bautechnik.

Issued in Berlin on 21 July 2025 Deutsches Institut für Bautechnik

Anja Rogsch
Head of Section

beglaubigt:
Klette

Annex 1

Composition of the ETICS

	Components National application documents shall be taken into account	Coverage [kg/m ²]	Thickness [mm]
Insulation material with associated method of fixing	Bonded ETICS: <ul style="list-style-type: none"> • Insulation product factory-prefabricated mineral wool (MW) product^{a)} <ul style="list-style-type: none"> - MW lamella • Adhesive <ul style="list-style-type: none"> - Sto-Baukleber (cement based powder requiring addition of 23 – 25 % of water) - StoColl CX (cement based powder requiring addition of 23 – 25 % of water) - StoColl IP Plus (cement based powder requiring addition of 21 – 23 % of water) - StoColl Mineral HP (cement based powder requiring addition of 23 – 25 % of water) - StoLevell Duo Plus (cement based powder requiring addition of 22 – 23 % of water) - StoLevell FT (cement based powder requiring addition of 23 – 25 % of water) - StoLevell Neo AimS (cement based powder requiring addition of 25 – 28 % of water) - StoLevell Uni (cement based powder requiring addition of 24 – 26 % of water) 	–	≤ 340
	Mechanically fixed ETICS with anchors and supplementary adhesive: <ul style="list-style-type: none"> • Insulation product factory-prefabricated mineral wool (MW) product^{a)} <ul style="list-style-type: none"> - MW panel - MW lamella • Supplementary adhesives (equal to bonded ETICS) • Anchors for insulation product all anchors with ETA according to EAD 330196-01-604¹ 	– –	60 to 400 60 to 200
Base coat	StoLevell Neo AimS Identical with the equally named adhesive given above.	5.5 to 10.0 (powder)	3.0 to 5.0
Glass fibre mesh	Sto-Glasfasergewebe Alkali- and slide-resistant glass fibre mesh with mass per unit area of 165 ± 15 g/m ² and mesh size of about 6.0 mm x 6.0 mm	–	–
	Sto-Glasfasergewebe F Alkali- and slide-resistant glass fibre mesh with mass per unit area of 165 ± 15 g/m ² and mesh size of about 4.0 mm x 4.0 mm	–	–

¹ EAD 330196-01-604

Plastic anchors made of virgin or non-virgin material for fixing of external thermal insulation composite systems with rendering (and previous versions)

	Components National application documents shall be taken into account	Coverage [kg/m ²]	Thickness [mm]
Key coat^{b)}	StoPrep Miral AimS Sto-Putzgrund Ready to use pigmented acrylic-resin dispersion liquids.	0,3 – 0,4 0,3	– –
Finishing coat	<ul style="list-style-type: none"> Ready to use paste – pure acrylate: Stolit AimS K (particle size 1.0 to 3.0 mm) Stolit AimS MP (thin, medium or thick layer) Ready to use paste – acrylic binder: StoLotusan K (particle size 1.0 to 3.0 mm) StoLotusan MP (thin, medium or thick layer) cement based powder requiring addition of 25 % of water StoMiral K (particle size 1.0 to 6.0 mm) StoMiral R (particle size 1.0 to 6.0 mm) StoMiral MP (fine structure) Ready to use paste – acrylic siloxane binder: StoSilco blue K (particle size 1.0 to 3.0 mm) StoSilco blue MP (particle size 1.0 to 3.0 mm) 	1.6 to 4.6 1.5 to 4.0 1.8 to 4.3 1.5 to 4.0 1.6 to 5.2 1.6 to 5.2 1.5 to 4.0 1.6 to 4.6 1.5 to 4.0	1.0 to 3.0 1.0 to 3.0 1.0 to 3.0 1.0 to 3.0 1.0 to 6.0 1.0 to 6.0 1.0 to 3.0 1.0 to 3.0 1.0 to 3.0
Decorative coat (optional)	StoColor Lotusan AimS StoColor Solical	0.2 to 0.4 l/m ² 0.2 to 0.4 l/m ²	– –
^{a)} Factory-prefabricated panels and lamella made of mineral wool (MW) with the following designation code and the other properties shall be used, provided that the manufacturer and the trade name of the MW are deposited with the DIBt MW – EN 13162 – T5 – DS(T+) – WS – WL(P) – MU1 ^{b)} The instruction to the installer concerning the use of a key coat remains the responsibility of the ETA-holder.			

Annex 2

Safety in case of fire (BWR 2)

2.1 Reaction to fire

Configurations	Organic content	Flame retardant content	Euroclass according to EN 13501-1
Base coat	max. 3,6 %	no flame retardant	
Mineral wool insulation product	Euroclass A1 according to EN 13501-1	no flame retardant	
Anchors	-	-	
Rendering system: Base coat with finishing coat and compatible key coat indicated in annex 1			
Stolit AimS	max. 8,5 %	min. 10,0 %	A2 - s1,d0
StoLotusan K/MP	max. 9,4 %	min. 8,0 %	
StoSilco blue K/MP			
StoMiral K/R/MP	max. 1,8 %	no flame retardant	

2.2 Cross heat of combustion for the MW-insulation product EN ISO 1716

PCS \leq 1.30 MJ/kg

2.3 Apparent density EN 1602

Description and characteristics	MW panel	MW panel	MW lamella
Tensile strength perpendicular to the faces [kPa]; EN 1607 - in dry conditions ^{a)}	$\sigma_{mt} \geq 14$	$\sigma_{mt} \geq 5$	$\sigma_{mt} \geq 80$
Apparent density [kg/m ³]; EN 1602	$120 \leq \rho_a \leq 140$	$73 \leq \rho_a \leq 140$	$80 \leq \rho_a \leq 140$
^{a)} Minimal value of all single values			

Annex 3

Hygiene, health and environment (BWR 3)

3.1 Water absorption (capillarity test)

Base coat:

Base coat	Thickness	Average water absorption [kg/m ²]	
		after 1 h	after 24 h
StoLevell Neo AimS	4-5 mm	0.087	0.299

Rendering system:

Finishing coat with base coat "StoLevell Neo AimS" indicated hereafter	Average water absorption [kg/m ²]	
	after 1 h	after 24 h
Stolit AimS K/MP	0.016	0.084
StoLotusan K/MP	0.015	0.465
StoMiral K/R/MP	0.049	0.198
StoSilco blue K/MP	0.039	0.745

3.2 Impact resistance (tested on small samples)

Rendering system: Base coat "StoLevell Neo AimS" with finishing coat indicated hereafter:	"Sto- Glasfasergewebe" [Category]	2 x "Sto- Glasfasergewebe" [Category]
Stolit AimS K/MP	II	II
StoLotusan K/MP	II	II
StoMiral K/R/MP	II	II
StoSilco blue K/MP	II	II

3.3 Water vapour permeability ETICS

Rendering system	Equivalent air thickness s_d [m]
Base coat only:	
StoLevell Neo AimS	≤ 1.0 m (Result determined with d = 3 mm: 0.02) ≤ 1.0 m (Result determined with d = 5 mm: 0.04)
Base coat "StoLevell Neo AimS" (4-5 mm) with finishing coat (3 mm) indicated hereafter:	
Stolit AimS K/MP	0.21
StoLotusan K/MP	0.27
StoMiral K/R/MP	0.13
StoSilco blue K/MP	0.25
Base coat "StoLevell Neo AimS" (4-5 mm), key coat "StoPrep Miral AimS" (0,3 kg/m²), finishing coat (3 mm) indicated hereafter and decorative coat "StoColor Lotusan AimS" or "StoColor Lotusan AimS" (0,3 l/m²)	
Stolit AimS K/MP	0.62
StoLotusan K/MP	0.60
StoMiral K/R/MP	0.22
StoSilco blue K/MP	0.46

Annex 4

Safety and accessibility in use (BWR 4)

4.1 Bond strength between base coat and MW lamella

		Conditioning		
		Initial state [kPa]	After hygrothermal cycles [kPa]	After freeze/thaw test
StoLevell Neo AimS	Average	127	60 ^{a)}	Test not required because freeze/thaw cycles not necessary
	Minimal value	86	27 ^{a)}	

^{a)} < 80 kPa, but failure in thermal insulation material

4.2 Bond strength between adhesive and substrate

substrate: concrete		Rupture type	Conditioning		
			Initial state [kPa]	2 d immersion in water and 2 h drying [kPa]	2 d immersion in water and 7 d drying [kPa]
Sto-Baukleber (5 mm)	Average	in adhesive	1210	1150	1620
	Minimal value		930	970	1210
StoColl CX (3 – 5 mm)	Average	in adhesive	1360	960	1830
	Minimal value		1305	875	1759
StoColl IP Plus (4 – 5 mm)	Average	in adhesive	1210	1150	1620
	Minimal value		930	970	1210
StoColl Mineral HP (5 mm)	Average	in adhesive	2080	1840	1790
	Minimal value		1927	1732	1732
StoLevell Duo plus (5 mm)	Average	in adhesive	1230	583	2020
	Minimal value		1166	501	1893
StoLevell FT (5 mm)	Average	in adhesive	1233	369	1157
	Minimal value		784	299	1026
StoLevell Neo AimS (4 – 5 mm)	Average	in adhesive	360	230	460
	Minimal value		338	217	446
StoLevell Uni (5 mm)	Average	in adhesive	1793	637	2560
	Minimal value		1586	467	2489

4.3 Bond strength between adhesive and MW lamella

		Rupture type	Conditioning		
			Initial state [kPa]	2 d immersion in water and 2 h drying [kPa]	2 d immersion in water and 7 d drying [kPa]
Sto-Baukleber (3 – 5 mm)	Average	in insulation product	102	92	78 ^{a)}
	Minimal value		91	81	70 ^{a)}
StoColl CX (3 – 5 mm)	Average	in insulation product	80	80	80
	Minimal value		80	77 ^{a)}	79 ^{a)}
StoColl IP Plus (4 – 5 mm)	Average	in insulation product	102	92	78 ^{a)}
	Minimal value		91	81	70 ^{a)}
StoColl Mineral HP (3 – 5 mm)	Average	in insulation product	140	110	110
	Minimal value		128	106	101
StoLevell Duo plus (3 – 5 mm)	Average	in insulation product	91	74 ^{a)}	92
	Minimal value		85	67 ^{a)}	80
StoLevell FT (3 – 5 mm)	Average	in insulation product	86	64 ^{a)}	68 ^{a)}
	Minimal value		73 ^{a)}	57 ^{a)}	56 ^{a)}
StoLevell Neo AimS (4 – 5 mm)	Average	in insulation product	122	92	107
	Minimal value		119	88	103
StoLevell Uni (3 – 5 mm)	Average	in insulation product	87	60 ^{a)}	81
	Minimal value		77 ^{a)}	55 ^{a)}	78 ^{a)}
^{a)} < 80 kPa but failure in thermal insulation material					

Minimal bonded surface area

$$S [\%] = 0.03 \text{ N/mm}^2 \times 100 / 0.08 \text{ N/mm}^2$$

$$S = 37.5 \%$$

The minimal bonded surface S of bonded ETICS is 50 % (systemic).

4.4 Wind load resistance

The following failure loads only apply to the listed combination of component characteristics and the characteristics of the insulation product in annex 1.

4.4.1 Safety in use of mechanically fixed ETICS using anchors

Failure loads – table 1

Apply to all anchors listed in the annex 1 mounted on the insulation panels surface			
Characteristics of the MW panels		Thickness	≥ 60 mm
		Tensile strength perpendicular to the faces	≥ 14 kPa
Plate diameter of anchor			≥ Ø 60 mm
Failure load [kN]	Anchors not placed at the panel joints (Static Foam Block Test)	R _{panel}	Minimal: 0.65 Average: 0.74
	Anchors placed at the panel joints (Static Foam Block Test)	R _{joint}	Minimal: 0.59 Average: 0.61
	Anchors not placed at the panel joints (Pull-through test, dry conditions)	R _{panel}	Minimal: 0.64 Average: 0.60
	Anchors not placed at the panel joints (Pull-through test, wet conditions) - series 2 ^{a)} - series 3 ^{a)}	R _{panel}	Minimal: 0.36 Average: 0.39 Minimal: 0.41 Average: 0.45
^{a)} according to EAD 040083-00-0404 clause 2.2.14.2			

Failure loads – table 2

Apply to all anchors listed in the annex 1 mounted on the insulation panels surface				
Characteristics of the MW panels		Thickness	≥ 80 mm	
		Tensile strength perpendicular to the faces	≥ 5.0 kPa	
Plate diameter of anchor			≥ Ø 90 mm	≥ Ø 140 mm
Failure load [kN]	Anchors not placed at the panel joints (Static Foam Block Test)	R _{panel}	Minimal: 0.48 Average: 0.49	Minimal: 0.56 Average: 0.69
	Anchors placed at the panel joints (Static Foam Block Test)	R _{joint}	Minimal: 0.38 Average: 0.39	Minimal: 0.44 Average: 0.54
	Anchors not placed at the panel joints (Pull-through test, dry conditions)	R _{panel}	Minimal: 0.54 Average: 0.61	no performance assessed
	Anchors not placed at the panel joints (Pull-through test, wet conditions) - series 2 ^{a)}	R _{panel}	Minimal: 0.40 Average: 0.46	no performance assessed
a) according to EAD 040083-00-0404 clause 2.2.14.2				

Failure loads – Table 3

Apply to all anchors listed in the annex 1 mounted on the insulation panels surface					
Characteristics of the MW lamella		Thickness		≥ 60 mm	
		Tensile strength perpendicular to the faces		≥ 80 kPa	
Plate diameter of anchor				≥ Ø 140 mm	
Failure load [kN]	Anchors placed at the panel joints (Pull-through test, dry condition)		R _{joint}	Minimal:	0.62
				Average:	0.66
	Anchors placed at the panel joints (Pull-through test, wet condition)		R _{joint}	Minimal:	0.51
				Average:	0.57
	Anchors placed at the panel joints (Static Foam Block Test)		R _{joint}	Minimal:	0.71

The failure loads specified above with a plate diameter of anchor of 60 mm apply to the following anchors with deep mounting only under the following conditions:

Anchor	Thickness of the MW panel [t]	Conditions of installation ^{a)}
ejotherm STR U ejotherm STR U 2G (ETA-04/0023)	$t \geq 80 \text{ mm}$	<ul style="list-style-type: none"> Maximum installation depth of the anchor plate: 15 mm (\triangleq thickness of insulation cover) Cutting depth 20 mm
	$t \geq 100 \text{ mm}$	<ul style="list-style-type: none"> Maximum installation depth of the anchor plate: 15 mm (\triangleq thickness of insulation cover) Cutting depth 35 mm
TERMOZ 8 SV (ETA-06/0180)	$t \geq 80 \text{ mm}$	<ul style="list-style-type: none"> Maximum installation depth of the anchor plate: 15 mm (\triangleq thickness of insulation cover)
^{a)} according to the appropriate ETA of anchor		

4.5 Render strip tensile test

The average value of crack width of the base coats reinforced with the different glass fibre meshes measured at a render strain value of 1 % is:

Base coat	Glass fibre mesh	Average value of crack width w_m (1%)
StoLevell Neo AimS	Sto-Glasfasergewebe	0,15 mm
	Sto-Glasfasergewebe F	no performance assessed

4.6 Bond strength after aging

Finishing coats with base coats indicated hereafter		7 d immersion in water and 7 d drying ^{b)} [kPa]	After hygrothermal cycles ^{c)} [kPa]
Stolit AimS K/MP	Average	100	89
	Minimal value	92	60 ^{a)}
StoLotusan K/MP	Average	92	no performance assessed
	Minimal value	83	
StoMiral K/R/MP	Average	98	76 ^{a)}
	Minimal value	94	53 ^{a)}
StoSilco blue K/MP	Average	98	no performance assessed
	Minimal value	91	

a) < 80 kPa but failure in thermal insulation material
b) finishing coat not tested on the rig
c) finishing coat tested on the rig

4.7 Reinforcement (glass fibre mesh)

Sto-Glasfasergewebe	Average warp	Average weft
Tensile strength in as-delivered state	≥ 40 N/mm	≥ 55 N/mm
Residual tensile strength after aging	≥ 20 N/mm	≥ 30 N/mm
Relative residual tensile strength after aging	≥ 50 %	≥ 50 %
Elongation in as-delivered state	3.7 %	3.8 %
Elongation after aging	1.8 %	2.1 %

Sto-Glasfasergewebe F	Average warp	Average weft
Tensile strength in as-delivered state	≥ 40 N/mm	≥ 45 N/mm
Residual tensile strength after aging	≥ 25 N/mm	≥ 30 N/mm
Relative residual tensile strength after aging	≥ 50 %	≥ 50 %
Elongation in as-delivered state	3.9 %	4.2 %
Elongation after aging	2.7 %	2.6 %

Annex 5

Energy economy and heat retention (BWR 6)

5.1 Thermal resistance and thermal transmittance

The nominal value of the additional thermal resistance R provided by the ETICS to the substrate wall is calculated in accordance with EN ISO 6946 from the nominal value of the insulation product's thermal resistance R_D given accompanied to the CE marking and from the thermal resistance of the rendering system R_{render} which is about $0.02 \text{ (m}^2 \cdot \text{K)/W}$.

$$R = R_D + R_{render}$$

The thermal bridges caused by mechanical fixing (anchors, profiles) increases the thermal transmittance U . This influence had to take into account according to EN ISO 6946.

$$U_c = U + \chi_p \cdot n$$

Where: U_c :	corrected thermal transmittance [$\text{W}/(\text{m}^2 \cdot \text{K})$]
n :	number of anchors per m^2
χ_p :	local influence of thermal bridge caused by an anchor. The values listed below can be taken into account if not specified in the anchor's ETA:
$\chi_p = 0.004 \text{ W/K}$	for anchors with a galvanized steel screw with the head covered by a plastic material
$\chi_p = 0.002 \text{ W/K}$	for anchors with a stainless steel screw covered by plastic anchors and for anchors with an air gap at the head of the screw