

Public-law institution jointly founded by the
federal states and the Federation

**European Technical Assessment Body
for construction products**



European Technical Assessment

**ETA-19/0619
of 7 May 2026**

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Trade name of the construction product

Product family
to which the construction product belongs

Manufacturer

Manufacturing plant

This European Technical Assessment
contains

This European Technical Assessment is
issued in accordance with Article 95(4) of
Regulation (EU) 2024/3110, on the basis of

This version replaces

Deutsches Institut für Bautechnik

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Mechanical fasteners for use in concrete

MKT

Metall-Kunststoff-Technik GmbH & Co. KG

Auf dem Immel 2

67685 Weilerbach

GERMANY

MKT Metall-Kunststoff-Technik GmbH & Co. KG

Auf dem Immel 2

67685 Weilerbach

24 pages including 3 annexes which form an integral part
of this assessment

EAD 330232-02-0601

ETA-19/0619 issued on 12 June 2024

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 36(3) of Regulation (EU) No 2024/3110.

Specific Part

1 Technical description of the product

The Wedge anchor BZ3 / BZ3 A4 / BZ3 HCR is a fastener made of zinc plated steel, stainless steel or high corrosion resistant steel which is placed into a drilled hole and anchored by torque-controlled expansion.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the fastener is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the fastener of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	see Annex B3, C1, C2
Characteristic resistance to shear load (static and quasi-static loading)	see Annex C3
Characteristic resistance for seismic performance categories C1 and C2	see Annex C4, C5
Displacements	see Annex C8, C9, C10
Stiffness	No performance assessed

3.2 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire	Class A1
Resistance to fire	see Annex C6, C7

3.3 Aspects of durability (BWR 2)

Essential characteristic	Performance
Durability	see Annex B1

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with the European Assessment Document EAD 330232-02-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.


Issued in Berlin on 7 May 2026 by Deutsches Institut für Bautechnik

Dipl.-Ing. Beatrix Wittstock
Head of Section


beglaubigt:
Ziegler

Wedge anchor BZ3, BZ3 A4 and BZ3 HCR


Installation condition



Installation condition with filling washer (optional with cap nut)



Installation condition with cap nut HM (optional with filling washer)




Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Product description
Product types and installation conditions

Annex A1

Marking



Usable length: $B = h_{\text{ef}} + t_{\text{fix}}$
 h_{ef} : (existing) effective anchorage depth
 t_{fix} : fixture thickness (including e.g. levelling layers or other non-load-bearing layers or additional filling washer)

Table A1: Length identification

Length identifier	A	B	C	D	E	F	G	H	I	J	K	L	M	N	O
Usable length B $\geq$	35	40	45	50	55	60	65	70	75	80	85	90	95	100	105

Length identifier	P	Q	R	S	T	U	V	W	X	Y	Z	AA	BB	CC	DD
Usable length B $\geq$	110	115	120	125	130	135	140	145	150	160	170	180	190	200	210

Length identifier	EE	FF	GG	HH	II	JJ	KK	LL
Usable length B $\geq$	220	230	240	250	260	270	280	290

Dimensions in mm

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Product description
Marking


Annex A2

Table A2: Material



Part	BZ3	BZ3 A4	BZ3 HCR
	Steel, zinc plated	Stainless steel CRC III	High corrosion resistant steel CRC V
Conical bolt	Steel, galvanized $\geq 5 \mu\text{m}$ fracture elongation $A_5 \geq 8\%$	Stainless steel fracture elongation $A_5 \geq 8\%$	High corrosion resistant steel fracture elongation $A_5 \geq 8\%$
Expansion sleeve	Stainless steel	Stainless steel	Stainless steel
Washer	Steel, galvanized $\geq 5 \mu\text{m}$	Stainless steel	High corrosion resistant steel
Filling washer VS			
Hexagon nut			
Cap nut HM			

Table A3: Fastener dimensions


Fastener size			M8	M10	M12	M16	M20
Width across hexagon nut / cap nut HM	s	[mm]	13	17	19	24	30
Length of fastener	L	[mm]	$h_{ef} + t_{fix} + 18,0$	$h_{ef} + t_{fix} + 21,5$	$h_{ef} + t_{fix} + 26,0$	$h_{ef} + t_{fix} + 33,0$	$h_{ef} + t_{fix} + 37,0$
Thickness of filling washer VS	t	[mm]	5				




Filling washer VS with reducing adapter



alternate filling washer



Setting tool BSW



Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Product description
Material and dimensions

Annex A3

Specifications of intended use

Wedge Anchor		M8	M10	M12	M16	M20
Anchorage subject to	Static or quasi-static action	✓				
	Seismic action	✓				
	performance categories	✓				
	Fire exposure	R30 / R60 / R90 / R120				
Base materials	Normal weight concrete	compacted reinforced or unreinforced normal weight concrete according to EN 206:2013+A2:2021				
	Steel fibre reinforced concrete (SFRC)	according to EN 206:2013+A2:2021 including steel fibres according to EN 14889-1:2006, clause 5, group I; maximum content of steel fibres 80 kg/m ³				
	Cracked or uncracked concrete	✓				
	Strength classes	C20/25 to C80/95 ¹⁾ according to EN 206:2013+A2:2021				
Drilling and cleaning	Hammer drilling (with cleaning)	✓				
	Hammer drilling (3x ventilate / without cleaning)	✓ ²⁾				
	Vacuum drilling (automatic cleaning)	✓				
h_{ef}	Variable, effective anchorage depth	35 mm to 90 mm	40 mm to 100 mm	50 mm to 125 mm	65 mm to 160 mm	90 mm to 140 mm

¹⁾ BZ3 M8 A4/HCR: C20/25 to C50/60

²⁾ Except BZ3 M8 A4/HCR

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions: all materials
- For all other conditions corresponding to corrosion resistance classes CRC according to EN 1993-1-4:2006 + A1:2015: stainless steel according to Annex A3, Table A2 of this ETA

Design:

- Anchorage is designed under the responsibility of an engineer experienced in anchorages and concrete work.
- Verifiable calculation notes and drawings are prepared taking account of the loads to be anchored. The position of the fastener is indicated on the design drawings (e.g. position of the fastener relative to reinforcement or to supports, etc.).
- Design method EN 1992-4:2018.

Installation:

- Use of the fastener only as supplied by the manufacturer without exchanging the components of the fastener (exception: when using the cap nut HM)
- The anchor can be set in pre- or through-setting installation.
- Optionally, the annular gap between fixture and stud of BZ3 can be filled to reduce the hole clearance. For this purpose, the filling washer (Annex A3) must be used in addition to the supplied washer. For filling use MKT Injection Adhesive VMH, VMU plus, VMZ or other high-strength injection mortar with compressive strength ≥ 40 N/mm².

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR


Intended use
Specifications

Annex B1

Table B1: Installation parameters

Anchor size				M8	M10	M12	M16	M20
Nominal drill hole diameter	d_0	[mm]		8	10	12	16	20
Cutting diameter of drill bit	$d_{cut} \leq$	[mm]		8,45	10,45	12,5	16,5	20,55
Minimum effective anchorage depth	$h_{ef,min}$	[mm]		35	40	50	65	90
Maximum effective anchorage depth	$h_{ef,max}$	[mm]		90	100	125	160	140
Depth of drill hole	Hammer drilling	$h_0 \geq$	[mm]	$h_{ef} + 8$	$h_{ef} + 9$	$h_{ef} + 10$	$h_{ef} + 14$	$h_{ef} + 14$
	vacuum drilling	$h_1 \geq$	[mm]	$h_{ef} + 10$	$h_{ef} + 11$	$h_{ef} + 13$	$h_{ef} + 17$	$h_{ef} + 17$
	Hammer drilling	$h_0 \geq$	[mm]	$h_{ef} + 23$	$h_{ef} + 23$	$h_{ef} + 24$	$h_{ef} + 28$	$h_{ef} + 28$
	without cleaning	$h_1 \geq$	[mm]	$h_{ef} + 25$	$h_{ef} + 25$	$h_{ef} + 27$	$h_{ef} + 31$	$h_{ef} + 31$
Diameter of clearance hole in the fixture ¹⁾	$d_f \leq$	[mm]		9	12	14	18	22
Projection after insertion of the anchor for mounting with cap nut HM (acc. to Annex B7, Figure 3)	C	[mm]		10,5	12,5	16,0	19,5	23,0
Installation torque	BZ3	T_{inst}	[Nm]	15	40	60	110	160
	BZ3 A4 / HCR	T_{inst}	[Nm]	15	40	55	100	200

¹⁾ For larger diameters of clearance hole in the fixture, see EN 1992-4:2018, chapter 6.2.2.2



Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Intended use
Installation parameters

Annex B2

Table B2: Minimum thickness of concrete member, minimum spacings, edge distances

Anchor size			M8	M10	M12	M16	M20
Minimum member thickness depending on h_{ef}	$h_{min} \geq$	[mm]	max (1,5· h_{ef} ; 80)		max (1,5· h_{ef} ;100)	max (1,5· h_{ef} ;120)	max (1,5· h_{ef} ;150)
Minimum edge distances and spacings							
Minimum edge distance	c_{min}	[mm]	40	45	55	65	90
	for $s \geq$	[mm]	see Table B4				
Minimum spacings	s_{min}	[mm]	35	40	50	65	95
	for $c \geq$	[mm]	see Table B4				
The following equation must be fulfilled for the calculation of the minimum spacing and edge distance during installation in combination with variable anchorage depth and member thickness:							
$A_{sp,rqd} \leq A_{sp,ef}$							
Required splitting area $A_{sp,rqd}$ and idealized splitting area $A_{sp,ef}$ according to Table B4.							

Table B3: Applicable concrete thickness h_{sp} and area A_{sp} to determine characteristic edge distance $c_{cr,sp}$

Anchor size			M8	M10	M12	M16	M20
Applicable concrete thickness	BZ3 BZ3 A4 BZ3 HCR	h_{sp} [mm]	$\min(h; h_{ef} + 1,5 \cdot c \cdot \sqrt{2})$				
Area to determine $c_{cr,sp}$ ¹⁾	BZ3	A_{sp} [mm ²]	$\frac{N_{Rk,sp}^0 - 2,573}{0,000436}$	$\frac{N_{Rk,sp}^0 + 2,040}{0,000693}$	$\frac{N_{Rk,sp}^0 + 3,685}{0,000692}$	$\frac{N_{Rk,sp}^0 + 3,738}{0,000875}$	$\frac{N_{Rk,sp}^0 + 2,423}{0,000453}$
	BZ3 A4 BZ3 HCR	A_{sp} [mm ²]	$\frac{N_{Rk,sp}^0 + 4,177}{0,000862}$	$\frac{N_{Rk,sp}^0 + 7,235}{0,000967}$	$\frac{N_{Rk,sp}^0 + 7,847}{0,000951}$	$\frac{N_{Rk,sp}^0 + 11,415}{0,000742}$	$\frac{N_{Rk,sp}^0 + 2,423}{0,000453}$

¹⁾ With $N_{Rk,sp}^0$ in kN

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Intended use

Minimum spacings and edge distances
Required area and applicable concrete thickness

Annex B3

Table B4: Areas to determine spacings and edge distances for installation

Anchor size				M8	M10	M12	M16	M20
The following equation must be fulfilled for the calculation of the minimum spacing and edge distance during installation in combination with variable anchorage depth and member thickness:								
$A_{sp,rqd} \leq A_{sp,ef}$								
Idealized splitting area $A_{sp,ef}$								
The edge distances and spacings shall be selected or rounded in steps of 5 mm.								
Member thickness: $h > h_{ef} + 1,5 \cdot c$								
Single anchor or anchor group with $s \geq 3 \cdot c$								
Idealized splitting area		$A_{sp,ef}$	[mm ²]	$(6 \cdot c) \cdot (1,5 \cdot c + h_{ef})$				
Anchor group ($s < 3 \cdot c$)								
Idealized splitting area		$A_{sp,ef}$	[mm ²]	$(3 \cdot c + s) \cdot (1,5 \cdot c + h_{ef})$				
Member thickness: $h \leq h_{ef} + 1,5 \cdot c$								
Single anchor or anchor group with $s \geq 3 \cdot c$								
Idealized splitting area		$A_{sp,ef}$	[mm ²]	$(6 \cdot c) \cdot h$				
Anchor group ($s < 3 \cdot c$)								
Idealized splitting area		$A_{sp,ef}$	[mm ²]	$(3 \cdot c + s) \cdot h$				
Required splitting area $A_{sp,rqd}$								
BZ3	cracked concrete	$A_{sp,rqd}$	[mm ²]	13 900	23 700	31 500	42 300	91 250
	uncracked concrete	$A_{sp,rqd}$	[mm ²]	22 500	34 700	41 300	50 200	110 000
BZ3 A4	cracked concrete	$A_{sp,rqd}$	[mm ²]	16 900	25 900	29 800	44 300	91 250
BZ3 HCR	uncracked concrete	$A_{sp,rqd}$	[mm ²]	19 700	35 700	35 300	54 800	110 000

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Intended use


Projected effective area to determine spacings and edge distances

Annex B4

Installation instructions

Hole drilling – Vacuum drilling

1




Vacuum drilling:

Drill hole perpendicular to concrete surface.
Proceed with step 3.

Hole drilling - Hammer drilling without cleaning


1



When the drill hole depth h_1 (see Annex B2, Table B1) is reached, move the drill back and forth at least three times with the machine switched on to remove the dust in the drill hole (venting the drill hole). Continue with step 3.

Hole drilling - Hammer drilling with cleaning


1



Hammer drilling:

Drill hole perpendicular to concrete surface.

2



Blow out dust. Alternatively vacuum clean down to the bottom of the hole.



Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR




Intended use

Installation instructions – hole drilling and cleaning

Annex B5

Installation instructions - continuation

Insert fastener		
3		Drive in fastener (optionally use setting tool).
4		Apply installation torque T_{inst} .

Insert fastener with filling of annular gap		
3		Drive in fastener with additionally mounted filling washer. (Optionally use setting tool).
4		Apply installation torque T_{inst} .
5		Fill the annular gap between anchor and fixture with injection adhesive (see Annex B1). Use enclosed reducing adapter. The annular gap is completely filled, when excess mortar seeps out.






Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Intended Use

Installation instructions - set fastener

Annex B6

Installation instruction – continuation

Install fastener with cap nut HM		
3		Check position of nut. Projection C after anchor has been inserted see Annex B2, Table B1.
4		Drive in fastener (optionally use setting tool).
5		Remove nut.
6		Screw on cap nut HM.
7		Apply installation torque T_{inst} .

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Product description

Installation instruction – set fastener with cap nut HM

Annex B7

Table C1: Characteristic values for tension load under static and quasi-static action, BZ3 (steel, zinc plated)

Fastener size			M8	M10	M12	M16	M20
Installation factor	γ_{inst}	[-]	1,0				
Steel failure							
Characteristic resistance	$N_{Rk,s}$	[kN]	19,8	30,4	44,9	79,3	126,2
Partial factor ⁴⁾	γ_{Ms}	[-]	1,5				
Pull-out							
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p,cr}$	[kN]	9,5	15,6	22,6	30,3	45,1
Increasing factor ⁵⁾ $N_{Rk,p,cr} = \psi_{c,cr} \cdot N_{Rk,p,cr} (C20/25)$	$\psi_{c,cr}$	[-]	$\left(\frac{f_{ck}}{20}\right)^{0,439}$	$\left(\frac{f_{ck}}{20}\right)^{0,265}$	$\left(\frac{f_{ck}}{20}\right)^{0,5}$	$\left(\frac{f_{ck}}{20}\right)^{0,339}$	$\left(\frac{f_{ck}}{20}\right)^{0,338}$
Characteristic resistance in uncracked concrete C20/25	$N_{Rk,p,ucr}$	[kN]	14,0	23,9	31,4	53,7	59,1
Increasing factor ⁵⁾ $N_{Rk,p,ucr} = \psi_{c,ucr} \cdot N_{Rk,p,ucr} (C20/25)$	$\psi_{c,ucr}$	[-]	$\left(\frac{f_{ck}}{20}\right)^{0,489}$	$\left(\frac{f_{ck}}{20}\right)^{0,448}$	$\left(\frac{f_{ck}}{20}\right)^{0,5}$	$\left(\frac{f_{ck}}{20}\right)^{0,203}$	$\left(\frac{f_{ck}}{20}\right)^{0,5}$
Splitting							
Characteristic resistance	$N^0_{Rk,sp}$	[kN]	$\min (N_{Rk,p} ; N^0_{Rk,c} \text{ } ^3)$				
Characteristic edge distance ²⁾	$C_{cr,sp}$	[mm]	$min\left(\frac{A_{sp} + 0,8 \cdot (h_{sp} - h_{ef})^2}{(3,41 \cdot h_{sp} - 0,59 \cdot h_{ef})} ; \frac{A_{sp}}{h_{sp} \cdot \sqrt{8}}\right) \geq 1,5 \cdot h_{ef}$				
Characteristic spacing	$s_{cr,sp}$	[mm]	$2 \cdot c_{cr,sp}$				
Factor	$\Psi_{h,sp}$	[-]	1,0				
Concrete cone failure							
Minimum, effective anchorage depth	$h_{ef,min}$	[mm]	35 ¹⁾	40	50	65	90
Maximum, effective anchorage depth	$h_{ef,max}$	[mm]	90	100	125	160	140
Characteristic edge distance	$C_{cr,N}$	[mm]	$1,5 \cdot h_{ef}$				
Characteristic spacing	$s_{cr,N}$	[mm]	$2 \cdot c_{cr,N}$				
Factor	cracked concrete $k_{cr,N}$	[-]	7,7	7,7	8,3	8,9	7,7
	uncracked concrete $k_{ucr,N}$	[-]	11,0				

¹⁾ Fastenings with anchorage depth $h_{ef} < 40$ mm are restricted to the use of structural components which are statically indeterminate and subject to internal exposure conditions only.

²⁾ Applicable concrete thickness h_{sp} and area A_{sp} to determine characteristic edge distance $c_{cr,sp}$ according to Table B3

³⁾ $N^0_{Rk,c}$ according to EN 1992-4:2018

⁴⁾ In absence of other national regulations

⁵⁾ For concrete strength classes $> C50/60$: $f_{ck} = 50$ N/mm²

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Annex C1

Performance

Characteristic values for **tension loads, BZ3** (Steel, zinc plated)

Table C2: Characteristic values for tension load under static or quasi-static action, BZ3 A4 and BZ3 HCR

Fastener size			M8	M10	M12	M16	M20
Installation factor	γ_{inst}	[-]	1,0				
Steel failure							
Characteristic resistance	$N_{Rk,s}$	[kN]	19,8	30,4	44,9	74,6	126,2
Partial factor ⁴⁾	γ_{Ms}	[-]	1,5				
Pull-out							
Characteristic resistance in cracked concrete C20/25	$N_{Rk,p,cr}$	[kN]	9,7	17,7	22,9	35,6	45,1
Increasing factor ⁵⁾ $N_{Rk,p,cr} = \psi_{c,cr} \cdot N_{Rk,p,cr} \text{ (C20/25)}$	$\psi_{c,cr}$	[-]	$\left(\frac{f_{ck}}{20}\right)^{0,488}$	$\left(\frac{f_{ck}}{20}\right)^{0,5}$	$\left(\frac{f_{ck}}{20}\right)^{0,435}$	$\left(\frac{f_{ck}}{20}\right)^{0,350}$	$\left(\frac{f_{ck}}{20}\right)^{0,338}$
Characteristic resistance in uncracked concrete C20/25	$N_{Rk,p,ucr}$	[kN]	19,9	25,2	42,5	51,9	59,1
Increasing factor ⁵⁾ $N_{Rk,p,ucr} = \psi_{c,ucr} \cdot N_{Rk,p,ucr} \text{ (C20/25)}$	$\psi_{c,ucr}$	[-]	$\left(\frac{f_{ck}}{20}\right)^{0,240}$	$\left(\frac{f_{ck}}{20}\right)^{0,364}$	$\left(\frac{f_{ck}}{20}\right)^{0,213}$	$\left(\frac{f_{ck}}{20}\right)^{0,196}$	$\left(\frac{f_{ck}}{20}\right)^{0,5}$
Splitting							
Characteristic resistance	$N^0_{Rk,sp}$	[kN]	$\min \left(N_{Rk,p} ; N^0_{Rk,c} \text{ }^3) \right)$				
Characteristic edge distance ²⁾	$c_{cr,sp}$	[mm]	$min\left(\frac{A_{sp} + 0,8 \cdot (h_{sp} - h_{ef})^2}{(3,41 \cdot h_{sp} - 0,59 \cdot h_{ef})} ; \frac{A_{sp}}{h_{sp} \cdot \sqrt{8}}\right) \geq 1,5 \cdot h_{ef}$				
Characteristic spacing	$s_{cr,sp}$	[mm]	$2 \cdot c_{cr,sp}$				
Factor	$\psi_{h,sp}$	[-]	1,0				
Concrete cone failure							
Minimum, effective anchorage depth	$h_{ef,min}$	[mm]	35 ¹⁾	40	50	65	90
Maximum, effective anchorage depth	$h_{ef,max}$	[mm]	90	100	125	160	140
Characteristic edge distance	$c_{cr,N}$	[mm]	$1,5 \cdot h_{ef}$				
Characteristic spacing	$s_{cr,N}$	[mm]	$2 \cdot c_{cr,N}$				
Factor	cracked concrete	$k_{cr,N}$	7,7	7,7	8,9	8,9	7,7
	uncracked concrete	$k_{ucr,N}$	11,0				

¹⁾ Fastenings with anchorage depth $h_{ef} < 40$ mm are restricted to the use of structural components which are statically indeterminate and subject to internal exposure conditions only

²⁾ Applicable concrete thickness h_{sp} and area A_{sp} according to Table B3 to determine characteristic edge distance $c_{cr,sp}$

³⁾ $N_{Rk,c}^0$ according to EN 1992-4:2018

⁴⁾ In absence of other national regulations

⁵⁾ For concrete strength classes $> C50/60$: $f_{ck} = 50$ N/mm²

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Annex C2

Performance

Characteristic values for tension loads, BZ3 A4 and BZ3 HCR

Table C3: Characteristic values for **shear load** under static and quasi-static action

Fastener size				M8	M10	M12	M16	M20
Installation factor		γ_{inst}	[-]	1,0				
Steel failure <u>without</u> lever arm								
Characteristic resistance – <u>unfilled</u> annular gap	BZ3	$V^0_{Rk,s}$	[kN]	15,7	26,8	38,3	60,0	83,8
	BZ3 A4	$V^0_{Rk,s}$	[kN]	20,3	31,8	41,6	71,7	108,5
	BZ3 HCR	$V^0_{Rk,s}$	[kN]	16,8	27,8	39,8	69,5	108,5
Characteristic resistance – <u>filled</u> annular gap	BZ3	$V^0_{Rk,s}$	[kN]	17,3	26,7	38,6	60,6	86,1
	BZ3 A4	$V^0_{Rk,s}$	[kN]	18,6	27,0	44,9	80,1	108,5
	BZ3 HCR	$V^0_{Rk,s}$	[kN]	16,8	27,8	44,9	80,1	108,5
Partial factor ²⁾		γ_{Ms}	[-]	1,25				
Ductility factor		k_7	[-]	1,0				
Steel failure <u>with</u> lever arm								
Characteristic bending resistance	BZ3	$M^0_{Rk,s}$	[Nm]	30	60	105	240	412
	BZ3 A4 / HCR	$M^0_{Rk,s}$	[Nm]	27	55	99	223	390
Partial factor ²⁾		γ_{Ms}	[-]	1,25				
Concrete pry-out failure								
Pry-out factor	BZ3	$k_{8,cr}$	[-]	2,8	3,1	2,8	3,1	3,3
		$k_{8,ucr}$	[-]	2,8	3,1	3,0	3,6	3,3
	BZ3 A4 / HCR	$k_{8,cr}$	[-]	2,7	2,8	2,9	2,9	3,3
		$k_{8,ucr}$	[-]	2,7	2,8	3,3	3,4	3,3
Concrete edge failure								
Effective length of fastener in shear loading		l_f	[mm]	$h_{ef}^{1)}$				
Outside diameter of fastener		d_{nom}	[mm]	8	10	12	16	20

¹⁾ Fastenings with anchorage depth $h_{ef} < 40$ mm are restricted to the use of structural components which are statically indeterminate and subject to internal exposure conditions only.

²⁾ In absence of other national regulations.

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance
Characteristic values for **shear loads**

Annex C3

Table C4: Characteristic values for **seismic loading**, performance category **C1**, **tension load**

Fastener size				M8	M10	M12	M16	M20
Effective anchorage depth	$h_{ef} \geq$	[mm]		40	40	50	65	90
Installation factor	γ_{inst}	[-]		1,0				
Steel failure								
Characteristic resistance	BZ3	$N_{Rk,s,C1}$	[kN]	19,8	30,4	44,9	79,3	126,2
	BZ3 A4 / HCR	$N_{Rk,s,C1}$	[kN]	19,8	30,4	44,9	74,6	126,2
Pull-out								
Characteristic resistance	BZ3	$N_{Rk,p,C1}$	[kN]	9,1	15,3	22,6	30,3	45,1
	BZ3 A4 / HCR	$N_{Rk,p,C1}$	[kN]	9,4	17,7	22,8	35,6	45,1

Table C5: Characteristic values for **seismic loading**, performance category **C1**, **shear load**

Fastener size				M8	M10	M12	M16	M20
Effective anchorage depth	$h_{ef} \geq$	[mm]		40	40	50	65	90
Steel failure without lever arm								
Characteristic resistance - unfilled annular gap	BZ3	$V_{Rk,s,C1}$	[kN]	Min (0,346* h_{ef} -2,2;13,4)	Min (0,094* h_{ef} +18,8;24,4)	Min (0,188* h_{ef} +20,6;33,8)	Min (0,176* h_{ef} +37,3;52,3)	83,8
	BZ3 A4	$V_{Rk,s,C1}$	[kN]	Min (0,424* h_{ef} -3,7;15,4)	Min (0,091* h_{ef} +19,9;25,3)	34,7	Min (0,165* h_{ef} +52,4;66,4)	108,5
	BZ3 HCR	$V_{Rk,s,C1}$	[kN]	Min (0,350* h_{ef} -3,0;12,7)	Min (0,079* h_{ef} +17,4;22,2)	33,2	Min (0,160* h_{ef} +50,7;64,3)	108,5
Characteristic resistance – filled annular gap	BZ3	$V_{Rk,s,C1}$	[kN]	Min (0,148* h_{ef} +8,0;14,7)	24,1	Min (0,082* h_{ef} +32,8;38,6)	60,2	86,1
	BZ3 A4	$V_{Rk,s,C1}$	[kN]	Min (0,934* h_{ef} -23,4;18,6)	Min (0,146* h_{ef} +17,9;26,6)	Min (0,153* h_{ef} +29,1;39,8)	Min (0,325* h_{ef} +46,6;74,2)	108,5
	BZ3 HCR	$V_{Rk,s,C1}$	[kN]	Min (0,845* h_{ef} -21,2;16,8)	Min (0,150* h_{ef} +18,5;27,5)	Min (0,153* h_{ef} +29,1;39,8)	Min (0,325* h_{ef} +46,6;74,2)	108,5
Factor for anchorages	unfilled annular gap	α_{gap}	[-]	0,5				
	filled annular gap	α_{gap}	[-]	1,0				

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance

Characteristic resistance for **seismic loading**, performance category **C1**

Annex C4

Table C6: Characteristic values for seismic loading, performance category C2, tension load

Fastener size				M8	M10	M12	M16	M20
Effective anchorage depth	$h_{ef} \geq$	[mm]		40	40	50	65	90
Installation factor	γ_{inst}	[-]		1,0				
Steel failure								
Characteristic resistance	BZ3	$N_{Rk,s,C2}$	[kN]	19,8	30,4	44,9	79,3	126,2
	BZ3 A4 / HCR	$N_{Rk,s,C2}$	[kN]	19,8	30,4	44,9	74,6	126,2
Pull-out								
Characteristic resistance	BZ3	$N_{Rk,p,C2}$	[kN]	min (0,150* h_{ef} -3,2; 3,6)	min (0,262* h_{ef} -3,2; 12,5)	min (0,415* h_{ef} -10,05; 19,0)	min (0,77* h_{ef} -30,25; 35,2)	$90 \leq h_{ef} \leq 100$: min (0,248* h_{ef} +12,8; 37,6)
	BZ3 A4 / HCR	$N_{Rk,p,C2}$	[kN]	min (0,198* h_{ef} -5,7; 3,2)	min (0,139* h_{ef} -0,6; 7,7)	min (0,292* h_{ef} -6,6; 13,8)	min (0,520* h_{ef} -14,8; 29,4)	$100 < h_{ef} \leq 140$: min (0,134* h_{ef} +24,2; 42,9)

Table C7: Characteristic values for seismic loading, performance category C2, shear load

Fastener size				M8	M10	M12	M16	M20
Effective anchorage depth	$h_{ef} \geq$	[mm]		40	40	50	65	90
Steel failure without lever arm								
Characteristic resistance - unfilled annular gap	BZ3	$V_{Rk,s,C2}$	[kN]	min (0,818* h_{ef} -25,5; 11,3)	min (0,177* h_{ef} +8,3; 19,0)	min (0,487* h_{ef} -6,1; 28,0)	min (0,195* h_{ef} +26,7; 43,3)	69,0
	BZ3 A4	$V_{Rk,s,C2}$	[kN]	min (0,226* h_{ef} -1,6; 10,4)	min (0,193* h_{ef} +6,5; 18,1)	min (0,170* h_{ef} +14,9; 26,8)	min (0,174* h_{ef} +32,7; 47,6)	88,9
	BZ3 HCR	$V_{Rk,s,C2}$	[kN]	min (0,220* h_{ef} -1,3; 8,6)	min (0,169* h_{ef} +5,7; 15,9)	min (0,162* h_{ef} +14,2; 25,6)	min (0,169* h_{ef} +31,7; 46,1)	88,9
Characteristic resistance – filled annular gap	BZ3	$V_{Rk,s,C2}$	[kN]	min (0,206* h_{ef} +1,5; 10,8)	min (0,111* h_{ef} +13,3; 19,9)	min (0,068* h_{ef} +24,2; 28,9)	min (0,142* h_{ef} +36,7; 48,8)	73,3
	BZ3 A4	$V_{Rk,s,C2}$	[kN]	min (0,071* h_{ef} +7,5; 10,7)	min (0,031* h_{ef} +14,8; 16,6)	min (0,201* h_{ef} +14,4; 28,5)	47,4	88,9
	BZ3 HCR	$V_{Rk,s,C2}$	[kN]	min (0,064* h_{ef} +6,8; 9,7)	min (0,032* h_{ef} +15,2; 17,1)	min (0,201* h_{ef} +14,4; 28,5)	47,4	88,9
Factor for anchorages	unfilled annular gap	α_{gap}	[-]	0,5				
	filled annular gap	α_{gap}	[-]	1,0				

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance
Characteristic resistance for **seismic loading**, performance category **C2**

Annex C5

Table C8: Characteristic values for tension and shear load under fire exposure, BZ3 (steel, zinc plated)

Fastener size			M8	M10	M12	M16	M20	
Tension load								
Steel failure								
Characteristic resistance	R30	$N_{Rk,s,fi}$	[kN]	1,2	2,6	4,6	7,7	9,4
	R60			1,0	1,9	3,3	5,6	8,2
	R90			0,7	1,3	2,1	3,5	6,9
	R120			0,6	1,0	1,5	2,5	6,3
Shear load								
Steel failure <u>without</u> lever arm								
Characteristic resistance	R30	$V_{Rk,s,fi}$	[kN]	4,0	7,5	12,3	20,7	11,0
	R60			2,7	5,1	8,5	14,2	10,6
	R90			1,4	2,7	4,6	7,7	10,2
	R120			0,8	1,6	2,7	4,5	10,0
Steel failure <u>with</u> lever arm								
Characteristic resistance	R30	$M^0_{Rk,s,fi}$	[Nm]	4,1	9,6	19,1	43,8	29,1
	R60			2,8	6,6	13,1	30,1	28,0
	R90			1,5	3,5	7,2	16,4	26,9
	R120			0,8	2,0	4,2	9,6	26,3

$N_{Rk,p,fi}$ and $N_{Rk,c,fi}$ according to EN 1992-4:2018

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance

Characteristic values under **fire exposure, BZ3** (steel, zinc plated)

Annex C6

Table C9: Characteristic values for tension and shear load under fire exposure, BZ3 A4 and BZ3 HCR

Fastener size			M8	M10	M12	M16	M20	
Tension load								
Steel failure								
Characteristic resistance	R30	$N_{Rk,s,fi}$	[kN]	4,0	6,9	11,0	18,1	36,9
	R60			2,9	5,0	8,0	13,1	27,4
	R90			1,8	3,1	4,9	8,1	17,9
	R120			1,2	2,1	3,4	5,6	13,1
Shear load								
Steel failure <u>without</u> lever arm								
Characteristic resistance	R30	$V_{Rk,s,fi}$	[kN]	8,5	17,6	32,0	52,6	73,5
	R60			6,2	12,6	22,6	37,1	51,8
	R90			3,9	7,5	13,1	21,5	30,1
	R120			2,8	5,0	8,4	13,8	19,2
Steel failure <u>with</u> lever arm								
Characteristic resistance	R30	$M^0_{Rk,s,fi}$	[Nm]	8,7	22,7	49,8	111,5	194,7
	R60			6,3	16,2	35,1	78,6	137,2
	R90			4,0	9,7	20,4	45,6	79,7
	R120			2,8	6,5	13,0	29,2	50,9

$N_{Rk,p,fi}$ and $N_{Rk,c,fi}$ according to EN 1992-4:2018

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance
Characteristic values under **fire exposure, BZ3 A4 and BZ3 HCR**

Annex C7

Table C10: Displacements under tension load, BZ3 (steel, zinc plated)

Fastener size			M8	M10	M12	M16	M20
Displacements under static or quasi-static action							
$\delta_{N0} = \delta_{N0\text{-factor}} \cdot N$							

Table C11: Displacements under tension load, BZ3 A4 and BZ3 HCR

Fastener size			M8	M10	M12	M16	M20
Displacements under static or quasi-static action							
$\delta_{N0} = \delta_{N0\text{-factor}} \cdot N$							

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance
Displacements under tension load

Annex C8

Table C12: Displacements under shear load, BZ3 (steel, zinc plated)

Fastener size			M8	M10	M12	M16	M20				
Displacements under static or quasi-static action $\delta_{V0} = \delta_{V0\text{-factor}} \cdot V$ $\delta_{V\infty} = \delta_{V\infty\text{-factor}} \cdot V$ V: acting shear load											
Effective anchorage depth	$h_{ef} \geq$	[mm]	35	40	50	65	90				
Factor for displacement	$\delta_{V0\text{-factor}}$	[mm/kN]	0,157	0,081	0,086	0,080	0,067				
unfilled annular gap	$\delta_{V\infty\text{-factor}}$	[mm/kN]	0,235	0,121	0,129	0,120	0,100				
Factor for displacement	$\delta_{V0\text{-factor}}$	[mm/kN]	0,002	0,039	0,047	0,038	0,016				
filled annular gap	$\delta_{V\infty\text{-factor}}$	[mm/kN]	0,004	0,059	0,070	0,057	0,024				
Displacement under seismic action C2 ¹⁾ unfilled annular gap											
Effective anchorage depth	$h_{ef} \geq$	[mm]	40	45	40	60	50	70	65	85	90
Displacements for DLS	$\delta_{V,C2(DLS)}$	[mm]	2,8	2,7	3,0	3,1	3,4	3,7	3,4	3,8	5,1
Displacements for ULS	$\delta_{V,C2(ULS)}$	[mm]	5,1	5,0	5,0	5,5	6,3	9,9	6,0	9,6	9,4
Displacement under seismic action C2 filled annular gap											
Effective anchorage depth	$h_{ef} \geq$	[mm]	40	45	40	60	50	70	65	85	90
Displacements for DLS	$\delta_{V,C2(DLS)}$	[mm]	0,5	0,4	1,4	0,9	1,4	0,7	1,4	1,2	1,3
Displacements for ULS	$\delta_{V,C2(ULS)}$	[mm]	1,7	1,9	5,8	4,5	4,5	3,1	5,0	3,9	5,2

¹⁾ For anchorages with clearance in the fixture the annular gap must also be considered.

Table C13: Displacements under shear load, BZ3 A4

Fastener size			M8	M10	M12	M16	M20			
Displacements under static or quasi-static action $\delta_{V0} = \delta_{V0\text{-factor}} \cdot V$										

¹⁾ For anchorages with clearance in the fixture the annular gap must also be considered

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR	Annex C9
Performance Displacements under shear load	

Table C14: Displacements under shear load, BZ3 HCR

Fastener size			M8	M10	M12	M16	M20				
Displacements under static or quasi-static action											
$\delta_{V0} = \delta_{V0\text{-factor}} \cdot V$			V: acting shear load								
$\delta_{V\infty} = \delta_{V\infty\text{-factor}} \cdot V$											
Effective anchorage depth	$h_{ef} \geq$	[mm]	35	40	50	65	90				
Factor for displacement	$\delta_{V0\text{-factor}}$	[mm/kN]	0,276	0,137	0,126	0,082	0,086				
<u>unfilled</u> annular gap	$\delta_{V\infty\text{-factor}}$	[mm/kN]	0,413	0,205	0,189	0,123	0,129				
Factor for displacement	$\delta_{V0\text{-factor}}$	[mm/kN]	0,308	0,042	0,040	0,025	0,086				
<u>filled</u> annular gap	$\delta_{V\infty\text{-factor}}$	[mm/kN]	0,462	0,064	0,060	0,037	0,129				
Displacement under seismic action C2 ¹⁾ <u>unfilled</u> annular gap											
Effective anchorage depth	$h_{ef} \geq$	[mm]	40	45	40	60	50	70	65	85	90
Displacements for DLS	$\delta_{V,C2(DLS)}$	[mm]	2,8	3,0	3,4	3,5	3,5	4,2	3,8	4,4	5,1
Displacements for ULS	$\delta_{V,C2(ULS)}$	[mm]	5,2	5,1	7,0	8,4	7,5	11,8	7,8	11,1	9,4
Displacement under seismic action C2 <u>filled</u> annular gap											
Effective anchorage depth	$h_{ef} \geq$	[mm]	40	45	40	60	50	70	65	85	90
Displacements for DLS	$\delta_{V,C2(DLS)}$	[mm]	0,9	0,6	1,2	0,5	1,5	1,5	1,6	1,6	4,1
Displacements for ULS	$\delta_{V,C2(ULS)}$	[mm]	2,5	2,6	5,4	3,6	6,0	7,1	6,2	6,2	8,4

¹⁾ For anchorages with clearance in the fixture the annular gap must also be considered

Wedge Anchor BZ3 / BZ3 A4 / BZ3 HCR

Performance
Displacements under shear load

Annex C10